

TABLE 1. DASH NUMBERS.

DASH NO	A	HEAT TREATMENT	FORMING 1/ PROCESS	ADDITIONAL 2/ REQUIREMENTS
001	.09375	ANNEALED	C	
003	.12500	ANNEALED	C	
005	.18750	ANNEALED	C	
007	.25000	ANNEALED	C	
009	.31250	ANNEALED	C	

1/ SEE REQUIREMENT 3
2/ SEE REQUIREMENT 4

REQUIREMENTS:

1. MATERIAL. STEEL, CORROSION RESISTANT, TYPE 310 (UNS S31000) AS SPECIFIED IN PROCUREMENT DOCUMENT.

2. LENGTH. STANDARD LENGTH OF WIRE IS 10 FEET MINIMUM, 12 FEET MAXIMUM.

3. FORMING PROCESS. COLD FINISHED - CODE "C"

4. ADDITIONAL REQUIREMENTS.

   PASSIVATED OVERALL - CODE "ps"
   CENTERLESS GROUND OVERALL - CODE "g"
   POLISHED OVERALL - CODE "p"

5. PART NUMBER. THE PART NUMBER CONSISTS OF THE BASIC MS NUMBER, PLUS A FORMING PROCESS CODE, PLUS A DASH NUMBER FROM TABLE I.

   EXAMPLE: MS14398C001
   - (SEE TABLE I)
   - COLD FINISHED (SEE REQUIREMENT 3)
   - BASIC MS NUMBER

6. MARKING. IRON AND STEEL PRODUCTS SHALL BE MARKED IN ACCORDANCE WITH FED-STD-183 WITH THE EXCEPTION THAT A PART NUMBER FROM THIS MILITARY STANDARD SHALL BE INCLUDED AS PART OF THE IDENTIFICATION MARKING.

NOTES:

1. ALL DIMENSIONS ARE IN INCHES.
2. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATIONS FOR BIDS, OR REQUEST FOR PROPOSAL, EXCEPT THE REFERENCED ADOPTED INDUSTRY DOCUMENTS SHALL GIVE THE DATE OF THE ISSUE ADOPTED.
3. FOR DESIGN FEATURE PURPOSES THIS STANDARD TAKES PRECEDENCE OVER PROCUREMENT DOCUMENTS REFERENCED HEREIN.

APPROVED 28 FEB 1985 REVISED

USER ACTIVITIES:
REVIEWER ACTIVITIES:
AIR FORCE-84
DLA-IS
This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document when applicable.

P.A.	AS	INTERNATIONAL INTEREST	TITLE	MILITARY STANDARD
Other Cust	MR 99		WIRE, NONELECTRICAL, ROUND, CORROSION RESISTANT, TYPE 310	MS14398
PROCUREMENT SPECIFICATION: QQ-S-763		SUPERSEDES:		PAGE 1 OF 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:42Z
Check the source to verify that this is the current version before use.