(METRIC)

A-A-2819A
March 23, 1994
SUPERSEDES
A-A-2819
December 10, 1992

COMMERCIAL ITEM DESCRIPTION

PAPER, TELETYPEWRITER, ROLL

The General Services Administration has authorized the use of this commercial item description, for all Federal Agencies.

1. Scope. This description covers friction feed single and multi-copy teletypewriter papers in roll form.

2. Classification.

Class 1 - Single copy.
  Grade A - 95 percent bleached chemical wood fibers.
  Grade B - Processed wood fibers.
Class 2 - Multi-copy, regular weight (carbon interleaved).
  Grade A - 95 percent bleached chemical wood fibers.
  Grade B - Processed wood fibers.
Class 3 - Auto-copy.
Class 4 - Multi-copy, special weight (carbon interleaved).
Class 5 - Multi-copy, carbonless, surface coated.
  Grade A - 95 percent bleached chemical wood fibers.
  Grade B - Processed wood fibers.
Class 6 - Multi-copy, carbonless, self imaging.
  Style A - For ribbon-equipped teleprinters.
  Style B - For ribbonless teleprinters.

3. Salient characteristic:

3.1 Materials used shall conform to the requirements specified herein. No polychlorinated biphenyls (PCBs) shall be added or used during the manufacture of the paper or in any coating operation on the base paper. The contractor shall submit a certificate stating that no PCBs have been added or used during the manufacturing or converting operations.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, N.Y. 10278.

Distribution Statement A:
Approved for public release
Distribution is unlimited

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 20261O-26T08:26Z
Check the source to verify that this is the current version before use.

3.2 Teletypewriter papers shall be furnished in rolls. Multicopy rolls shall be assembled as indicated in the contract or purchase order with the number of plies necessary to furnish the number of copies specified.

3.3 The stock for papers used in class 1, grade A and class 2, grade A, class 4, grade A, class 5, grade A and class 6, grade A, shall be a minimum of 95 percent bleached chemical wood fibers. Stock used for class 1, grade B, class 2, grade B, and class 5, grade B, shall be made from processed wood fibers. Manifold paper used in class 4 papers shall conform to the requirements for type V manifold paper specified in UU-P-328.

3.4 Rolls shall not be less than 213.12 mm (8 25/64 inches) nor more than 215.50 mm (8 31/64 inches) wide. Colors shall be as specified in the contract or purchase order. Rolls shall have an outside diameter of not more than 127.00 mm (5 inches). The minimum length of paper on the rolls shall be as indicated in Table 1.

Table 1. Minimum Paper Length in meters (feet)

Copies	Class 1	Class 2	Class 3	Class 4	Class 5	Class 6	
						Style A	Style B
1	99.1 (325)	-	-	-	-	-	112.2 (368)
2	-	50.3 (165)	73.2 (240)	63.7 (209)	59.4 (195)	60.4 (198)	54.6 (179)
3	-	30.5 (100)	52.4 (172)	39.6 (130)	38.1 (125)	39.0 (128)	37.2 (122)
4	-	21.3 (70)	40.8 (134)	29.0 (95)	28.3 (93)	28.7 (94)	27.7 (91)
5	-	-	33.2 (109)	22.9 (75)	22.3 (73)	22.9 (75)	21.9 (72)
6	-	-	28.0 (92)	-	18.3 (60)	18.9 (62)	18.3 (60)
7	-	-	24.4 (80)	-	15.5 (51)	15.8 (52)	15.5 (51)
8	-	-	21.6 (71)	-	13.7 (45)	14.0 (46)	13.7 (45)
9	-	-	19.2 (63)	-	11.9 (39)	12.2 (40)	12.2 (40)

3.5 Rolls shall be one continuous length. Individual plies shall not be spliced. The edges of the plies shall be shear cut. Rolls shall be wound tightly and evenly and plies of multi-copy rolls shall be of equal width. Single copy rolls shall have the outer end secured by spot gluing that will keep the roll from unraveling, yet permit separation, without the need for cutting the top layers of the roll. Multi-copy rolls shall have the outer end secured with a gummed sticker or label. All rolls shall have a contrasting color signal imprinted on the outermost ply to indicate approach to the end of the roll. The signal shall be not less than 6.35 mm (1/4 inch) wide and shall be 1.5 to 3 m (5 to 10 feet) in length ending not less than 1.5 m (5 feet) of the core end of the roll. The signal shall not impair the legibility of the copy printed on the paper.

3.6 The finish of teletypewriter papers shall be smooth but not glazed. The surfaces shall be free of lint and shall not pick in the teleprinter machines. The surface shall absorb teletype ribbon ink quickly without smearing or blurring of the printed characters.

3.7 Cores shall have the same width as the roll width specified, with a tolerance of + 0, - 1.59 mm (1/16 inch). Nominal 215.9 mm (8.5 inch) wide rolls shall be wound on a fiber core having an inside diameter of 25.4 mm + 1.27 - 0.00 mm (1 inch + 0.05 - 0.00 inch), and a wall thickness of 3.175 mm +/- 0.7925 mm (1/8 inch +/- 1/32 inch).

3.8 Workmanship. The end item shall be free of any defects such as, paper dust, grit spots, wrinkles, folds, holes, tears and smudges or any other defects that may affect appearance or serviceability. The edges of the end item shall not be nicked or uneven and shall be clean cut and lint free.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:26Z
Check the source to verify that this is the current version before use.

4. Requirements and Test Methods. All classes of teletypewriter papers shall meet the requirements of Table II.

Table II Physical Requirements

Class	Grade, Style, Ply	TAPPI Test Methods[1]			
		T410 Basis Weight[2] gm/m^2 (lb.)	T411 Caliper 0.001 mm (0.001 in)	T414 Tear Strength avg, min. gms MD	CD
1	A	68 (18)	762-1118 (30-44)	28	34
1	B	68 (18)	762-1118 (30-44)	26	36
2	A, all plies	60 (16)	762-965 (30-38)	24	30
2	B, all plies	60 (16)	762-965 (30-38)	24	32
3	Top sheet	60 (16)	762-965 (30-38)	20	22
3	Auto-copy sheets	49 (13)	381-635 (15-25)	18	18
4	First sheet	60 (16)	762-965 (30-38)	20	20
4	Inner sheet	34 (9)	– –	–	–
5	A, first sheet	56 (15)	660-1067 (26-42)	20	25
5	A, inner plies	53-68 (14-18[3])	635-1067 (25-42)	20	25
5	A, bottom sheet	56 (15)	584-864 (23-34)	20	25
5	B, first sheet	53 (14)	787-965 (31-38)	18	22
5	B, inner plies	60 (16)	787-965 (31-38)	18	22
5	B, bottom sheet	56 (15)	559-889 (22-35)	18	22
6	A, first sheet, white	56 (15)	686-889 (27-35)	20	25
6	A, first sheet, colored	56 (15)	686-889 (27-35)	20	20
6	A, inner plies	41-56 (11-15[3])	584-1041 (23-41)	16	18
6	B, all plies	45 (12)	584-1041 (23-41)	16	18

[1] TAPPI tests shall be in accordance with TAPPI T400 for the applicable test methods
[2] Tolerance of +/- 5% and (sized 17 x 22-500)
[3] Tolerance does not apply.

Carbon paper used for classes 2 and 4 multi-copy teletypewriter rolls shall be black and shall produce clear, legible copies on each ply of the multi-copy set specified. The carbon paper shall not bleed, offset nor transfer.

4.1 Bleaching: To obtain an acceptable brightness, in accordance with the performance standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleaching process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to require proof of such conformance prior to firsty delivery and thereafter as may be otherwise provided for under the provisions of the contract.

5. Quality Assurance.

5.1 Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

5.2 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may utilize this own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in this commercial item description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

5.2.1 Sampling for visual defects shall be performed in accordance with MIL-STD-105, Inspection S-4 with an acceptable quality level (AQL) of 4.0 percent defective. The sample unit shall be one roll of teletype paper.

5.2.2 Sampling for dimensional defects shall be performed in accordance with MIL-STD-105, Inspection S-3 with an acceptable quality level (AQL) of 4.0 percent defective. The sample unit shall be one roll of teletype paper.

5.2.3 Testing of component material shall be conducted on each mill run of paper received for compliance with the characteristics listed in section 2. In cases where individual mill runs are not segregated, testing shall be conducted using material from each lot of finished rolls utilizing sampling in accordance with MIL-STD-105, Inspection Level S-2. A sample unit shall consist of 10 square feet of teletype paper. The lot shall be the number of finished rolls offered for inspection at one time. In all cases, test results shall include all values upon which the results are based and there shall be no failure to meet the sample unit requirements.

6. Regulatory Requirements.

6.1 The contractor shall certify that for teletypewriter paper Classes 3, 5 and 6 the minimum content standard shall be no less than 20% post consumer materials in accordance with Executive Order 12873, section 504 (a), dated October 20, 1993 (See definition of post consumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(a) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

6.2 The contractor shall certify that for teletypewriter paper Classes 1, 2 and 4 the minimum content standard shall be no less than 50% recovered materials including 20% post consumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definition of post consumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(b) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

6.3 Recycled Content Labeling. The recycled content shall be marked on the product or unit pack.

7. Packaging, packing, labeling, and marking. Packaging, packing, labeling, and marking shall be as specified in the contract or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

8. Reference Documents. The reference documents in effect on the date of the solicitation shall be used to determine compliance with the stated requirements.

(A) TAPPI test methods are available from the Technical Association of the Pulp and Paper Industry, P.O. Box 105113, Atlanta, GA 30348.
(B) MIL-STD-105 is available from Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.
(C) Federal Specification UU-P-328 is available from the Business Service Center at the General Services Administration, Regional Offices in Boston, MA; New York, NY; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Denver, CO;San Francisco, CA; Los Angles, CA; and Seattle, WA.
(D) Copies of Executive Order 12873, dated October 20, 1993 may be obtained from: The White House Publications Office, New Executive Office Building,White House, Att: Publications,Washington, DC. 20500 (202) 395-7332

9. Ordering Data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

A) Title, number, and date of this specification
B) Class, grade or style required
C) Number of copies required
D) Color or colors required
E) Whether bleaching without use of chlorine, chlorine dioxide, or chlorine compound is required.
F) Packaging, packing, labeling and marking

MILITARY INTEREST:
Custodian:
Air Force - 84:

Review activities:
Army - GL
Air Force - 84

CIVIL AGENCIES INTEREST:
COMMERCE - NIST
NASA - JFK

PREPARING ACTIVITY:
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.