DATA ITEM DESCRIPTION

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 110 hours per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. TITLE	2. IDENTIFICATION NUMBER
Quality Assurance (QA) Checklist Report for Surface Deck Preparation	DI-QCIC -81298

3 DESCRIPTION / PURPOSE

3.1 The quality assurance (QA) checklist report provides a means for keeping a record of all data during the installation of non-skid, surface, and primer applications aboard ship. It will be used to

Continue on page 2 of 3 pages

4. APPROVAL DATE (YYMMDD)	5. OFFICE OF PRIMARY RESPONSIBILITY (OPR)	6a. DTIC APPLICABLE	6b. GIDEP APPLICABLE
921230	SUPSH/PAS 600		

7 APPLICATION / INTERRELATIONSHIP

7.1 This data item description contains the format and content preparation instructions for the data product generated by the specific and discrete task requirement as delineated in the contract.

8. APPROVAL LIMITATION	9a. APPLICABLE FORMS	9b. AMSC NUMBER
		N6851

10. PREPARATION INSTRUCTIONS

10.1 Format. The QA Checklist Report shall be presented on 8.5 x11 inch bond paper in the contractor's format.

10.2 Content. The report shall contain a title page identifying the following:

a. The title of the report and the ship name and hull number
b. compartment location (including frame numbers)
c. size of the area involved (square feet)
d. contract number and delivery order number
e. name and phone number of person(s) preparing the report

10.2.1. Measurements. Measurements shall be identified for each phase of the installation (e.g. one or more measurements per hour) intervals and for each start and stop phase.

a. Time (2400 clock)
b. air temperature (Fahrenheit)
c. wet bulb temperature (Fahrenheit)
d. relative humidity (Percentage)
e. deck temperature (Fahrenheit)
f. dew point (Fahrenheit)

Continue on page 2

11. DISTRIBUTION STATEMENT

DISTRIBUTION STATEMENT A: Approved for Public Release; Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:45Z
Check the source to verify that this is the current version before use.

Block 3. Description/Purpose Continues

provide the government evidence of the contractors knowledge and method of complying with environmental aspects of the contract, applicable specifications and product performance.

Block 10. Preparation Instructions continue

10.2.2 Surface Preparation. For surface preparation the report shall identify the following:

a. The date, name and time the surface preparation was completed.
b. Comments and recommendations resulting from the pre-inspection.
c. Blast method including type and size of abrasive.
d. Deck cleanliness (rating) and profile average at the end of the surface completion.

10.2.3 Primer Application. For primer application the report shall identify:

a. date and time of primer completion
b. name of inspector
c. pre-inspection comments and recommendations
d. number of hours deck was left uncoated
e. primer manufacturer and product name
f. primer batch
g. storage temperature, shelf-life and date of primer

10.2.3.1 Application method and the average wet film thickness (WFT).

10.2.3.2 A diagram indicating the locations of the readings shall be included.

10.2.3.3 Any other pertinent information necessary to show clarification shall be included.

10.2.4 Non-skid/Underlayment Application. For Non-skid application the report shall identify:

a. date and time of completion
b. name of inspector
c. comment and recommendations prior to non-skid application
d. average primer dry film thickness (DFT)
e. number of hours before non-skid was applied
f. non-skid manufacturer and product name
g. non-skid batch number
h. temperature at which the non-skid was stored

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:45Z
Check the source to verify that this is the current version before use.

Block 10. Preparation Instructions Continue

10.2.4.1 A diagram indicating the location of the DFT readings shall be included.

10.2.4.2 The induction time (if any) application method and spread rate shall be specified.

10.2.4.3 Any other pertinent information necessary for clarification shall be included.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:45Z
Check the source to verify that this is the current version before use.