INCH-POUND

MIL-DTL-46027M (MR)
17 September 2021
SUPERSEDING
MIL-DTL-46027K (MR)
w/AMENDMENT 2
16 March 2015

DETAIL SPECIFICATION

ARMOR PLATE, ALUMINUM ALLOY, WELDABLE 5083, 5456, & 5059

This specification is approved for use by the Department of the Army and is available for use by all Departments and Agencies of the Department of Defense

1. SCOPE

1.1 Scope. This specification covers AA5083, AA5456, & AA5059 wrought aluminum alloy armor plate for both welded and unwelded applications in nominal thicknesses from 0.250 to 3.000 inch, inclusive with additional greater thicknesses for AA5083 from 3.001 to 10.500 (see 6.2).

1.2 Weldability. All three classes of material covered by this specification have demonstrated to be weldable to itself and other weldable alloys (see 6.3).

1.3 Classification. The wrought aluminum armor should be of the following classes as specified (see 6.2).

1.3.1 Class I. Class I is wrought aluminum armor that conforms to the Aluminum Association designation for the 5083 aluminum alloy. The applicable gauge range for class I is 0.250-10.500 inches.

Comments, suggestions, or questions on this document should be addressed to: Director, U.S. Army DEVCOM, Army Research Laboratory (ARL), Weapons and Materials Research Directorate, Specifications & Standards Office, Attn: FCDD-RLW-MC, Aberdeen Proving Ground, MD 21005-5069. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil/.

AMSC N/A FSC 9535

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

1.3.2 Class II. Class II is wrought aluminum armor that conforms to the Aluminum Association designation for the 5456 aluminum alloy. The applicable gauge range for class II is 0.250-3.000 inches.

1.3.3 Class III. Class III is wrought aluminum armor that conforms to the Aluminum Association designation for the 5059 aluminum alloy. The applicable gauge range for class III is 0.250-3.000 inches.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the contract or purchase order.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-662	-	V50 Ballistic Test for Armor
MIL-STD-3057	-	Arc Welding of Armor Grade Aluminum

(Copies of these documents are available online at https://quicksearch.dla.mil/).

2.3 Non-Government publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the contract or purchase order.

THE ALUMINUM ASSOCIATION, INC.

ANSI H35.2	-	American National Standard Dimensional Tolerances for Aluminum Mill Products
Teal Sheets	-	International Alloy Designations and Chemical Composition Limits for Wrought Aluminum and Wrought Aluminum Alloys

(Copies of these documents are available online at https://www.aluminum.org/).

ASTM INTERNATIONAL

ASTM B557	-	Standard Test Methods for Tension Testing Wrought and

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

		Cast Aluminum and Magnesium-Alloy Products
ASTM E716	-	Standard Practices for Sampling and Sample Preparation of Aluminum and Aluminum Alloys for Determination of Chemical Composition by Spark Atomic Emission Spectrometry
ASTM E1251	-	Standard Test Method for Analysis of Aluminum and Aluminum Alloys by Spark Atomic Emission Spectrometry
ASTM E3061	-	Standard Test Method for Analysis of Aluminum and Aluminum Alloys by Inductively Coupled Plasma Atomic Emission Spectrometry (Performance Based Method)
ASTM G38	-	Standard Practice for Making and Using C-Ring Stress-Corrosion Test Specimens
ASTM G47	-	Standard Test Method for Determining Susceptibility to Stress-Corrosion Cracking of 2XXX and 7XXX Aluminum Alloy Products

(Copies of these documents are available online at https://www.astm.org/.)

2.4 Order of precedence. Unless otherwise noted herein or within the contract or purchase order, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order (see 6.2), first article testing shall be required, and all test samples required by this specification shall be made available to the contracting officer or his authorized representative for approval in accordance with 4.3. First article testing shall be completed before production material is submitted for acceptance testing. The approval of the first article samples authorizes commencement of production but does not relieve the supplier of the responsibility to comply with all the applicable provisions of this specification. The first article samples and acceptance test plates shall be manufactured by the process proposed for use on production items.

3.2 Chemical composition. The chemical compositions for classes I, II, and III alloys defined by the Aluminum Association Teal Sheets, “International Alloy Designations and Chemical Composition Limits for Wrought Aluminum and Wrought Aluminum Alloys” are listed within table I and shall be within those limits. A certification of conformance of the chemical composition of the alloy shall be furnished with the ballistic test plates.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical composition, percent. [1/]

ELEMENTS	SYMBOL	CLASS I 5083 ALLOY [2/]	CLASS II 5456 ALLOY [2/]	CLASS III 5059 ALLOY [2/]
Silicon	Si	0.40	0.25	0.45
Iron	Fe	0.40	0.40	0.50
Copper	Cu	0.10	0.10	0.25
Manganese	Mn	0.40 - 1.0	0.50 - 1.0	0.6 - 1.2
Magnesium	Mg	4.0 - 4.9	4.7 - 5.5	5.0 - 6.0
Chromium	Cr	0.05 - 0.25	0.05 - 0.20	0.25
Zinc	Zn	0.25	0.25	0.40 - 0.9
Titanium	Ti	0.15	0.20	0.20
Zirconium	Zr	---	---	0.05 - 0.25
Other, max. Each	---	0.05	0.05	0.05
Other, max. Total [3/]	---	0.15	0.15	0.15
Aluminum	Al	Remainder	Remainder	Remainder

[1/] Except for "Aluminum" and "others", analysis normally is made for elements for which specific limits are shown.
[2/] Where single units are shown, these indicate the maximum amounts permitted.
[3/] The sum of those "others" metallic elements 0.010 percent or more each, expressed to the second decimal before determining the sum.

3.3 Mechanical properties. Unless otherwise specified in the contract or purchase order (see 6.2), the mechanical properties of the test specimen taken in the longitudinal (L) direction shall meet the minimum mechanical properties listed in table II. If mechanical property requirements differ from those contained in table II, or if any other properties are required, the ballistic requirements shall be negotiated between the procuring activity and the supplier.

TABLE II. Minimum mechanical properties. [1/,2/]

Thickness, inches	Tensile Strength, Ksi			Yield Strength, 0.2% Offset, Ksi			Elongation percent		
	5083	5456	5059	5083	5456	5059	5083	5456	5059
0.250 to 0.499, incl.	45.0	54.0	53.0	35.0	47.0	39.0	8	6	8
0.500 to 2.000, incl.	45.0	50.0	52.0	37.0	45.0	39.0	8	6	7
2.001 to 3.000, incl.	44.0	50.0	47.0	35.0	44.0	39.0	9	8	8
3.001 to 10.500, incl.	43.0	TBD	TBD	31.0	TBD	TBD	11	TBD	TBD

[1/] The gage length shall be 1.400 inch for plates having a nominal thickness of 0.500 inch.
[2/] Values are taken in the Longitudinal Direction.

3.4 Weldability. When the vehicle requires weldments the fabricators (OEMs and kit manufacturers, etc.) are required to demonstrate weldability (which includes the Proofing Projectile Impact Testing (PPIT) formerly known as ballistic shock testing) for armor to armor and armor to non-armor applications in accordance with MIL-STD-3057, "Arc Welding of Armor Grade Aluminum". Since the alloys referenced by this standard are not all specified in MIL-STD-3057, it is strongly suggested that the contract or drawing for the vehicle specify weldability requirements as outlined in paragraph 6.3. PPIT procedures and associated striking velocities for a variety of class I and class III plate thicknesses are listed in MIL-STD-3057. For any newly

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

introduced armor material, configuration, or unproven thickness being used for armor applications, the aluminum fabricators shall qualify a weld procedure in accordance with MIL-STD-3057, and this requires PPIT testing.

3.5 Ballistic limit. The protection ballistic limit, BL(P), shall be as specified in Appendix A. No ballistic limit shall be specified for plate thickness of 0.250 to 0.499 inch, inclusive. When a complete penetration cannot be obtained for any class of armor material, the following rule shall be in effect until a new ballistic acceptance round can be developed and utilized. When the ballistic velocities of four (4) partial penetrations are above the minimum ballistic requirement for the specific thickness, the material shall be certified as acceptable with a V_{50} (which obviously cannot be explicitly determined) above the minimum requirement.

3.6 Stress corrosion resistance. When stress corrosion testing is specified in the contract or purchase order (see 6.2) and unless otherwise specified in the contract or purchase order (see 6.2), plate 0.750 inch and over in thickness shall be resistant to stress corrosion cracking, with a minimum of 5 of the 9 specimens showing no evidence of cracking at the end of 96 hours.

3.7 Thermal processing. After final strain hardening performed during plate fabrication, any thermal processing exceeding 200°F (93°C) excluding fabrication by welding shall necessitate recertification for conformance to 3.3, 3.5 and 3.6.

3.7.1 Storage of plates prior to application. After final strain hardening performed during plate fabrication, any extended outdoor storage (including container storage, e.g. CONEXs) exceeding 3 years shall necessitate recertification for conformance to 3.3, 3.5, and 3.6 by the entity owning the plates. MIL-DTL-46027 plates with unknown chain of custody shall also be recertified. For plates procured and qualified prior to the date of publication, this storage requirement while not mandatory is recommended. For optimal long term storage precautions that may obviate this storage and subsequent conformance requirement (see 6.5).

3.8 Dimensions. Dimensions for plates delivered for fabrication shall have an overall dimension tolerance of +0.500/-0.000 for width and length unless otherwise specified in the contract or purchase order (see 6.2).

3.8.1 Tolerances. Unless otherwise specified in the contract or purchase order (see 6.2), the plates shall not vary from the specified ordered dimensions by an amount greater than that specified by ANSI H35.2/H35.2M, except for thickness.

3.8.2 Thickness. Thickness tolerance for production armor and ballistic test plates shall be as specified in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

TABLE III. Thickness tolerances.

Ordered Thickness (Inches)		SPECIFIED WIDTH (Inches)								
		OVER	0.00	39.37	59.06	78.74	98.43	118.11	137.80	157.48
		THRU	39.37	59.06	78.74	98.43	118.11	137.80	157.48	177.17
OVER	THRU	TOLERANCES - INCHES (PLUS and MINUS)								
0.250	0.315		0.012	0.014	0.015	0.018	0.022	0.027	0.035	0.043
0.315	0.394		0.015	0.017	0.020	0.023	0.027	0.033	0.041	0.051
0.394	0.630		0.023	0.023	0.027	0.032	0.035	0.043	0.053	0.065
0.630	0.984		0.031	0.031	0.037	0.043	0.047	0.058	0.070	0.085
0.984	1.575		0.039	0.039	0.047	0.055	0.065	0.075	0.090	0.105
1.575	2.362		0.055	0.055	0.060	0.070	0.085	0.100	0.115	---
2.362	3.150		0.075	0.075	0.085	0.100	0.105	0.125	---	---
3.150	3.937		0.100	0.100	0.115	0.125	0.130	0.160	---	---
3.937	6.299		0.130	0.130	0.145	0.165	---	---	---	---
6.300	8.000		0.160	0.160	0.160	0.165	---	---	---	---
8.001	10.500		0.190	0.190	0.190	0.190	---	---	---	---

3.9 Marking for identification. Unless otherwise specified in the contract or purchase order (see 6.2) each plate shall be marked on one plate edge with the manufacturer's name or CAGE code, the basic number of this specification, the plate thickness in inches, the alloy designation and the lot number or code relating to the lot number (see 4.2). The height of the characters shall be 3/8 of an inch or greater. Impression stamping shall not be used unless permitted by the procuring activity (see 6.2). Each plate shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet, the rows being spaced not more than 6 inches apart and alternately staggered. The characters shall be not less than 3/8 inch in height and shall be applied using a suitable marking fluid whose residue shall not contain more than traces of halogen-bearing compounds and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the plate material or its performance and shall be sufficiently stable to withstand normal handling.

3.9.1 Ballistic test plates. In addition to the markings in 3.9, each ballistic test plate shall be marked with the letters ‘PRE’ for First Article test plates and ‘ACC’ for Acceptance test plates. This marking shall be impression stamped on the horizontal edge face of the ballistic plate in letters 3/8 inch high or greater. Ballistic retest plates shall be marked "R1" and "R2" respectively (see A.5.2).

3.10 Ballistic test plate information. For each lot of aluminum alloy armor, a properly completed Aluminum Armor Test Data Form (see figure 1) shall be submitted with each ballistic test plate that represents that particular processing lot.

3.11 Workmanship. Plate produced under this specification shall be uniform in quality and clean, smooth and sufficiently free from buckles, blisters, hard spots, damaged ends, laminations and other defects which may affect its use. Minor scratches, gouges, dents and similar damage are acceptable if the thickness is not reduced below the minimum material tolerance thickness.

3.11.1 Surface and Edge Condition. The surface and edge condition of the plate shall be free of surface cracks, edge cracks, and edge laminations as defined in the contract or purchase order (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

REQUEST FOR BALLISTIC TEST OF ALUMINUM ALLOY ARMOR										
SPECIFICATION: MIL-DTL-46027 **REVISION: M**									**AMENDMENT: N/A**	
FIRING RECORD:			**DATE:**			**TEST CONTRACT NO:**				
	PLATE MANUFACTURER / PRODUCER					**PRIME CONTRACTOR**				
Name:										
Address:										
POC:										
Phone No:										
Fax No:										
TEST ITEM IDENTIFICATION:								Ordered Thickness:		
Lot No. _____ **Plate No.** _____			**Alloy:** _____ **Temper:** _____					**Class:** _____ **Type:** _____		
PURPOSE: ☐ Acceptance ☐ First Article ☐ Development ☐ Reduced Testing ☐ Audit Testing										
SAMPLE: ☐ Primary ☐ Retest (Firing Record No. of Failed Sample)										
CHEMISTRY ANALYSIS	**Si**	**Fe**	**Cu**	**Mn**	**Mg**	**Cr**	**Zn**	**Ti**	**Zr**	
V	**Li**	**Ag**	**Ni**	**Mn+Cr**	**Zr+Ti**	**Other - Each**			**Other - Total**	**Al**
										Rem.
MECHANICAL PROPERTIES:										
UTS (ksi):			0.2% YS (ksi):					Elongation (%):		
WELDABILITY:	Thickness		Required Velocity		Actual Velocity			Pass/Fail		
BALLISTIC TEST RESULTS: **SEPARATELY HEAT TREATED TEST PLATE : YES** ☐ **NO** ☐										
Test: **Projectile:**	**Obl. (deg)**		**Actual Thickness (in)**		**Required V_{50} (fps)**		**Actual V_{50} (fps)**		**Pass/ Fail**	
	NOTES:									
SPALL:	Spall Size:		Two Projectile Calibers:				Pass / Fail:			
Lot [☐ met] [☐ failed to meet] the ballistic requirements of specification MIL-DTL-46027										
Government Representative:			Date:		Supplier Representative:				Date:	

Figure 1. Aluminum Armor Test Data Form.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Conformance inspection (see 4.4).

4.2 Lot. A lot shall consist of all plates of the same alloy; same source of molten metal representing the ingots poured, and ordered thickness which has been processed together by the same mill practice. Unless otherwise specified in the contract or purchase order (see 6.2), the weight of the finished plate in the lot shall not exceed 50,000 pounds and shall be submitted for inspection as a unit.

4.3 First article inspection. When specified in the contract or purchase order, (see 6.2) and before production has commenced, samples of specified material shall be made available to the contracting officer or his authorized representative for approval in accordance with 4.3.1. The approval of the first article samples authorizes the commencement of production but does not relieve the supplier of responsibility for compliance with all applicable provisions of this specification. The first article samples shall be produced using the mill production practice proposed for use in production.

4.3.1 First article inspection. First article inspection, except as otherwise indicated in this specification, shall utilize the same requirements and test methods as the conformance inspection or production acceptance inspection shown in 4.4.

4.4 Conformance inspection. Conformance inspection or production acceptance inspection shall include the examination of 4.6 and the tests of 4.7.

4.5 Sampling.

4.5.1 First article inspection.

4.5.1.1 Chemical composition. One (1) sample for chemical analysis shall be removed from each plate selected for ballistic testing and shall meet the requirements of 3.2 when tested as specified in 4.7.1.

4.5.1.2 Mechanical properties. One tension test specimen shall be removed from each plate that has been selected for ballistic testing and shall meet the requirements when tested as specified in 4.7.2.

4.5.1.3 Ballistic tests. Two (2) plates, 12 inches by 36 inches of each thickness to be supplied on the contract, shall be submitted for ballistic testing in accordance with Appendix A. The orientation of these plates with respect to the rolling direction shall be at the option of the producer (see 6.2). For ordered plate thicknesses exceeding 4.000”, the ballistic test plates shall be symmetrically machined from both top and bottom plate rolling surfaces to attain 4.000” (i.e. centered around the T/2 plane) with a thickness tolerance of +/- 0.060".

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

4.5.1.4 Stress corrosion tests. Nine (9) stress corrosion test specimens shall be removed from the same plate that has been selected for ballistic testing. The location and type of specimen shall be as specified in 4.7.5.

4.5.2 Conformance inspection.

4.5.2.1 Chemical composition. The sample shall meet the chemical composition requirements of 3.2 when tested as specified in 4.7.1.

4.5.2.1.1 Ingot analysis. At least one sample shall be taken from the molten metal representing the ingots poured as a unit from the same source molten metal. Complete ingot analysis records shall be available to the Government at the producer's facility.

4.5.2.1.2 Product analysis. When sampling has not been made in accordance with 4.5.2.1.1, one sample shall be randomly taken for each 4,000 pounds or less in a lot. Complete product analysis records shall be available to the Government at the contractor's facility.

4.5.2.2 Mechanical properties. Samples for tension tests shall be selected from each lot in accordance with table IV. Each sample shall be randomly selected from a different plate in the lot, and only one tension test specimen shall be made from each sample. The sample shall meet the requirements when tested as specified in 4.7.2.

4.5.2.2.1 Thermal stability. When verification of thermal stability is required, mechanical testing of thermally stressed specimens shall be conducted. Samples for tension tests shall be selected from each lot in accordance with table IV. Each sample shall be randomly selected from a different plate in the lot and thermally prepared prior to testing as directed in 4.7.2.1. Only one tension test specimen shall be made from each sample. The samples shall meet the minimum acceptance requirements for mechanical properties in table 2 when tested as specified in 4.7.2.

TABLE IV. Number of tension tests.

Lot size, pounds	Minimum number of samples 1/
To 8,000, incl.	2
8,001 to 12,000, incl.	3
12,001 to 20,000, incl.	4
20,001 up	5

1/ If a lot consists of only one plate, one sample shall be required.

4.5.2.3 Ballistic testing. One plate, 12 inches by 36 inches, shall be randomly selected from each lot for ballistic testing. The orientation of the plate with respect to the rolling direction shall be at the option of the producer (see 6.2). The sample shall meet the requirements when tested as specified in 4.7.4.

4.5.2.4 Stress corrosion tests. When required (see 6.2), one plate, 12 inches by 12 inches, shall be randomly selected from each lot for stress corrosion testing. The plate shall meet the requirements when tested as specified in 4.7.5.

4.6 Examination.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

4.6.1 Visual. Each plate shall be examined for compliance with the identification marking (see 3.8) and workmanship (see 3.11) requirements.

4.6.2 Dimensions. Plates within a lot shall be measured to determine compliance with requirements of paragraph 3.7 in accordance with the sampling procedures approved by the procuring activity (see 6.2).

4.7 Test specimens.

4.7.1 Chemical composition. Samples for chemical analysis shall be prepared and tested in accordance with one or more ASTM methods of E716, E1251, and E3061. In case of any dispute, analysis by method E3061shall be the basis for acceptance or rejection.

4.7.2 Mechanical properties. Tension test specimens shall be prepared and tested in accordance with ASTM B557. Specimens shall be taken in the longitudinal (L) direction. For material less than 0.500 inch in thickness, a standard rectangular tension test specimen shall be used. For plate in nominal thickness 0.500 to 1.500 inches, inclusive, tension test specimens shall be taken with the axis midway between the two plate surfaces. For plate in nominal thickness greater than 1.500 inches, the axis of the tension test specimen shall be three-fourths of the distance from one surface to the other.

4.7.2.1 Thermal stability specimens. When demonstration of thermal stability is required (see 4.5.2.2.1), mechanical properties of artificially aged specimens shall be determined (see 6.2(d)), specimens will follow the preparation of 4.7.2. The tensile specimens shall be artificially aged at 212°F (100°C) for 24 hours, removed and passively air cooled (without forced air) to 77°F (25°C), and then the tension tests shall be performed in accordance with ASTM B557.

4.7.3 Weldability. The thickness of the weldments specified in the contract or drawing shall be used to determine the proofing projectile and striking velocity in accordance with MIL-STD-3057.

4.7.4 Ballistic testing. The ordered thickness specified in the contract or purchase order shall be used to determine the test projectile in accordance with table V. Ballistic testing shall be in accordance with Appendix A. Test plate thickness, as measured by the ballistic testing agency, shall be used in conjunction with table V and Appendix A to determine the required V_{50} protection ballistic limit for that plate. Thickness shall be determined as the average of at least four thickness measurements read on a deep throat micrometer or by means of an ultrasonic device to the nearest 0.001 of an inch and rounded off to the nearest 0.005 of an inch. Measurements shall be made on the intended impact area. In those cases where the BL(P) is within ±10 fps of the minimum required value for the measured average thickness (to the nearest 0.005-inch), an interpolation of the appropriate ballistic limit table shall be performed. The average plate thickness, computed to the nearest 0.001-inch, shall be used to determine the minimum required BL (P) for that plate.

4.7.4.1 Ballistic testing facility. Unless otherwise specified in the contract or purchase order (see 6.2), the ballistic test plates shall be forwarded to the Commander, USA ATC, ATTN: TEDT-AT-SL-V, Building 358, 6850 Lanyard Road, APG, MD 21005-5059 or to an approved Government facility for ballistic testing for first article or production acceptance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

4.7.4.2 Incomplete penetrations. When a complete penetration cannot be obtained, the following rule shall be in effect until a new ballistic acceptance round can be developed and utilized. When the ballistic velocities of four (4) partial penetrations are above the minimum ballistic requirement for the specific thickness, the material shall be certified as acceptable with a V_{50} (which obviously cannot be explicitly determined) above the minimum requirement.

TABLE V. Acceptance ballistic test plates.

Ordered Thickness, Inches	Projectile	Angle of Obliquity in Degrees
0.500 – 0.749	Cal. .30 AP	30
0.750 – 1.000	Cal. .50 FSP	0
1.001 – 1.700 1/	20mm FSP	0
1.001 – 1.700 1/	Cal. .30 AP M2	0
1.701 – 2.000	Cal. .30 AP M2	0
2.001 – 10.500	Cal. .50 AP M2	0

1/ Two (2) types of projectiles for the same thickness range.

4.7.5 Capability requirements for resistance to stress corrosion. When stress corrosion testing is required (see 6.2), specimens shall be prepared in accordance with ASTM G38 and tested in accordance with ASTM G47 with nine specimens each prepared per sample per lot. The stress corrosion specimens shall be stressed to 30 ksi.

4.8 Rejection and retest. Unless otherwise specified in the contract or order (see 6.2) and except as specified in 4.7.2 and 4.7.3, rejection and retest shall be conducted in accordance with 4.8.1, 4.8.1.1, 4.8.2, and 4.8.3.

4.8.1 Rejection of first article plates. When one or more first article test specimens fail to meet the requirements of 4.3, the product lot and process, represented by the test plates or specimens shall be subject to rejection, except as otherwise provided in a sampling plan approved by the procuring activity and in requirements of 4.8.1.1.

4.8.1.1 Retest of first article samples. Resubmission and retest of first article samples shall not be made until the manufacturer has made necessary corrections in the processing of the material to the satisfaction of the procuring activity. If one of the retest specimens fails, the lot shall be permanently rejected with no further testing permitted.

4.8.2 Ballistic. Rejection and retest of ballistic test plates shall be in accordance with A.5.2.

4.8.3 Stress corrosion. Immediately upon notification of the failure of the stress corrosion specimens, the manufacturer may at their expense test thirteen additional specimens for retesting. A minimum of seven specimens out of the thirteen additional specimens shall show no cracks upon examination at the end of 96 hours when tested as specified in 4.7.5. If the retest also fails, the manufacturer may elect to resubmit the lot after retreatment of the entire lot. After retreatment, the lot must pass the requirements outlined in 4.7.2, 4.7.4 and 4.7.5.

4.9 Reduced testing. At the discretion of the procuring activity and as specified in the contract or purchase order (see 6.2), the amount of testing may be reduced provided the results on consecutive

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

lots indicate that a uniform product meeting the testing requirements is being produced and providing that the manufacturer agrees in writing to maintain the same manufacturing procedures. Testing for a given plate thickness shall return to standard (non-reduced testing) conditions of one plate per lot, whenever a ballistic test plate fails to meet ballistic requirements.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel components are to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The armor specified herein is intended for use on combat vehicles to protect the occupants against small arms fire, fragments, and shrapnel. Alloys 5083, 5456 and 5059 will be considered for multiple applications that require weldability, ballistic and blast performance.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Specify classification of alloy, and ordered thickness (see 1.1 and 1.3).
(c) When first article is required (see 3.1 and 4.3).
(d) Special mechanical properties (to include thermal stability mechanical properties) and ballistic requirements if different (see 3.3).
(e) When stress corrosion testing is required and if the test conditions are different (see 3.6, 4.5.2.4, and 4.7.5).
(f) Dimension and tolerance requirements, if different (see 3.8 and 3.8.1).
(g) If markings are different and when impression stamping is permissible (see 3.9).
(h) Define surface cracks, edge cracks and edge laminations for the specific application (see 3.11.1)
(i) If the weight of finished plate can exceed 50,000 pounds (see 4.2).
(j) The orientation of the ballistic plate is different (see 4.5.1.3 and 4.5.2.3).
(k) Dimensional sampling procedure approved by the procuring activity (see 4.6.2).
(l) If approval was requested and received for a different ballistic testing facility (see 4.7.4.1)
(m) Rejection and retest requirements, if different (see 4.8).
(n) If reduced testing is allowed (see 4.9).
(o) Packaging requirements (see 5.1).
(p) Striking velocities for those thicknesses not covered (see MIL-STD-3057).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

6.3 Weldability. The U.S. Army DEVCOM, Ground Vehicle Systems Center, DEVCOM ARL, and the Aberdeen Test Center have conducted testing and found that class I and class III alloys can be welded and demonstrate good shock resistance when tested with the method described in in MIL-STD-3057, "Arc Welding of Armor Grade Aluminum". Qualification of new plate thicknesses and configurations under PPIT may be achieved in accordance with MIL-STD-3057, section 5.3.6.3.9: Proofing projectile and velocity. Additional tests have demonstrated that material covered by this specification is weldable to itself and other weldable 7000, 5000, and 6000 series alloys using a 5000 series filler metal. It is not weldable to 2000 series alloys by conventional welding techniques. Any deviations from these conditions should be demonstrated in accordance with MIL-STD-3057 prior to acceptance by the procuring activity.

6.4 Density. The density of the specified alloys listed in this specification are as follows:

AA5083 = 0.096 lb/in^3 (2.66 g/cc)
AA5456 = 0.096 lb/in^3 (2.66 g/cc)
AA5059 = 0.096 lb/in^3 (2.66 g/cc)

6.5 Long Term Storage. Al-Mg (5XXX) alloys are susceptible to degradation of mechanical properties and corrosion resistance after extended durations at elevated temperatures beyond 131°F (55°C) and additional preparations for long term storage are recommended. Due to surface heating produced by direct sunlight and/or cumulative trapped heat in poorly ventilated CONEX type shipping and storage containers, ventilated indoor warehouse storage is recommended for optimal storage of MIL-DTL-46027 qualified plates. Outdoor storage that provides overhead shading from direct sunlight is also acceptable. Horizontally stacked plates should be separated by nonmetallic spacers to facilitate easy access and manipulation by heavy equipment and to provide optimum airflow to dissipate heat and maintain lower temperatures. Any MIL-DTL-46027 qualified plates with full documentation of the recommended long term storage methods listed above are eligible to waive the recertification requirements in 3.7.1.

6.6 Metric units. When metric divisions are required, units for inch, foot, foot-pounds, feet per second, and pounds per square inch may be converted to the metric equivalent by multiplying them by the following conversion factors:

English	Multiply by	Equals	Metric SI unit
inch	0.0254	=	meter (m)
foot	0.3048	=	meter (m)
pound	0.4536	=	kilogram (kg)
foot-lb	1.3558	=	joule (j)
feet/second	0.3048	=	meter per second (m/s)
pounds/sq. inch	0.00689	=	Mega Pascal (MPa)
pound/cubic inch	27.6799	=	gram (g) per cubic centimeter (cm)
Fahrenheit (°F)	(t°F - 32)/1.8 = t°C		Centigrade (°C)

6.7 Subject term (key word) listing.

Ballistic testing M1114 HMMWV

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

Caliber .30 AP M2	Military vehicles
Caliber .50 AP M2	Stress corrosion
Caliber .50 FSP	20-mm FSP

6.8 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

ARMOR PLATE, ALUMINUM ALLOY, WELDABLE 5083, 5456, & 5059

A.1 SCOPE

A.1.1 Scope. This appendix covers the minimum ballistic limits for acceptable requirements of aluminum alloy armor plate, weldable, 5083, 5456, and 5059 when tested in accordance with the provisions of this specification. When there is mutual agreement between contractor and procuring activity, this appendix becomes a mandatory part of this specification and the information contained herein is intended for compliance.

A.2 APPLICABLE DOCUMENTS

A.2.1 Government documents.

A.2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

STANDARDS

DEPARTMENT OF DEFENSE

MIL-STD-662 - V50 Ballistic Test for Armor

(Copies of this document are available online at https://quicksearch.dla.mil/).

A.3 DEFINITIONS

A.3.1 Complete penetration, (CP). A complete penetration occurs when the impacting projectile, or any fragment thereof, or any fragment of the test specimen perforates the witness plate, resulting in a crack or hole which permits light passage when a 60-watt, 110-volt bulb is placed proximate to the witness plate.

A.3.2 Fair impact. An impact may be considered fair when an un-yawed fragment simulator or test projectile strikes an unsupported area of the target material at a specified obliquity at a distance of at least two projectile diameters from any previous impact or disturbed area resulting from an impact, or from any crack, or from any edge of the test specimen.

A.3.3 Gap. A gap is the difference in fps between the high partial penetration velocity and the low complete penetration velocity used to compute the ballistic limit when the high partial penetration velocity is lower than the low complete penetration velocity.

A.3.4 Partial penetration, (PP). Any impact which is not a complete penetration may be considered a partial penetration.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

A.3.5 Witness plate. A thin sheet located behind and parallel to the ballistic test sample which is used to detect penetrating projectiles or spall.

A.4 REQUIREMENTS

A.4.1 Resistance to penetration. The minimum required V50 ballistic limit shall be in accordance with the values shown in tables A-I through A-V.

A.5 TESTS

A.5.1 Ballistic tests. Testing shall be in accordance with MIL-STD-662, V50 Ballistic Test for Armor, except that nothing in this procedure shall be construed to supersede or invalidate the requirements of this specification.

A.5.1.1 Temperature Conditioning. Prior to the test, the test item(s) shall be temperature conditioned at least eight hours. Thermostatic control shall be such that the average temperature of the item during the test shall be 72 ± 15°F (22 ± 8°C).

A.5.1.2 Protection ballistic limit, BL(P).

A.5.1.2.1 Normal circumstances. The BL(P) shall consist of an equal number of fair impact complete and partial penetration velocities attained by the up-and-down firing method. All BL(P)'s shall be computed using the highest partial penetration velocities and the lowest complete penetration velocities. Firing shall continue until either a 4-round BL(P) having a maximum velocity spread of 60 fps or a 6-round BL(P) having a maximum velocity spread of 90 fps has been attained, whichever comes first in the normal sequence of firing. If both occur simultaneously, the 6-round BL(P) shall be reported.

A.5.1.2.2 Large zone of mixed results. In the event that the zone of mixed results (difference between the high partial penetration velocity and the low complete penetration velocity, the PP[P] velocity being higher than the low CP[P] velocity) exceeds 90 fps, the firing data shall be compared with the specification minimum ballistic requirements. If the lowest complete penetration velocity is equal to or above the minimum specified ballistic limit velocity for the plate thickness, the ballistic limit shall be computed on the basis of 4- or 6-rounds using the smallest possible velocity spread. If the lowest complete penetration velocity is below the minimum allowable ballistic limit velocity, then testing shall continue until a 10-round ballistic limit has been attained using the smallest possible velocity spread. Ten-round ballistic limits shall be reported as agreed upon between the contractor and procuring activity.

A.5.1.2.3 Reduction of large velocity gap in borderline cases. If the ballistic limit, which has been determined, is within ± 10 fps from the minimum allowable ballistic limit and a gap exists which is greater than 25 fps, then another round, or rounds, shall be fired to reduce the gap to 25 fps or less. The ballistic limit shall then be recomputed using the above criteria. The recomputed BL(P) shall be reported as the BL(P) of the plate (in borderline cases, a reduction of the gap between the

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

high partial penetration velocity and the low complete velocity should result in a better evaluation of the BL(P)).

A.5.2 Rejection and retest of ballistic plates.

A.5.2.1 First article tests (rejection). Unless otherwise specified in the contract or purchase order, failure of any of the first article test plates to meet the minimum ballistic requirements shown in the appendix of this specification indicates failure of the product and process.

A.5.2.2 First article (retests). Resubmission of ballistic retest plates shall not be made until the manufacturer has made the necessary corrections in the processing of the material to the satisfaction of the procuring activity. Two retest plates shall be submitted for first article testing, and both tests shall pass; otherwise, the armor material shall be rejected.

A.5.2.3 Acceptance tests (rejection). Unless otherwise specified in the contract or purchase order, failure of a test plate to meet the ballistic requirements indicates failure of the lot; however, the final decision shall depend on the outcome of retests, if submitted.

A.5.2.4 Acceptance tests (retests). If a test plate representing a lot fails to meet the ballistic requirement, the manufacturer, upon notification of the failure may submit at their own expense two additional test plates from the same lot for ballistic retest. If either of these plates fails the ballistic test, the lot shall be rejected. The manufacturer may elect to resubmit the lot after retreatment of the entire lot by submitting two additional test plates. If either of these plates fails, the lot shall be permanently rejected.

A.5.3 Disposal of ballistic test plates.

A.5.3.1 First article test plates. Upon request of the applicant within 15 days after ballistic testing, first article plates shall be returned "as is" to the applicant, at their own expense, unless the plates were destroyed in testing.

A.5.3.2 Acceptance test plates. Acceptance test plates that comply with the requirements of this specification are considered part of the lot they represent, and ownership of the test plates passes to the Government with the acceptance of that lot. Acceptance test plates that fail to comply with the requirements of this specification are considered part of the lot they represent and remain the property of the producer. The now rejected lot also remains the property of the producer. The failed plates shall be returned, upon request, as in A.5.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-I. Minimum required ballistic limits - caliber .30 AP M2 projectiles at 30° obliquity.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
0.460	1290	0.570	1452	0.680	1599
0.465	1298	0.575	1459	0.685	1605
0.470	1305	0.580	1466	0.690	1612
0.475	1313	0.585	1473	0.695	1618
0.480	1321	0.590	1480	0.700	1624
0.485	1328	0.595	1487	0.705	1630
0.490	1336	0.600	1494	0.710	1637
0.495	1343	0.605	1500	0.715	1643
0.500 1/	1351	0.610	1507	0.720	1649
0.505	1358	0.615	1514	0.725	1655
0.510	1366	0.620	1521	0.730	1661
0.515	1373	0.625	1527	0.735	1668
0.520	1381	0.630	1534	0.740	1674
0.525	1388	0.635	1541	0.745	1680
0.530	1395	0.640	1547	0.749 2/	1685
0.535	1402	0.645	1554	0.750	1686
0.540	1410	0.650	1560	0.755	1692
0.545	1417	0.655	1567	0.760	1699
0.550	1424	0.660	1573	0.765	1705
0.555	1431	0.665	1580	0.770	1711
0.560	1438	0.670	1586	0.775	1717
0.565	1445	0.675	1593	0.780	1723

1/ Specification requirements begin for this ordered thickness.
2/ Specification requirements end for this ordered thickness (See table A-II).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-II. Minimum required ballistic limits - caliber .50 fragment simulating projectiles at 0° obliquity.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
0.720	1681	0.835	2046	0.950	2485
0.725	1696	0.840	2064	0.955	2506
0.730	1711	0.845	2081	0.960	2527
0.735	1725	0.850	2099	0.965	2549
0.740	1740	0.855	2117	0.970	2570
0.745	1755	0.860	2135	0.975	2592
0.750 [1/]	1770	0.865	2153	0.980	2614
0.755	1785	0.870	2171	0.985	2636
0.760	1801	0.875	2190	0.990	2658
0.765	1816	0.880	2209	0.995	2680
0.770	1832	0.885	2227	1.000 [2/]	2703
0.775	1848	0.890	2246	1.005	2726
0.780	1863	0.895	2265	1.010	2749
0.785	1879	0.900	2284	1.015	2772
0.790	1895	0.905	2304	1.020	2795
0.795	1912	0.910	2323	1.025	2819
0.800	1928	0.915	2343	1.030	2842
0.805	1945	0.920	2363	1.035	2866
0.810	1961	0.925	2383	1.040	2890
0.815	1978	0.930	2403	1.045	2914
0.820	1995	0.935	2423	1.050	2939
0.825	2012	0.940	2444	1.055	2963
0.830	2029	0.945	2464	1.060	2988

[1/] Specification requirements begin for this ordered thickness.
[2/] Specification requirements end for this ordered thickness (See table A-III and table A-IV).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-III. Minimum required ballistic limits - 20 mm fragment simulating projectiles at 0° obliquity.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
0.980	1389	1.150	1664	1.320	1991
0.985	1397	1.155	1673	1.325	2001
0.990	1404	1.160	1682	1.330	2012
0.995	1412	1.165	1691	1.335	2022
1.001[1/]	1420	1.170	1700	1.340	2033
1.005	1427	1.175	1709	1.345	2043
1.010	1435	1.180	1718	1.350	2054
1.015	1443	1.185	1727	1.355	2065
1.020	1450	1.190	1736	1.360	2076
1.025	1458	1.195	1745	1.365	2087
1.030	1466	1.200	1755	1.370	2098
1.035	1474	1.205	1764	1.375	2109
1.040	1481	1.210	1773	1.380	2120
1.045	1489	1.215	1783	1.385	2131
1.050	1497	1.220	1792	1.390	2142
1.055	1505	1.225	1801	1.395	2153
1.060	1513	1.230	1811	1.400	2165
1.065	1521	1.235	1821	1.405	2176
1.070	1529	1.240	1830	1.410	2187
1.075	1537	1.245	1840	1.415	2199
1.080	1546	1.250	1849	1.420	2210
1.085	1554	1.255	1859	1.425	2222
1.090	1562	1.260	1869	1.430	2234
1.095	1570	1.265	1879	1.435	2245
1.100	1579	1.270	1889	1.440	2257
1.105	1587	1.275	1899	1.445	2269
1.110	1596	1.280	1909	1.450	2281
1.115	1604	1.285	1919	1.455	2293
1.120	1613	1.290	1929	1.460	2305
1.125	1621	1.295	1939	1.465	2317
1.130	1630	1.300	1949	1.470	2329
1.135	1638	1.305	1959	1.475	2341
1.140	1647	1.310	1970	1.480	2353
1.145	1656	1.315	1980	1.485	2366

[1/] Specification requirements begin for this ordered thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-III. Minimum required ballistic limits - 20 mm fragment simulating projectiles at 0° obliquity - Continued.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
1.490	2378	1.570	2585	1.650	2809
1.495	2390	1.575	2598	1.655	2823
1.500	2403	1.580	2612	1.660	2838
1.505	2415	1.585	2625	1.665	2853
1.510	2428	1.590	2639	1.670	2867
1.515	2441	1.595	2653	1.675	2882
1.520	2453	1.600	2666	1.680	2897
1.525	2466	1.605	2680	1.685	2912
1.530	2479	1.610	2694	1.690	2928
1.535	2492	1.615	2708	1.695	2943
1.540	2505	1.620	2722	1.700 [2/]	2958
1.545	2518	1.625	2737	1.705	2973
1.550	2531	1.630	2751	1.710	2989
1.555	2544	1.635	2765	1.715	3004
1.560	2558	1.640	2780	1.720	3019
1.565	2571	1.645	2794	1.725	3035

[2/] Specification requirements end for this ordered thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-IV. Minimum required ballistic limits - caliber .30 AP M2 projectiles at 0° obliquity.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
0.980	1792	1.170	2016	1.360	2218
0.985	1798	1.175	2022	1.365	2223
0.990	1804	1.180	2027	1.370	2229
0.995	1810	1.185	2033	1.375	2234
1.001 1/	1817	1.190	2038	1.380	2239
1.005	1823	1.195	2044	1.385	2244
1.010	1829	1.200	2050	1.390	2249
1.015	1836	1.205	2055	1.395	2254
1.020	1842	1.210	2060	1.400	2259
1.025	1848	1.215	2066	1.405	2264
1.030	1854	1.220	2071	1.410	2269
1.035	1860	1.225	2077	1.415	2273
1.040	1866	1.230	2082	1.420	2278
1.045	1872	1.235	2088	1.425	2283
1.050	1878	1.240	2093	1.430	2288
1.055	1884	1.245	2098	1.435	2293
1.060	1890	1.250	2104	1.440	2298
1.065	1896	1.255	2109	1.445	2303
1.070	1902	1.260	2114	1.450	2308
1.075	1907	1.265	2120	1.455	2313
1.080	1913	1.270	2125	1.460	2318
1.085	1919	1.275	2130	1.465	2322
1.090	1925	1.280	2136	1.470	2327
1.095	1931	1.285	2141	1.475	2332
1.100	1937	1.290	2146	1.480	2337
1.105	1942	1.295	2151	1.485	2342
1.110	1948	1.300	2157	1.490	2347
1.115	1954	1.305	2162	1.495	2352
1.120	1960	1.310	2167	1.500	2356
1.125	1965	1.315	2172	1.505	2361
1.130	1971	1.320	2177	1.510	2366
1.135	1977	1.325	2183	1.515	2371
1.140	1983	1.330	2188	1.520	2376
1.145	1988	1.335	2193	1.525	2380
1.150	1994	1.340	2198	1.530	2385
1.155	2000	1.345	2203	1.535	2390
1.160	2005	1.350	2208	1.540	2394
1.165	2011	1.355	2213	1.545	2399

1/ Specification requirements begin for this ordered thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-IV. Minimum required ballistic limits - caliber .30 AP M2 projectiles at 0° obliquity - Continued.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
1.550	2404	1.720	2559	1.890	2705
1.555	2409	1.725	2563	1.895	2709
1.560	2413	1.730	2568	1.900	2713
1.565	2418	1.735	2572	1.905	2717
1.570	2423	1.740	2576	1.910	2722
1.575	2427	1.745	2581	1.915	2726
1.580	2432	1.750	2585	1.920	2730
1.585	2437	1.755	2590	1.925	2734
1.590	2441	1.760	2594	1.930	2738
1.595	2446	1.765	2598	1.935	2742
1.600	2450	1.770	2603	1.940	2746
1.605	2455	1.775	2607	1.945	2751
1.610	2460	1.780	2611	1.950	2755
1.615	2464	1.785	2616	1.955	2759
1.620	2469	1.790	2620	1.960	2763
1.625	2473	1.795	2624	1.965	2767
1.630	2478	1.800	2629	1.970	2771
1.635	2482	1.805	2633	1.975	2775
1.640	2487	1.810	2637	1.980	2779
1.645	2492	1.815	2641	1.985	2783
1.650	2496	1.820	2646	1.990	2787
1.655	2501	1.825	2650	1.995	2791
1.660	2505	1.830	2654	2.000 [2/]	2796
1.665	2510	1.835	2658	2.005	2800
1.670	2514	1.840	2663	2.010	2804
1.675	2519	1.845	2667	2.015	2808
1.680	2523	1.850	2671	2.020	2812
1.685	2528	1.855	2675	2.025	2816
1.690	2532	1.860	2680	2.030	2820
1.695	2537	1.865	2684	2.035	2824
1.700	2541	1.870	2688	2.040	2828
1.705	2545	1.875	2692	2.045	2832
1.710	2550	1.880	2697	2.050	2836
1.715	2554	1.885	2701	2.055	2840

[2/] Specification requirements end for this ordered thickness (See table A-V).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-V. Minimum required ballistic limits - caliber .50 AP M2 projectiles at 0° obliquity.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
1.950	2041	2.140	2168	2.330	2287
1.955	2045	2.145	2171	2.335	2290
1.960	2048	2.150	2174	2.340	2293
1.965	2051	2.155	2177	2.345	2296
1.970	2055	2.160	2180	2.350	2299
1.975	2058	2.165	2184	2.355	2303
1.980	2062	2.170	2187	2.360	2306
1.985	2065	2.175	2190	2.365	2309
1.990	2068	2.180	2193	2.370	2312
1.995	2072	2.185	2196	2.375	2315
2.001 1/	2075	2.190	2200	2.380	2318
2.005	2079	2.195	2203	2.385	2321
2.010	2082	2.200	2206	2.390	2324
2.015	2085	2.205	2209	2.395	2327
2.020	2089	2.210	2212	2.400	2330
2.025	2092	2.215	2216	2.405	2333
2.030	2095	2.220	2219	2.410	2336
2.035	2099	2.225	2222	2.415	2339
2.040	2102	2.230	2225	2.420	2342
2.045	2105	2.235	2228	2.425	2345
2.050	2109	2.240	2231	2.430	2348
2.055	2112	2.245	2234	2.435	2351
2.060	2115	2.250	2238	2.440	2354
2.065	2119	2.255	2241	2.445	2357
2.070	2122	2.260	2244	2.450	2360
2.075	2125	2.265	2247	2.455	2363
2.080	2128	2.270	2250	2.460	2366
2.085	2132	2.275	2253	2.465	2369
2.090	2135	2.280	2256	2.470	2372
2.095	2138	2.285	2259	2.475	2375
2.100	2142	2.290	2263	2.480	2378
2.105	2145	2.295	2266	2.485	2380
2.110	2148	2.300	2269	2.490	2383
2.115	2151	2.305	2272	2.495	2386
2.120	2155	2.310	2275	2.500	2389
2.125	2158	2.315	2278	2.505	2392
2.130	2161	2.320	2281	2.510	2395
2.135	2164	2.325	2284	2.515	2398

1/ Specification requirements begin for this ordered thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-V. Minimum required ballistic limits - caliber .50 AP M2 projectiles at 0° obliquity - Continued.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
2.520	2401	2.710	2510	2.900	2614
2.525	2404	2.715	2513	2.905	2617
2.530	2407	2.720	2516	2.910	2620
2.535	2410	2.725	2518	2.915	2622
2.540	2413	2.730	2521	2.920	2625
2.545	2416	2.735	2524	2.925	2628
2.550	2419	2.740	2527	2.930	2630
2.555	2421	2.745	2529	2.935	2633
2.560	2424	2.750	2532	2.940	2636
2.565	2427	2.755	2535	2.945	2639
2.570	2430	2.760	2538	2.950	2641
2.575	2433	2.765	2541	2.955	2644
2.580	2436	2.770	2543	2.960	2647
2.585	2439	2.775	2546	2.965	2649
2.590	2442	2.780	2549	2.970	2652
2.595	2445	2.785	2552	2.975	2654
2.600	2447	2.790	2554	2.980	2657
2.605	2450	2.795	2557	2.985	2660
2.610	2453	2.800	2560	2.990	2662
2.615	2456	2.805	2563	2.995	2665
2.620	2459	2.810	2565	3.000 [2/]	2668
2.625	2462	2.815	2568	3.005	2670
2.630	2465	2.820	2571	3.010	2672
2.635	2468	2.825	2574	3.015	2675
2.640	2470	2.830	2576	3.020	2677
2.645	2473	2.835	2579	3.025	2679
2.650	2476	2.840	2582	3.030	2681
2.655	2479	2.845	2585	3.035	2684
2.660	2482	2.850	2587	3.040	2686
2.665	2485	2.855	2590	3.045	2688
2.670	2487	2.860	2593	3.050	2690
2.675	2490	2.865	2595	3.055	2693
2.680	2493	2.870	2598	3.060	2695
2.685	2496	2.875	2601	3.065	2697
2.690	2499	2.880	2604	3.070	2699
2.695	2501	2.885	2606	3.075	2702
2.700	2504	2.890	2609	3.080	2704
2.705	2507	2.895	2612	3.085	2706

[2/] Class II and class III specification requirements end for this ordered thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-V. Minimum required ballistic limits - caliber .50 AP M2 projectiles at 0° obliquity - Continued.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
3.090	2708	3.285	2794	3.480	2877
3.095	2711	3.290	2796	3.485	2880
3.100	2713	3.295	2799	3.490	2882
3.105	2715	3.300	2801	3.495	2884
3.110	2717	3.305	2803	3.500	2886
3.115	2720	3.310	2805	3.505	2888
3.120	2722	3.315	2807	3.510	2890
3.125	2724	3.320	2809	3.515	2892
3.130	2726	3.325	2811	3.520	2894
3.135	2728	3.330	2814	3.525	2896
3.140	2731	3.335	2816	3.530	2898
3.145	2733	3.340	2818	3.535	2901
3.150	2735	3.345	2820	3.540	2903
3.155	2737	3.350	2822	3.545	2905
3.160	2740	3.355	2824	3.550	2907
3.165	2742	3.360	2827	3.555	2909
3.170	2744	3.365	2829	3.560	2911
3.175	2746	3.370	2831	3.565	2913
3.180	2748	3.375	2833	3.570	2915
3.185	2751	3.380	2835	3.575	2917
3.190	2753	3.385	2837	3.580	2919
3.195	2755	3.390	2839	3.585	2921
3.200	2757	3.395	2841	3.590	2923
3.205	2759	3.400	2844	3.595	2925
3.210	2762	3.405	2846	3.600	2928
3.215	2764	3.410	2848	3.605	2930
3.220	2766	3.415	2850	3.610	2932
3.225	2768	3.420	2852	3.615	2934
3.230	2770	3.425	2854	3.620	2936
3.235	2772	3.430	2856	3.625	2938
3.240	2775	3.435	2858	3.630	2940
3.245	2777	3.440	2861	3.635	2942
3.250	2779	3.445	2863	3.640	2944
3.255	2781	3.450	2865	3.645	2946
3.260	2783	3.455	2867	3.650	2948
3.265	2786	3.460	2869	3.655	2950
3.270	2788	3.465	2871	3.660	2952
3.275	2790	3.470	2873	3.665	2954
3.280	2792	3.475	2875	3.670	2956

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

APPENDIX A

TABLE A-V. Minimum required ballistic limits - caliber .50 AP M2 projectiles at 0° obliquity - Continued.

Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps	Thickness, inches	Required BL(P), fps
3.675	2958	3.850	3029	4.025	3098
3.680	2960	3.855	3031	4.030	3100
3.685	2962	3.860	3033	4.035	3102
3.690	2964	3.865	3035	4.040	3104
3.695	2967	3.870	3037	4.045	3106
3.700	2969	3.875	3039	4.050	3108
3.705	2971	3.880	3041	4.055	3110
3.710	2973	3.885	3043	4.060	3112
3.715	2975	3.890	3045	4.065	3114
3.720	2977	3.895	3047	4.070	3116
3.725	2979	3.900	3049	4.075	3118
3.730	2981	3.905	3051	4.080	3120
3.735	2983	3.910	3053	4.085	3122
3.740	2985	3.915	3055	4.090	3124
3.745	2987	3.920	3057	4.095	3125
3.750	2989	3.925	3059	4.100	3127
3.755	2991	3.930	3061	4.105	3129
3.760	2993	3.935	3063	4.110	3131
3.765	2995	3.940	3065	4.115	3133
3.770	2997	3.945	3067	4.120	3135
3.775	2999	3.950	3069	4.125	3137
3.780	3001	3.955	3071	4.130	3139
3.785	3003	3.960	3073	4.135	3141
3.790	3005	3.965	3075	4.140	3143
3.795	3007	3.970	3077	4.145	3145
3.800	3009	3.975	3079	4.150	3147
3.805	3011	3.980	3081	4.155	3149
3.810	3013	3.985	3083	4.160	3151
3.815	3015	3.990	3085	4.165	3152
3.820	3017	3.995	3087	4.170	3154
3.825	3019	4.000 3/,4/	3088	4.175	3156
3.830	3021	4.005	3090	4.180	3158
3.835	3023	4.010	3092	4.185	3160
3.840	3025	4.015	3094	4.190	3162
3.845	3027	4.020	3096	---	---

3/ Class I specification requirements end for this ordered thickness.

4/ For plates ordered in 4.001” to 6.000”, deduct 70fps from the required BL(P) of the final machined thickness; for plates ordered in 6.001” to 10.500”, deduct 100fps from the required BL(P) of the final machined thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Custodians:
Army - MR

Preparing activity:
ARMY - MR

(Project 9535-2021-003)

Review activities:
Army - AR, AT, AV, TE
DLA - IS

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:40Z
Check the source to verify that this is the current version before use.