MILITARY SPECIFICATION

DETERGENT, EXTERNAL REMOVABLE FUEL TANKS

This amendment forms a part of Military Specification MIL-D-81956A, dated 3 July 1980, and is approved for use by all Departments and Agencies of the Department of Defense

PAGE 2

3 2.2, delete in entirety and substitute:.

"3.2.2 Active ingredient concentration. The detergent shall contain up to 55% water and up to 0.5% corrosion inhibitor, with the balance of the cleaner being the active ingredient (see 4.7.2)."

3.3, delete in entirety and substitute:

"3 3 Effectiveness. When the detergent is tested as specified in 4.7 4, the reading obtained after the tank is cleaned shall be less than 10 parts per million (ppm)."

PAGE 6

4.7.4 1, delete in entirety and substitute:

"4.7.4.1 Safety check equipment. For checking the flammable vapors inside the tank, a Portable Gas Detection and Alarm System, Catalog No. 0023-7350, manufactured by Bacharach Instrument Co , a division of Ambac Industries or equivalent shall be used."

4.7.4.3, add the following to the end of the paragraph.

"Five hundred and twenty five ml of tap water shall be poured into the drum and the cap shall be closed The can shall be agitated so that all surfaces are coated with water. The drum shall be opened and drained by removing the drain plug A meter reading shall be taken and recorded "

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:29Z
Check the source to verify that this is the current version before use.

4.7.4.5, delete the last four lines and substitute:

"all the cleaner has drained thoroughly, the drum shall be filled three times with clear, warm water at approximately 29-35°C (85-95°F), and be allowed to drain thoroughly each time A check shall be made for the presence of combustible vapors and a meter reading shall be taken. The reading obtained in paragraph 4 7.4.3 shall be subtracted from this value. The final value obtained after subtraction shall not exceed 10ppm."

4 7.5. delete in entirety and substitute.

"4.7 5 Corrosion. Three specimen panels shall be used for this test. They shall conform to QQ-A-200/16 and be 6 inches x 1 inch x 0 050 inches thick The panels shall be cleaned by dipping in hot methyl alcohol, cool distilled water, and acetone, and dried for 1 hour at 100° ± 3°C (212° ± 5°F). Each panel shall then be weighed to the nearest tenth of a milligram (0.1 mg) and the weight recorded. The panels shall then be processed in the following manner. One panel shall be totally immersed in a 1:5 solution of the detergent in water Another panel in a 1.10 solution and the third panel in a 1 20 solution Immersion time shall be 4 hours at 25° ± 1°C (77° ± 2°F) After this time, each panel shall be removed, rinsed in deionized or distilled water, rinsed again with methyl alcohol, and dried for 1 hour at 100° ± 3°C (212° ± 5°F) The panels shall then be cooled to room temperature and reweighed to the nearest 0 1 mg and the weight recorded "

Custodians.
Army - AV
Navy - AS

Preparing Activity:
Navy - AS
Project No 7930-0375

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:29Z
Check the source to verify that this is the current version before use.