MILITARY SPECIFICATION

SHELTER AND ENTRANCE ASSEMBLY - CHEMICAL-BIOLOGICAL SHELTER SYSTEM: INFLATABLE

This amendment forms a part of MIL-S-51422B(EA), dated 24 September 1987, and is approved for use within the Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1.1: Under FEDERAL SPECIFICATIONS add the following:

"L-P-1040 - Plastic Sheets and Strips (Polyvinylfluoride)."

PAGE 4

3.1.3:

Lines 1 to 6 (inclusive): Delete these lines in their entirety and substitute the following:

"3.1.3 Window material. The material used in the windows shall be a homogeneous polyvinylfluoride laminate sheet 0.008 ± 0.001 inches thick formed by heat and pressure from a minimum of two sheets of material conforming to the requirements of type I, transparent, grade C, class I of L-P-1040 except for the following:

(1) The haze requirement for the single sheet is eliminated.

(2) The material is not limited to the 0.001 inch thickness.

In addition, the polyvinylfluoride laminate shall conform to the following requirements:"

Item (b): Delete in its entirety and substitute the following:

"(b) The window material shall maintain flexibility and there shall be no indication of cracking or delamination at either -25°F or -60°F when tested as specified in 4.4.10.2."

AMSC N/A FSC 4240

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.

4.4.10.2:

Line 4: Insert the following sentence after the words "...shall not be determined.":

"A second 4 inches by 4 inches specimen shall be exposed for 60 ± 10 minutes at a temperature of -25°F ± 1.8°F and tested as specified in Method 5874 of Fed. Test Method Std. 191 except that the hydrostatic resistance shall not be determined."

Lines 4 and 5:

Delete "Samples" and substitute "Both samples".

Delete "(if laminated)".

4.4.10.3, line 3: Delete "test" and substitute "tests".

Custodian:

Army - EA

Preparing activity:

Army - EA

Project No. 4240-A947

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.