DD-G-451C
AMENDMENT-4
June 15, 1972
SUPERSEDING
Int. Amendment-3(GSA-FSS)
September 27, 1971

FEDERAL SPECIFICATION

GLASS, PLATE, SHEET, FIGURED (FLOAT, FLAT, FOR GLAZING, CORRUGATED, MIRRORS AND OTHER USES)

This amendment, which forms a part of Federal Specification DD-G-451C, dated January 12, 1968, was approved by the Commissioner, Federal Supply Service, General Services Administration for use of all Federal agencies.

PAGE 5

Table II, column four. Opposite "gaseous inclusion", delete "1/64 inch" and substitute "1/16 inch". Opposite "Crush" in column four delete "Medium ^{C}" and substitute "Medium ^{e}".

PAGE 6

Table III. Delete "72" in the heading of column four and substitute "75".

PAGE 7

Table V. Opposite "wave, ream, strings, and lines" delete "45° C" and in its place substitute the following, and add the following for wave:

Defects	q4 AA quality		q5 A quality	
	Central	Outer	Central	Outer
Ream strings, and lines.	Light	Light	Light	Light
Wave	Medium	Medium	Medium	Medium

PAGE 8

Table VI. Opposite "wave, strings, and lines" delete "90°C and 45°C" and in its place substitute the following, and add the following for wave:

Defects	q6 B quality		q7 A silvering quality		q8 B silvering quality	
	Central	Outer	Central	Outer	Central	Outer
Ream strings, and lines.	Heavy	Heavy	Light	Light	Medium	Medium
Wave	Heavy	Heavy	Medium	Medium	Medium	Medium

Under "Notes" delete "(A), (B), (C), (E), (G)" and in its place substitute "(a), (b), (e), and (g)". Add notes (C) and (K) as follows:

(c) Intensity - ream, strings and lines. When evaluated using the shadowgraph the intensities of these defects are defined as having shadowgraph readout at distances greater than or equal to the following (see 4.4.4):

Intensity	Minimum distance	
	Inches	Centimeters
Medium	2	5.1
Heavy	1	2.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

(k) Intensity - wave. When evaluated using the shadowgraph the intensities of wave are defined as having shadowgraph readouts at distances greater than or equal to the following (see 4.4.4):

Intensity	Minimum distance	
	Inches	Centimeters
Medium	10	25.4
Heavy	6 or 8	15.2, 20.3

PAGE 9

Table VIII. Delete "1/64" opposite 5/16 in the minus column under tolerance, thickness and substitute "1/32".

PAGE 12

Table XI. Delete "Waveness, excessive".

Paragraph 4.3.2. Title, delete and in its place substitute" Ream, strings and distortion, type I." In the second line from the bottom delete "table II, III, V, and VI" and in its place substitute "tables II and III".

Paragraph 4.4.2. First sentence, delete "measure" between "transmittance" and "by illuminating".

PAGE 13

Add a new paragraph as follows:

4.4.4 Ream, strings, lines, and wave, type II, shadowgraph. Focus a light projector with a 500 watt lamp and an objective lens with an approximate 2 inch (5.1 cm.) aperture and an approximate 12 inch (30.5 cm.) focal length on a flat white projection screen positioned 25 feet (7.6 m) from the light source in a dark room. Place the glass in a vertical position parallel to the screen between the light and the screen. Move the glass slowly toward the screen with a vertical oscillating motion. The shadowgraph readout is the distance at which the distortion just blends with the general shadow of the glass on the screen (see table V and VI).

Paragraph 5.2.1. Add the following: and each container shall be marked on both sides with the words GLASS - DO NOT DROP OR THROW; GLASS-HANDLE WITH CARE; or a similar precautionary marking with letters a minimum of 1-inch high.

MILITARY INTEREST: Project No. 5620-0021

Custodians:

Army - ME
Navy - YD
Air Force - 84

Review activity:

MC

User activity:

CE, MI

Preparing activity:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.