INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

WOOD PRESERVATION: TREATING PRACTICES

This Interim Amendment was developed by the Department of Agriculture, Forest Service, Washington, DC 20250 based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized Federal agencies to use this Interim Amendment as a valid exception to Federal Specification TT-W-571I, dated October 28, 1968.

PAGE 9

Table III. Delete, and in its place substitute the attached new table.

PAGE 10

Footnote 1. Add the following at the beginning of the paragraph.

"All retentions are based on compositions composed of oxide formulations."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

TABLE III. Treatment of wood with water-borne preservatives

Form of product and service conditions	Assay zone	Minimum net retention of solid preservative [1]					Treating specifications [2] (AWPA Standard C1 and others listed below)
		Acid copper chromate (Fed. Spec. TT-W-546)	Ammoniacal copper arsenite (Fed. Spec. TT-W-549)	Chromated copper arsenate (Fed. Spec. TT-W-550) Type I, II, or III	Chromated zinc chloride (Fed. Spec. TT-W-551)	Fluor-chrome-arsenate-phenol mixture (Fed. Spec. TT-W-535) Type I or Type II	
	In.	Pcf.	Pcf.	Pcf.	Pcf.	Pcf.	
Timbers [2]							C2
For use under moderate weathering conditions [11]	gage only	0.50	0.40	0.40	0.61	0.31	
For use in protected locations not in ground contact	gage only	.25	.25	.25	.46	.22	
Timbers, glued laminated (including laminates prior to gluing)							C28
For use under moderate weathering conditions [11]	(5)	.50	.40	.40	.61	.31	
For use in protected locations not in ground contact	(5)	.25	.25	.25	.46	.22	
Lumber [2]							C2
For use under moderate weathering conditions [11]	0-5/8	.50	.40	.40	.61	.31	
For use in protected locations not in ground contact	0-5/8	.25	.25	.25	.46	.22	
Plywood							C9
For use under moderate weathering conditions [11]	(6)	.50	.40	.40	.61	.31	
For use in protected locations not in ground contact	(6)	.25	.25	.25	.46	.22	
Poles, round [7]							
Utility							C4
Southern and ponderosa pines	0.5-2.0	----	.6	.6	----	----	
Red pine	.1-1.6	----	.6	.6	----	----	
Jack and lodgepole pines	.1-.75	----	.6	.6	----	----	
Pacific Coast Douglas-fir	.25-1.0	----	.6	.6	----	----	
Inland Douglas-fir	.1- .6	----	.6	.6	----	----	
Western larch	.1- .6	----	.6	.6	----	----	
Western redcedar	.1- .6	----	.6	.6	----	----	
Building [9]	0-1.5	----	.70	.70	----	----	C23
Posts, round							
Fence [7]	gage only	.50	.40	.40	----	----	C5
Building [9]	0-1.5	----	.70	.70	----	---	C23

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.