A-A-51071
30 October 1986

COMMERCIAL ITEM DESCRIPTION

MIRROR, MOUTH EXAMINING, (Plastic, Plane Glass, Disposable)

The General Services Administration has authorized the use of this commercial item description in preference to Military Specification MIL-M-36552A.

This commercial item description covers a disposable mouth examining mirror suitable for patient use in preventive dentistry programs.

Salient characteristics:

The disposable mirror shall consist of a reflective glass disc securely encased in a one-piece molded plastic frame and handle. To provide for disc security, the top edge of the plastic frame shall be bent over the disc or, as an alternate, the frame shall be tapered inwardly to provide a force fit. The mirror face shall have a smooth reflective surface free from pits, scratches, cracks, ripples or other surface imperfections affecting reflectivity. The mirror frame and handle shall have a smooth finish free from sharp edges or projections.

The mirror glass shall be of good quality, polished glass. The composition used shall be capable of withstanding five (5) repeated soap and water washings witnout dulling the surface of the mirror. The back of the glass shall be coated with chemically deposited silver, protected by a film of electrolytically deposited copper. The copper surface shall be provided with a heavy coating of water-resistant enamel. The glass, silver, copper and enamel interfaces shall be firmly adherent. The front and back surfaces of the glass shall be flat and parallel. The reflective surface shall provide a clear undistorted image so that a patient can interpret results of flossing and brushing stained tooth areas under normal unintensified illumination.

Plastics used for the mirror frame and handle shall be acrylonitrile-butadiene-styrene (ABS) cellulose acetate, or polystyrene. The plastics shall have a minimum average Izod impact strength at 23^{0} Centigrade of 1.5 foot-pounds per inch of notch when tested in accordance with ASTM D256-81 and a minimum average tensile of 4000 pounds per square inch when tested in accordance with ANSI/ASTM D638-80.

The overall length of mirror shall be 6 $\pm$ 1/2 inch. The plane of the mirror head (face) shall be at 30 degrees $\pm$ 10 degrees to the major plane of the handle. The cross section of the handle shall be suitable for finger manipulation. The cross section of the neck shall be sufficient to maintain mirror integrity. The proximal end of handle shall have a suitable hole or slot or both. The mirror glass and coatings shall be a minimum of 0.050 inches to a maximum of 0.075 inches in thickness. The mirror head shall have a thickness of 0.10 to 0.15 inch. The diameter of exposed mirror face shall be 5/8 to 1 inch.

Workmanship. The mirror shall be free from defects which may affect proper functioning, appearance, or serviceability.

FSC 6520

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil - Downloaded: 2026-10-28T08:50Z
Check the source to verify that this is the current version before use.

Unit. Package (PG). One package containing seventy-two mirrors constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more inspection characteristics. The unit of product for inspection purposes shall be one mirror. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, AQL 2.5, and sampling for tests (when applicable) shall be conducted at inspection level S-1, AQL 1.0.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U. S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:50Z
Check the source to verify that this is the current version before use.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Number is covered by this document:

6520-00-935-4135	MIRROR, MOUTH EXAMINING, Plastic, Plane Glass, Disposable, 72s.

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians

Army-MD
Navy-MS
Air Force-03

CIVIL AGENCY COORDINATING ACTIVITY.

VA-OSS

PREPARING ACTIVITY:

DoD-NB

AGENT:

DLA-DH

4S651

Project No. 6520-1751

Location: S2-8-22

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:50Z
Check the source to verify that this is the current version before use.