MIL-W-63389 (AR)
AMENDMENT 4
25 MARCH 1983
SUPERSEDING
AMENDMENT 3
14 December 1982

MILITARY SPECIFICATION

WARHEAD, GUIDED MISSILE, HE, M207E1
LINER FOR

This Amendment forms a part of Military Specification MIL-W-63389 (AR), dated 7 January 1980, and is approved for use by the U.S. Army Armament Research and Development Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

* 2.1 DRAWINGS:

Delete "(SEE 6.4)"
Change title of drawing 9332524 from "Liner" to "Liner, Improved TOW" (Make this change in title wherever reference to drawing 9332524 appears)

PAGE 2

Add 3.5 as follows:

"3.5 Data Requirements: The contractor shall generate data in accordance with requirements of data item description cited in 6.4."

PAGE 6

* 4.4.2.1 Delete Page 6 and substitute pages 6 and 6A attached.

PAGE 7

* Add 6.4 as follows:

"6.4 Data Requirements. Contract data requirements will include DI-L-1410, Ammunition Data Card on DD Form 1423, Contract Data Requirements List."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:46Z
Check the source to verify that this is the current version before use.

FSC 1336

Paragraph	Data Requirement	Applicable DID"
6.5	Ammunition Data Card	DI-L-1410"

NOTE: The margins of this amendment are marked with an asterisk or vertical line to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1336-A 462)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:46Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-63389 (AR)
Amendment 4

PARAGRAPH	TITLE		SHEET 1 OF 2		DRAWING NUMBER 9332524
4.4.2.1	Liner, Improved TOW				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major					
101	Runout of base with datums A & B		0.25%	3.2	Gage
102	Length from base to datum B		0.40%	3.2	Gage
103	Length from datum A to datum B		0.40%	3.2	Gage
104	Straightness on large outside surface		0.25%	3.2	Gage
105	Wall thickness variation in any axial plane		0.25%	3.2	Gage
106	Wall thickness variation in any transverse plane (See Note 2)		100%	3.2	Gage
107	Length from datum B to inside spherical radius		0.40%	3.2	Gage
108	Length from datum B to basic dimension at apex end		0.40%	3.2	Gage
109	Length from large to small basic		0.40%	3.2	Gage
110	Wall thickness at large basic dimension at apex end		0.25%	3.2	Gage
111	Wall thickness at small basic dimension at apex end		0.25%	3.2	Gage
112	Outside diameter		0.25%	3.2	Gage
113	Runout of outside diameter with datums A & B		0.40%	3.2	Gage
114	Runout between two basic dimensions on outside surface at apex end (See Note 8 on Dwg.)		0.25%	3.2	Gage

NOTES:

2. Measurements shall be taken on both 42° and 28° angle surfaces.

DRDAR-QA Form 160 Jul 77

Source: https://assistdamir... Downloaded: 2026-10-25T02:46:47
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-W-63389 (AR)
Amendment 4

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.1	Liner, Improved TOW	2 OF 2	9332524
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined (Cont'd)				
115	Wall thickness at apex end		0.40%	3.2	Gage
116	Inside diameter		0.40%	3.2	Gage
117	Length of liner step		0.40%	3.2	Gage
118	Wall thickness in area as shown by notes 4 and 5 on dwg.		0.40%	3.2	Gage
119	Evidence of discontinuity of machined surface		100%	3.2	Visual
Minor					
201	Surface finish improper		0.65%	3.2	Gage
202	Evidence of poor workmanship		1.00%	3.2	Visual
203	Presence of four slots		0.65%	3.2	Visual
204	Inside spherical radius, apex (See Note 1)		0.65%	3.2	Gage
205	Outside spherical radius, apex		0.65%	3.2	Gage

NOTE: 1. All new and resharpened tooling shall be certified prior to use. A cast of the inside spherical radius of the liner shall be made from "dental plaster" or equivalent, which shall be inspected by an optical comparator of 10X magnification or greater. This inspection shall be performed at the beginning of the shift, half way through the shift and whenever tooling is changed.

NOTES:

DRDAR-QA Form 160 Jul 77

Source: https://assist.dla.mil -- Downloaded: 2026-10-03T02:26Z
Check the source to verify that this is the current version before use.