MIL-C-44103A
AMENDMENT-1
9 July 1986

MILITARY SPECIFICATION

CLOTH, DUCK, POLYESTER, FIRE, WATER AND WEATHER RESISTANT

This amendment forms a part of Military Specification MIL-C-44103A, dated 6 August 1985, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 2

2.3: Delete and substitute:

"2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this document shall take precedence. Nothing in this document, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained."

PAGE 3

3.1, line 2, after "and shall": Add ", unless otherwise indicated (see 3.5.2),".

PAGE 4

3.5.1.1, line 1: Delete "Forest Green 433" and substitute: "Camouflage Green 483".



DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-21T23:54Z
Check the source to verify that this is the current version before use.

PAGE 4 (cont'd)

Table II: Delete and substitute:

"TABLE II. Spectral reflectance requirements for Camouflage Green 483

| Wavelengths Nanometers | Reflectance factors (percent) Max. | Min. |
|---|---|---|
| 600 | 12 | 5 |
| 620 | 12 | 5 |
| 640 | 12 | 5 |
| 660 | 13 | 5 |
| 680 | 15 | 7 |
| 700 | 21 | 12 |
| 720 | 30 | 20 |
| 740 | 42 | 30 |
| 760 | 50 | 39 |
| 780 | 56 | 45 |
| 800 | 60 | 47 |
| 820 | 63 | 49 |
| 840 | 65 | 50 |
| 860 | 66 | 51" |

Table III: Delete all minimum reflectance values for wavelengths 700 through 860 nanometers and substitute "45" respectively.

PAGE 5

3.5.2 and 3.5.2.1: Delete and substitute:

"3.5.2 Colorfastness. The finished cloth shall show fastness to accelerated weathering equal to or better than the standard sample or equal to or better than the rating of 'fair' when tested as specified in 4.2.3. The cloth shall show fastness to dry-crocking equal or better than the standard sample or shall have an AATCC Chromatic Transference Scale rating not lower than 1.5 when tested as specified in 4.2.3."

Table IV, under "Spray rating": Delete the "After weathering" requirement in entirety.

"Dynamic absorption, percent", for "Initial" and "After weathering": Delete maximum values of "25" and substitute "10".

PAGE 6

Table V: Delete requirements for "After-flame time, seconds (Method 5903)" and "Char length, inches (Method 5903)" in entirety.



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:54Z
Check the source to verify that this is the current version before use.

PAGE 6 (cont'd)

3.6.3, line 2: Delete "0.013" and "0.032" and substitute: "0.020" and "0.040" respectively.

PAGE 7

Add the following:

"4.1.2 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material."

PAGE 9

4.2.3, third sentence: Delete and substitute:

"The physical and chemical values specified in section 3 apply to the results of the determination made on the sample unit for test purposes, as specified in applicable test method. The sample unit shall be 5 continuous yards full width."

Table VI, line 12, after "Weathering": Delete "(after 300 hours)" and substitute "(after 100 hours)".

Line 13, in "Requirement paragraph" column: Delete "3.5.2.1" and substitute "3.5.2".

In "test method" column, after "5671": Add "5/".

PAGE 10

Table VI, for "Water repellency: Spray rating": Delete the "After weathering" entry in entirety.

For "Flame-resistance": Delete "After-flame time (Method 5903)" and "Char length" entries in entirety.

For "After-flame time (Method 5905): Initial", in Test method column, after "5905": Add "4/".

Footnote 3/: Delete "ten", "five", and "five" and substitute: "eight", "four" and "four" respectively.



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:54Z
Check the source to verify that this is the current version before use.

Table VI: Add the following footnote: "5/ Except that the filters shall be removed".

4.3.1, line 2: Delete "Forest Green 433" and substitute: "Camouflage Green 483".

Custodians:

Army - GL
Navy - NU

Review activities:

Army - MD
Navy - MC
DLA - CT

Preparing activity:

Army - GL

Project No. 8305-0087



Source: https://assist.dla.mil -- Downloaded: 202640-21T23:54Z
Check the source to verify that this is the current version before use.