MIL-P-28577A(YD)

10 June 1977

SUPERSEDING
MIL-P-28577(YD)
14 May 1971

MILITARY SPECIFICATION

# PRIMER, LATEX, CORROSION RESISTANT, FOR METAL SURFACES

**This specification is approved for use by the Naval Facilities Engineering Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.**

## 1. SCOPE

1.1 Scope. This specification covers a latex, corrosion-resistant primer suitable for use on exterior and interior metal surfaces for maintenance applications. (See 6.1).

## 2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

| | |
|---|---|
| TT-E-506 | - Enamel, Alkyd, Gloss, Tints and White |
| PPP-P-1892 | - Paint, Varnish, Lacquer, and Related Materials; Packaging, Packing, and Marking of. |
| PPP-T-60 | - Tape: Pressure-Sensitive Adhesive; Waterproofing (For Packaging). |

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Facilities Engineering Command, Code 0432, 200 Stovall Street, Alexandria, VA 22332, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-P-28578 - Paint, Water Reducible, Semi-Gloss, Exterior and Interior

STANDARDS

FEDERAL

FED-STD-141 - Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling and Testing

FED-STD-595 - Colors

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

B117 - Salt Spray (Fog) Testing.

D562 - Consistency of Paints Using the Stormer Viscosimeter.

D609 - Preparation of Steel Panels for Testing Paint, Varnish, Lacquer and Related Products

D1475 - Density of Paint, Varnish, Lacquer and Related Products.

D2247 - Coated Metal Specimens at 100 Percent Relative Humidity.

D2486 - Scrub Resistance of Interior Latex Flat Wall Paints.

D3273 - Resistance of Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber.

D3335 - Low Concentrations of Lead in Paint by Atomic Absorption Spectrophotometry.



Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Materials. Materials shall be as specified herein. Materials not specified shall be selected by the supplier and shall be subject to all the provisions of this specification. The primer shall be free of materials that would be toxic to personnel under normal conditions of use.

3.2 Composition.

3.2.1 Pigment. The pigment portion of the primer shall include an anti-corrosive pigment such as basic calcium zinc molybdate or barium metaborate. Latitude is given in the selection of hiding and extender pigments, provided that the other requirements of this specification are met. Tinting pigments may be used to match the color desired (see 6.2), provided that the other requirements of this specification are met.

3.2.2 Vehicle. The vehicle shall consist of an acrylic or modified acrylic copolymer produced by emulsion polymerization. Minimum amounts of necessary additives such as oil or alkyd vehicles, preservatives, antifoam agents, and pigment dispersants may be added provided that the other requirements of this specification are met.

3.3 Quantitative requirements. The primer shall conform to the quantitative requirements of Table I.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

TABLE I. Quantitative Requirements of the Primer

| Characteristics | Requirements | |
|---|---|---|
| | Minimum | Maximum |
| Pigment, percent by weight of primer | 30 | 35 |
| Nonvolatile organic material, percent by weight or primer | 25 | -- |
| Weight per gallon, pounds | 10 | 11 |
| Consistency, Krebs-Stormer, shearing rate 200 r/min | | |
| Grams | 125 | 175 |
| Equivalent Krebs Units (K.U.) | 65 | 75 |
| Drying time | | |
| Set to touch, hours | -- | 1/2 |
| Dry hard, hours | -- | 6 |
| Scrub resistance, cycles | 500 | -- |
| Lead, metal, percent by weight of non-volatile matter | --- | 0.06 |

3.4 Qualitative requirements.

3.4.1 Color. The color shall be as specified in the procurement document (see 6.2) and tinted to a practical match to FED-STD-595.

3.4.2 Condition in container. The paint, as received, shall be ready-mixed and shall show no evidence of mold growth, livering, skinning, putrefaction, rust from corrosion of the container, or hard settling of the pigment. Any settled pigment shall be readily dispersible in the liquid portion by hand stirring to form a smooth homogeneous paint, free from persistent foam.

3.4.3 Storage stability. The primer, as received, shall withstand the freeze-thaw test and the heat storage test described in 4.2.4 with a viscosity change not greater than 5 K.U. After completion of these tests, the primer applied to a glass panel shall dray to a smooth, uniform finish.



Source: https://assist.dla.mil -- Downloaded: 202640-20T13:17Z
Check the source to verify that this is the current version before use.

3.4.4 Mechanical stability. When tested as specified in 4.2.5, the primer shall show no coagulation or flocculation.

3.4.5 Application properties.

3.4.5.1 Working properties. The primer shall be easily applied by brush, roller or spray equipment. When tested as described in 4.2.6, the primer shall brush easily at package consistency and shall permit lapping without difficulty. When dry the surface shall present a smooth, uniform appearance without streaking, conspicuous laps, or objectionable brush marks.

3.4.5.2 Recoating properties. After the primed surface has been recoated and after two hours air drying, as specified in 4.2.6, the film shall show no irregularity. There shall be no picking or rolling up of the previous coat.

3.4.6 Film irregularity. When tested as specified in 4.2.7, the primer shall show no mud-cracking or other film irregularity.

3.4.7 Fungus resistance. When primer coated panels are examined as specified in 4.2.8, they shall have a rating of 6 or greater as described in ASTM D3273.

3.4.8 Flexibility. The primer, tested as described in 4.2.9, shall show no evidence of cracking, chipping, or flaking.

3.4.9 Adhesion. A film of the primer when tested as described in 4.2.10, shall show no removal of the primer by the adhesive tape beyond 2 mm (1/16 inch) on either side of the score line.

3.4.10 Wet adhesion. A film of the primer when tested as described in 4.2.11, shall show no adhesion failure between primer and alkyd undercoat.

3.4.11 Flash rusting resistance. When tested as described in 4.2.12, the primer shall show no rust bleed through or underfilm corrosion.

3.4.12 Humidity resistance. The coating system prepared as described in 4.2.13, after exposure to 100 percent humidity conditions for 250 hours shall show no rust bleed through, no blisters greater than size 6 and of medium density, and no greater than 3 mm (1/8 inch) rust creepage from the scribed.

3.4.13 Salt spray resistance. The coating system prepared as described in 4.2.14, after exposure to 5 percent salt spray for 250 hours shall show no blisters greater than size 6 and of medium density, and no greater than 3 mm (1/8 inch) rust creepage from the scribe.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

## 4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the Contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the Contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Sampling and inspection. Sampling and inspection shall be in accordance with Method 1031 of FED-STD-141.

4.2 Tests. Samples selected in accordance with 4.1.1 shall be tested as specified in Table II and 4.2.1 through 4.2.14. Nonconformance to the requirements of the applicable test methods or failure to pass any test shall be cause for rejection of the lot which the sample represents.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

TABLE II. Index

| Characteristic | Requirement Preference | Test Method | Paragraph Reference |
|---|---|---|---|
| Pigment | Table I | | 4.2.1 |
| Nonvolatile organic material | Table I | | 4.2.1 |
| Weight per gallon | Table I | D1475[1/], 4184[2/] | |
| Consistency | Table I | D562[1/], 4281[2/] | |
| Drying time | Table I | 4061[2/] | |
| Scrub resistance | Table I | D2486[1/] | |
| Lead content | Table I | D3335[1/] | |
| Color | 3.4.1 | 4250[2/] | 4.2.2 |
| Condition in container | 3.4.2 | 3011[2/] | 4.2.3 |
| Storage stability | 3.4.3 | | 4.2.4 |
| Mechanical stability | 3.4.4 | | 4.2.5 |
| Working properties | 3.4.5.1 | 4321[2/] | 4.2.6 |
| Recoating properties | 3.4.5.2 | | 4.2.6 |
| Film irregularity | 3.4.6 | | 4.2.7 |
| Fungus resistance | 3.4.7 | D3273[1/] | 4.2.8 |
| Flexibility | 3.4.8 | 6221[2/] | 4.2.9 |
| Adhesion | 3.4.9 | | 4.2.10 |
| Wet adhesion | 3.4.10 | | 4.2.11 |
| Flash rusting resistance | 3.4.11 | | 4.2.12 |
| Humidity resistance | 3.4.12 | D2247[1/] | 4.2.13 |
| Salt spray resistance | 3.4.13 | D117[1/] | 4.2.14 |

1/ ASTM.
2/ FED-STD-141



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

4.2.1 Pigment and nonvolatile organic materials. Spread thinly approximately 5 grams of well-mixed primer sample over the surface of a tared petri dish of borosilicate glass, approximately 100 mm in diameter, and obtain exact weight. Dry in a vented regular oven at 105 ± 2°C (220 ± 5°F) to constant weight. (This requires overnight drying.) After obtaining the weight of the total nonvolatile material, ash in a muffle furnace, raising temperature gradually to 450-500°C (840-930°F). Allow 2 hours for complete combustion of the organic material. The furnace door should be opened carefully when removing sample as the remaining pigment is very light and easily scattered. Place sample in desiccator and cool to room temperature. Obtain the weight of the ashed material.

4.2.1.1 Calculations.

Wt. of total nonvolatile material - wt. of ashed material = wt. of nonvolatile organic material

$$\frac{\text{wt. of ash} \times 100}{\text{total wt. of sample}} = \text{pigment, percent by wt. of primer}$$

$$\frac{\text{wt. of nonvolatile organic material} \times 100}{\text{total wt. of sample}} = \text{nonvolatile organic material, percent by wt. of primer.}$$

4.2.2 Color. The primer shall be applied to a clean, smooth, plate-glass panel with a 0.003 inch (approximately 0.006 inch gap clearance) Bird film applicator or similar blade which produces the same film thickness. Allow the film to dry for 24 hours. Compare the color of the dried film in accordance with Method 4250 of FED-STD-141.

4.2.3 Condition in container. Examine the primer as received in accordance with Method 3011 of FED-STD-141 for compliance with 3.4.2.

4.2.4 Storage stability.

4.2.4.1 Specimens and exposure. Fill two resin-lined friction-top cans with the sample as received, and close the cans tightly. Expose one can and contents three times to the following freeze-thaw cycles:

a. Low temperatures of -9 ± 2°C (15 ± 3°F) for 16 hours.

b. High temperatures of 25 ± 3°C (77 ± 5°F) for 8 hours.

Store the other can and contents in an over at 50°C (120°F) for two weeks.



Source: https://assist.dla.mil -- Downloaded: 202610-20T13:17Z
Check the source to verify that this is the current version before use.

4.2.4.2 Procedure.

a. At the completion of the exposure measure the consistency (ASTM D562) of both specimens and compare with the original consistency to determine compliance with 3.4.3.

b. Brush each primer specimen on a glass panel and observe while brushing and after drying whether the panel is normal and usable in all respects. Compare with the unexposed primer with respect to freedom from coagulation, agglomeration, speckiness and change in sheen or color.

4.2.5 Mechanical stability. Fill a quart resin-lined friction top can 3/4 full with the primer and close the can tightly. Rotate on a jar roller[1/] for one week. Compare with the unexposed primer with respect to freedom from coagulation, flocculation or change in consistency greater than 10 percent of the unexposed primer.

4.2.6 Working properties. Determine the brushing properties in accordance with Method 4331 of FED-STD-141. For the substrate, use cold rolled steel panels[2/] conforming to ASTM D609, Type 1, prepared for coating by Method D, and brush to a wet film thickness of approximately 3 mils. After two hours air drying, apply a second coat of the primer in the same manner as the first coat. Examine the film for picking and rolling up of the first coat during application. After 24 hours, examine the dried film for any irregularities.

4.2.7 Film irregularity. Apply one coat of the primer to a cold rolled steel panel conforming to ASTM D609, Type 1, prepared for coating by Method D, with a 0.007 inch (approximately 0.015 inch gap clearance) film applicator. Allow the film to dry in a horizontal position for 24 hours. Examine the film for mud-cracking or other film irregularities for compliance with 3.4.6.

4.2.8 Fungus resistance. Test the primer in accordance with ASTM D3273 for compliance with 3.4.7.

4.2.9 Flexibility. The primer film shall be applied to an electrolytic tin plate panel[2/] prepared in accordance with Method 2012 of FED-STD-141. Draw down a film using a 0.002 inch (approximately 0.004 inch gap clearance) film applicator. Air dry for 24 hours at a temperature of 23 ± 1°C (73 ± 2°F), then heat for 3 hours at 105 ± 2°C (220 ± 5°F).

1/ Available from Norton Chemical Process Product Division, formerly U.S. Stoneware Inc., Akron, OH 44309

2/ Available from the Q-Panel Company, 15601 Industrial Parkway, Cleveland, OH 44135



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

After heating, condition the panel for 30 minutes at 23 ± 1°C (73 ± 2°F) and relative humidity of 50 ± 4 percent. Bend the panel over a 6-mm (1/4-inch) mandrel and examine in accordance with Method 6221 of FED-STD-141 for compliance with 3.4.8.

4.2.10 Adhesion (Tape Method). The primer shall be applied to a cold rolled steel panel conforming to ASTM D609, Type 1, prepared for coating by Method D. Draw down a film using a 0.003 inch (approximately 0.006 inch gap clearance) film applicator and allow to dry at room temperature for 72 hours. Score a line to the metal substrate across the width of the film using a sharp knife. Apply pressure sensitive tape, conforming to PPP-T-60, perpendicular to and across the score line and extending it approximately 25 mm (one inch) on each side of the score line. Press the tape, using a rubber roller, in a firm contact with the primer coating. Grasp a free end of the tape, and as rapidly as possible, strip it from the panel by pulling the tape back on itself at an angle of 180°. Observe for compliance with 3.4.9.

4.2.11 Wet adhesion. Prepare the panels in accordance with Method 6142 of FED-STD-141, except use enamel conforming to TT-E-506 as undercoat. Apply the primer by drawdown as above in a direction perpendicular to the long axis of the panel to obtain a dry film thickness of 0.002 inch and a width of approximately 50 mm (2 inches). Allow the primer to dry for 48 hours at 23 ± 1°C (73 ± 2°F) and relative humidity of 50 ± percent. Make a cut (the entire width of the test panel) perpendicular to the long axis of the glass panel through the center of the test film with a sharp knife held at a 45o angle. Place the panel on the apparatus described in Method 6141 of FED-STD-141 so that the test primer is approximately in the center of the brush stroke and scrub the water-immersed panel with the brush described in Method 6142 of FED-STD-141. The brush shall move in a direction parallel to the long axis of the glass and perpendicular to the cut made in the test film. The brush shall travel at a rate of 37 ± 2 cycles per minute (74 separate strokes ± four strokes per minute) for 500 cycles. Observe for compliance with 3.4.10.

4.2.12 Flash rusting resistance. The primer shall be applied to a cold rolled steel panel conforming to ASTM D609, Type 1, prepared for coating by Method D. Draw down a film using a 0.003 inch (approximately 0.006 inch gap clearance) film applicator. Allow the coated panel to dry in a horizontal position for 48 hours at 23 ± 1°C (73 ± 2°F) and relative humidity of 80 ± 5 percent. Examine the film for flush rusting or bleed rusting. Remove a portion of the dried primer with a suitable organic solvent and examine for underfilm corrosion. Observe for compliance with 3.4.11.

4.2.13 Humidity resistance.

4.2.13.1 Panel preparation. Test panels shall be 75 by 200 mm (3 by 8 inches) cold rolled steel panels conforming to ASTM D609, Type 1, prepared



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

for coating by Method D. The panels shall be coated with two coats of primer and one finish coat of paint conforming to MIL-P-28578, using a 0.003 inch (approximately 0.006 inch gap clearance) film applicator. Dry time between coats is 24 hours and the finished panels shall be cured one week before scribing and exposure. A 50 mm (2 inch) "X" shall be scribed to the metal on the lower half of the panel before exposure testing. The cut edges of the panels shall be protected with a suitable coating stable under the conditions of the test, such as carnauba wax.

4.2.13.2 Exposure testing. Place the panels, coated side down in a humidity cabinet as described in ASTM D2247 1/. Use a continuous condensation cycle and a 38 ± 1°C (100 ± 2°F) air temperature for 250 hours. Observe the exposed panels for compliance with 3.4.12.

4.2.14 Salt spray resistance. Panel preparation for this test is that described in 4.2.13.1. Place the panels in an exposure cabinet as described in ASTM B117 using a 5 percent salt solution. Expose the panels for 250 hours. Observe the exposed panels for compliance with 3.4.13.

4.3 Inspection of packaging. The preservation, packing, and marking of the primer shall be inspected to determine conformance to the requirements of Section 5 of this specification.

5. PACKAGING

5.1 Preservation, packing and marking. The primer shall be preserved, packed, and marked in accordance with PPP-P-1892. The level of preservation shall be A, B, or C, and the level of packing shall be A, B, or C, as specified (see 6.2). The primer shall be furnished in 1-liter or 4-liter (1-quart or 1-gallon) multiple friction plug metal cans, in 20 liter (5-gallon) lug cover steel pails, or in 1750 liter (55-gallon) full removable cover metal drums, as specified (see 6.2). All containers shall be resin-lined.

6. NOTES

6.1 Intended use. This specification covers the primer of a water reducible coating system for medium performance applications consisting of two coats of primer and one coat of semi-gloss paint. The primer is intended for interior and exterior use over bare or previously coated metal surfaces. The primer may be used in damp areas or used as an alternate to Rule 442. It is highly recommended that the primer be of a different color or tint than the top coat paint to assure application of an adequate coating system.

1/ A suitable cabinet is available from the Q-Panel Company, 15601 Industrial Parkway, Cleveland, OH 44135.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

6.2 Ordering data.

6.2.1 Procurement requirements. Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Color required (see 3.4.1)
c. Level or preservation and level of packing required (see 5.1)
d. Quantities to be packaged (see 5.1)

6.2.2 Contract data requirements. When this specification is used in a procurement which incorporates a DD Form 1423 and invokes the provisions of paragraph 7-104.9 (n) of the Armed Services Procurement Regulation, the data requirements identified below will be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved Contract Data Requirements List (DD Form 1423) incorporated into the contract. When the provisions of ASPR 7-104.9 (n) are not invoked, the data specified below shall be delivered in accordance with the contract requirements. Deliverable data required by this specification is cited in the following paragraph:

| Paragraph | Data Requirement | Applicable DD 1664 |
|---|---|---|
| 4.1.1 | Certificate of Compliance | DI-E-2121 |

(Copies of Data Item Descriptions required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)



Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.

6.3 Formulation. Typical formulations that meet this specification are given in Tables IIIa and IIIb.

TABLE IIIa. Typical Formulation for 100 Gallons of Primer

| Constituent | Amount (Pounds) |
|---|---|
| Water-ground mica, 325 mesh | 24.70 |
| Calcium Carbonate (precipitated grade) | 222.27 |
| Red Iron Oxide | 49.39 |
| Basic Calcium Zinc Molybdate 1/ | 49.39 |
| Zinc Oxide 2/ | 11.85 |
| Linseed Oil (Pure Raw) | 56.01 |
| Acrylic Copolyer Vehicle (45.4% T.S.) 3/ | 458.56 |
| Thickener, defoamer, pigment dispersant, driers, wetting agent ethylene glycol and coalescent 4/ | 60.91 |
| Water | 151.58 |
| Mildewcide 5/ | 2.14 |
| Total | 1086.80 |

1/ Molywhite 212, Sherwin Williams Comp. Pigments Division.
2/ Kadox 515, New Jersey Zinc.
3/ Rhoplex MV-9, Rohm and Haas Company, Phila., PA.
4/ As required to produce necessary properties.
5/ Skane M-8, Rohm and Haas Company, Phila., PA.



Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.

TABLE IIIb - Typical Formulation for 97.7 Gallons of Primer

| Constituent | Amount (Pounds) |
|---|---|
| Water | 248.0 |
| Thickener1/ | 3.5 |
| Potassium Tripolyphosphate (KTPP) | 1.0 |
| Dispersant2/ | 6.0 |
| Ethylene Glycol | 30.0 |
| Filming Aid3/ | 12.0 |
| Dibutyl Phthalate | 8.0 |
| Wetting Agent4/ | 3.0 |
| Flash Rust Inhibitor5/ | 10.0 |
| Defoamer6/ | 2.0 |
| Preservative7/ | 1.5 |
| Titanium Dioxide8/ | 150.0 |
| Inhibitive Pigment9/ | 100.0 |
| Disperse in high-speed mill; then add the following constituents: | |
| Resin10/ | 353.0 |
| Defoamer6/ | 1.0 |
| Water | 95.0 |
| Total | 1024.0 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

1/ Collosize Hydroxgethyl Collulose QP-1500, Union Carbide, New York, N. Y.
2/ Tamol 850 Rohm and Haas, Phila., PA.
3/ Dalpad A, Dow, Midland, MI.
4/ Igepal CO-630, GAF, Newark, N. J. or equal.
5/ Drew XPD 11-043-2, Drew Chemical, Boonton, N. J.
6/ Balab 748, Witco, New York, N. Y. or equal.
7/ Dowicil 75, Dow, Midland, MI or equal
8/ Ti-Pure R960, DuPont, Wilmington, DE or equal.
9/ Nalzin SC-1, NL Industries, Newark, N.J.
10/ UCAR Vehicle 4358, Union Carbide, New York, N. Y.

6.4 Unit of purchase. The primer should be purchased by volume, the unit being one U. S. gallon of 231 cubic inches (approximately 3.7 liters) at 68°F (20°C) until IS packages are available.

Preparing Activity

Navy - YD

(Project Number 8010-N131)



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID



OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander (Code 0432)
Naval Facilities Engineering Command
200 Stovall Street
Alexandria, VA 22332

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL-P-28577A(YD) PRIMER, LATEX, CORROSION RESISTANT, FOR METAL SURFACES

| NAME OF ORGANIZATION AND ADDRESS | CONTRACT NUMBER |
|---|---|
| | MATERIAL PROCURED UNDER A<br>☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT |

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

| SUBMITTED BY *(Printed or typed name and address - Optional)* | TELEPHONE NO. |
|---|---|
| | DATE |

**DD FORM 1 JAN 72 1426** REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.