MIL-P-28578A(YD)
10 June 1977

SUPERSEDING
MIL-P-28578(YD)
14 May 1971

MILITARY SPECIFICATION

PAINT, WATER REDUCIBLE, SEMI-GLOSS, EXTERIOR AND INTERIOR

This specification is approved for use by the Naval Facilities Engineering Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a water reducible, semi-gloss paint for use on exterior and interior metal surfaces treated with a primer conforming to MIL-P-28577. (See 6.1).

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

TT-E-506	- Enamel, Alkyd, Gloss, Tints and White.
PPP-P-1892	- Paint, Varnish, Lacquer, and Related Materials; Packaging, Packing, amd Marking of.

MILITARY

MIL-P-28577	- Primer, Water Reducible, Corrosion Resistant, for Metal Surfaces.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Facilities Engineering Command, Code 0432, 200 Stovall Street, Alexandria, VA 22332, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-141 - Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling and Testing.

FED-STD-595 - Colors

(Copies of specifications, standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

B117 - Salt Spray (Fog) Testing

D476 - Titanium Dioxide Pigments

D562 - Consistency of Paints Using the Stormer Viscosimeter

D609 - Preparation of Steel Panels for Testing Paint, Varnish Lacquer and Related Products

D1475 - Density of Paint, Varnish, Lacquer and Related Products

D2247 - Coated Metal Specimens at 100 Percent Relative Humidity

D2486 - Scrub Resistance of Interior Latex Flat Wall Paints

D3273 - Resistance of Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber

D3335 - Low Concentrations of Lead in Paint by Atomic Absorption Spectrophotometry.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Materials: Materials shall be as specified herein. Materials not specified shall be selected by the supplier and shall be subject to all the provisions of this specification. The paint shall be free of material that would be toxic to personnel under normal conditions of use.

3.2 Composition.

3.2.1 Pigment. The opaque white pigment portion of white and tinted paints shall consist of chalk-resistant rutile titanium dioxide conforming to ASTM D476, Type III or IV for white paints and Type IV only for tinted paints. Tinting pigments shall be lightfast and alkali resistant. Latitude is given in the selection of extender pigments provided other requirements of this specification are met.

3.2.2 Vehicle. The vehicle shall consist of an acrylic or modified acrylic copolymer produced by emulsion polymerization (See 4.2.14). Minimum amounts of necessary additives such as preservatives, antifoam agents, and pigment dispersants may be added provided that the other requirements of this specification are met.

3.3 Quantitative requirements. The paint shall conform to the quantitative requirements of Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

TABLE I. Quantitative Requirements of the Paint

Characteristics	Requirements Minimum	Maximum
Pigment, percent by weight of paint	20	25
Titanium dioxide pigment, pounds per gallon of white paint	2.0	---
Nonvolatile organic material, percent by weight of paint	25	---
Weight per gallon, pounds	10	11
Consistency, Krebs-Stormer, shearing rate 200 r/min		
Grams	100	175
Equivalent Krebs Units (K.U.)	60	75
Fineness of grind	6	---
Drying time		
Set to touch, hours	---	1
Dry hard, hours	---	24
Daylight directional reflectance, white only, percent	85	---
Gloss, specular, 60°	40	60
Opacity, dry, contrast ratio (0.005 inch wet film thickness)		
White paint	0.97	---
Tinted paint	0.99	---
Scrub resistance, cycles	600	---
Lead, metal, percent by weight of nonvolatile matter	---	0.06

Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.

3.4 Qualitative requirements.

3.4.1 Color. The color shall be as specified in the procurement document (see 6.2). When tested as in 4.2.2, the color shall match standard chip in FED-STD-595.

3.4.2 Condition in container. The paint, as received, shall be ready-mixed and shall show no evidence of mold growth, livering, skinning, putrefaction, rust from corrosion of the container, or hard settling of the pigment. Any settled pigment shall be readily dispersible in the liquid portion by hand stirring to form a smooth homogeneous paint, free from persistent foam.

3.4.3 Storage stability. The paint, as received, shall withstand the free-thaw test and the heat storage test described in 4.2.4 with a viscosity change not greater than 5 K.U. After completion of these tests, the paint applied to a glass panel shall dry to a smooth uniform finish.

3.4.4 Mechanical stability. When tested as specified in 4.2.5, the paint shall show no coagulation or flocculation.

3.4.5 Application properties.

3.4.5.1 Working properties. The paint shall be easily applied by brush, roller or spray equipment. When tested as described in 4.2.6, the paint shall brush easily at package consistency and shall permit lapping without difficulty. When dry, the surface shall present a smooth, uniform appearance without streaking conspicuous laps, or objectionable brush marks.

3.4.5.2 Recoating properties. After the painted surface has been recoated and after two hours air drying, as specified in 4.2.6, the film shall show no irregularity. There shall be no picking or rolling up of the previous coat.

3.4.6 Film irregularity. When tested as in 4.2.7, the paint shall show no mud-cracking or other film irregularity.

3.4.7 Fungus resistance. When painted panels are examined as specified in 4.2.8, they shall show no fungus growth. A suitable and legal biocide shall be used. A certificate of compliance to this effect is required.

3.4.8 Flexibility. The paint, tested as described in 4.2.9, shall show no evidence of cracking, chipping, or flaking.

3.4.9 Wet adhesion. A film of the paint when tested as described in 4.2.10, shall show no adhesion failure between paint and alkyd undercoat.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

3.4.10 Humidity resistance. The coating system prepared as described in 4.2.11, after exposure to 100 percent humidity conditions for 250 hours shall show no rust bleed through, no blisters greater than size 6 and of medium density, and no greater than 3 mm (1/8 inch) rust creepage from the scribe.

3.4.11 Salt spray resistance. The coating system prepared as described in 4.2.12, after exposure to 5 percent salt spray for 250 hours shall show no blisters greater than size 6 and of medium density, and no greater than 3 mm (1/8 inch) rust creepage from the scribe.

3.4.12 Accelerated weathering resistance. After exposure of the coating system in accordance with 4.2.13, to 60° specular gloss and daylight reflectance shall be no less than 80 percent of the original values.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Sampling and Inspection. Sampling and inspection shall be in accordance with Method 1031 of FED-STD-141.

4.2 Tests. Samples selected in accordance with 4.1.1 shall be tested as specified in Table II and 4.2.1 through 4.2.14. Nonconformance to the requirements of the applicable test methods or failure to pass any test shall be cause for rejection of the lot which the sample represents.

Source: https://assist.dla.mil -- Downloaded: 20260-20T13:17Z
Check the source to verify that this is the current version before use.

TABLE II. Tests and Methods

Characteristic	Requirement Reference	Test Method	Paragraph Reference
Pigment	Table I		4.2.1
Titanium dioxide	Table I	7081[1/]	-
Nonvolatile organic material	Table I		4.2.1
Weight per gallon	Table I	D1475[2/], 4184[1/]	-
Consistency	Table I	D562[2/], 4261[1/]	-
Fineness of grind	Table I	4411[1/]	-
Drying time	Table I	4061[1/]	-
Daylight directional reflectance[3/]	Table I	6121[1/]	-
Gloss, specular 60°	Table	6101[1/]	-
Dry opacity	Table I	4121[1/]	-
Scrub resistance	Table I	D2486[2/]	-
Lead content	Table I	D3335[2/]	-
Color	3.4.1	4250[1/]	4.2.2
Condition in container	3.4.2	3011[1/]	4.2.3
Storage stability	3.4.3		4.2.4
Mechanical stability	3.4.4		4.2.5
Working properties	3.4.5.1		4.2.6
Recoating properties	3.4.5.2		4.2.6
Film irregularity	3.4.6		4.2.7
Fungus resistance	3.4.7	D3273[2/]	4.2.8
Flexibility	3.4.8	6221[1/]	4.2.9
Wet adhesion	3.4.9		4.2.10
Humidity resistance	3.4.10	D2247[2/]	4.2.11
Salt spray resistance	3.4.11	B117[2/]	4.2.12
Accelerated weathering resistance	3.4.12	6152[1/]	4.2.13
Vehicle identification	3.2.2		4.2.14

1/ FED-STD-141
2/ ASTM
3/ Apply the paint to a substrate having a minimum reflectance of 80 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

4.2.1 Pigment and nonvolatile organic material. Spread thinly, approximately 5 grams of well-mixed paint sample over the surface of a tared petri dish of borasilicate glass, approximately 100 mm diameter, and obtain exact weight. Dry in a vented regular over at 105°C to constant weight. (This requires overnight drying.) After obtaining the weight of the total nonvolatile material, ash in a muffle furnace, raising temperature gradually to 450-500°C (840°-930°F). Allow 2 hours for complete combustion of the organic material. The furnace door should be opened carefully when removing sample as the remaining pigment is very light and easily scattered. Place sample in desiccator and cool to room temperature. Obtain the weight of the ashed material.

4.2.1.1 Calculations.

Wt. of total nonvolatile material - wt. of ashed material = wt. of nonvolatile organic material

$$\frac{\text{wt. of ash} \times 100}{\text{total wt. of sample}} = \text{pigment, percent by weight}$$

$$\frac{\text{wt. of nonvolatile organic material} \times 100}{\text{total wt. of sample}} = \text{nonvolatile organic material, percent by wt. of primer}$$

4.2.2 Color. The paint shall be applied to a clean, smooth, plate-glass panel with a 0.003 inch (approximately 0.006 inch gap clearance) Bird film applicator or similar blade which produces the same film thickness. Allow the film to dry for 24 hours. Compare the color of the dried film in accordance with Method 4250 of FED-STD-141.

4.2.3 Condition in container. Examine the paint as received in accordance with Method 3011 of FED-STD-141 for compliance with 3.4.2.

4.2.4 Storage stability.

4.2.4.1 Specimens and exposure. Fill two resin-lined friction-top cans with the sample as received, and close the cans tightly. Expose one can and contents three times to the following freeze-thaw cycles:

a. Low temperature of -9± 2°C (15 ± 3°F) for 16 hours.

b. High temperature of 25 ± 3°C (77 ± 5°F) for 8 hours.

Store the other can and contents in an oven at 50°C (120°F) for two weeks.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

4.2.4.2 Procedure.

a. At the completion of the exposure, measure the consistency (ASTM D562) of both specimens and compare with the original consistency to determine compliance with 3.4.3.

b. Brush each paint specimen on a glass panel and observe while brushing and after drying whether the panel is normal and usable in all respects. Compare with the unexposed paint with respect to freedom from coagulation, agglomeration, speckiness and change in sheen or color.

4.2.5 Mechanical stability. Fill a quart resin-lined friction-top can 3/4 full with the paint and close the can tightly. Rotate on a jar roller[1/] for one week. Compare with the unexposed paint with respect to freedom from coagulation, flocculation, or change in consistency greater than 10 percent of the unexposed primer.

4.2.6 Working properties. Determine the brushing properties in accordance with Method 4331 of Fed. Test Method Std. No. 141. For the substrate use cold rolled steel panels[2/] conforming to ASTM D609, Type 1, prepared for coating by Method D, and brush to a wet film thickness of approximately 3 mils. After two hours air drying, apply a second coat of the paint in the same manner as the first coat. Examine the film for picking and rolling up to the first coat during application. After 24 hours, examine the dried film for any irregularities.

4.2.7 Film irregularity. Apply one coat of the paint to a cold rolled steel panel conforming to ASTM D609, Type 1, prepared for coating by Method D, with a 0.007 inch (approximately 0.015 inch gap clearance) film applicator. Allow the film to dry in a horizontal position for 24 hours. Examine the film for mud-cracking or other film irregularities for compliance with 3.4.6.

4.2.8 Fungus resistance. Test the paint in accordance with ASTM D3273 for compliance with 3.4.7.

4.2.9 Flexibility. The paint film shall be applied to an electrolytic tin plate panel[2/] prepared in accordance with Method 2012 of FED-STD-141. Draw down a film using a 0.002 inch (approximately 0.004 inch gap clearance) film applicator. Air dry for 24 hours at a temperature of 23 $\pm$ 1°C (73 $\pm$ 2°F), then heat for 3 hours at 105 $\pm$ 2°C (220 $\pm$ 5°F). After heating, condition the panel for 30 minutes at 23 $\pm$ 1°C (73 $\pm$ 2°F) and relative humidity of 50 $\pm$ 4 percent. Bend the panel over a 6-mm (1/4-inch) mandrel, and examine in accordance with Method 6221 of FED-STD-141 for compliance with 3.4.8.

1/ Available from Norton Chemical Process Product Division, formerly U.S. Stoneware Inc., Akron, OH 44309.
2/ Available from the Q-Panel Company, 15601 Industrial Parkway, Cleveland, OH 44135.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

4.2.10 Wet adhesion. Prepare the panels in accordance with Method 6142 of FED-STD-141, except use enamel conforming to TT-E-506 as undercoat. Apply the paint by drawdown as above in a direction perpendicular to the long axis of the panel to obtain a dry film of 0.002 inch and a width of approximately 50 mm (2 inches). Allow the paint to dry for 48 hours at 23 ± 1°C (73 ± 2°F) and relative humidity of 50 ± 5 percent. Make a cut (the entire width of the panel) perpendicular to the long axis of the glass panel through the center of the test film with a sharp knife held at a 45° angle. Place the panel on the apparatus described in Method 6141 of FED-STD-141 so that the test primer is approximately in the center of the brush stroke and scrub the water-immersed panel with the brush described in Method 6142 of FED-STD-141. The brush shall move in a direction parallel to the long axis of the glass panel and perpendicular to the cut made in the test film. The brush shall travel at a rate of 37 ± 2 cycles per minute (74 separate strokes ± 4 strokes per minute) for 600 cycles. Observe for compliance with 3.4.9.

4.2.11 Humidity resistance.

4.2.11.1 Panel preparation. Test panels shall be 75 by 200 mm (3 by 8 inches cold rolled steel panels conforming to ASTM D609, Type 1, prepared for coating by Method D. The panels shall be coated with two coats of primer conforming to MIL-P-28577 and one finish coat of paint conforming to MIL-P-28578, using a 0.003 inch (approximately 0.006 inch gap clearance) film applicator. Drying time between coats is 24 hours and the finished panels shall be cured one week before scribing and exposure. A 50 mm (2 inch) "X" shall be scribed to the metal on the lower half of the panel before exposure testing. The cut edges of the panels shall be protected with a suitable coating stable under the conditions of the test, such as carnauba wax.

4.2.11.2 Exposure testing. Place the panels, coated side down in a humidity cabinet as described in ASTM D2247[1/]. Use a continuous condensation cycle and a 38 ± 1°C (100 ± 2°F) air temperature for 250 hours. Observe the exposed panels for compliance with 3.4.10.

4.2.12 Salt spray resistance. Panel preparation for this test is that described in 4.2.11.1 Place the panels in an exposure cabinet as described in ASTM B117 using a 5 percent salt solution. Expose the panels for 250 hours. Observe the exposed panels for compliance with 3.4.11.

4.2.13 Accelerated weathering resistance. Panel preparation for this test is that described in 4.2.11.1 Measure the 60° specular gloss as described in Method 6101 of FED-STD-141, and the daylight reflectance as described in Method 6121 of FED-STD-141. Then subject the panel to accelerated weathering using a single carbon arc as light source, in accordance with Method 6152 of FED-STD-141, for 400 hours. After

1/ A suitable cabinet is available from the Q-Panel Company, 15601 Industrial Parkway, Cleveland, OH 44135.

Source: https://assist.dla.mil -- Downloaded: 202640-20T13:17Z
Check the source to verify that this is the current version before use.

exposure rinse the panel with clean water and allow to dry for one hour, and again measure the 60° specular gloss and the daylight reflectance. Observe the exposed panels for compliance with 3.4.12.

4.2.14 Vehicle identification. Weigh 15 grams of a well-mixed paint sample into a 100 ml centrifuge tube with lip. Mix the sample with a small amount of hot acetone (at boiling point), and dilute with mixing to 85 ml hot acetone (Caution! Acetone is highly flammable. Keep away from open flame). Centrifuge at 25 Hz for 30 minutes. Decant and concentrate decantate to approximately 35 ml using hot plate. Cool to room temperature to precipitate the resin. Redissolve the precipitate in acetone, and produce a film on a sodium chloride disc such that a trial infrared spectrum has a 5.8 µm absorbance band between 0.6 and 1.0 absorbance units. Vacuum dry the coated disc for one hour at 65 ± 5°C (150 ± 10°F) and obtain a final infrared spectrum. Identify the latex resin by comparison with published spectra of acrylic resins.

4.3 Inspection of packaging. The preservation, packing, and marking of the paint shall be inspected to determine conformance to the requirements of Section 5 of this specification.

5. PACKAGING

5.1 Preservation, packing, and marking. The paint shall be preserved, packed, and marked in accordance with PPP-P-1892. The level of preservation shall be A, B, or C, and the level of packing shall be A, B, or C, as specified (see 6.2). The paint shall be furnished in 1-liter or 4-liter (1-quart or 1-gallon) multiple friction plug metal cans, in 20-liter (5-gallon) lug cover steel pails, or in 1750-liter (55-gallon) full removable cover metal drums, as specified (see 6.2). All containers shall be resin-lined.

5.2 Special marking. The following special marking shall also be applied to unit containers: "This paint shall be used only in conjunction with a primer conforming to MIL-P-28577, Primer, Latex, Corrosion Resistant, for Metal Surfaces."

6. NOTES

6.1 Intended use. This specification covers the semi-gloss paint topcoat of a water reducible coating system consisting of two coats of primer and one coat of semi-gloss paint. The topcoat is intended for interior and exterior use. It is not intended to be applied at surface temperatures below 10°C (50°F) since painting at lower temperatures can interfere with proper film formation. The paint should be applied at least 2°C (5°F) above the dew point since excessive wetness may cause the paint to sag. The paint is water reducible, but application should be made with no dilution to get the maximum film build. If reduction is desired, potable water may be used not to exceed 5 percent by volume. Water can be used to clean equipment.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.

6.2 Ordering data.

6.2.1 Procurement requirements. Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Color required (see 3.4.1)
c. Level of preservation and level of packing required (see 5.1)
d. Quantities to be packaged (see 5.1)

6.2.2 Contract data requirements. When this specification is used in a procurement which incorporates a DD Form 1423 and invokes the provisions of paragraph 7-104.9 (n) of the Armed Services Procurement Regulation, the data requirements identified below will be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved Contract Data Requirements List (DD Form 1423) incorporated into the contract. When the provisions of ASPR 7-104.9 (n) are not invoked, the data specified below shall be delivered in accordance with the contract requirements. Deliverable data required by this specification is cited in the following paragraph:

Paragraph	Data Requirement	Applicable DD 1664
4.1.1	Certificate of Compliance	DI-E-2121

(Copies of Data Item Descriptions required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

6.3 Unit of purchase. The paint shall be purchased by volume, the unit being one U.S. gallon of 231 cubic inches (approximately 3.7 liters) at 68°F (20°F) until IS packages are available.

Preparing Activity

Navy - YD

(Project Number 8010-N132)

☆ U. S. GOVERNMENT PRINTING OFFICE: 1977-703-020/3676

Source: https://assist.dla.mil -- Downloaded: 202640-20T13:17Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commander
Naval Facilities Engineering Command (FAC 04M2C)
200 Stovall Street
Alexandria, VA 22332

Source: https://assist.dla.mil -- Downloaded: 202640-20T13:17Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil – Downloaded: 2026-10-20T13:17Z
Check the source to verify that this is the current version before use.