The documentation and process conversion measures necessary to comply with this revision shall be completed by 29 September 1999.

INCH-POUND

MIL-PRF-19500/397E
29 June 1999
SUPERSEDING
MIL-S-19500/397D
22 December 1994

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, TRANSISTOR, PNP, SILICON
TYPES 2N3743, 2N4930, AND 2N4931
JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for PNP, silicon, high-voltage transistor. Four levels of product assurance are provided for each device type as specified in MIL-PRF-19500. For JAN product assurance levels (see 6.3.1). Two levels of product assurance for die (element evaluation) are provided.

1.2 Physical dimensions. See figure 1 (similar to TO-39) (see 3.3.1) and figure 2 for JANHC and JANKC (die) dimensions.

1.3 Maximum ratings.

Type	P_T 1/ T_A = +25°C	P_T 2/ T_C = +25°C	V_{CBO}	V_{EBO}	V_{CEO}	I_C	T_J and T_{STG}
	W	W	V dc	V dc	V dc	A dc	°C
2N3743	1.0	5	300	5	300	200	-65 to +200
2N4930	1.0	5	200	5	200	200	-65 to +200
2N4931	1.0	5	250	5	250	200	-65 to +200

1/ Derate linearly at 5.71 mW/°C above T_A > +25°C.
2/ Derate linearly at 28.6 mW/°C above T_C > +25°C.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Defense Supply Center Columbus, ATTN: DSCC-VAC, 3990 East Broad St., Columbus, OH 43216-5000, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5961

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics at T_A = +25°C.

Limits	$\|h_{fe}\|$	h_{FE1} 1/	h_{FE4} 1/	$V_{BE(sat)2}$ 1/	$V_{CE(sat)1}$ 1/	C_{obo}
	I_C = 10 mA dc V_{CE} = 20 V dc f = 20 MHz	I_C = 0.1 mA dc V_{CE} = 10 V dc	I_C = 30 mA dc V_{CE} = 10 V dc	I_C = 30 mA dc I_B = 3 mA dc	I_C = 30 mA dc I_B = 3 mA dc	I_E = 0 V_{CB} = 20 V dc f ≥ 0.1 MHz
				V dc	V dc	pF
Min	2.0	30	50			
Max	8.0		200	1.2	1.2	15

1/ Pulsed (see 4.5.1).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATION

DEPARTMENT OF DEFENSE

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

STANDARD

DEPARTMENT OF DEFENSE

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Defense Automated Printing Service, 700 Robbins Avenue, Building 4D (DPM-DODSSP), Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated specifications or specification sheets), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.




FIGURE 1. Physical dimensions.


Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

Ltr	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
CD	.305	.335	7.75	8.51	
CH	.240	.260	6.10	6.60	
HD	.335	.370	8.51	9.40	
LC	.200 TP		5.08 TP		6
LD	.016	.021	0.41	0.53	6, 7
LL	.500	.750	12.70	19.05	7
LU	.016	.019	0.41	0.48	7
L1		.050		1.27	7
L2	.250		6.35		7
P	.100		2.54		5
TL	.029	.045	0.74	1.14	3, 4
TW	.028	.034	0.71	0.86	9
Q		.050		1.27	4
r		.010		0.25	10
α	45°TP		45°TP		6

NOTES:
1. Dimensions are in inches. Lead 1 is emitter, lead 2 is base, and lead 3 is collector.
2. Metric equivalents are given for general information only.
3. Symbol TL is measured from HD maximum.
4. Details of outline in this zone are optional.
5. Symbol CD shall not vary more than .010 inch (0.25 mm) in zone P. This zone is controlled for automatic handling.
6. Leads at gauge plane .054 inch (1.37 mm) +.001 inch (0.03 mm) -.000 inch (0.00 mm) below seating plane shall be within .007 inch (0.18 mm) radius of TP relative to tab. Device may be measured by direct methods or by gauge.
7. Symbol LU applies between L_1 and L_2. Dimension LD applies between L_2 and LL minimum.
8. Lead number three is electrically connected to case.
9. Beyond r maximum, TW shall be held for a minimum length of .011 inch (0.28 mm).
10. Symbol r applied to both inside corners of tab.
11. In accordance with ANSI Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions – Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.



Letter	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
A	.041	.041	1.04	1.04
C	.041	.041	1.04	1.04

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.
3. The physical characteristics of the die are:
   Thickness: .006 inch (0.15 mm) to .012 inch (0.30 mm).
   Top metal: Aluminum 17,500 Å minimum, 20,000 Å nominal.
   Back metal: Gold 2,500 Å minimum, 3,000 Å nominal.
   Back side: Collector.
   Bonding pad: B = .004 inch (0.10 mm) x .005 inch (0.13 mm).
   E = .004 inch (0.10 mm) x .0055 inch (0.14 mm).

FIGURE 2. JANHC and JANKC (A-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Associated specification. The individual item requirements shall be in accordance with MIL-PRF-19500, and as specified herein.

3.2 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.3 Interface requirements and physical dimensions. The Interface requirements and physical dimensions shall be as specified in MIL-PRF-19500, and figure 1, (similar to TO-39) herein.

3.3.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.5 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in paragraph 1.3, 1.4, and table I.

3.6 Electrical test requirements. The electrical test requirements shall be the subgroups specified in table I herein.

3.7 Qualification. Devices furnished under this specification shall be products that are authorized by the qualifying activity for listing on the applicable qualified manufacturers list before contract award (see 4.2 and 6.2).

4. VERIFICATION

4.1 Classification of Inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3)

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500.

4.3 Screening (JANS, JANTX, and JANTXV levels only). Screening shall be in accordance with table IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table IV of MIL-PRF-19500)	Measurement	
	JANS level	JANTX and JANTXV levels
9	I_{CBO1}	Not applicable
11	I_{CBO1} and h_{FE4} ΔI_{CBO} = 100 percent of initial value or 50 nA dc, whichever is greater	I_{CBO1} and h_{FE4}
12	See 4.3.1	See 4.3.1
13	Subgroups 2 and 3 of table I herein; ΔI_{CBO1} = 100 percent of initial value or 50 nA dc, whichever is greater; Δh_{FE4} = ±15 percent	Subgroup 2 of table I herein; ΔI_{CBO1} = 100 percent of initial value or 50 nA dc, whichever is greater; Δh_{FE4} = ±20 percent

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

4.3.1 Power burn-in conditions. Power burn-in conditions are as follows:

$V_{CB} \geq 30$ V dc, $T_A = +30°C \pm 5°C$

NOTE: No heatsink or forced air cooling on the devices shall be permitted. P_T adjusted to achieve T_J of +187.5°C ±12.5°C

4.3.2 Screening JANHC or JANKC. Screening of die shall be in accordance with MIL-PRF-19500.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500, and table I herein. Electrical measurements (end-points) shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in tables VIa (JANS) and VIb (JAN, JANTX, and JANTXV) of MIL-PRF-19500 and paragraphs 4.4.2.1 and 4.4.2.2 herein. Electrical measurements (end-points) shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein. Delta measurements shall be in accordance with table II herein.

4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B4	1037	V_{CE} = 30 V dc, 2000 cycles.
B5	1027	V_{CE} = 5 V dc, see MIL-PRF-19500.

4.4.2.2 Group B inspection, (JAN, JANTX, and JANTXV). 1/

Step	Method	Condition
1	1039	Steady-state life: Test condition B, 340 hours, V_{CB} = 10 to 30 V dc, T_J = 175°C min. No heat sink shall be permitted. n = 45 devices, c = 0
2	1039	The steady state life test of step 1 shall be extended to 1,000 hours for each die design. Samples shall be selected from a wafer lot every twelve months of wafer production, however, Group B shall not be required more than once for any single wafer lot. n = 45, c = 0.
3	1032	High-temperature life (non-operating), T_A = +200°C. n = 22, c = 0

1/ Separate samples may be used for each step. In the event of a group B failure, the manufacturer may double the sample size from either the failed assembly lot or from another assembly lot from the same wafer lot. If the new “assembly lot” option is exercised, the failed assembly lot shall be scrapped.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

4.4.2.3 Group B sample selection. Samples selected from group B inspection shall meet all of the following requirements:

a. For JAN, JANTX, and JANTXV samples shall be selected randomly from a minimum of three wafers (or from each wafer in the lot) from each wafer lot. For JANS, samples shall be selected from each inspection lot. See MIL-PRF-19500.

b. Must be chosen from an inspection lot that has been submitted to and passed group A, subgroup 2, conformance inspection. When the final lead finish is solder or any plating prone to oxidation at high temperature, the samples for life test (subgroups B4 and B5 for JANS, and group B for JAN, JANTX, and JANTXV) may be pulled prior to the application of final lead finish.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-PRF-19500 and in 4.4.3.1 (JANS).and 4.4.3.2 (JAN, JANTX, and JANTXV) herein for group C testing. Electrical measurements (end points) shall be in accordance with group A, subgroup 2.

4.4.3.1 Group C inspection, table VII (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Test condition E.
C6	1026	VCB 10 to 30 V dc; T_J = + 175°C minimum. No heat sink or forced-air cooling on the devices shall be permitted.

4.4.3.2 Group C inspection, table VII (JAN, JANTX, and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Test condition E.
C6		Not applicable

4.4.3.3 Group C sample selection. Samples for subgroups in group C shall be chosen at random from any lot containing the intended package type and lead finish procured to the same specification which is submitted to and passes group A tests for conformance inspection. Testing of a subgroup using a single device type enclosed in the intended package type shall be considered as complying with the requirements for that subgroup.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

4.5.2 Thermal resistance (to be performed for qualification inspection only). Thermal resistance measurements shall be conducted in accordance with MIL-STD-750, method 3131. The following details shall apply:

a. I_M measurement ..... 10 mA dc

b. V_{CE} measurement voltage (same as V_H) ..... 20 V dc

c. I_H collector heating current ..... 0.15 A dc

d. V_H Reference point temperature shall be +25°C ≤ T_R ≤ +35°C and recorded before the test is started.

e. Mounting arrangement shall be with heat sink to case.

f. Maximum limit shall be $R_{\theta JC}$ = 35°C/W

4.5.2.1 Thermal resistance for JANS. Thermal resistance measurements shall be conducted in accordance with MIL-STD-750, method 3131. The limit of $R_{\theta JC(max)}$ shall be 35°C/W. The following test conditions shall apply to both group B and screening step 3C, for screening step 3C, t_H shall be 10 ms minimum:

a. I_M measurement ..... 10 mA

b. V_{CE} measurement voltage (same as V_H) ..... 25 V dc

c. I_H collector heating current ..... 0.2 A dc

d. V_H collector-emitter heating voltage ..... 25 V dc

e. t_H heating time ..... 1 second minimum

f. t_{MD} measurement delay time ..... 50 µs maximum

g. t_{SW} sampling window time ..... 10 µs maximum

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 1 2/						
Visual and mechanical 3/ examination	2071	n = 45 devices, c = 0				
Solderability 3/ 4/	2026	n = 15 leads, c = 0				
Resistance to 3/ 4/ 5/ solvent	1022	n = 15 devices, c = 0				
Temp cycling 3/ 4/	1051	Test condition C, 25 cycles. n = 22 devices, c = 0				
Heremetic seal 4/	1071	n = 22 devices, c = 0				
Fine leak						
Gross leak						
Electrical measurements 4/		Group A, subgroup 2				
Bond strength 3/ 4/	2037	Precondition T_A = +250°C at t = 24 hrs or T_A = +300°C at t = 2 hrs, n= 11 wires, c = 0				
Subgroup 2						
Breakdown voltage, collector to base	3001	Bias condition D, I_C = 100 µA dc	$V_{(BR)CBO}$			
2N3743				300		V dc
2N4930				200		V dc
2N4931				250		V dc
Breakdown voltage, collector to emitter	3011	Pulsed (see 4.5.1), bias condition D, I_C = 1.0 mA dc	$V_{(BR)CEO}$			
2N3743				300		V dc
2N4930				200		V dc
2N4931				250		V dc
Breakdown voltage, emitter to base	3026	Bias condition D, I_E = 100 µA dc	$V_{(BR)EBO}$	5		V dc

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 2 - Continued						
Collector to base cutoff current 2N3743 2N4930 2N4931	3036	Bias condition D, $I_E = 0$ V_{CB} = 250 V dc V_{CB} = 150 V dc V_{CB} = 200 V dc	I_{CBO1}		250	nA
Emitter to base cutoff current	3061	Bias condition D, V_{EB} = 4 V dc	I_{EBO}		150	nA dc
Forward current transfer ratio	3076	Pulsed (see 4.5.1), I_C = 0.1 mA dc, V_{CE} = 10 V dc	h_{FE1}	30		
Forward current transfer ratio	3076	Pulsed (see 4.5.1), I_C = 1.0 mA dc, V_{CE} = 10 V dc	h_{FE2}	40		
Forward current transfer ratio	3076	Pulsed (see 4.5.1), I_C = 10 mA dc, V_{CE} = 10 V dc	h_{FE3}	40		
Forward current transfer ratio	3076	Pulsed (see 4.5.1), I_C = 30 mA dc, V_{CE} = 10 V dc	h_{FE4}	50	200	
Forward current transfer ratio	3076	Pulsed (see 4.5.1), I_C = 50 mA dc, V_{CE} = 20 V dc	h_{FE5}	30		
Collector to emitter voltage (saturated)	3071	Pulsed (see 4.5.1), I_C = 30 mA dc, I_B = 3 mA dc	$V_{CE(sat)1}$		1.2	V dc
Collector to emitter voltage (saturated)	3071	Pulsed (see 4.5.1), I_C = 10 mA dc, I_B = 1 mA dc	$V_{CE(sat)2}$		1.0	V dc
Base emitter voltage (saturated)	3066	Test condition A, I_C = 10 mA dc, I_B = 1 mA dc, pulsed (see 4.5.1)	$V_{BE(sat)1}$		1.0	V dc
Base emitter voltage (saturated)	3066	Test condition A, I_C = 30 mA dc, I_B = 3 mA dc, pulsed (see 4.5.1)	$V_{BE(sat)2}$		1.2	V dc

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 3						
High-temperature operation:		T_A = +125°C				
Collector to base cutoff current	3036	Bias condition D	I_{CBO2}		100	µA dc
2N3743		V_{CB} = 250 V dc				
2N4930		V_{CB} = 150 V dc				
2N4931		V_{CB} = 200 V dc				
Low-temperature operation:		T_A = -55°C				
Forward current transfer ratio	3076	Pulsed (see 4.5.1) V_{CE} = 10 V dc, I_C = 30 mA dc	h_{FE6}	25		
Subgroup 4						
Open circuit (output capacitance)	3236	V_{CB} = 20 V dc I_E = 0, f ≥ 0.1 MHz	C_{obo}		15	pF
Input capacitance (output open circuited)	3240	V_{EB} = 1 V dc I_C = 0, f ≥ 0.1 MHz	C_{ibo}		400	pF
Small-signal current gain	3306	V_{CE} = 20 V dc, I_C = 10 mA dc, f = 20 MHz	$\|h_{fe}\|$	2	8	
Small-signal current gain	3206	V_{CE} = 10 V dc, I_C = 10 mA dc, f = 1 kHz	h_{fe}	30	300	
Subgroup 5						
Safe operating area (dc operation)	3051	T_C = +25°C, t ≥ 1 second, 1 cycle				
Test 1		I_C = 50 mA dc, V_{CE} = 20 V dc				
Test 2		I_C = 10 mA dc, V_{CE} = 100 V dc				
Test 3						
2N3743		I_C = 3.3 mA dc, V_{CE} = 300 V dc				
2N4930		I_C = 5 mA dc, V_{CE} = 200 V dc				
2N4931		I_C = 4 mA dc, V_{CE} = 250 V dc				
Electrical measurements		See table I, group A, subgroup 2 herein				

1/ For sampling plan, see MIL-PRF-19500.
2/ For resubmission of failed subgroup A1, double the sample size of the failed test or sequence of tests.
3/ Separate samples may be used.
4/ Not required for JANS.
5/ Not required for laser marked devices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

TABLE II. Groups E inspection (all quality levels) for qualification only.

Inspection	MIL-STD-750		Qualification conformance inspection
	Method	Conditions	
Subgroups 1, 2, and 3			
Not applicable			
Subgroup 4			22 devices, c = 0
Thermal resistance	3131	See 4.5.2	
Subgroup 5			5 devices, c = 0
Barometric pressure (2N3743 and 2N4931 only)	1001	Pressure = 8 mmHg, normal mounting, t = 60 seconds, minimum	

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of material is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Points' packaging activity within the Military Department or Defense Agency, or within the Military Departments' System Command. Packaging data retrieval is available from the managing Military Departments' or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Notes. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Issue of DODISS to be cited in the solicitation and, if required, the specified issue of individual documents referenced (see 2.2.1).

b. Lead finish (see 3.3.1).

c. Type designation and product assurance level.

d. Packaging requirements (see 5.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

6.3 Substitution information. Devices form this specification supersedes the following commercial Part or Identifying Number (PIN). This information in no way implies that manufacturers' PIN's are suitable as a substitute for the military PIN.

Military PIN	Superseded commercial types
2N3743	SUN1446H, SS4238H
2N4930	SUN1446H, SS5152H
2N4931	SUN1446H, ST1390H, ST147H

6.3.1 Replacement data. JANTX devices are direct replacements for JAN devices (example, JANTX2N3743 for JAN2N3743).

6.4 Suppliers of JANHC and JANKC die. The qualified die suppliers with the applicable letter version (example, JANHCA2N3743) will be identified on the qualified products list.

JANC ordering information	
PIN	Manufactures
	33178
2N3743	JANHCA2N3743
	JANKCA2N3743
2N4930	JANHCA2N4930
	JANKCA2N4930
2N4931	JANHCA2N4931
	JANKCA2N4931

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

6.6 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturer's List QML-19500 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or purchase orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Defense Supply Center Columbus, DSCC-VQE, Columbus, OH 43216.

Custodians:
Army - CR
Navy - EC
Air Force - 11
NASA - NA
DLA - CC

Preparing activity:
DLA - CC

Review activities:
Army - AR, AV, MI
Navy - AS, CG, MC
Air Force – 13, 15, 19

(Project 5961-2127)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete blocks 4, 5, 6, and 7, and send to preparing activity.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-PRF-19500/397E	2. DOCUMENT DATE *(YYYYMMDD)*

3. DOCUMENT TITLE SEMICONDUCTOR DEVICE, TRANSISTOR, PNP, SILICON, TYPE 2N3743, 2N4930, AND 2N4931, JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME *(Last, First Middle Initial)*	b. ORGANIZATION	
c. ADDRESS *(Include Zip Code)*	d. TELEPHONE *(Include Area Code)* (1) Commercial (2) DSN *(If applicable)*	7. DATE SUBMITTED *(YYYYMMDD)*

8. PREPARING ACTIVITY

a. NAME Alan Barone	b. TELEPHONE *(Include Area Code* (1) Commercial 614-692-0510 (2) DSN 850-0510
c. ADDRESS *(Include Zip Code)* DSCC-VAC 3900 E. Broad Street Columbus, Ohio 43216-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman Road, Suite 2533 Fort Belvoir, Virginia 22060-6221 Telephone (703)767-6888 DSN 427-6888

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:31Z
Check the source to verify that this is the current version before use.