MILITARY SPECIFICATION

CLOTH, INTERLINING, COTTON OR SYNTHETIC, AND NYLON

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one type of interlining cloth.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

PPP-P-1134 - Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

MILITARY

MIL-W-43334 - Webbing and Tape, Textile, Packaging and Packing of

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, DC 20580.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Warp yarn. The warp yarn shall be made from 100 percent polyester or 100 percent cotton, or any combination of the two fibers, or from 45 percent up to 100 percent polyester, and the remaining percentage rayon.

3.1.2 Filling yarn. The filling yarn shall be made from 100 percent nylon monofilament.

3.2 Physical requirements. The cloth shall conform to the requirements shown in table I when tested as specified in 4.4.

TABLE I. Physical requirements

Weight ounces Per sq. yd. (minimum)	Yarns per inch (minimum)		Thickness inch	Stiffness inch pounds Filling		Weave
	Warp	Filling		(min)	(max)	
6.3	31	24	.026 + .006	.100	.200	Plain

3.3 Width. The minimum width inclusive of selvages of the finished cloth shall be as specified (see 6.2).

3.4 Color. The color shall be natural unless otherwise specified (see 6.2).

3.5 Dimensional stability. The cloth shall not shrink more than 2.0% in the warp direction when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

3.6 Length and put-up.

3.6.1 Full width. Unless otherwise specified (see 6.2), the finished cloth shall be furnished in continuous lengths each not less than 40 yards. Each length shall be put up in full width rolls as specified in PPP-P-1134.

3.6.2 Narrow width. Unless otherwise specified (see 6.2), the narrow width cloth shall be furnished on rolls of 140 yards ± 10 yards, and put up as specified in MIL-W-43334.

3.7 Fiber identification. Each roll of cloth shall be labeled, ticketed or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.8 Workmanship. The finished cloth shall conform to the quality established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliances are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

4.2.2 Examination of the end item. Defects found during examination shall be classified in accordance with 4.2.2.1 through 4.2.2.3.

4.2.2.1 Yard-by-yard examination The required yardage of each roll shall be examined and defects clearly noticeable at normal inspection distance (3 feet) shall be classified as listed. The defects found shall be counted regardless of their proximity to each other, except when two or more defects represent a single local condition of the cloth, only one shall be scored. A continuous defect shall be counted as one defect for each yard or fraction thereof in which it occurs. The sample unit shall be 1 yard, full width of the finished cloth. The acceptable quality level shall be 4.0 defects per 100 units (yards). The sample size shall be in accordance with inspection level I of MIL-STD-105. The lot size shall be expressed in units of one yard each. The number of rolls selected shall be in accordance with table II.

Defects
Hole, cut or tear
Smash
Grease or oil stain
Embedded crease or wrinkle
Knots 1/

1/ To be scored when larger than limits shown on figure 1 of FED-STD-4.

4.2.2.1.1 Overall examination. Each defect shall be counted no more than once in each roll examined. The sample unit shall be one roll. The size (number of rolls selected as sample) and the acceptance number shall be as shown in table II.

Defects
Width less than specified 1/
Overall uncleanness 1/
Baggy, ridgy, or wavy cloth
Not labeled in accordance with the Textile Fiber Products Identification Act.

1/ Shall not be scored unless it occurs for more than 5 yards per roll.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

TABLE II. Sample size

Lot size (yards)	Sample size (rolls)	Acceptance number
Up to 1200 1/	3	0
1201 up to and including 3200	5	0
3201 up to and including 10,000	8	0
10,001 up to and including 35,000	13	1
35,001 up to and including 150,000	20	2
150,001 and over	32	3

1/ If a lot contains fewer than three rolls, each roll in the lot shall be examined.

4.2.2.2 Examination for length.

4.2.2.2.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.2.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the ticket.

4.2.2.3 Examination for compliance with the Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll in the sample shall be examined for this defect. The lot shall be unacceptable if two or more rolls in the sample are not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.

4.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing and marking requirements comply with section 5 requirements.

4.4 Testing of the end item. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table III shall be followed. The physical and chemical values specified in section 3, except where otherwise specified, apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

3 continuous yards, full width, of the finished cloth. All test reports shall contain the individual values utilized in expressing the final result. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more units fail to meet any requirement specified. The sample size shall be as follows:

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III. Test methods

Characteristic	Requirement paragraph	Test method
Warp yarn		
Polyester identification	3.1.1	1/
Cotton or rayon identification	3.1.1	1/
Filling yarn		
Nylon	3.1.2	1/
Fiber content		
Warp	3.1.1	1/
Filling	3.1.2	1/
Weight	3.2	5041
Yarns per inch		
Warp	3.2	5050
Filling	3.2	5050
Thickness	3.2	5030
Stiffness (filling direction)	3.2	5202
Weave	3.2	Visual 2/
Dimensional stability (warp direction)	3.5	5552

1/ Unless otherwise specified a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ One determination shall be made on each sample unit and the results reported as "pass" or "fail".

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging (full width cloth). Packaging shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C. The cloth, put-up as specified, shall be packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing (full width cloth). Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Levels A, B and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Packaging (narrow width cloth). Packaging shall be level A, B, or C (see 6.2).

5.3.1 Levels A, B and C. Tape, put up as specified in 3.6.2, shall be packaged in accordance with the applicable requirements of MIL-W-43334.

5.4 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.4.1 Levels A, B and C. Tape shall be packed in accordance with the applicable requirements of MIL-W-43334.

5.5 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of PPP-P-1134 or MIL-W-43334, as applicable.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use as waistband interlining for men's trousers.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Width required (see 3.3).
(c) Color required if other than specified (see 3.4).
(d) Length required when other than specified (see 3.6).
(e) Selection of applicable levels of packaging and packing (see 5.1 and 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Army - MD
Navy - MC
Air Force - 82

Preparing activity:

Army - GL

Project No. 8305-0450

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
US ARMY NATICK LABORATORIES
NATICK, MA 01760

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STSNL-TD C

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314



Commander
US Army Natick Laboratories
ATTN: STSNL-TDC
Natick, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE MIL-C-43920- CLOTH, INTERLINING, COTTON OR SYNTHETIC, AND NYLON

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:59Z
Check the source to verify that this is the current version before use.