INCH-POUND
MIL-G-43958
INTERIM AMENDMENT 1
19 July 1996

MILITARY SPECIFICATION

GLOVES, CLOTH, BLACK, LINED, GIRL'S, Jr. R.O.T.C.

This interim amendment is approved for use within the Department of the Army, with MIL-G-43958 dated 17 December 1976.

PAGE 2

2.1, under "Specifications, Military": Delete "MIL-C-29135 - Cloth, Knitted, Nylon, Simplex"

PAGE 3

3.3.1: Delete and substitute:

"3.3.1 Basic material. The basic material for the outer shell shall be a nylon simplex jersey cloth. The cloth shall be black 3231. The finished cloth shall have a smooth sueded finish on both sides of the material and shall be fully heat set to meet the dimensional stability requirements. The width of the cloth shall be as specified.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:11Z
Check the source to verify that this is the current version before use.

Characteristic	Requirement	Test method
Yarn:		
Denier	40-70	2/
Multifilament		2/
Luster	semi-dull or dull	2/
Colorfastness		
Light	"good" ("4")	5660 1/
Laundering	"good" ("4")	5614 1/
Perspiration	"good" ("4")	5680 1/
Crocking (Munsell min.)	8.5	5651 1/
Weight (oz./sq. yard)	5.5-8.0	5041 1/
Wales per inch (min.)	52	5070 1/
Courses per inch (min.)	40	5070 1/
Bursting strength (pounds min.)	100	5120 1/
Stretch (percent)		
Length direction (max.)	30	3/ 4/
Width direction	45-75	3/ 4/
Type of knit	simplex jersey	2/
Dimensional stability (percent shrinkage)		
Length (max.)	10	5552 1/
Width (max.)	10	5552 1/
Nonfibrous Material (max. percent)	2.0	2611 1/
pH	5.0-8.5	2811 1/
Color matching		5/

1/ FED-STD-191

2/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

3/ Test specimen. The test specimen shall be a rectangle, 4 inches by not less than 5 inches. The long dimension shall be parallel to the length (wales) of the cloth for length tests and parallel to the width (courses) for width tests. The test specimen shall be taken no nearer the selvage than 1/10 the width of the cloth. Two parallel lines, 3 inches apart, shall be drawn at right angles to the long dimension of the specimen. In addition, a line shall be drawn parallel to the long dimension of the specimen and 1 inch in from either edge for properly aligning the specimen in the jaws.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:11Z
Check the source to verify that this is the current version before use.

4/ Test apparatus. The test device shall be an apparatus such as an Instron or equivalent wherein the specimen is held between two clamps. The face of the jaw shall measure 1 inch by 1 inch, and the face of the fixed jaw shall measure 1 inch by 1-1/2 inch or more with the long dimension perpendicular to the direction of application of the load. The specimen shall be placed symmetrically in the clamps of the apparatus with the long dimension parallel and the short dimension at right angles to the direction of the application of the load. Using the specified guidelines, the specimen shall be aligned with one outside edge of the front jaws of each clamp. The proper weight shall be added to insure a total of 6 pounds (including the weight of the lower jaws). The load shall be applied for 15 seconds and the distance between jaws measured by a pair of dividers or other suitable instrument. The elongation at the required load shall be expressed as the percent increase in the length of the specimen between the jaws. The percent stretch shall be calculated as follows:

$$\text{Percent stretch} = \frac{\text{Stretch dimension - Original 3-inch dimension}}{\text{Original dimension (3 inches)}} \times 100$$

5/ The color of the finished cloth shall match the standard sample under artificial daylight having a color temperature of 7500^{o} Kelvin, and shall be a good approximation to the standard sample under incandescent lamplight at 2800^{o} Kelvin."

Preparing activity:
DLA-CT

(Project 8445-0135)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:11Z
Check the source to verify that this is the current version before use.