MIL-M-43946A
25 January 1984
SUPERSEDING
MIL-M-43946
31 March 1976

MILITARY SPECIFICATION

MAINTENANCE KIT: WET WEATHER CLOTHING

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a maintenance kit for the repair of parkas and trousers, wet weather at the organizational and direct support maintenance levels.

2. APPLICABLE DOCUMENTS

2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

H-B-643	-	Brushes, Acid Swabbing
L-P-378	-	Plastic Sheet and Strip, Thin Gauge, Polyolefin
TT-T-548	-	Toluene; Technical
CCC-C-446	-	Cloth, Muslin, Cotton
PPP-B-636	-	Boxes, Shipping, Fiberboard
PPP-C-96	-	Cans, Metal, 28 Gage and Lighter

MILITARY

MIL-C-5024	-	Lubricant, Inner Tube, Aircraft Tire
MIL-C-43906	-	Cloth, Coated, Nylon, Polyurethane Double Coated

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed: U.S. Army Natick Research and Development Center, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8405

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

* 2.2 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 Components. The maintenance kit shall consist of the following components:

a. One roll of coated nylon cloth
b. Two half-pints of adhesive
c. One pint of toluene
d. Thirty brushes
e. One sheet of polyethylene film
f. One talcing bag
g. One roller
h. Instruction sheets

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

3.2 Materials.

3.2.1 Cloth, coated, nylon. The nylon coated cloth shall conform to MIL-C-43906. One piece, 6 ± 1/4 inches wide by 6 ± 1/8 yards in length, cut in the warp direction, shall be wound (heavier coated side outward) on a cylinderical core. The core shall be 1 inch in diameter by 6 inches in length and shall be made of wood, paperboard tubing, or other suitable core stock.

3.2.2 Adhesive. The adhesive shall be a polyurethane type, Durance No. 8541 or equal (see 6.3). The adhesive shall be unit packed in two half-pint round cans conforming to type V, class 2, No. 50 or No. 50/25 tin-plate of PPP-C-96. The friction plugs shall be securely closed and each container shall be marked with the word "ADHESIVE", and "Date of Manufacture (Month, Year)", in characters 5/16 inch high, minimum. The age of the adhesive at tune if delivery of the maintenance kits to the government shall not exceed two months. If the contractor proposes to furnish an adhesive considered to be equal to the adhesive specified, the contractor shall first furnish a halfpint of the adhesive, with physical property data, to the contracting officer for subsequent evaluation by the responsible military agency.

3.2.3 Toluene (cleaning solvent). The toluene shall conform to TT-T-548. The toluene shall be unit packed in a one-point square can conforming to type V, class 4, No. 25 or No. 50/25 tin-plate of PPP-C-96. The container shall be clearly labeled on the broad face of the can with the following, in letters 5/16 inch high minimum:

"TOLUENE - CLEANING SOLVENT

WARNING: Avoid prolonged or repeated contact with skin

Avoid breathing of vapors

Flammable"

3.2.4 Brushes. The brushes shall conform to type II, class 1, size 2 of H-B-643. The thirty brushes shall be secured together in a bundle with tape or an elastic band.

3.2.5 Polyethylene sheet. The polyethylene sheet shall conform to type I, class 1, grade A, finish 1, 0.002 inch thick of L-P-378. The sheet shall measure 15 by 18 ± 1/8 inches. The sheet shall be folded in half twice, once in length and once in width.

3.2.6 Talcing bag. One ounce minimum of the compound specified in 3.2.6.1 shall be placed in the center of a one foot square or diameter piece of the cloth specified in 3.2.6.2. The cloth shall be drawn up around the compound on all sides to form a pouch which shall then be securely closed with a 1/8 inch wide elastic band located approximately three inches from the bottom of the bag.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

3.2.6.1 Talc-mica compound. The talc-mica compound shall conform to MIL-C-5024 or shall be powdered mica, no coarser in fineness than number 160 mesh.

3.2.6.2 Cloth, muslin, cotton. The muslin cloth shall conform to type III, class 2 of CCC-C-446.

3.2.7 Roller, wood. The roller shall be 1-1/2 ± 1/8 inches in diameter by 4 ± 1/4 inches in length and shall be made from any species of wood. The roller shall be smooth and free of splinters and rough edges.

3.2.8 Instructions for use. The instructions for use shall be printed on one side only on 8 by 10-1/2 inches white bond paper using 12 point elite type. All pages shall be stapled together in the upper left hand corner and then folded twice, once in length and once in width. Contents of the instructions for use shall be as follows:

INSTRUCTIONS FOR USE OF
MAINTENANCE KIT, WET WEATHER CLOTHING

This kit is for repair of punctures and tears in Parkas and Trousers, Wet Weather, at the Organizational Maintenance and Direct Support Levels.

CONTENTS

1 Each	Instructions
2 Half-pints	Adhesive, Liquid Urethane base, half-pint can
30 Each	Brush (Throwaway)
1 Sheet	Polyethylene film, 2 mil dropcloth (reuseable)
1 Roll	Cloth, Nylon, Polyurethane coated 6 yards by 6 inches
1 Each	Talcing Bag
1 Each	Roller, Wood, 1-1/2 inches diameter by 4 inches long
1 Pint	Toluene (Cleaning Solvent)

ADDITIONAL REQUIRED ITEMS OR EQUIVALENT:

The following items are not components of this maintenance kit but are necessary items which should be available to maintenance personnel when repairs to wet weather clothing are being accomplished.

1 Box	Paper Towels (FSN 7920-634-1745)
1 Pair	Shears, Heavy Duty, 10 inches (FSN 5110-596-9703)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS

1. PRECAUTIONS

a. Avoid breathing adhesive solvent vapors.

b. Avoid prolonged contact of adhesive and of cleaning solvent on skin.

c. Use with adequate ventilation.

d. Adhesive and toluene cleaning solvent are flammable. Keep from heat and open flame.

e. Close can of adhesive tightly and immediately after application.

f. Store kit in cool place.

g. Avoid working under dusty conditions; dust may inactivate adhesive coated surfaces.

h. USE NO ADHESIVE OTHER THAN FROM THIS KIT. (Many other adhesives stick well when patched garment is dry, but stick poorly when patched garment gets wet).

2. GENERAL PROCEDURE

In brief, the repair consists of (a) cleaning the area to be repaired, (b) applying adhesive to patch and to the work, (c) allowing adhesive on both to dry about an hour, and (d) pressing patch in place.

3. DETAILED PROCEDURE

a. PREPARE PATCHES

(1) Cut a piece of the patching fabric from the kit.

(2) Make it large enough to provide all the patches that will be needed that day.

(3) Clean the lighter coated side (duller and less smooth) by wiping with paper towels wet (but not dripping) with toluene solvent. Allow to dry.

(4) Stir the adhesive and apply to the cleaned side of the piece. Spread rapidly with a minimum of strokes. Overlap strokes as little as possible. (When a large piece of fabric is being coated a paint brush may be used or two or three kit brushes may be taped together).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

(5) Dry until the piece can be cut into patches without the adhesive fouling the shears. This may take an hour, but might be as little as 20 minutes on warm dry days.

(6) Cut patches in the required sizes and shapes as needed (generally rectangular). Round off corners. The patch should cover the damage and extend into the surrounding area of the garment about 3/4 inch in all directions.

(7) These adhesive-coated patches may then be applied in the subsequent patching procedures at any time during the rest of the day.

NOTE: When making one patch only, proceed as above except apply the adhesive after the one patch is cut. Hold the patch down with the point of a small stick, pencil, or other similar device and apply the adhesive by brushing outwards from the center of the patch all around.

b. PREPARE PUNCTURED, TORN, OR WORN AREA

(1) If heavily soiled, pre-clean the damaged area. If area is wetted with water or other cleaning fluid, dry thoroughly.

(2) Trim off any badly frayed or curled edges.

(3) Spread out the garment area to be patched on a flat work surface.

(4) When the hole to be patched is wide or where there is a large porous area to be patched, slip the polyethylene film (from the kit) under the garment layer to be patched. This will help keep the adhesive from messing up the garment and work surface.

(5) Wipe the area to be patched, using a toluene wetted cloth or paper towel. Dry.

(6) Using the patch from 3.a. above as a template, place it in what will be its final position on the torn area, and make a tracing along its border. Use a No. 2 or softer pencil for tracing.

(7) Remove the patch and apply one even coat of the adhesive within the tracing and just including the tracing line. Do not brush directly into open tears and holes. Brush rapidly with a minimum of strokes.

(8) Dry until no sign of wetness or tackiness (generally an hour or less).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

c. PATCH ASSEMBLY

(1) Carefully set the patch from 3.a. exactly on the marked prepared area in 3.b. and press together firmly.

(2) Roll the patch with heavy hand pressure using roller provided in the kit then dust the patched area using the talcing bag furnished with the kit.

(3) The garment may be worn immediately. If it is to be packed for storage or shipment, allow one hour drying under good ventilation to dissipate solvents completely.

3.3 Adhesive performance. The adhesive shall have a minimum peel strength of 6 pounds per inch dry and 4 pounds per inch wet when tested as specified in 4.3.1.1.

3.4 Workmanship. The maintenance kits shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

3.5 Toxic products and formulations. The materials used shall have no adverse effect on the health of personnel when used for its intended purpose. Questions pertinent to its effect shall be referred by the procuring activity to the appropriate departmental medical service who will act as an advisor to the procuring activity.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Toxicological data and formulations. The contractor shall furnish the toxicological data and formulations required to evaluate the safety of the material for proposed use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

* 4.3 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.3.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified or qualified in this document or applicable purchase document.

4.3.1.1 Testing of adhesive. Testing of the adhesive component shall be performed as specified in 4.4 for conformance to the adhesive performance requirement specified in 3.3. The lot shall consist of adhesive made in one batch by the adhesive contractor, i.e., adhesive that was manufactured all at one time. The sample unit shall be one half-pint of adhesive. The sample size shall be five. The performance requirement shall be applicable to each sample unit. There shall be no evidence of failure of any sample unit to meet the requirement specified in 3.3.

4.3.1.1.1 Certification. The contractor shall furnish a certificate of compliance certifying that each lot of adhesive consists of adhesive made in one batch by the adhesive contractor that the adhesive is Durane No. 8541 or equal; and that the adhesive is not more than two months old at time of delivery to the Government.

* 4.3.2 Visual examination. The end item shall be examined in accordance with the classification of defects set forth below. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0. The sample unit shall be one complete kit.

Examine	Defect
General	Any component omitted or not as specified Any defective component
Coated cloth	Any defect in coating Not cut in warp direction Length and width not as specified Not wound on cylindrical core or not wound with the heavier coated side facing outward
Adhesive	Markings on container omitted, incomplete or illegible Not packaged in the specified container Friction plug on container not securely closed Container not filled to full capacity
Toluene	Not packaged in specified container Container not filled to full capacity Markings on container incomplete, illegible or omitted

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

Examine	Defect
Brushes	Less than 30 brushes per kit Brushes not secured in a bundle
Polyethylene sheet	Size not as specified Not folded as specified
Talcing bag	Not constructed as specified Not securely closed
Roller	Not made of wood Not smooth, not free of splinters or rough edges Not size specified
Instruction sheet	Omitted, incorrect, illegible, or incomplete Size or kind of type not as specified Pages not stapled as specified Not fabricated from white bond paper or size of paper not as specified

* 4.3.3 Packaging inspection. An examination shall be made to determine that the preservation, packing, and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully packaged with the exception that it need not be closed. Defects of closure listed below shall be examined on shipping containers fully packaged. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Examine	Defects
Marking (exterior and interior)	Omitted; incorrect; incomplete; illegible; of improper size, location, sequence or method of application.
Materials	Any component omitted, damaged or not as specified.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps, loose or inadequate sealing, strapping, taping or inadequate stapling. Bulged or distorted container.
Content	Number of maintenance kits per shipping container is more or less than specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

* 4.3.4 Palletization examination. An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully packaged. The lot size shall be the number of palletized unit loads in the inspection lot. The inspection level shall be S-1 and the AQL shall be 6.5 defects per hundred units.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirements.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

4.4 Adhesive peel strength.

4.4.1 Preparation of test specimens. Cut two rectangular pieces of the coated cloth conforming to 3.2.1, 8 $\pm$ 1/16 inches long by 5 $\pm$ 1/16 inches wide. The long dimension shall be the warp. Clean the lighter coated side of one piece by wiping with a paper towel wetted with toluene and the heavier side of the other piece in the same manner, and allow to dry. Brush a full coat of the adhesive on each of the two cleaned surfaces, except for 3 $\pm$ 1/4 inches at one end of each piece. Spread the adhesive uniformly and quickly, with a minimum of working and over-lapping of strokes. Allow to dry for one hour minimum. Carefully assemble the two matching adhesive coated faces of the two pieces together, keeping the warp directions aligned. Press the two pieces together firmly with a hand roller. Cut four 1 $\pm$ 1/16 inch wide specimens in the warp direction.

4.4.2 Test procedure. Condition the four specimens for 24 hours minimum under standard conditions as specified in section 4 of FED-STD-191. Test two of the specimens for peel strength of the adhesive by Method 5960 of FED-STD-191 and report the average. Immerse the other two specimens in distilled water at 70 $\pm$ 2°F for two hours minimum. Immediately after removal from the water, the specimens shall be tested for peel strength as specified above and the average reported.

5. PACKAGING

* 5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

5.1.1 Level A. Each maintenance kit consisting of the components specified in 3.1 shall be compactly arranged (metal cans positioned upright) within a snug-fitting water resistant full telescope metal stayed paperboard box. Alternatively, a snug-fitting fiberboard box may be used conforming to style FTC, grade W6c or W6s of PPP-B-636.

* 5.1.2 Commercial. Each maintenance kit shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial (see 6.2).

* 5.2.1 Level A packaging. Twelve maintenance kits, preserved as specified in 5.1, shall be packed in snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Level A unit packs shall be packed upright, two in length, three in width, and two in depth. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.3.3.

* 5.2.2 Level B packaging. Twelve maintenance kits, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. Level A unit packs shall be packed upright, two in length, three in width, and two in depth. Each shipping container shall be closed in accordance with method II of the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.3.3.

* 5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.3.3.

* 5.2.3 Commercial packing. Maintenance kits, packaged as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Palletization. When specified (see 6.2), maintenance kits packed as specified in 5.2, shall be palletized in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

* 5.3 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

5.3.1 Special marking. Each unit pack and shipping container shall be marked in accordance with the applicable type II shelf-life item marking requirements specified in MIL-STD-129. The INSPECTION/TEST DATE shall be 18 months after the DATE ASSEMBLED.

5.3.3 Precautionary marking. Each unit pack and shipping container shall be legibly printed, stenciled or stamped in black ink with capital letters with the following precautionary marking:

CAUTION - FLAMMABLE MATERIALS

6. NOTES

6.1 Intended use. The maintenance kit is for repair of a puncture, tear or worn out area in the Parka and Trousers, Wet Weather, MIL-P-43907.

* 6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
c. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
d. When palletization is required (see 5.3).

6.3 Adhesive. Durane No. 8541 adhesive may be obtained from the following source (see 3.2.2):

Raffi and Swanson Company
100 Eames Street
Wilmington, Massachusetts 01887

6.4 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Navy - MC
Air Force - 82
DSA - CT

User activity:

Air Force - 45

Preparing activity:

Army - GL

Project No. 8405-0735

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use i submitting comments and suggestions for improvements. All users of military standardization documents are invited to provid suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, wa too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-M-43946A	Maintenance Kit: Wet Weather Clothing

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION (Mark one)
	☐ VENDOR
b. ADDRESS (Street, City, State, ZIP Code)	☐ USER
	☐ MANUFACTURER
	☐ OTHER (Specify): _____

5. PROBLEM AREAS

a. Paragraph Number and Wording.

b. Recommended Wording.

c. Reason/Rationale for Recommendation.

6. REMARKS

7a. NAME OF SUBMITTER (Last, First, MI) – Optional	b. WORK TELEPHONE NUMBER (Include Area Code) – Optional
c. MAILING ADDRESS (Street, City, State, ZIP Code) – Optional	8. DATE OF SUBMISSION (YYMMDD)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, 1 APR 83

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:07Z
Check the source to verify that this is the current version before use.