MIL-S-43939(GL)
AMENDMENT-1

21 March 1977

MILITARY SPECIFICATION

SHIRT, MAN'S, POLYESTER/COTTON, DURABLE PRESS

This amendment forms a part of Military Specification MIL-S-43939(GL) dated 13 January 1976.

PAGE 5

3.2.3.3, line 8: Delete "(120°F), (49°C)" and substitute "(115°F), (46°C)".

PAGE 6

3.2.3.3, instruction 2, line 2: Delete "(120°F), (49°C)" and substitute "115°F), (46°C)".

PAGE 8

3.6: Delete entirely and substitute:

"3.6 End item seam appearance and bond strength of fusibles.

3.6.1 Seam appearance rating. The seam appearance of the armhole, side, underarm, pocket, yoke, collar and cuffs on the finished shirts shall have a minimum average rating of 3.0 after five washings when tested as specified in 4.2.3.

3.6.2 Bond strength of fusibles. After the shirt has been laundered 25 times, it shall show no bubbling or delamination of the fused plies of material when tested as specified in 4.2.3. There shall show no "strike-through" of the adhesive after fusing."

PAGE 13

Operation 6.c., line 3: Delete "3/8 inch (9.5 mm)" and substitute "3/8 to 7/16 inch (9.5 to 11 mm)".

PAGE 14

Operation 7.d: Delete entirely.

FSC 8405

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:05Z
Check the source to verify that this is the current version before use.

PAGE 18

Operation 18.a., second sentence: Delete entirely and substitute: "The facings shall finish 1-3/4 ± 1/4 inches (44 ± 6 mm) wide."

PAGE 21

Operation 22.b: Delete entirely and substitute: "22.b. Press the bottom, side seams and underarm seams on a hot head pressing machine."

Operation 22.c., line 1, after "cuffs": Add ", sleeves, collar stand".

Operation 22, under "NOTE", line 3: Delete "7.d".

PAGE 24

4.2.1, in column for "Sample unit for testing": Delete "1 yard full width" and substitute "two 24 by 24 inch specimens 1/".

Preceding "Table IV": Add "1/ Prepared by the contractor during the same period and under the same conditions as for the fusing of end item parts."

PAGE 25

4.2.3, line 4: Delete "one finished shirt" and substitute "two finished shirts".

Line 5, after "appearance requirements": Insert ", and the other shirt shall be used to evaluate for bubbling and delamination."

4.3.1.2, under "Overhead lighting procedure", line 2: Delete "124-1969" and substitute "124-1975".

PAGE 26

4.3.1.3.1, line 10: Delete "hot" and substitute "warm".

Lines 11 and 12: Delete "140° ± 5°F (60° ± 3°C)" and substitute "115° ± 5°F (46° ± 3°C)".

4.3.1.4, last three sentences: Delete entirely and substitute: "The shirts to be used for evaluation of bubbling and delamination shall be laundered 25 times as specified in 4.3.1.3.1 and the collars and cuffs shall be examined visually for bubbling or delamination. In addition, during laundering of the shirts, sufficient quantity of fusible interlining fused to basic fabric shall also be laundered 25 times for subsequent testing of adhesion properties as specified in 4.2.1".

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:05Z
Check the source to verify that this is the current version before use.

PAGE 30

6.7, line 10: Delete "30 pounds" and substitute "30 ounces".

Custodian:

Army - GL

Review activities:

Army - MD
DLA - CT

Preparing activity:

Army - GL

Project No. 8405-A728

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:05Z
Check the source to verify that this is the current version before use.