INCH-POUND

MIL-DTL-11484/326
08 July 2013

DETAIL SPECIFICATION SHEET

LAPEL BUTTON, NATIONAL INTELLIGENCE MEDAL FOR VALOR
OFFICE OF THE DIRECTOR OF NATIONAL INTELLIGENCE

This specification is approved for use by all
Departments and Agencies of the Department of Defense

The requirements for acquiring the product described herein shall consist of this specification sheet, the latest issue of MIL-DTL-11484, and a request from the Office of the Director of National Intelligence.

MATERIAL: Red Brass 85/15 (UNS Alloy C-230)

FINISH: 24K Gold Plated, Matte Finish, Polished Highlights and shall match The Institute of Heraldry (TIOH) Metal Finish Chip Number 8.

DIMENSIONS:
HEIGHT: 11/16 inch (REF)
WIDTH: 11/16 inch (REF)
THICKNESS: 0.110 ± 0.010 inch

ATTACHING DEVICE:
1. Attaching device shall be prong with pick and flat ball type clutch.

2. The prong shall be centered on the reverse side and fused or soldered to the lapel button.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T17:57Z
Check the source to verify that this is the current version before use.

NOTES:

1. The term (REF) refers to the measurements taken from the Government furnished hub or die.

2. The TIOH epoxy color chip #20, dark blue, is used where indicated.

3. If hard enamel is used then the material will be Gilding Metal 95/5 (UNS Alloy C-210).

4. This item is not authorized for commercial sale, and may be produced only under government contract and at the request of the Office of the Director of National Intelligence.

Custodian:
Army - IH

Preparing activity:
Army - IH

Review activity:
DLA - CT

(Project No. 8455-2013-162)

Civil Agency:
ODNI - NIAP

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T17:57Z
Check the source to verify that this is the current version before use.