MILITARY SPECIFICATION

CLEANING AND POLISHING PAD, NON-METALLIC
(FOR AIRCRAFT)

This amendment forms a part of Military Specification
MIL-C-83957A (USAF), 23 July 1975

Page 1

Under "American Society for Testing and Materials", delete "ASTM D1117-69" and substitute "ASTM D1117-74".

Page 3

Paragraph 3.6 Breaking strength. Delete in its entirety and substitute the following:

"3.6 Breaking strength. When tested as specified in 4.5.2 the dry breaking strength of the Type I pads shall be a minimum of 40 pounds per inch in the "machine" direction and a minimum of 30 pounds per inch in the "across the web" direction. When tested as specified in 4.5.2 the dry breaking strength of the Type II pads shall be a minimum of 20 pounds per inch in the "machine" direction and a minimum of 30 pounds per inch in the "across the web" direction."

Under Table II, Water and Chemical Resistance - LOSS IN TENSILE STRENGTH-%, make the following changes:

"TEST SOLUTION	TYPE I	TYPE II
Water	Delete "7", substitute "20"	Delete "10", substitute "30"
Mineral Spirits	Delete "10, substitute "20"	
MIL-C-25769	Delete "25", substitute "35"	

Page 5

Paragraph 4.3.1 Lot. Delete "100 pounds" and substitute "1000 pounds".

FSC 7920

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:54Z
Check the source to verify that this is the current version before use.

Paragraph 4.5.2 Water and chemical resistance. Between the third and fourth sentences add the following sentences: "Rinse the exposed pads (test samples) with a gentle stream of tap water to remove the chemical residues. Drain the bulk of the water. Place the pads between several thicknesses of absorbent paper towels and press gently to remove the balance of the water. Do not distort the pads in a way that would affect their structural integrity. Dry in a forced draft oven at 105 $\pm 2^{\circ}$ C until dry, approximately 30 minutes."

Paragraph 4.5.2 Water and chemical resistance. In the fourth sentence change "ASTM D1117-69" to read "ASTM D1117-74" and change "2X7 inches" to read "2X6 inches".

Paragraph 4.5.4 Requirements for crimped, cut filament polyester. Change "ASTM D1117-69" to read "ASTM D1117-74".

Custodian:
Air Force - 99

Preparing Activity:
Air Force - 99

Project Number:
7920-F241

U. S. GOVERNMENT PRINTING OFFICE: 1977-703-020/2155

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:54Z
Check the source to verify that this is the current version before use.