MIL-C-19853C
22 April 1982
SUPERSEDING
MIL-C-19853B
28 August 1979

MILITARY SPECIFICATION

CARBON REMOVING COMPOUND (FOR USE IN AGITATED TANK)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers requirements for the acquisition of two types of material that will remove or loosen carbon from components of internal combustion engines and compressor sections of jet engines.

1.2 Classification. The carbon removing compound shall be furnished in the following types as specified (see 6.2):

Type I - Phenolic
Type II - Non-phenolic

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. Unless otherwise specified, the following specifications, standards, and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

QQ-A-250/4	- Aluminum Alloy 2024, Plate and Sheet.
QQ-A-250/13	- Aluminum Alloy Alclad 7075, Plate and Sheet.
QQ-M-44	- Magnesium Alloy Plate and Sheet (AZ31B).
QQ-P-416	- Plating, Cadmium (Electrodeposited).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Engineering Specifications and Standards Department (Code 93), Naval Air Engineering Center, Lakehurst, NJ 08733, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6850

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-M-3171	- Magnesium Alloy, Process for Pretreatment and Prevention of Corrosion on.
MIL-L-6082	- Lubricating Oil, Aircraft Reciprocating Engine (Piston).
MIL-S-7952	- Steel, Sheet and Strip, Uncoated, Carbon (1020 & 1025) (Aircraft Quality).
MIL-A-8625	- Anodic Coatings, for Aluminum and Aluminum Alloys.

STANDARDS

FEDERAL

FED-STD-313	- Material Safety Data Sheet, Preparation and Submission of.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-290	- Packaging of Petroleum and Related Products.

(Copies of specifications, standards, handbooks, drawings and publications required by manufacturers in connection with specific acquisition functions should be obtained from the acquisition activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and supplement thereto, if applicable.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ANSI/ASTM D 891-59(1976) - Specific Gravity of Industrial Aromatic Hydrocarbons and Related Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

U.S. PHARMACOPEIAL CONVENTION, INC.

United States Pharmacopeia (USP)

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042.)

(Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Qualification. The carbon removing compound furnished under this specification shall be products which are qualified for listing on the applicable qualified products list at the time set for opening of bids (see 4.3 and 6.3).

3.2 Materials. The carbon removing compound shall be liquid at 25°C (77°F). Its composition shall be optional with the manufacturer but shall be restricted by other requirements specified herein (see 6.6). The compound shall contain no benzene.

3.3 Toxicity. The material shall have no adverse effect on the health of personnel when used for its intended purpose. Questions pertaining to the toxic effect shall be referred by the acquiring activity to the appropriate departmental medical service who will act as an advisor to the acquiring activity. Material safety data sheets shall be prepared and submitted in accordance with FED-STD-313. One copy of which shall be forwarded to the preparing activity of the specification, one copy to the acquiring activity and one copy to the Naval Environmental Health Center (see 6.4).

3.4 Alkalinity. The alkalinity of the carbon removing compound, when determined in accordance with 4.5.1, shall have a pH value not less than 9.00 nor more than 12.00.

3.5 Specific gravity. The specific gravity of the carbon removing compound, when determined in accordance with 4.5.2, shall be not less than 1.15.

3.6 Flammability. The carbon removing compound, when tested in accordance with 4.5.3, shall continue to burn no longer than 3 seconds after the removal of the flame.

3.7 Volatility. The volatility of the carbon removing compound, as received, shall be no greater than the volatility of the lower layer of the control formula product when the compound is tested in accordance with 4.5.4.

3.8 Separation of layers (type I only). When the carbon removing compound is tested individually with 12-1/2 grain hard water, distilled water and 1 percent sodium chromate solution as specified in 4.5.5, the mixtures formed shall, on standing for two hours, separate sharply into two distinct layers. The aqueous layer shall be uppermost. The volume of the upper layer shall be 25 + 2 ml in each case. There shall be no evidence of clots, curd or precipitate at the end of two hours after mixing.

3.9 Phenolic content (type II only). The type II compound, when tested as specified in 4.5.6, shall contain less than 0.03 percent by weight of phenol and/or cresol.

Source: https://assist.dla.mil -- Downloaded: 202610-19T06:47Z
Check the source to verify that this is the current version before use.

3.10 Storage stability. After being stored as specified in 4.5.7, the carbon removing compound shall show no sediment, curd or scum in the solvent layer or interface or any other evidence of deterioration and shall conform to the requirement of 3.12 when tested as specified in 4.5.10.

3.11 Oil removal. The carbon removing compound, when tested as specified in 4.5.9, shall exhibit oil removal effectiveness equal to or greater than that shown by the control formula product similarly tested.

3.12 Carbon removal. The carbon removing compound, when tested as specified in 4.5.10, shall possess carbon removal capability and speed of carbon removal equal to or greater than the control formula product.

3.13 Corrosiveness. The carbon removing compounds, when tested as specified in 4.5.11, shall cause no visible trace of corrosion, oxidation or discoloration of steel or anodized aluminum alloy and shall cause no visible corrosion and not more than slight discoloration of polished aluminum alloy, cadmium plated steel or chrome pickled magnesium alloy.

3.14 Rinsing properties. The carbon removing compound, when tested as specified in 4.5.12, shall be completely rinsed from the surface of the anodized aluminum alloy panel. The panel shall show no evidence of a sticky film, soap, lime, curd or physical dirt after it has been rinsed. The final rinse water on the panel surface shall form a smooth layer free from water break.

3.15 Compatibility (type I only). After mixing the carbon removing compound with an equal volume of control formula product in accordance with 4.5.13, the combined volume of the upper and lower layers thus formed shall be respectively equal to the sum of the original volumes of the upper and lower layers of the material prior to mixing. The resulting mixture shall be equal to or better than the control formula product in carbon removing capability.

3.16 Emulsification. The emulsion, formed when the carbon removing compound is shaken with 12-1/2 grain hard water in accordance with 4.5.14, shall show no sediment, curd, scum, or clear solvent. Creaming shall be acceptable.

3.17 Cold stability. The carbon removing compound, after being exposed to a temperature of -18 + 5°C (0 + 9°F) for one hour in accordance with 4.5.15, shall return to its original condition.

3.17 Temperature cycle (stability). After the carbon removing compound, with a steel strip partially immersed, has been stored in a glass bottle for five days as specified in 4.5.16, the compound shall show no marked variation in appearance compared to the original compound stored at room temperature in the dark. The immersed portion of the steel strip shall show no evidence of pitting, corrosion or uneven darkening. The unexposed portion of the strip shall show no evidence of corrosion. There

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

shall be no difference in appearance between the carbon removing compound that has undergone the temperature cycle (stability) test and an unexposed sample one hour after each has been shaken for one minute. The sample which has been heated shall meet the requirements for carbon removal capability (see 3.12).

3.19 Workmanship. The carbon removing compound ingredients shall be intimately blended and processed in a manner that will produce the high quality compound necessary to meet the requirements of this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection conditions. Unless otherwise specified, all tests shall be performed at a room temperature of 21° to 32°C (70° to 90°F). In case of dispute, unless otherwise specified, the test specimens shall be conditioned for a minimum of 3 hours and tested in an atmosphere of 50 ± 4% relative humidity and a temperature of 23 ± 1.1°C (73.4 ± 2°F).

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 Qualification inspection. The qualification inspection shall consist of all the examinations and tests (see table I) required under this specification.

4.3.1 Retention of qualification. In order to retain qualification of a product approved for listing on the Qualified Products List (QPL), the manufacturer shall verify by certification to the qualifying activity that the manufacturer's product complies with the requirements of this specification. The time of periodic verification by certification shall be in two-year intervals from the date of original qualification. The Government reserves the right to re-examine the qualified product whenever deemed necessary to determine that the product continues to meet any or all of the specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

4.3.2 Qualification samples. The qualification sample shall consist of 2 gallons of the carbon removing compound. The samples shall be forwarded to the Supply Officer, Naval Air Development Center, Warminster, PA 18974, Attention: Director, Aircraft and Crew Systems Technology Directorate, Code 60622. The samples shall be plainly identified by securely attached durable tags or labels marked with the following information:

Sample for qualification inspection.
CARBON REMOVING COMPOUND (FOR USE IN AGITATED TANK)
Type
Name of manufacturer.
Product code number.
Batch or lot number.
Date of manufacture.
Submitted by (name) (date) for qualification inspection in accordance with the requirements of MIL-C-19853C under authorization of (reference authorizing letter (see 6.3)).

4.3.3 Inspection report and other data. The manufacturer shall submit a report, in duplicate, to accompany the qualification inspection samples. This report shall include the results of the manufacturer's tests, reported quantitatively, where applicable, in the units specified for all of the requirements specified herein, except storage stability. Tests not conducted due to lack of special test facilities or materials shall be so noted in the report. In addition, a statement of the complete formulation of the finished material shall be furnished. Each ingredient shall be identified by a definite chemical name. Trade names alone will not be considered satisfactory. The formulation shall be clearly identified by the manufacturer's formula number. The percent of each ingredient shall also be furnished. In addition, the report shall include toxicological data and formulations required to evaluate the safety of the material for proposed use.

4.4 Quality conformance inspection. The quality conformance inspection shall consist of examination of filled containers for conformance to the packaging, packing, and marking requirements and examining and testing of the quality conformance samples (see 4.4.1.1) for all the requirements of this specification except storage stability.

4.4.1 Sampling and acceptability criteria.

4.4.1.1 Lot-by-lot sampling. Each case or large container shall be carefully identified by manufacturer's batch or control lot number. Individual samples shall not be mixed. Samples shall be placed in separate airtight and watertight containers, which shall be nearly filled, covered and sealed to prevent atmospheric effects, and shall be labeled completely with information on the lot or batch number, date of sampling, contract number, and specification number.

4.4.1.2 Size of lot. For the purpose of sampling, a lot of carbon removing compound shall consist of a manufacturer's batch. If the material cannot be identified by batch, a lot shall consist of not more than 2,000 gallons of carbon removing compound offered for delivery at one time. A batch is defined as the end product of all raw materials mixed or blended in a single operation within a 24 hour period.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

4.4.1.3 Sampling for tests. A 1-gallon sample of carbon removing compound shall be taken from each of two containers selected at random from each lot. Each sample shall be clearly identified by the product code number as specified in 4.4.1.1 and shall be subjected to all tests in this specification except storage stability. The contractor shall retain in his possession and available for inspection for each lot a certificate to the effect that the material has been processed in the same manner and degree and using the same base ingredients as the approved qualification sample. The tests shall be performed in duplicate, one determination from each sample. Where applicable, the average of the two determinations shall be reported as the test result. The lot shall be unacceptable if any test fails to meet the requirement.

4.4.2 Inspection of the end item. Inspection of the end item shall be as specified in 4.4.2.1 and 4.4.2.2.

4.4.2.1 Visual examination. The sample unit for this examination shall be one filled unit container. The content shall be examined for the defects listed below. The samples for this examination shall be selected at random in accordance with MIL-STD-105, inspection level S-3 and an acceptable quality level (AQL) 2.5 defects per hundred units.

Examine	Defect
Material	Not as specified
Appearance	Presence of foreign matter
	Not homogeneous

4.4.2.2 Net content. The sample unit for this examination shall be one filled container. The sample size shall be as specified in table II. The lot shall be unacceptable if the average net content per container for all units examined is less than specified. The volume shall be corrected to 15.6°C (60°F).

4.4.2.3 Packaging inspection. The sampling and inspection of the preservation-packaging, packing and marking shall be in accordance with the requirements of MIL-STD-290.

4.5 Test methods.

4.5.1 Alkalinity. The test for alkalinity (pH) of the carbon removing compound, as received, shall be performed at 25°C (77°F). The results shall be obtained electrometrically, using an alkali resistant glass electrode.

4.5.2 Specific gravity. The specific gravity of the carbon removing compound, as received, shall be determined by any suitable procedure specified in ANSI/ASTM D 891-59(1976).

4.5.3 Flammability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

4.5.3.1 Preparation of panel. One end of a clean metal panel, 1 by 6 inches, shall be held at an angle of approximately 45 degrees. The carbon removing compound, as received, shall be poured along the upper edge of the panel, allowing the liquid to drain freely over the surface. The liquid wetting the reverse side of panel shall be wiped clean before proceeding with the test.

4.5.3.2 Procedure. A microburner flame, not exceeding 3/16 inch in length, shall be passed back and forth along the lower edge of the panel within a 2 second period. This operation shall be repeated three times at 3 second intervals. If the liquid ignites, the burner shall be removed and observation made to determine whether the liquid continues to burn. If the liquid continues to burn, the duration of burning shall be noted.

4.5.4 Volatility. One Petri dish, 9 centimeters in diameter and 1.5 centimeters deep, shall be placed on each pan of a two pan beam balance. Sufficient carbon removing compound shall be added to cover the bottom of one of the dishes to a depth of approximately 1.0 centimeter. The control formula product, before water is added, shall be carefully poured into the other dish until the dishes are counter-balanced. The balance with the Petri dish on the pans shall be exposed for 30 minutes in a draft-free atmosphere having a temperature of 24 + 3°C (75 + 5°F). At the end of the exposure period, the comparative loss in weights shall be observed.

4.5.5 Separation of layers (type I only). Seventy five milliliters (ml) of the carbon removing compound, as received, shall be placed in each of three 100-ml glass stoppered graduated cylinders. Twenty five milliliters of 12-1/2 grain per gallon hard water, prepared as described in 4.5.14.1, shall be added to one of the cylinders. Twenty five milliliters of distilled water shall be added to the second cylinder. Twenty five milliliters of a 1.0 percent by weight sodium chromate solution shall be added to the third cylinder. Each cylinder shall be stoppered and shaken vigorously for 30 seconds. The mixture shall then be allowed to stand undisturbed for two hours. At the end of two hours the volume of the separated upper layers shall be noted as well as the formation of clots, curds or precipitates.

4.5.6 Phenol content (type II only).

4.5.6.1 Qualification test.

4.5.6.1.1 Apparatus. A liquid chromatography apparatus capable of quantitative separation of phenol and cresol shall be used. One such apparatus is the Hewlett-Packard Model 1084-A equipped with a reverse phase column (RP-8-1/4"x25 cm), an internal UV detector (254 mm), an automatic variable injector, an integrating recorder, and optionally, an external variable absorbancy detector. Any apparatus that is capable of quantitatively discerning phenol and cresol may be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

4.6.5.1.2 Procedure. A weighed portion of type II compound shall be diluted in a methyl alcohol (liquid chromatography grade): demineralized water (4:1) solution to yield an approximate 4.5 to 5.0 mg/ml solution. Twenty microliters of the solution shall be injected into the apparatus in operation under the following conditions:

Flow rate	- 1.0 ml/min
Column Temp.	- 40°C (104°F)
Pressure	- 140 bar
Recorder chart speed	- 0.5 cm/min
Attenuation	- 7 (equivalent to 0.0128 A-U/cm)

Under these conditions, phenol and cresol are eluted at 14.06 and 17.61 minutes respectively, from time of injection. The percent by weight totals shall not exceed those specified in 3.9.

4.5.6.1.3 Column purging. Prior to next sample injection, the column shall be purged as follows:

Demineralized water for 4.9 minutes, then
30% methyl alcohol for 15 minutes, then
95% methyl alcohol for 5 minutes, then
demineralized water for 5 minutes.

4.5.6.2 Quality conformance test. The manufacturer shall submit a certificate of compliance for the phenol content requirement. The certificate shall be signed by an authorized representative of the manufacturer and shall state that the compound is in conformance with 3.9.

4.5.7 Storage stability. One gallon of the carbon removing compound, as received, shall be placed in a glass container. Add a clean steel strip conforming to MIL-S-7952. The strip shall have been polished with 320 or 400A silicon carbide paper and cleaned as specified in 4.5.11.1. The surface area of both sides of the steel strip shall be equivalent to 100 square inches. The closed container shall be stored in the dark for six months at 24 ± 3°C (75 ± 5°F) following which the carbon removing compound shall be examined for sediment, curd or scum in the solvent layer or at the interface for other evidence of deterioration. If the carbon removing compound proves satisfactory, it shall be subjected to the carbon removal test (see 4.5.10).

4.5.8 Samples for test.

4.5.8.1 Test sample. Add sufficient distilled water to the carbon removing compound, as received, to provide 15 percent of the sample. Mix the solution thoroughly. Cover the container and allow the solution to stand for one hour.

4.5.8.2 Control formula product. The control formula product shall be prepared in strict conformance with the formula specified in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

4.5.9 Oil removal. A 0.020 by 3 by 6 inch anodized aluminum alloy panel shall be coated with grade 1065 or 1100 oil conforming to MIL-L-6082 and completely immersed in the lower layer of the test sample (see 4.5.8.1). Another panel shall be similarly immersed in the lower layer of the control formula product. After 30 minutes the panels shall be removed and rinsed thoroughly under tap water at 25°C (77°F). The effectiveness of the oil removal exhibited by the test sample shall be compared to that shown by the control formula product.

4.5.10 Carbon removal. A used, vapor degreased (with trichloroethylene) carbon covered, aluminum alloy aircraft engine piston shall be cut into eight sections. Seven hundred milliliters of the thoroughly mixed test sample (see 4.5.8.1) shall be poured into a one liter tall form beaker, which shall be covered and allowed to stand for one hour. A second beaker shall be prepared using the same amount of control formula product. A piston section shall be placed in each container with each section completely immersed in the lower layer. After the piston sections have soaked for 30 minutes, they shall be removed, rinsed with tap water, brushed with a soft brush and compared visually. If the carbon has not been removed sufficiently to make a satisfactory comparison, the soaking and the brushing shall be repeated. The removal effected by the test sample shall be compared to that of the control formula product. Care should be taken that sections of piston to be used in this test be taken from the same piston in such a manner that specimens with approximately equal amounts of carbon will be used in this test.

4.5.11 Corrosiveness.

4.5.11.1 Preparation of test panels. Test panels, 1 by 6 by 0.05 inches, shall be made from each of the metals specified in table IV. The panels shall be cleaned with CP acetone using a swab of absorbent cotton. The panels shall then be wiped with a paper towel, dipped in absolute ethyl alcohol and again wiped with a paper towel.

4.5.11.2 Procedure. One each of the cleaned panels prepared as specified in 4.5.11.1 shall be placed in a tall form beaker in such a way that no two panels touch each other. Add sufficient test sample (see 4.5.8.1) to completely cover the panels so that the top of the panels are beneath the upper layer and totally submerged in the bottom layer. Following an immersion time of 18 hours at room temperature, the panels shall be removed, rinsed with tap water, distilled water and then with absolute alcohol. The panels shall then be examined for evidence of corrosion, oxidation or discoloration.

4.5.12 Rinsing properties. A 1 by 6 by 0.05 inch anodized aluminum panel shall be completely immersed in the lower layer of the test sample (see 4.5.8.1) for 5 minutes. The panel shall be removed and thoroughly rinsed in a beaker containing water at 82°C (180°F). After removing the panel, it shall be examined immediately for the presence of water breaks, a sticky film, soap, lime, curd or physical dirt. The above procedure shall be repeated using kerosene at room temperature as the rinsing agent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

4.5.13 Compatibility (type I only). Thoroughly shake 100 ml of the test sample (see 4.5.8.1) and 100 ml of the control formula product. Pour the two into a 250 ml glass stoppered graduated cylinder. The mixture shall be thoroughly shaken and allowed to remain undisturbed for one hour. It shall be noted if the volume of the separated layers is equivalent to the sum of the volumes of the respective layers of the components. If the mixture separates satisfactorily, a sufficient volume of the same mixture shall be prepared to ascertain the effectiveness of the mixture as a carbon remover by subjecting it to test described in 4.5.10.

4.5.14 Emulsification.

4.5.14.1 Preparation of synthetic 12-1/2 grain hard water. Dissolve 250 milligrams (mg) of USP grade calcium acetate and 176 mg of USP magnesium sulfate in one liter of distilled water which has been boiled and cooled immediately prior to use.

4.5.14.2 Procedure. Ten milliliters of the lower layer of the test sample shall be placed in a glass stoppered graduated cylinder and 90 ml of the hard water added. The cylinder shall be closed and shaken vigorously for 30 seconds. The emulsion shall then be allowed to stand for 4 hours. It shall be noted if there is any sediment, curd, scum or clear solvent, or if creaming has resulted.

4.5.15 Cold stability. Approximately 100 ml of the thoroughly shaken test sample (see 4.5.8.1) shall be poured into a suitable size test tube and cooled to -18 ± 5°C (0 ± 9°F). The remover shall then be allowed to return to room temperature. The test tube and contents shall be inverted 10 times and then allowed to stand undisturbed for 1 hour. It shall then be noted if the test sample returns to its original condition.

4.5.16 Temperature cycle (stability).

4.5.16.1 Preparation of test sample. A 5-ounce portion of well shaken test sample (see 4.5.8.1) shall be poured into each of two chemically clean 12-ounce pressure resistant clear glass bottles which shall be 9-1/2 inches in height and 2-1/2 inches in outside diameter with shoulders 5 inches from the base. One bottle shall be capped and stored in the dark for at least 6 days at room temperature. A strip of steel, 0.020 by 1/2 by 6 inches, conforming to MIL-S-7952, shall be polished with 320 or 400A silicon carbide paper to remove surface contamination. The steel strip shall then be cleaned as specified in 4.5.11.1. The steel strip shall then be partially immersed in the test sample contained in the other test bottle and the bottle shall be capped.

4.5.16.2 Procedure. The capped bottle containing the steel strip shall be placed in an oil bath and heated at a uniform rate to a temperature of 60 ± 2°C (140 ± 4°F) in 5 hours. This temperature shall be maintained for 3 hours. No heat shall be applied to the bath overnight with the bottle being allowed to return to room temperature while in the bath. The above heating and cooling cycle shall be repeated for 5 days.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

On the morning of the sixth day, the bottle shall be removed from the bath, uncapped and the steel strip carefully withdrawn from the test sample. The strip shall be rinsed first with tap water and then with distilled water and dried. The portion of the steel strip which had been immersed in the test sample shall be examined for evidence of pitting, corrosion, and uneven darkening. The part of the strip above the surface of the test sample shall be examined for evidence of corrosion. The test sample which has undergone test with the steel strip shall be compared to the test sample in the bottle which has been stored in a dark place. Any difference in appearance shall be noted. The opened bottle shall be capped and the two bottles shall be thoroughly shaken for 1 minute, allowed to stand undisturbed for 1 hour at room temperature, then examined. If considered satisfactory, the compound which had been heated shall also be tested for carbon removal capability in accordance with 4.5.10.

5. PACKAGING

5.1 Packaging, packing and marking. The carbon removing compounds shall be packaged, packed and marked in accordance with the provisions of MIL-STD-290. Unless otherwise specified by the acquiring activity, the carbon removing compound shall be packed in 5-gallon containers and level A packaging and packing shall be employed.

5.1.1 Label. In addition to any marking required by MIL-STD-290 or the contract or order, each container shall have a label marked with the following precautions:

PRECAUTIONS:

1. Carbon removing compound contained herein is harmful to skin and eyes and
   contains the following toxic ingredients (list ingredients):
2. Avoid contact of carbon removing compound with rubber, asphaltic base floors and walkways.
3. Avoid use in enclosed and unventilated areas.
4. Store carbon remover indoors or in an area well-protected against weather conditions.
5. Store below 27°C (80°F).
6. Discard any bulging or distorted containers.
7. Content may be under pressure in storage. Open cautiously to avoid injury.

6. NOTES

6.1 Intended use. The carbon removing compounds covered by this specification are intended for removing or loosening carbon from components of internal combustion engines and compressor sections of jet engines by means of immersion at room temperature in agitated tanks. These compounds may be used effectively in conjunction with ultrasonic cleaning devices. Water or a 0.5 to 1.0 percent sodium chromate solution should be added to retard evaporation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

Type I - The use of type I should be limited to activities that are equipped for the disposal of phenols.

Type II - Type II is designed for use at all activities.

6.2 Ordering data.

6.2.1 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.
b. Type desired (see 1.2).
c. Quantity of carbon removing compound in terms of U.S. Gallons at 15.6°C (60°F).
d. Type and capacity of containers in which carbon removing compound is to be furnished.
e. Applicable levels of packaging and packing, if not as specified in 5.1 (see 6.2.1).

6.2.1 Options. In the preparation of contracts or orders, it must be noted that various options, choices and alternatives, as indicated in MIL-STD-290, may be exercised in the preparation of this carbon removing compound for delivery.

6.3 Qualification. With respect to products requiring qualificaiton, awards will be made only for products which are at the time set for opening of bids, qualified for inclusion in the applicable Qualified Products List whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for the Qualified Products List is the Naval Air Systems Command, Department of the Navy, Washington, DC 20361; however, information pertaining to qualification of products and authorization for submittal of sample may be obtained from the Director, Aircraft and Crew Systems Technology Directorate, Code 60622, Naval Air Development Center, Warminster, PA 18974.

6.3.1 Withdrawal from qualified products list. Material furnished under contract shall be identical to carbon removing compound samples which have been submitted by the manufacturer and have been inspected and approved for inclusion in the Qualified Products List. In the event that material furnished under contract is found to deviate from the composition of the approved product or that the product fails to perform satisfactorily in service, approval of such material will be subject to immediate withdrawal from the Qualified Products List.

6.4 Safety data sheet. A copy of the material safety data sheet should be forwarded to the Navy Environmental Health Center, Naval Station, Norfolk, VA 23511.

Source: https://assist.dla.mil -- Downloaded: 20260-19T06:47Z
Check the source to verify that this is the current version before use.

6.5 Safety. Contact the local industrial hygienist for safe handling advice.

6.6 Seal. Neither type of carbon removing compound furnished under this specification contains a seal.

6.7 Cross-reference of classification. The classification under this revision differs from that of the previous as follows (see 1.2):

MIL-C-19853C	MIL-C-19853B
Type I - Phenolic	Type I - Single layer (Phenols permitted)
Type II - Non-phenolic	Type II - Two layer - contains water seal (phenols prohibited)

6.8 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Navy - AS
Air Force - 11

Preparing activity:
Navy - AS

(Project No. 6850-0674)

Review activities:
Navy - MS
DLA - GS

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification inspection.

Inspection	Paragraph	
	Requirement	Test method
Alkalinity	3.4	4.5.1
Specific gravity	3.5	4.5.2
Flammability	3.6	4.5.3
Volatility	3.7	4.5.4
Separation of layers (Type I only)	3.8	4.5.5
Phenol Content (type II only)	3.9	4.5.6
Storage stability	3.10	4.5.7
Oil removal	3.11	4.5.9
Carbon removal	3.12	4.5.10
Corrosiveness	3.13	4.5.11
Rinsing properties	3.14	4.5.12
Compatibility (type I only)	3.15	4.5.13
Emulsification	3.16	4.5.14
Cold stability	3.17	4.5.15
Temperature cycle(stability)	3.18	4.5.16

TABLE II. Net content.

Lot size (containers)	Sample size (containers)
Up to 50	5
51 - 500	7
501 - 35,000	8
35,001 and over	11

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

TABLE III. Control formula product. 1/

Ingredients	Percent composition by weight
Cresol (USP)	33.62
Phenol (USP)	1.00
Oleic acid (USP)	6.80
Potassium hydroxide (45 percent)	3.52
Methylene chloride	54.90
Ethylene diamine tetraacetic acid	0.16

1/ Eighty five (85) parts by volume of the control formula product shall be mixed with fifteen (15) parts by volume of distilled water.

TABLE IV. Metal test panels.

No.	Metal	Specification	Surface	Specification
1	Aluminum clad Aluminum alloy	QQ-A-250/13	-	-
2	Aluminum alloy	QQ-A-250/4	Anodized	MIL-A-8625
3	Steel	MIL-S-7952	Polished	-
4	Steel	MIL-S-7952	Cadmium	QQ-P-416
5	Magnesium alloy	QQ-M-44 condition H	Chrome pickled	MIL-M-3171 type I

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:47Z
Check the source to verify that this is the current version before use.