A-A-0051489 (DM)
11 June 1986

INTERIM COMMERCIAL ITEM DESCRIPTION

CATHETER, URETHRAL, RUBBER, FOLEY

The General Services Administration has authorized the use of this interim commercial item description which was developed by the Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA, 19101, based upon currently available technical information.

This interim commercial item description covers a sterile rubber urethral catheter of the Foley design.

Salient characteristics.

Material. The catheter shall be manufactured of natural rubber. The catheter may have a thin coating of silicon or teflon.

Style and design. The catheter shall be of the Foley design with one drainage and one inflation lumen. The catheter shall be a minimum of 13 inches in length, excluding the funnel. The catheter shall be in accordance with all design requirements of American Society for Testing and Materials (ASTM) Standard F623.

Sterility. Catheters shall be tested for sterility in accordance with the current United States Pharmacopiea (USP).

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:56Z
Check the source to verify that this is the current version before use.

Product Quality Level

Physical properties testing. Catheters shall be tested for breaking strength and ultimate elongation before and after accelerated aging. Federal Test Methods number 4111 and number 4121 of Federal Test Method Standard No. 601 shall be used for breaking strength and ultimate elongation respectively, except that two specimens shall be cut from each catheter and the median determination described in the Test Methods disregarded. One specimen shall be tested aged and one shall be tested unaged. Aging shall be performed using Test Method 7221 or 7231 of Standard 601. The breaking strength (described as breaking force in the Test Method) shall be as indicated in Table I and the ultimate elongation shall be 750 percent minimum for unaged specimens. The breaking strength and ultimate elongation shall not decrease by more than 25 percent after aging.

Table I. Physical characteristics

Size (French)	Breaking strength (pounds)
14	20
16	28
18	36
20	44
22	52
24	60
26	68

In addition, catheters shall not become tacky, or brittle, or hard, after aging. Ten catheters shall be tested from each lot. More than one test failure (each, aged and unaged) shall be cause for rejection.

Performance. Catheters shall be tested for performance in accordance with the performance tests of ASTM Standard F623. As an alternate test method for the Balloon Integrity and Balloon Volume Maintenance Tests, catheters may be overinflated with 50 cc of air, submerged in water, and the entire inflation system checked for leakage. Sampling for performance tests shall be S-1 (minimum) with an AQL of 1.0, except for deflation reliability. For deflation reliability, any test failure shall be cause for rejection.

As an alternate test method for shaft size, the shaft may be measured by any acceptable method without cutting the shaft.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:56Z
Check the source to verify that this is the currentversion before use.

Certificate of biocompatibility. A certifcate of compliance, stipulating offered items meet the requirements specified herein, shall be acceptable, provided that the contractor has supplied acceptable items to the Government within the past three years, and that there has been no changes to material formulation and method of processing. The certificate shall include the current contract number and applicable NSN, the date of actual testing, the test method and results, the name and title of the person evaluating test results, and a statement to the effect that material formulation and processing have not changed since the testing was performed.

Visual examination. Catheters shall be examined for compliance with all requirements of this specification.

Workmanship. The catheter shall be processed in such a manner as to be uniform and free from defects that will affect life, serviceability, or appearance.

Unit. Package (PG). Each catheter shall be individually packaged in a peel open type container capable of maintaining sterility of contents unless package is damaged or opened. One package containing 12 individually packaged catheters, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:56Z
Check the source to verify that this is the current version before use.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. The unit of product for test purposes shall be one catheter.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:56Z
Check the source to verify that this is the currentversion before use.

NOTE: The following National Stock Numbers are covered by this document:

NSN	ITEM IDENTIFICATION
6515-01-098-3623	CATHETER, URETHRAL, Rubber, Round Tip, Modified Foley, with cc (ml) Bag, Valve Type, 14 Fr, 12s
6515-01-098-8355	CATHETER, URETHRAL, Rubber, Round Tip, Modified Foley, with cc (ml) Bag, Valve Type, 16 Fr, 12s
6515-01-098-8356	CATHETER, URETHRAL, Rubber, Round Tip, Modified Foley, with cc (ml) Bag, Valve Type, 18 Fr, 12s
6515-01-098-8357	CATHETER, URETHRAL, Rubber, Round Tip, Modified Foley, with cc (ml) Bag, Valve Type, 20 Fr, 12s
6515-01-098-8358	CATHETER, URETHRAL, Rubber, Round Tip, Modified Foley, with cc (ml) Bag, Valve Type, 22 Fr, 12s
6515-01-098-8360	CATHETER, URETHRAL, Rubber, Round Tip, Modified Foley, with cc (ml) Bag, Valve Type, 24 Fr, 12s
6515-01-098-8359	CATHETER, URETHRAL, Rubber, Round Tip, Modified Foley, with cc (ml) Bag, Valve Type, 26 Fr, 12s

Ordering data (Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order).

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS

PGC 05970

Project No. 6515-3757

☆U.S. GOVERNMENT PRINTING OFFICE: 1986 — 605-036/44065

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:56Z
Check the source to verify that this is the current version before use.