A-A-51500
20 June 1986

COMMERCIAL ITEM DESCRIPTION

NAIL, BONE, HANSEN-STREET
DIAMOND CROSS SECTION, ONE END THREADED

The General Services Administration has authorized the use of this commercial item description.

This commercial item description covers bone nails of the Hansen-Street design, diamond cross section, one end threaded, suitable for intramedullary surgical procedures.

Salient characteristics:

Characteristics. Bone nails shall be in accordance with ASTM F455 for Type II intramedullary nails. Nails shall have one end threaded.

Material. Bone nails shall be fabricated from material conforming to the composition specified in ASTM F138, Grade 2. Grain size of the raw material shall be five or finer.

Surface preparation. Description of surface characteristics and methods of surface preparation shall be in accordance with ASTM F86.

Finish. The completed bone nail shall have a bright, smooth, mirror finish, properly passivated.

Corrosion properties. Bone nails shall show no evidence of corrosion when subjected to the following tests:

Intergranular corrosion. The intergranular corrosion susceptibility test specified in ASTM F138.

Saline. Bone nails shall be completely immersed into Normal Saline Solution (USP), and while immersed, placed into an oven at a temperature of 37° + 1°C for a period of seven days, removed from the oven and examined for corrosion while still immersed.

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:56Z
Check the source to verify that this is the current version before use.

Boil. Bone nails shall be scrubbed with soap and water, rinsed thoroughly in distilled water, and dried. After cleaning, the instruments shall be boiled in distilled water in a glass beaker for 30 minutes,and allowed to remain submerged for an additional 24 hours.

Workmanship. The bone nails shall be free from defects which detract from their appearance or impair their serviceability.

Product Quality Level.

Visual and dimensional examination. Shall be examined to verify that design, construction and workmanship are in accordance with applicable requirements.

Materials. The supplier shall be responsible for performing tests to assure that materials are in accordance with requirements specified.

Unit. Each (EA). One bone nail, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:56Z
Check the source to verify that this is the current version before use.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105. The acceptable quality level (AQL) shall be 0.65 for an insppectin level of S-4. The unit of product for test purposes shall be one bone nail.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:56Z
Check the source to verify that this is the current version before use.

NOTE: The following National Stock Numbers and their respective sizes and styles are covered by this document:

National Stock Number	Length	Diameter
6515-01-139-8524	32cm	11mm x 8mm
6515-01-139-8525	34cm	11mm x 8mm
6515-01-139-8526	36cm	11mm x 8mm
6515-01-139-8527	38cm	11mm x 8mm
6515-01-139-8528	40cm	11mm x 8mm
6515-01-139-8529	42cm	11mm x 8mm
6515-01-139-8530	44cm	11mm x 8mm
6515-01-139-8531	46cm	11mm x 8mm
6515-01-139-8532	48cm	11mm x 8mm
6515-01-139-8533	50cm	11mm x 8mm
6515-01-139-8534	32cm	13mm x 11mm
6515-01-139-8535	34cm	13mm x 11mm
6515-01-139-8536	36cm	13mm x 11mm
6515-01-139-8537	38cm	13mm x 11mm
6515-01-139-8538	40cm	13mm x 11mm
6515-01-139-8539	42cm	13mm x 11mm
6515-01-139-8540	44cm	13mm x 11mm
6515-01-139-8541	46cm	13mm x 11mm
6515-01-139-8542	48cm	13mm x 11mm
6515-01-139-8543	50cm	13mm x 11mm
6515-01-139-8544	52cm	13mm x 11mm

Ordering data (Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order).

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS

06094

Project No. 6515-3273

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:56Z
Check the source to verify that this is the current version before use.