A-A-0051520 (DM)
10 July 1986

INTERIM COMMERCIAL ITEM DESCRIPTION

SCREW, BONE, CANCELLOUS

The General Services Administration has authorized the use of this interim commercial item description which was developed by the Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA, 19101, based upon currently available technical information.

This interim commercial item description covers a bone screw implant suitable for scaphoid and routine large cancellous fragment procedures.

Salient characteristics.

Bone screw shall have a major thread diameter of 6.5 mm. Shaft diameter shall be 4.5 mm. Core diameter shall be 3.0 mm. Head of screw shall be in accordance with ASTM F543 (Figure 5).

Bone screw shall have an effective thread length of 32 mm. Thread profile shall be in accordance with ISO 5835/1 for deep, code HB 6,5 thread.

Tolerances shall be in accordance with ASTM F543.

Material. Bone screw shall be fabricated from cold drawn wire conforming to the composition specified in ASTM F138, Grade 2.

Surface preparation. Description of surface characteristics and methods of surface preparation shall be in accordance with ASTM F86.

Finish. The completed bone screw shall have a mirror finish, properly passivated.

Corrosion properties. Bone screws shall show no evidence of corrosion when subjected to the following tests:

Intergranular corrosion. The intergranular corrosion susceptibility test specified in ASTM F138.

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:57Z
Check the source to verify that this is the current version before use.

Saline. Bone screws shall be completely immersed into Normal Saline Solution (USP), and while immersed, placed into an oven at a temperature of 37° + 1°C for a period of seven days, removed from the oven and examined for corrosion while still immersed.

Boil. Bone screws shall be scrubbed with hot alkaline cleaner to the point of being free from water break, rinsed in distilled water, and boiled in distilled water in a glass beaker for 30 minutes. Screws shall be allowed to remain submerged for an additional 24 hours prior to examination.

Workmanship. The bone screw shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Each (EA). One bone screw, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Responsibility for compliance. All items must meet all requirements specified herein. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all the requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:57Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. The acceptable quality level (AQL) shall be 0.65 for an inspection level of S-2. The unit of product for test purposes shall be one bone screw.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:57Z
Check the source to verify that this is the currentversion before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

NSN	ITEM IDENTIFICATION
6515-01-168-0109	SCREW, BONE CANCELLOUS, Spherical Head, Hexagonal Socket, 6.5 mm Thread Diameter by 50 mm Length
6515-01-168-0110	SCREW, BONE CANCELLOUS, Spherical Head, Hexagonal Socket, 6.5 mm Thread Diameter by 55 mm Length
6515-01-168-3791	SCREW, BONE CANCELLOUS, Spherical Head, Hexagonal Socket, 6.5 mm Thread Diameter by 60 mm Length

Ordering data (Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order).

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS

Project No. 6515-3776

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:57Z
Check the source to verify that this is the current version before use.