METRIC
DOD-C-24654
25 July 1985

MILITARY SPECIFICATION

COATINGS, EPOXY, POTABLE WATER TANKS (METRIC)

This specification is approved for use by all Departments and Agencies of the Department of Defense

1 SCOPE

1 1 Scope. This specification covers epoxy coating systems for protecting interior surfaces of steel or aluminum tanks used for the transportation and storage of potable water It provides for three classes, (two) of which are suitable for use under Air Pollution Regulations

1 2 Classification Coating systems covered by this specification shall be of the following types as specified (see 6 2)

Type I - For use on steel surfaces.
Type II - For use on aluminum surfaces
Class 1 - For use where air pollution regulations for solvents in marine coatings do not apply.
Class 2 - For use where air pollution regulations for solvents in marine coatings apply.
Class 3 - For use in geographical areas where solvent content in paint is limited to 0.34 kilograms per liter (kg/liter) (2 8 pounds per gallon).

2 APPLICABLE DOCUMENTS

2 1 Government documents

2 1 1 Specifications and standards Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein

SPECIFICATIONS

FEDERAL
PPP-B-585 - Boxes, Wood, Wirebound
PPP-B-636 - Boxes, Shipping, Fiberboard

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to Commander, Naval Sea Systems Command, SEA 55Z3, Department of the Navy, Washington, DC 20362-5101 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter

FSC 8010

DISTRIBUTION STATEMENT A Approved for public release, distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

FEDERAL (Continued)
PPP-C-96 - Cans, Metal, 28 Gage and Lighter.
PPP-P-704 - Pails, Metal: (Shipping, Steel, 1 through 12 Gallons).

MILITARY
MIL-C-11133 - Crates, Shipping, Wood, Open, Wirebound

STANDARDS

FEDERAL
FED-STD-141 - Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing.
FED-STD-313 - Material Safety Data Sheets Preparation and the Submission of.
MILITARY
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of specifications and standards required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer)

2.2 Other publications The following documents form a part of this specification to the extent specified herein The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)
A 366 - Standard Specification for Steel, Sheet, Carbon, Cold-Rolled, Commercial Quality. (DoD adopted)
D 185 - Standard Test Methods for Coarse Particles in Pigments, Pastes, and Paints (DoD adopted)
D 523 - Standard Test Method for Specular Gloss. (DoD adopted)
D 562 - Standard Test Method for Consistency of Paints Using the Stormer Viscometer (DoD adopted)
D 714 - Standard Method for Evaluating Degree of Blistering of Paints. (DoD adopted)
D 1210 - Standard Test Method for Fineness of Dispersion of Pigment-Vehicle Systems (DoD adopted)
D 1364 - Standard Test Method for Water in Volatile Solvents (Fischer Reagent Titration Method). (DoD adopted)
D 1475 - Standard Test Method for Density of Paint, Varnish, Lacquer, and Related Products. (DoD adopted)
D 1640 - Standard Test Methods for Drying, Curing, or Film Formation of Organic Coatings at Room Temperature (DoD adopted)
D 1729 - Standard Practice for Visual Evaluation of Color Difference of Opaque Materials (DoD adopted)
D 2369 - Standard Test Method for Volatile Content of Coatings (DoD adopted)
D 2621 - Standard Method for Infrared Identification of Vehicle Solids from Solvent-Type Paints

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) (Continued)

D 2698 - Standard Method for Determination of the Pigment Content of Solvent-Reducible Paints by High-Speed Centrifuging (DoD adopted)

D 3271 - Standard Method for Direct Injection of Solvent-Base Paints Into a Gas Chromatograph for Solvent-Analysis.

D 3278 - Standard Test Methods for Flash Point of Liquids by Setaflash Closed-Cup Apparatus. (DoD adopted)

D 3335 - Standard Test Method for Low Concentrations of Lead, Cadmium, and Cobalt in Paint by Atomic Absorption Spectroscopy (DoD adopted)

D 3630 - Standard Practice for Determining Constituents Classified as Hazardous Contained in Protective Coatings

E 260 - Standard Recommended Practice for General Gas Chromatography Procedures

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC , AGENT

National Motor Freight Classification

(Application for copies should be addressed to the National Motor Freight Traffic Association, Inc , ATA TRAFFIC Dept., 1616 "P" Street, NW, Washington, DC 20036)

SOUTH COAST AIR QUALITY MANAGEMENT DISTRICT

Rules and Regulations - Rule 102, 442, 443 and 1107

(Application for copies should be addressed to the South Coast Air Quality Management District, 9150 E. Flair Drive, El Monte, CA 91731)

STANDARD METHODS FOR THE EXAMINATION OF WATER AND WASTEWATER

204A - Color, Visual Comparison Method.

207 - Odor.

211A - Taste Threshold Test

408E - Chlorine Residual, DPD Colorimetric Method.

510C - Phenol, Direct Photometric Method.

(Application for copies should be addressed to the American Public Health Association, 1015 Fifteenth Street, NW, Washington, DC 20036)

UNIFORM CLASSIFICATION COMMITTEE AGENT

Uniform Freight Classification Ratings, Rules and Regulations

(Application for copies should be addressed to the Uniform Classification Committee Agent, Tariff Publication Officer, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

(Industry association specifications and standards are generally available for reference from libraries They are also distributed among technical groups and using Federal agencies)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

2 3 Order of precedence In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence

3 REQUIREMENTS

3 1 Qualification The coatings furnished under this specification shall be products which are qualified for listing on the applicable qualified products list at the time set for opening of bids (see 4 3 and 6 4)

3 2 Materials The epoxy coating system shall be composed principally of an epoxy resin converted with either amine adduct or polyamides to yield stable products meeting the requirements of this specification and certified in accordance with 4 3 2 Ketimine converted epoxy coating systems shall not be acceptable for potable water tank use

3 2 1 Solvents For types I and II coatings, the following solvent content requirements shall apply

3 2 1 1 Class 1 coating system The solvent portion shall not contain ketones Certification shall be in accordance with 4 3.2

3 2 1 2 Class 2 coating system The solvent portion shall conform to requirements specified herein by volume.

(a) Aromatic compounds with eight or more carbon atoms except ethyl benzene 8 percent maximum
(b) Ethyl benzene, trichloroethylene, and toluene 20 percent maximum.
(c) Total of aldehydes or olefins, less than 5 percent
(d) Ketones negative
(e) Total of a, b, and c 20 percent maximum

3 2 1 3 Class 3 coating system The total solvent content shall not exceed 0 34 kilogram/liter (2 8 pounds per gallon).

3.2 2 Toxicity The material shall have no adverse effect on the health of personnel when used for its intended purpose Phenolic compounds, asbestos containing fillers and harmful metallic compounds such as lead, mercury, and arsenic shall not be permitted, and the contractor shall provide certification to this effect in accordance with 4.3.2. Questions pertinent to this effect shall be referred by the contracting activity to the appropriate service medical department which will act as advisor to the contracting activity For qualification purposes, documented evidence of acceptance of the paint product for contact with potable water, and a Material Safety Data Sheet (MSDS) for the paint components, shall be forwarded to the Chief, Naval Medical Command (NAVMED), Department of the Navy, Washington, DC 20372. No coating systems shall be qualified to this specification unless approved for contact with potable water by NAVMED although the other tests specified herein may be conducted in advance of the medical review if desired

3 3 Identification characteristics Values for identification characteristics shall be provided by individual manufacturers for characteristics as indicated by "X" in table I The values shall be established for each coating system

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

prior to qualification testing The purpose of these values is to serve as a basis for determining that the material being offered is essentially the same as that which was approved under qualification testing. Subject to approval by the Naval Sea Systems Command (NAVSEA), alternative means of identification (for example, infrared spectrographic examination and chemical analysis), may be substituted for the characteristics in table I, provided appropriate data are submitted by the contractor Quality conformance inspection shall be as specified (see 4.4)

TABLE I. Identification characteristic values.

Characteristic	Coating component 1/	Mixed coating 2/	Applied coating 3/
Chemical nature	X		
Percent of principal constituents (5 percent or more of total)	X		
Percent pigment	X		
Percent nonvolatile vehicle	X		
Percent volatile	X		
Pigment components	X		
Total vehicle components	X		
Nonvolatile vehicle components	X		
Volatile vehicle components	X		
Epoxy resin content	X		
Amine nitrogen content	X		
Water in paint	X		
Coarse particles	X		
Consistency	X	X	
Mass per liter	X	X	
Flash point	X	X	
Condition in container		X	
Fineness of grind	X	X	
Dilution stability		X	
Dry-hard time		X	
Pot life		X	
Solvent retention test			X
MEK rub test			X
Color (dry film)			X
Gloss			X
Application properties			X
Chlorine residual test			X
Color in water test			X
Taste in water test			X
Odor in water test			X
Headspace IR analysis (Gas Chromatograph Analysis ASTM D 3271)			X
Phenolic equivalent test			X
Water extractable substances			X
Adhesion			X

See footnotes at end of table

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

TABLE I Identification characteristic values. - Continued

Characteristic	Coating component 1/	Mixed coating 2/	Applied coating 3/
Immersion tests			X
Aluminum alloy compatibility (type II only)			X
Sag test			X

1/ Coating components are individually packaged components such as the epoxy base (component A) and hardener (component B).
2/ Mixed coatings are the epoxy base and hardener mixed for application.
3/ Applied coating is the total coating system as applied (number and type of coats and approximate dry film thickness as tested for qualification approval)

3.3.1 Infrared identification. Products approved under this specification shall be given infrared analysis as specified in 4.5 1 5 and 4 5 1 6, and the spectrums filed for reference in surveillance testing of contractors products.

3 3.2 Gas chromatographic identification. Products approved under this specification shall be given gas chromatographic analysis as specified in 4 5 1 7, and the curves filed for reference in surveillance testing of contractors products.

3 3.3 Energy dispersive X-ray (EDX) identification. Products approved under this specification shall be given X-ray analysis as specified in 4 5 1 4, and the results filed for reference in surveillance testing of contractors products.

3 3 4 Service performance. The contractor shall prepare service performance data as specified in 4.3.2 on a minimum of two potable water tank applications with the QPL request The coating systems shall continue to provide protection against corrosion with a total of 10 percent maximum touch-up for a minimum period of 5 years The coating system shall provide superior performance (10 percent maximum touch-up) for a period of time not less than 5 years

3 3 5 Material safety data sheet The contracting activity shall be provided a material safety data sheet (MSDS) as specified in 4 3 2 at the time of contract award The MSDS form and requirements for its preparation are found in FED-STD-313 The MSDS shall be included with each shipment of the material covered by this specification The MSDS shall list the complete composition of the product, provide available pertinent toxicity information, and delineate acceptable personal protective measures for use when applying the product. Those constituents comprising more than 5 percent shall be stated to the nearest 5 percent, those comprising less than 5 percent shall be stated to the nearest 0 5 percent, and those comprising less than 0 5 percent shall be so indicated

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

3 4 Qualitative requirements

3.4.1 Curing agents. Curing agents shall be safe to handle during mixing operations from a toxicological standpoint. The mixing ratio shall be one to four parts curing agent component to four parts resin component by volume for the primers and the finish coat Ketimine curing agents, phenolic compounds and ketones shall not be acceptable in the curing agent component as specified in 4.3.2

3 4.2 Pot life The pot life of the coatings, mixed and ready for application, shall be a minimum of 4 hours at 21 degrees Celsius (°C) (70 degrees Fahrenheit (°F)), and 80 percent relative humidity, and shall conform to 3.4.7 when tested in accordance with 4 5 2.2

3 4 3 Color The epoxy coating system shall be composed of coats having a 45-degree directional reflectance of not less than 30 with the exception of the prime coat Succeeding coats shall be of contrasting color, and the topcoat shall be white, blue, or a very light pastel shade Color retention test shall be accordance with 4.5.3.4.

3 4.4 Flash point. Coatings shall not flash at temperatures lower than 35°C (95°F) when tested in accordance with ASTM D 3278

3 4 5 Dilution stability. When thinned, the mixed paint shall remain stable and uniform showing no precipitation, separation, or curdling (see 4.5.2 1).

3.4 6 Odor. The odor shall be characteristic of the volatiles permitted. Testing shall be in accordance with 4.5.3.6.

3.4 7 Application characteristics. The coating systems shall be readily applied by brush (touch up areas only) and spray, using commercially available equipment (see 4.5 2.4 and 4 5.2.5). The coatings shall exhibit reasonable leveling without excessive sagging when applied at proper film thickness as recommended by the manufacturer. Adhesion between coats shall be adequate for performance in service without undue restrictions concerning timing, temperature, or other conditions associated with application Adhesion testing shall be in accordance with 4.5.4.3. The sag resistance (multinotch blade) when performed in accordance with 4.5.2 6 shall be not less than 150 percent of the recommended wet film thickness of the coating under test.

3 4.8 Condition in container Each coating system shall be usable in accordance with 4 5.2.3, shall be readily broken up with a paddle to a smooth uniform consistency, and shall not liver Each coating shall not increase more than one-third in viscosity, or alternatively shall have no viscosity increase which cannot be compensated for by addition of a maximum of 5 percent of thinner similar to that used in the coating, or increase more than one-fifth in time of dry, nor show any other objectionable properties for at least 1 year.

3 4.9 Immersion resistance. The coating systems when tested in accordance with 4.5.4.3 through 4.5 4.5 shall show no film failure other than moderate change in appearance and a maximum failure of 3 percent of the total area. Coatings shall show no pinhole rusting, loss of adhesion, or blisters more numerous than "few" nor larger than size no 4 when compared to the photographic standards of ASTM D 714 The 3 percent failure shall be a combination of all

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

blister sizes Very fine blisters (no 8 size of ASTM D 714) or surface imperfections that may appear during the first 2 weeks (see 4 5 4 4) whose rate of growth is negligible or very slow shall not be counted Blister formation within 12 7 millimeters (mm) (1/2 inch) of the panel edge shall not be considered a failure

3 4 10 Solvent retention test The cured film of the coating system shall not retain solvents in excess of 5 percent when tested as specified in 4 5 3 8 An alternative that may be used to determine degree of solvent retention is Scanning Differential Coulometry

3 4 11 MEK rub test The cured film of the coating system shall not soften nor erode when exposed to methyl ethyl ketone (MEK) when tested as specified in 4 5 3 9

3 4 12 Phenolic equivalents The cured film of the coating system shall not leach phenolic compounds in excess of 1 part per million (p/m) when tested as specified in 4 5 3 10

3 4 13 Water extractable substances The coating system shall not release more than 0 5 milligrams (mg) of water extractable material per 6 45 square centimeters (cm^2) of coated surface when tested as specified in 4 5 4.2

3 4 14 Pigment components by atomic absorption (AA) analysis The pigments shall not contain compounds of arsenic, cadmium, chromium, lead, or mercury when tested as specified in 4 5 1 4

3 4 15 Total vehicle components The infrared spectra of the total vehicle component in either component A or component B shall not have the 5 7 to 5 9 mm absorption peak, indicating the presence of ketone solvents when tested as specified in 4 5 1 5

3 4 16 Nonvolatile vehicle components. The infrared spectra of the nonvolatile component in either component A or component B shall coincide with those submitted by the coating manufacturer when tested as specified in 4 5 1.6

3 4 17 Chlorine residual. A decrease of 50 percent or more in chlorinated water concentration after 24 hours shall constitute a failure when tested as specified in 4 5 3 3

3 4 18 Color in water Color unit values exceeding 10 shall constitute a failure when tested as specified in 4 5 3 4.

3 4 19 Taste in water. Threshold taste values exceeding 2 shall constitute a failure when tested as specified in 4 5 3 5.

3 4 20 Odor in water Threshold odor values exceeding 2 shall constitute a failure when tested as specified in 4 5 3 6

3 4 21 Headspace infrared analysis The presence of strong absorption peaks of greater than 10 percent in the vapor infrared spectra in the 3 4, 5 8, 6 2, 6 8, 7 2, 12.0, 12 4, 13 0, or 13 4 micrometer (µm) regions shall constitute a failure when tested as specified in 4 5.3 7

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

3 4.22 Aluminum alloy compatibility. Type II coating shall inhibit aluminum oxide penetration of the film as specified in 4 8 Not applicable to type I

4 QUALITY ASSURANCE PROVISIONS

4 1 Responsibility for inspection Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements

4 1 1 Inspection system The contractor shall provide and maintain an inspection system as specified in the contract or order (see 6 2)

4 2 Classification of inspections The inspection requirements specified herein are as follows

(a) Qualification inspection (see 4 3)
(b) Quality conformance inspection (see 4 4)

4 3 Qualification inspection. Qualification inspection shall be conducted at a laboratory satisfactory to NAVSEA Qualification inspection shall include the submission of ingredient samples and certification data as specified in 4 3 1 and 4 3.2 and qualification tests as specified in table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

TABLE II. Test procedures.

Item	Applicable test method in FED-STD-141	Applicable ASTM test method	Test paragraph	Requirement paragraph	Quality conformance	Qualification inspection
Chemical nature						X
Percent of principal constituents (5 percent or more of total)						X
Percent pigment	4021	-----	4.5.1.1	1/	X	X
Percent volatile	----	D 2369	-------	1/	X	X
Percent nonvolatile vehicle	4053	------	-------	1/	X	X
Water in paint	----	D 1364	-------	1/	X	X
Coarse particles	----	D 185	-------	1/	X	X
Consistency	----	D 562	-------	1/	X	X
Mass per liter	----	D 1475	-------	1/	X	X
Dry-hard time	----	D 1640	-------	1/	X	X
Fineness of grind	----	D 1210	-------	1/	X	X
Flash point	----	D 3278	-------	1/	X	X
Pot life	----	------	4.5.2.2	1/	X	X
Color (dry film)	----	D 1729	-------	1/		X
Gloss	----	D 523	-------	1/		X
Epoxy resin content	7401	------	4.5.1.2	1/		X
Amine nitrogen content	7391	------	4.5.1.3	1/		X
Pigment components	----	D 2698	4.5.1.4	1/ 3.4.14		X
Total vehicle components	----	------	4.5.1.5	1/ 3.4.15		X
Nonvolatile vehicle components	----	D 2621	4.5.1.6	1/	X	
Volatile vehicle components	----	E 260	4.5.1.7	1/		X
Dilution stability	4203	------	4.5.2.1	1/ 3.4.5	X	X
Condition in container	3011	------	4.5.2.3	1/ 3.4.8	X	X
Brushing properties	4321	------	4.5.2.4	3.4.7		
Spraying properties	4331	------	4.5.2.5	3.4.7		
Chlorine residual test	----	------	4.5.3.3	1/ 3.4.17		X
Color in water test	----	------	4.5.3.4	1/ 3.4.18		X

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

TABLE II. Test procedures. - Continued

Item	Applicable test method in FED-STD-141	Applicable ASTM test method	Test paragraph	Requirement paragraph	Quality conformance	Qualification inspection
Taste in water test	----	------	4.5.3.5	1/ 3.4.19		X
Odor in water test	----	------	4.5.3.6	1/ 3.4.20		X
Headspace IR analysis (standard gas chromatographic analysis)	----	D 3271	4.5.3.7	1/ 3.4.21		X
Solvent retention test	----	------	4.5.3.8	1/ 3.4.10	X	X
MEK rub test	----	------	4.5.3.9	1/ 3.4.11	X	X
Ketone test	----	------	4.5.1.5	3.4.11		
Phenolic equivalent test	----	------	4.5.3.10	1/ 3.4.12		X
Water extractable substances	----	------	4.5.4.2	1/ 3.4.13		X
Adhesion	----	------	4.5.4.3	1/ 3.4.7		X
Resistance to hot distilled water	----	D 714	4.5.4.4	3.4.9		
Resistance to superchlorinated water	----	D 714	4.5.4.5	3.4.9		
Service performance	----	------	4.6	3.3.4		
Toxicity	----	------	4.7	3.2.2		
Aluminum alloy compatibility (type II only)	----	------	4.8	1/ 3.4.22		X
Application properties	----	------	------	3.4.7		X
Immersion tests	----	------	------	3.4.9		X

1/ Required for product identification characteristics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

4 3 1 Qualification samples The contractor shall submit in accordance with 3 1 to the designated laboratory samples of component A, component B, and the designated thinner for the coating system

4 3 2 Certification data/report The contractor shall certify that each lot of paint is in accordance with this specification (see 6 2 2) In addition to the requirements covered by the data ordering document, the certification data/report shall include the following information

(a) Identification characteristic values of the submitted coating system as specified in 3 3
(b) Certification that the submitted coating system does not contain ketimine curing agent, phenolic compounds, ketone solvents, asbestos-containing fillers, coal tar pitch, nor harmful metallic compounds as specified in 3 2, 3 2 1 and 3 2 2
(c) Service performance data on submitted coating system as specified in 3 3 4
(d) Material safety data sheet as specified in 3 3 5
(e) Certification for conformance to solvent content (see 3 2 1)
(f) Evidence that the submitted coating has been accepted for contact, and in potable water
(g) Certification of composition/toxicity in accordance with prescribed criteria (see 3 2 2 and 3 3 5)

4 4 Quality conformance inspection Quality conformance inspection shall consist of any test determined by NAVSEA to be necessary for conformance to this specification (see 3 1 through 3 4).

4 4 1 Lot For purposes of quality conformance inspection, a lot shall consist of epoxy paint from a single, uniform batch, or uniform blend of batches (for each component) offered for delivery at one time Two representative samples of component A and component B from each lot of paint (total of four samples per lot) shall be forwarded to a designated Government laboratory for quality conformance tests The four samples per lot shall be packaged in separate containers Minimum size for each sample shall be 1 liter (L) (1 quart)

4 5 Test procedures The epoxy coatings shall be tested in accordance with applicable methods specified in table II and other methods as specified in 3 1, 3.2, 3 3, and 3 4

4 5 1 Special analysis of coating components

4 5 1 1 Percent pigment The percentage of pigment in components A and B shall be found using method 4021 of FED-STD-141 with the following exceptions

(a) The extraction mixture shall be acetone (American Chemical Society (A C S) reagent grade) (see 3 3)
(b) The solids shall be dried in a vacuum oven at 105 ± 2°C (221 ± 3 6°F) and no more than 10 mm mercury (Hg) for 2 hours (see 3 3)

4 5 1 2 Epoxy resin content Epoxy resin content shall require the use of the resin solution extracted from the epoxy base component (either component

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

A or component B, depending on the commercial product) during the pigment extraction of 4 5 1. The solution shall be concentrated by using a rotary evaporator to remove enough solvent, so that when tested in accordance with method 4042 of FED-STD-141, the nonvolatile content shall be at least 80 percent The epoxide equivalent of this residue shall then be determined in accordance with method 7401 of FED-STD-141 using the nonvolatile fraction, as specified herein, in the final calculation

4 5 1 3 Amine nitrogen content Amine nitrogen content shall require the use of the resin solution extracted from the hardener (either component A or component B depending on the commercial product) during the pigment extraction (see 4 6 1.1) The solution shall be concentrated by using a rotary evaporator to remove enough solvent so that, when tested in accordance with method 4042 of FED-STD-141, the nonvolatile content shall be at least 80 percent The total amine value of the resin shall then be determined in accordance with method 7391 of FED-STD-141 and corrected by dividing the final result by the nonvolatile fraction as specified herein

4 5 1 4 Pigment components by atomic absorption (AA) analysis. The pigments in individual component A and component B shall be separated by high speed centrifuging as specified in ASTM D 2698 The pigments should then be submitted for AA analysis (see ASTM D 3335 and ASTM D 3630) for the identification of metallic elements The AA analysis should be documented for pigment identification purpose Nonconformance to 3.4 14 shall constitute rejection of pigment content of epoxy coatings for use in potable water tanks

4 5 1 5 Total vehicle components by infrared analysis After the pigment separation in 4 5 1 4, place the liquid total vehicle sample between sodium chloride plates and immediately without drying, record the infrared spectrum from 2 to 15 µm The infrared spectra should be documented for total vehicle identification Nonconformance to 3 4 15 shall constitute failure of this test and rejection of the paint

4 5.1 6 Nonvolatile vehicle components by infrared analysis Place another total vehicle sample between sodium chloride plates, dry at 105 to 110°C (221 to 230°F) for 15 minutes, and conduct infrared analysis over the 2 to 15 µm range in accordance with ASTM D 2621 The infrared spectra shall be documented for nonvolatile vehicle identification as specified in 3 3 for identification characteristics and conformance to 3 4 16

4.5 1 7 Volatile vehicle components. Component A and component B shall be analyzed individually by gas chromatography (GC) in accordance with ASTM E 260, using such apparatus, columns, operating conditions, and allowable options as are necessary to accommodate the various volatile chemical components The accuracy of the analysis shall be 0 25 percent or less absolute by mass for each component, and the reproducibility shall be 0 25 percent or less absolute by mass over three or more runs Peaks 0 5 percent of the sample or greater shall be identified and quantified Depending on the equipment available, the volatile components may be distilled from components A and B (separately) and tested in the gas chromatograph, or the whole component sample may be injected into the instrument and the volatile components separated In either case, calibrate the instrument with known ingredients before testing for the unknown volatiles as specified (see 3 3)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

4.5.2 Special analysis of mixed coating.

4.5.2.1 Dilution stability. Reduce one part by volume of mixed coating with one part by volume of the specific thinner furnished by the paint manufacturer and test in accordance with method 4203 of FED-STD-141 for compliance with 3.4.5.

4 5.2 2 Pot life. One pint of mixed coating shall be conditioned in a water bath maintained at 23 ± 1°C (73.4 ± 2°F). Test shall be terminated at the end of the pot life specified in 3 4.2 and conformance to 3.4.7 verified.

4.5.2.3 Condition in container. The contractor shall determine package condition in accordance with method 3011 of FED-STD-141 and observe for compliance with 3.4 8.

4.5.2.4 Brushing properties. Coating shall be prepared according to the manufacturer's directions. Coating shall be applied without further reduction in accordance with method 4321 of FED-STD-141 and observed for compliance with 3.4.7.

4.5.2 5 Spraying properties. Prepare the coating according to the manufacturer's directions. Without further reduction, spray on a sandblasted steel panel to the recommended wet film thickness Observe for spraying properties in accordance with method 4331 of FED-STD-141 and for compliance with 3.4.7.

4.5 2 6 Sag resistance Sag resistance shall be performed in accordance with method 4494 of FED-STD-141.

4.5 3 Special testing of applied coating

4.5 3.1 Sample preparation Sample testing is required by 3 1, 3 2, 3.3, and 3 4 Using a 0 15 mm (0 006 inch) 0 3 mm (0 012 inch) gap clearance film applicator, draw-down a 304.8 mm (12 inch) wide film of the epoxy primer on a 12 7 mm (1/2 inch) thick polyethylene sheet. Air dry the epoxy primer for 24 hours at 20 ± 3°C (68 ± 5°F), then draw-down the second coat lengthwise on the primer film If the coating system requires a third coat, apply after 24 hours of drying Allow the completed coating system to cure for 7 days at 20 ± 3°C (68 ± 5°F) after the application of the final coat

4.5 3 2 Bell jar preparation Attach a bell jar of 500 milliliters (mL) capacity to the coated surface with molten paraffin wax The bell jar should also be fitted with a tightly fitted stopper to prevent the loss of volatile halogen reactants during testing

4.5.3 3 Chlorine residual test Fill the bell jar with 200 p/m chlorinated water and age for 24 hours. Remove the chlorinated water by suction and rinse the bell jar twice with distilled water. Then refill the bell jar with 10 p/m chlorinated water and determine the exact chlorine concentration by using the DPD colorimetric method of Standard Method 408E Age the chlorinated water for 24 hours and measure the residual chlorine concentration Results shall conform to the requirements of 3 4 17

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

4 5 3 4 Color in water test Remove the remaining chlorinated water from the bell jar used in the chlorine residual test of 4 5 3 3. Rinse out the bell jar twice with distilled water Then refill with 0 2 p/m chlorine water and determine the exact chlorine concentration by using the DPD colorimetric method of Standard Method 408E Age for 24 hours and then withdraw approximately 100 mL of sample for the water color test specified in Standard Method 204A The pH of the water sample shall also be reported with the calculated color unit Calculated results shall conform to the requirements of 3.4 18.

4.5 3.5 Taste in water test Taste in water test shall be conducted only after a coating system has been found to comply with all other requirements of this specification The remaining chlorinated water in the bell jar, after conducting the color in water test specified in 4 5 3 4, shall be used for the taste in water test specified in Standard Method 211A The temperature of the water bath to be used for this test shall be 40°C (104°F) Threshold taste values shall conform to the requirements of 3 4 19

4 5 3 6 Odor in water test Remove the remaining chlorinated water from the bell jar used in the taste in water test of 4 5 3 5 Rinse out the bell jar twice with distilled water Then refill with 0 2 p/m chlorine water and determine the exact chlorine concentration by using the DPD colorimetric method of Standard Method 408E. Age the water for 24 hours and conduct the odor in water test in accordance to the directions specified in Standard Method 207 Temperature of the water bath to be used for this test is 40°C Threshold odor values shall conform to the requirements of 3 4.20.

4.5.3.7 Headspace infrared analysis. Remove the chlorinated water from the previous odor in water test of 4 5 3 6 Cap the empty bell jar and age the captive atmosphere for 24 hours The air in the bell jar is then sampled for infrared analysis The sampling train should consist of a one-hole rubber stopper attached to a drying tube and a rubber tubing leading to an evacuated 1 0 meter (m) (3 28 feet) gas cell. The vapor infrared spectra should be obtained in the 2 to 15 mm region The requirements of 3 4 21 shall apply to the obtained spectra. As an alternative, a standard gas chromatographic analysis may be performed in accordance with ASTM D 3271

4.5.3 8 Solvent retention test. Dry film of the coating system which had cured for 7 days shall be placed into a high-speed mill (blade type) and ground for 2 minutes. The resultant paint particles shall be ground finer than U S sieve no. 50 Approximately 1 gram of sample, as measured on an analytical balance, shall be dried at 105°C (302°F) for 2 hours Mass loss shall then be determined and reported as percent solvent retained The requirements of 3 4.10 shall apply.

4.5 3 9 MEK rub test The cured condition of the epoxy film shall be determined by placing a cotton ball, wetted down with MEK, on the surface for approximately 1 minute. At the end of this soaking period, a cotton Q-tip soaked with the test solvent, shall be used to vigorously rub the test surface. A cured epoxy coating shall not erode nor soften under this procedure. The requirements of 3 4.11 shall apply

4.5.3.10 Phenolic equivalent. The dry film of the coating system which has been cured for 7 days shall be placed into a high-speed mill (blade type) and ground for 2 minutes The resultant coating particles shall be ground

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

finer than U S sieve no 50 Approximately 1 gram of sample, as measured on an analytical balance shall then be placed in a paper thimble and lowered into the Soxhlet extractor The 500 mL flask in this assembly shall be filled with 300 mL of distilled water and a couple of boiling chips The sample shall be refluxed for several hours until four complete siphoning of the sample chamber occur Colorimetric phenol test shall be conducted after the water extract has been cooled to room temperature using either Standard Methods 510C, without distillation, or a commercial 4-aminoantipyrine colorimetric kit, similar to Fisher Phenol Test Kit Model P-12 The requirements of 3 4 12 shall apply

4 5 4 Special panel tests

4 5 4 1 Panel preparation The test panels required for adherence to 3 4 7 shall be mild steel conforming to ASTM A 366, cold rolled, 76.2 mm (3 inches) by 127 mm (5 inches) by 3 175 mm (1/8 inch) blasted to a near white metal appearance with a minimum surface profile of 0 025 to 0 050 mm (1 5 to 4 0 mils) peak to valley Panels shall be cleaned after blasting using clean, dry compressed air, vacuum or solvent mixture of 1 1 xylene and isopropanol Prepare eight test panels for each of the coating systems being evaluated The number and order of application of the coats and dry film thicknesses shall be in accordance with the manufacturer's specification for the coatings under test The coatings shall be applied to each side using standard spray equipment, allowing 48 hours drying time between coats at 20 ± 3°C (68 ± 5°F) The coated panels shall be cured for 7 days at 20 ± 3°C (68 ± 5°F) after the application of the final coat For aluminum compatability, see 4 8

4 5 4 2 Water extractable substances After curing is completed but prior to undertaking the extractions, the panel surfaces shall be examined and carefully rinsed with deionized distilled water to remove any extraneous materials present Place two of the coated panels diagonally upright on opposite sides of each of two 1-liter beakers. Preheat a quantity of deionized distilled water to 49°C (120°F), add 1000 grams of the heated water to each test beaker and 1000 grams to an empty beaker, which shall be carried through the procedure as a blank Cover the beakers with watch glasses and place in a 49 ± 1°C (120 ± 2°F) oven for 48 hours After 48 hours, remove panels and composite the water from the two test beakers, containing the extractant from 387 cm^2 (60 square inches (in^2)) of test panel surfaces, and evaporate to about 100 mL in a pyrex flask on a hot plate Transfer the extractant to a clean, tared, platinum dish, flushing the flask three times with deionized distilled water to remove the last traces of the extractant The latter shall be evaporated to a few mL on a low temperature hot plate, and the last of the water shall be removed by evaporation in an oven maintained at 100°C (212°F). The platinum dish shall be cooled in a dessicator for 30 minutes and the residue measured to the nearest tenth of a milligram After deducting the blank, calculate the amount of extractives as milligrams of extractive per square inch of coated panel surface Nonconformance to 3 4.13 shall consitute a failure of this test.

4 5 4 3 Adhesion. Two separate panels prepared as specified in 4 5 4 1 shall be used for adhesion testing (method 6301 of FED-STD-141 or Elcometer Adhesion) On one panel the adhesion of each coat shall be tested by knife just prior to application of the next coat and of the coating systems just prior to the start of the hot distilled water test specified in 4.5 4 4 After the completion of the immersion test, the adhesion between the immersed and the

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

second retained panels shall be compared. The requirements of 3 4.7 and 3 4 9 shall apply Adhesion shall be equal to or greater than material submitted for original test qualification

4 5 4 4 Resistance to hot distilled water Three panels prepared in accordance with 4 5 4 1 shall be immersed in 82°C (180°F) distilled water for 1680 hours or to failure The extent, nature and time of failure shall be reported and the requirements of 3 4 9 shall apply.

4.5 4 5 Resistance to super-chlorinated water at 25°C (77°F) A panel prepared in accordance with 4 5 4 1 shall be immersed in 100 p/m chlorinated water at room temperature or 25°C (77°F) for 170 hours The panel shall be removed and immediately examined and reported for any change in appearance, film failure or loss of apparent hardness and adhesion of the coating by visual observation and knife test The requirements of 3 4 9 shall apply

4 6 Service performance Service performance shall meet the requirements of 3 4 4 based on durability data from tank preservation records

4 7 Toxicological data A manufacturer of material shall submit documentary evidence of acceptance of the product for contact with potable water, and shall provide an MSDS to NAVMED NAVMED may request additional proprietary information from the manufacturer, as desired, to evaluate the toxicity of the product The proprietary information, which shall be held in confidence by NAVMED, shall include the name, formula, and approximate percentage by mass and volume of each ingredient in the product, the results of any toxicological testing of the product, and any such other information as may be needed to permit an accurate appraisal of any toxicity problem associated with the handling, storage, application, use, and disposal of the material The requirements of 3 2 2 shall apply

4 8 Aluminum alloy compatibility Three aluminum samples shall be prepared in accordance with 4 5 4 1 and shall be submitted to a temperature of 149°C (300°F) for 24 hours The presence of aluminum hydroxide or aluminum oxides penetrating the film shall be cause for failure The requirements of 3 4 22 shall apply

4 9 Inspection conditions Unless otherwise specified, all inspections shall be performed in accordance with the test conditions specified in the applicable test methods specified herein

4 10 Inspection of packaging. Sample packages and packs, and the inspection of the preservation-packaging, packing and marking for shipment and storage shall be in accordance with the requirements of section 5 and the documents specified therein

5 PACKAGING

(The packaging requirements specified herein apply only for direct Government acquisition)

5 1 Packaging, packing and marking Epoxy coating components shall be delivered in 4-L (1-gallon) or 20-L (5-gallon) amounts as specified (see 6 2) in suitable unitized packaging Containers shall be as follows

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

5 1 1 Four-liter (1 gallon) cans. Four-liter (1-gallon) cans shall conform to type V, class 2 of PPP-C-96 Interior of cans may be unlined, exterior plan B coating and side seam stripping shall be required Wire handles shall be required for 4-L cans.

5 1 2 Twenty-liter (5 gallon) pails. Twenty-liter (5-gallon) pails shall conform to type II, class 3 of PPP-P-704 Interior coating is not required Wire handles or bails shall be treated to resist corrosion

5 2 Packing Packing shall be level A, B, or C as specified (see 6 2)

5 2 1 Levels A and B.

5 2 1 1 Cans Each kit shall be packaged in a fiberboard box conforming to PPP-B-636, class weather resistant for level A, and class domestic for level B Other options, variety, grade, and style shall be at the contractor's option Each box shall be provided with fiberboard separators and pads, as necessary, to provide support to all panels of the shipping containers Fiberboard separators and pads shall be of the same material as the box Class weather resistant boxes shall be closed, waterproofed, and reinforced in accordance with method V of the appendix to PPP-B-636. Class domestic boxes shall be closed in accordance with method I of the appendix to PPP-B-636

5.2 1.2 Pails. Twenty-liter (5-gallon) pails shall require no further packing for level A and B The two 20-L pails, one each of components A and B (or one 20-L pail if blister pack is used), shall be packed in a snug fitting box or crate conforming to one of the following, as applicable a box conforming to PPP-B-585, class 2, style optional, a box conforming to PPP-B-636, type CF, class weather resistant, grade VIIc, with the option that the maximum weight shall be increased to 68 kg (150 pounds) if applicable, a crate conforming to MIL-C-11133, type II, class and style optional, grade A, process 2

5 2 2 Level C. Epoxy coating, packaged as specified in 5 1, shall be packed in containers acceptable to the common carrier which shall ensure safe delivery at destination in a satisfactory condition at the lowest applicable rate Container packing or method of shipment shall comply with Uniform Freight Classification Ratings, Rules and Regulations or National Motor Freight Classification or other carrier rules, as applicable, to the mode of transportation

5 3 Marking In addition to any special marking required herein, or by the contract or order (see 6 2), interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3 1 Special marking In addition to the markings required by the contract or order (see 6 2), each container containing class 2 or 3 material (interior and exterior), shall be marked with the following.

"The volatile content of the material in this container is not photochemically reactive as defined by Rule 102 of the South Coast Air Quality Management District."

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

"CAUTION

Avoid contact with skin and eyes Avoid prolonged or repeated breathing of vapor. Use with adequate ventilation Keep container tightly closed

Class 2 - FLAMMABLE"

6. NOTES

6 1 Intended use This specification covers a high grade coating system of the epoxy resin type consisting of the required components intended for coating and protecting from corrosion deterioration the interior surfaces of potable water tanks, without contributing to the toxicity, taste, odor, and color of the potable water

6 1 1 Coatings selection.

6 1 1 1 Class 1. Class 1 coating applications are acceptable in geographic areas where their volatile composition is not regulated by any existing air pollution control regulations.

6 1 1 2 Class 2 Class 2 coatings are acceptable for use in Los Angeles County and other areas where the rules specified in 6.6 apply

6.1.1.3 Class 3 Class 3 coatings are acceptable for use in areas where air pollution regulations limit solvent content to 0.34 kg/L (2 8 pounds per gallon)

6 1 2 Coating applications.

6 1 2 1 New applications Coatings in accordance with this specification should be applied as specified in the manufacturer's instructions or technical data sheet For potable water tank applications, NAVSEA instructions govern when they conflict with, strengthen or otherwise elaborate on manufacturer's instructions

6.1 2 2 Touch-up applications. Coating systems should be maintained by using coating systems of the same type and class as the original application

6 2 Ordering data.

6.2.1 Acquistion requirements Acquisition documents should specify the following:

(a) Title, number and date of this specification.
(b) Type and class required (see 1.2)
(c) Inspection system in accordance with MIL-I-45208 (see 4.1.1)
(d) Quantity of kits and size of component containers (see 5.1).
(e) Level of packaging and packing required (see 5.1 and 5.2).
(f) Special marking required (see 5.3 1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

6 2 2 Data requirements When this specification is used in an acquisition which incorporates a DD Form 1423, Contract Data Requirements List (CDRL), the data requirements identified below shall be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved CDRL incorporated into the contract When the provisions of FAR 52 227-7031 are invoked and the DD Form 1423 is not used, the data specified below shall be delivered by the contractor in accordance with the contract or purchase order requirements Deliverable data required by this specification is cited in the following paragraph

Paragraph no	Data requirement title	Applicable DID no	Option
4 3 2	Certification/data report	UDI-A-23264	10 2 1

(Data item descriptions related to this specification, and identified in section 6 will be approved and listed as such in DoD 5000 19L , Vol II, AMSDL Copies of data item descriptions required by the contractors in connection with specific acquisition functions should be obtained from the Naval Publications and Forms Center or as directed by the contracting officer)

6 2 2 1 The data requirements of 6 2 2 and any task in sections 3, 4, or 5 of this specification required to be performed to meet a data requirement may be waived by the contracting/acquisition activity upon certification by the offeror that identical data were submitted by the offeror and accepted by the Government under a previous contract for identical item acquired to this specification This does not apply to specific data which may be required for each contract regardless of whether an identical item has been supplied previously (for example, test reports)

6 2 3 In order to evaluate the cost of material purchased under this specification, contracting officers should request manufacturers to furnish a statement with each bid giving the square feet per gallon per 1 mil dry film thickness on a smooth surface without provisions for loss and the total solids by volume for both the primers and finish coats after addition of the curing agent Cost considerations should also include the labor involved in applying two coats versus three coats

6 3 The coating kit and its components shall be purchased by volume, the unit being 1 U S liquid gallon or 231 cubic inches at 20°C (68°F)

6 4 With respect to products requiring qualification, awards will be made only for products which are, at the time set for opening of bids, qualified for inclusion in Qualified Products List QPL-24654 whether or not such products have actually been so listed by that date The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or purchase orders for the products covered by this specification The activity responsible for the Qualified Products List is the Naval Sea Systems Command, SEA 55Z3, Department of the Navy, Washington, DC 20362-5101 and information pertaining to qualification of products may be obtained from that activity Application for qualification tests shall be made in accordance with "Provisions Governing Qualification SD-6" (see 6 4 1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

6 4.1 Copies of "Provisions Governing Qualification SD-6" may be obtained upon application to Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120

6 5 Infrared and other data (see 3.3 1, 3 3 2, and 3.3 3) developed by a qualifying laboratory will be kept on file for reference in surveillance testing that may be required to establish that material furnished under this specification for use by the Government or in connection with Government contracts will be equal, within manufacturing tolerances, to the products submitted for and approved under qualification

6 6 Volatile content class 2 Although the class 2 and class 3 container markings refer to the South Coast Air Quality Management District, the coating system may also be used where the solvent composition of 3 2 1 2 is specified. This includes other air pollution control districts or similar areas controlling the emission of solvents into the atmosphere Information regarding Los Angeles County Air Pollution Rules 102, 442, 443, and 1107 may be obtained from South Coast Air Quality Management District, 9150 E. Flair Drive, El Monte, CA 91731

Custodians
Navy - SH
Air Force - 99

Review activities:
Navy - YD, MS
Air Force - 50, 84

User activities
Army - ME
Navy - CG, MC

Preparing activity:
Navy - SH
(Project 8010-1060)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements All users of military standardization documents are invited to provide suggestions This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems Enter in block 6 any remarks not related to a specific paragraph of the document If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 55Z3)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12503 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 55Z3)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
DOD-C-24654	COATINGS, EPOXY, POTABLE WATER TANKS (METRIC)

3a. NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5 PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6 REMARKS

7a NAME OF SUBMITTER *(Last, First, MI)* – Optional	b WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8 DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:43Z
Check the source to verify that this is the current version before use.