METRIC

DOD-C-24667(NAVY)
AMENDMENT 2
9 February 1987
SUPERSEDING
DOD-C-24667(NAVY)
AMENDMENT 1
30 October 1986

MILITARY SPECIFICATION

COATING SYSTEM, NONSKID, FOR ROLL OR SPRAY APPLICATION (METRIC)

This amendment forms a part of DOD-C-24667(NAVY), dated 11 September 1986, and is approved for use within the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

* 1.2, Composition L, second and third line: Delete and substitute: "area deck coating, except for types IIIA and IIIB (not abrasive to the steel arresting cable)."

1.2, Class 2: Delete and substitute: "Class 2 - For application by spray except for types IIIA and IIIB."

PAGE 4

3.1.1, delete the following:

"Subject to approval by the Naval Sea Systems Command (NAVSEA), alternative means of identification may be substituted for the characteristics in table I, provided appropriate data are submitted by the contractor."

PAGE 6

* 3.2, line 3, delete and substitute: "if the topcoats designed as a self-priming system, for grade A only. The type III coating system".

PAGE 7

3.3.4: Delete and substitute:

"3.3.4 Color. The coating shall be supplied in one of the following colors from FED-STD-595, as specified (see 6.2.1): Red to match color 31136; yellow to match color 33538; olive drab to match color 34087; dark gray to match color 36076; haze gray to match color 36270; black to match color 37038; and white to match color 37875. The color shall be a visual match to the specified color chip."

AMSC N/A FSC 8010
DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:49Z
Check the source to verify that this is the current version before use.

* 3.3.6.1: Delete and substitute:

"3.3.6.1 Topcoats. Grade A, class 1 nonskid topcoat shall cover not less than 0.49 square meters per liter (m^2/L) (20 square feet per gallon (ft^2/gal)) nor more than 0.74 m^2/L (30 ft^2/gal). Grade B, class 1 (rolled) nonskid topcoat shall cover not less than 0.61 m^2/L (25 ft^2/gal) nor more than 0.86 m^2/L (35 ft^2/gal). Grade B, class 1 (trowelled) nonskid topcoat shall cover not less than 0.49 m^2/L (20 ft^2/gal) nor more than 0.54 m^2/L (22 ft^2/gal). Grades A and B, class 2 nonskid topcoat, shall cover no more than 1.5 m^2/L (60 ft^2/gal)."

PAGE 9

* 3.4.2: Delete and substitute:

"3.4.2 Toxicity. The materials used in the components shall have no adverse effect on the health of personnel engaged in mixing and application of the nonskid system when Occupational Safety and Health Administration (OSHA) guidelines are observed. The nonskid system shall be lead free. Cadmium and chromate containing materials are prohibited (see 4.9)."

3.4.5, lines 3 and 4: Delete and substitute: "content for types IA, IIA, and IIIA; and 295 grams/liter of volatile organic compounds for the low volatile organic content for types IB, IIB, and IIIB of".

PAGE 11

4.3.2, lines 1 and 2: Delete "Navy haze gray color 36076" and substitute "Navy dark gray to match color 36076".

* 4.3.2: Add after second sentence: "Approval of qualification for type IB shall also constitute approval of qualification of that system for type IA of the same grade, class and composition. Approval of qualification for type IIB shall also constitute approval of qualification of that system for type IIA of the same grade, class and composition. Approval of qualification for type IIA or type IIB shall also constitute approval of qualification of that system for type IA or type IB respectively of the same grade, class and composition. Systems that are submitted for qualification for grade A that do not pass the durability requirements for grade A but pass the durability requirements for grade B shall be qualified for grade B of the same type, class and composition provided that the system passes all the other requirements for that type, class and composition. Approval of qualification for type III does not constitute approval for type I and II."

PAGE 17

* 4.6.12, line 26: Delete "3.3.12." and substitute "3.3.11".

* 4.6.13, line 1: Delete "3 mm (6 by 6 by 1/8 inch)" and substitute "5 or 6 mm (6 by 6 by 3/16 or 1/4 inch)".

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:49Z
Check the source to verify that this is the current version before use.

PAGE 18

* 4.6.13.1.2, line 3: After "(3/4 inch)" add the following: "center to center".

PAGE 21

* 4.9: Add the following new paragraph:

"4.9 Toxicity. To determine conformance to requirements of 3.4.2, the manufacturer of the material shall disclose the formulation of his product to the Naval Medical Command, MEDCOM-242, Washington, DC 20372. The disclosure of proprietary information, which shall be held in confidence by the Naval Medical Command, shall include: the name, formula, and approximate percentage by weight and volume of each ingredient in the product; the results of any toxicological testing of the product; identification of its pyrolsis products; and any such other information as may be needed to permit an accurate appraisal of any toxicity problem associated with the handling, storage, application, use, disposal, or combustion of the material. Information submitted shall be clearly marked or identified to show it is being provided in connection with qualification under DOD-C-24667."

PAGE 23

* 6.1: Add the following: "Although laboratory testing is done between 10°C (50°F) and 32°C (90°F), coatings are applied in the fleet between 4°C (40°F) and 49°C (120°F)."

PAGE 26

6.7: Delete and substitute:

"6.7 Supersession data. This specification supersedes MIL-D-23003A(SH) dated 25 February 1980 and MIL-D-24483A(SHIPS) dated 19 August 1974 as follows:

DOD-C-24667(NAVY)	MIL-D-23003A(SH)	MIL-D-24483A(SHIPS)
Type IA, composition G, grade B		
Class 1	Type III	--------
Class 2	--------	Type I
Type IA, composition L, grade B		
Class 1	Type IV	--------
Class 2	--------	Type II
Type IIA, composition G, grade B,		
Class 1	Type V	--------
Class 2	--------	--------
Type IIIA	Type III	--------

"

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:49Z
Check the source to verify that this is the current version before use.

* 6.9: Add the following new paragraph:

"6.9 Reference formula. Coatings made in laboratory quantities according to the following formula meet all requirements of this specification for type IA, composition G, grade B, class 1 and will be used by the testing laboratory for comparison purposes. Coatings offered to the Government under this specification are not required to conform to this formula. Use of this formula does not release the contractor from any requirement of this specification.

	Percent by weight
Component A;	
Amidoamine resin (for example, Genamid 2000 by Henkel)	0.49
Polyamide/epoxy resin solution (for example, Versamid 280B75 by Henkel)	6.87
Component B:	
Liquid epoxy resin (for example, Epon 828 by Shell)	10.57
Thickening agent (for example, Thixatrol ST by NL Industries)	0.32
Talc (for example, MP 30-36 by Pfizer)	18.12
Titanium dioxide (for example, TiPure R960 by DuPont)	0.48
Carbon black (for example, TT-P-350)	.35
Xylene	7.84
Aluminum metal aggregate (for example, LSA-284 by Reynolds)	54.96
Total	100.00 "

NOTE: The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Review activity:
Navy - AS

Preparing activity:
Navy - SH
(Project 8010-N335)

Source: https://assist.dla.mil -- Downloaded: 202640-20T00:49Z
Check the source to verify that this is the currentversion before use.