METRIC

MIL-D-3691D
9 December 1985
SUPERSEDING
MIL-D-003691C(EA)
31 October 1977
MIL-D-3691B
20 July 1970

MILITARY SPECIFICATION

DYE MIX, VIOLET (METRIC)

This specification is approved for use by all
Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a mixture of two anthraquinone dyes.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

L-P-378 - Plastic Sheet and Strip, Thin Gauge, Polyolefin

: Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed: to: Commander, U.S. Army Chemical Research and Development Center, ATTN: SMCCR-SPD-TS, Aberdeen Proving Ground, MD 21010-5423 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter. :

AMSC N/A FSC 6820

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-D-3284 - Dye, Disperse Red 9 (Metric)
MIL-D-3464 - Desiccants, Activated, Bagged, Packaging Use and Static Dehumidification
MIL-D-3668 - Dye, 1,4-Diamino-2,3-Dihydroanthraquinone (Metric)

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads

(Copies of specifications and standards required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

UNIFORM FREIGHT CLASSIFICATION RULES

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

ASTM STANDARDS

D 1895 - Apparent Density, Bulk Factor, and Pourability of Plastic Materials (DOD Adopted)
D 3951 - Commercial Packaging (DOD Adopted)
E 11 - Wire-Cloth Sieves for Testing Purposes (DOD Adopted)

(Application for copies should be addressed to ASTM, 1916 Race Street, Philadelphia, PA 19103.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Composition. Dye Mix, Violet shall be a uniformly blended mixture of dyes and shall conform to the composition of table I as evidenced by its passing the test specified in 4.2.4.1. No other material shall be used in the preparation of the dye mix.

TABLE I. Composition

Dye	Percent by weight
Dye, Disperse Red 9 conforming to MIL-D-3284	20 ± 2
Dye, 1,4-Diamino-2,3-dihydroanthraquinone conforming to MIL-D-3668	80 ± 2

3.2 Chemical and physical characteristics. Dye Mix, Violet shall conform to the chemical and physical characteristics of table II when tested as specified therein.

TABLE II. Chemical and physical characteristics

Characteristic	Requirement	Test paragraph
Volatile matter, percent by weight, maximum	2.5	4.2.4.2
Particle size, minimum percent by weight passing:		4.2.4.3
250-micrometer sieve	97	
150-micrometer sieve	90	
75-micrometer sieve	70	
Apparent density, grams per milliliter	0.35 ± 0.15	4.2.4.4

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Quality conformance inspection.

4.2.1 Lotting. A lot shall consist of the Dye Mix, Violet offered for acceptance at one time which has been produced by one manufacturer, at one plant, from the same materials, and under essentially the same manufacturing conditions provided the operation is continuous. The minimum lot size shall be 2,270 kilograms. In the event the process is a batch operation (see 6.3), several batches may be mixed together to form a lot provided the batches are subjected to some physical mixing operation intended to make the final product substantially uniform and homogeneous; otherwise, each batch shall constitute a lot. No more than one lot of Disperse Red 9 dye and no more than one lot of 1,4-Diamino-2,3-dihydroanthraquinone dye shall be used to prepare a lot of Dye Mix, Violet.

4.2.2 Sampling.

4.2.2.1 For examination of packaging. Sampling shall be conducted in accordance with MIL-STD-105.

4.2.2.2 For Dye Mix, Violet test. See 6.6 for sampling and testing precautions. Three representative specimens of approximately 200 grams (g) each shall be randomly removed from the lot of dye mix offered for acceptance and shall be placed in separate clean, dry, containers labeled to identify the lot represented.

4.2.3 Inspection procedure.

4.2.3.1 For examination of packaging. The sample unit shall be one filled and closed shipping container, ready for shipment. Sample containers shall be examined for the following defects using an AQL of 2.5 percent defective:

(a) Contents per container not as specified
(b) Container not as specified
(c) Polyethylene liner or closure thereof not as specified (level B only)
(d) Container closure not as specified
(e) Container damaged or leaking
(f) Desiccant not as specified or missing (level B only)
(g) Marking incorrect, missing, or illegible
(h) Palletization not as specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

4.2.3.2 For Dye Mix, Violet test. Each specimen taken in 4.2.2.2 shall be tested as specified in 4.2.4. Failure of any test by any specimen shall be cause for rejection of the lot represented.

4.2.4 Tests. See 6.6 for sampling and testing precautions. Reagent grade chemicals shall be used throughout the tests. Where applicable, blank determinations shall be run and corrections applied where significant. Tests shall be conducted as follows:

4.2.4.1 Composition.

(a) Standard solutions. Prepare a maximum standard solution and a minimum standard solution as follows: Dissolve the applicable amounts of standard dyes (see 6.4) specified in table III in ethanol or isopropanol in a 500-milliliter (mL) volumetric flask. Dilute to the volume mark with the alcohol and mix thoroughly. Pipet a 10-mL aliquot into a 250-mL volumetric flask, dilute to the volume mark with the alcohol, and mix thoroughly. Cell spacers or variable path length cells may be used in lieu of the prescribed dilution procedures.

(b) Specimen solution. Prepare a solution of the specimen in ethanol or isopropanol by substituting 0.3200 g of the specimen for the standard dyes in table III and proceeding as specified in (a).

TABLE III. Composition of standard solutions

Standard dye	Maximum standard solution	Minimum standard solution
1-Methylaminoanthraquinone, grams	0.0518	0.0634
1,4-Diamino-2,3-dihydroanthraquinone, grams	0.1747	0.1837

(c) Procedure. Using a suitable recording spectrophotometer, record the absorbance curves of the two standard solutions prepared in (a) from 350 to 700 nanometers. Use the alcohol used for preparing the standard solutions as the reference liquid in the spectrophotometer. Using the same instrument and balancing used for the standard solutions, record the absorbance curve of the specimen solution prepared in (b) from 350 to 700 nanometers. The absorbance curve of the specimen solution shall fall between the maximum standard solution curve and the minimum standard solution curve.

4.2.4.2 Volatile matter. Weigh to the nearest milligram approximately 5 g of the specimen in a tared, glass-stoppered weighing bottle. Remove the stopper and dry to constant weight at 70° to 75°C. Cool to room temperature in a desiccator and weigh. Calculate the percent by weight volatile matter as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

$$\text{Percent volatile matter} = \frac{100(A - B)}{W}$$

where: A = Weight of specimen and stoppered bottle before heating in grams,
B = Weight of specimen and stoppered bottle after heating in grams, and
W = Weight of specimen in grams.

4.2.4.3 Particle size. Use sieves conforming to ASTM E 11. Nest the sieves in order of decreasing mesh size (with the sieve of largest mesh on top) on a receiving pan. Weigh to the nearest 0.1 g approximately 10 g of the specimen and then use one of the following procedures:

(a) Dry method. Place the weighed specimen on the top sieve and brush the material with a camel's-hair brush until no more specimen passes through the sieve. Remove the sieve and weigh the material retained. Repeat this procedure with each of the other sieves. Calculate the percent material passing through each sieve.

(b) Wet method. Mix the weighed specimen with sufficient water in a beaker by stirring with a glass rod to produce a smooth paste. Carefully wash the thoroughly wetted specimen through the sieves. (The use of a wetting agent is permitted.) Dry the sieves in an oven at 70° to 75°C and weigh the material remaining on each sieve. Calculate the percent by weight material passing through each sieve.

4.2.4.4 Apparent density. Determine apparent density in accordance with ASTM D 1895, method A.

5. PACKAGING

5.1 Unit packing. Dye Mix, Violet shall be unit packed level B or commercial as specified (see 6.2).

5.1.1 Level B. Uniform quantities of no less than 65 and no more than 130 kilograms ± 1/4 percent of the marked net weight of dye shall be packed in a fiber drum conforming to rule 51, section 2 of the Uniform Freight Classification for a weight limit of over 225 but not over 300 pounds, with an aluminum barrier of 7.62 micrometers minimum thickness incorporated into one of the inner plies of the sidewall. Each drum shall be provided with a close-fitting bag liner formed from polyethylene of 101.6 micrometers minimum thickness conforming to type I, class 1, grade and finish optional of L-P-378. Seams shall be completely heat sealed and shall meet the heat seal strength requirements of L-P-378. The filled bag shall be closed by heat-sealing, tying, or knotting. A minimum of eight units of desiccant conforming to MIL-D-3464 shall be placed on top of the closed liner. Drum closure shall be fully gasketed and shall form a tight seal between the rim and the top of the drum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

5.1.2 Commercial. Uniform quantities of no less than 65 and no more than 130 kilograms ± 1/4 percent of the marked net weight of dye shall be unit packed in accordance with ASTM D 3951.

5.2 Packing. Dye, unit packed as specified in 5.1, shall require no further protection for shipment other than unitization.

5.3 Unitization. Shipping containers shall be unitized in accordance with the applicable requirements of MIL-STD-147 except that the pallet shall be as specified in the contract (see 6.2).

5.4 Marking. Marking for level B shipments shall be in accordance with MIL-STD-129. Marking for commercial shipments shall be in accordance with ASTM D 3951. All shipments shall be marked to show lot number and date of manufacture. In addition, each container shall be durably and legibly marked with contrasting letters and background to show the net weight of contents and the following information:

CAUTION

Avoid contact with skin or clothing.
In case of contact, flush with water.
Avoid breathing dye or combustion products.
Mask during manufacture or use where potential for exposure exists.

6. NOTES

6.1 Intended use. Dye Mix, Violet is intended for use in the manufacture of violet signaling smoke mixtures.

6.2 Ordering data. Acquisition documents should specify the following:

(a) Title, number, and date of this specification.
(b) Level of unit packing required (see 5.1).
(c) Type of pallet required (see 5.3).

6.3 Batch. A batch is defined as that quantity of material which has been manufactured by some unit chemical process.

6.4 Dyes of known purity. Dyes of known purity conforming to MIL-D-3668 and MIL-D-3284, respectively, for use in 4.2.4.1 may be obtained by authority of the Procuring Contracting Officer (PCO). Alternately, the contractor may prepare his own standard dyes and obtain verification of their purities by authority of the PCO from Commander, U.S. Army Armament, Munitions and Chemical Command, Product Assurance Directorate, Aberdeen Proving Ground, MD 21010-5423.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

6.5 Significant places. For the purpose of determining conformance with this specification, an observed or calculated value should be rounded off "to the nearest unit" in the last right-hand place of figures used in expressing the limiting value, in accordance with the rounding-off method of ASTM E 29.

6.6 Sampling and testing precautions. This specification requires inspection of chemical material which is potentially hazardous to personnel. All applicable safety rules, regulations, and procedures must be followed in the handling and processing of this material.

Custodians:

Army - EA
Navy - OS

Review activities:

Army - MD
Navy - AS
DLA - GS

Preparing activity:

Army - EA

Project No. 6820-0085

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 Alexandria, VA

POSTAGE WILL BE PAID BY

Commander
U.S. Army Chemical Research and Development Center
ATTN: SMCCR-SPD-TS
Aberdeen Proving Ground, MD 21010-5423

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-D-3691D	DYE MIX, VIOLET (METRIC)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:14Z
Check the source to verify that this is the current version before use.