COMMERCIAL ITEM DESCRIPTION

PAD, FLOOR POLISHING MACHINE (THIN)

The General Services Administration has authorized the use of this commercial item description in preference to types II and V of Interim Federal Specification OO-P-0040.

This commercial item description covers two types of thin, floor maintenance pads used for polishing, buffing, scrubbing, and stripping floors. The round, thin floor pads shall be suitable for mounting on power-driven, rotary-disc type floor maintenance machines, operating in a speed range between 150 and 350 rpm. The rectangular floor pads are for mounting on the oscillating type floor maintenance machines. The floor pads are intended for heavy duty floor care maintenance and shall be suitable for use on various type floors.

The round, thin pad is recommended only for specific uses when the pad is to be discarded after each use, such as hospitals; i.e., operating rooms, contagious disease wards, and other areas where isolation is required; also small office areas that do not have the capability to wash and dry the reusable and hence more economical thick pads.

The floor pads shall be of the following types and classes (see notes).

Type I - Thin floor pads, nylon
(6.5 mm (1/4 inch) minimum thick)
Class 1 - Buffing and polishing
Class 2 - Scrubbing
Class 3 - Stripping

Type II - Thin floor pad, nylon and polyester
(10 mm (3/8 inch) minimum thick).
Class 1 - Buffing and polishing
Class 2 - Scrubbing
Class 3 - Stripping

The round floor pads shall be of the following diameters when ordered according to size (see notes):

Size 13 - 330.2 mm (13 inches)	Size 18 - 457.2 mm (18 inches)
Size 14 - 355.6 mm (14 inches)	Size 19 - 482.6 mm (19 inches)
Size 15 - 381.0 mm (15 inches)	Size 20 - 508.0 mm (20 inches)
Size 16 - 406.0 mm (16 inches)	Size 21 - 533.4 mm (21 inches)
Size 17 - 431.8 mm (17 inches)	Size 22 - 558.8 mm (22 inches)

The rectangular floor pads shall be of the following sizes when ordered:

Size 254 mm x 508 mm (10 x 20 inches)
Size 305 mm x 762 mm (12 x 30 inches)
Size 305 mm x 914 mm (12 x 36 inches)
Size 305 mm x 1067 mm (12 x 42 inches)
Size 457 mm x 711 mm (18 x 28 inches)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

All sizes of the pads shall be as specifed within a tolerance of plus or minus 3.2 mm (1/8 inch).

Salient characteristics.

Design. The floor pads shall be suitably designed and fabricated for use with either rotary disc or oscillating electric floor machines. The floor pads shall be resilient so that the entire surface area of the pad contacts the floor. The pads shall be uniformly impregnated with abrasive particles within plus or minus 15 percent uniformity. Any concentrations or blotches of abrasive particles within the pad, when viewed toward a bright light source, shall be tested specifically for the 15 percent uniformity requirement.

Material. The materials used in the manufacture of floor maintenance pads shall not support the growth of bacteria and must be of such denier, density, strength, quality, and workmanship to produce a cohesive pad, uniform in structure, and reversible with equal performance on both sides. The materials shall be either nylon or a blend of nylon and polyester and suitable for the intended use in accordance with good commercial practice. Abrasive particles shall be made of either natural or synthetic abrasives. The bonding adhesives shall be such that the pads shall not disintegrate in water, detergent solutions, oil, wax, or other material normally encountered in floor maintenance operations.

Type I, nylon floor pads. Type I, nylon floor pads, shall be made of one piece, unified mat. The materials of the pads shall be formed or bonded into a solid disc. Pads of spirally wound ribbons of interlocking fibers are not acceptable.

Class 1. The abrasive content for the type I, class 1 buffing and polishing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 200 mesh screen. A minimum of 90 percent of the abrasive particles shall pass through a 270 mesh screen.

Class 2. The abrasive content for the type I, class 2 scrubbing pads shall be no more than 60 percent by weight. One hundred percent of the total abrasive particles shall pass through a 150 mesh screen. A minimum of 75 percent of the particles shall pass through a 200 mesh screen. A minimum of 95 percent of the remaining particles shall pass through a 270 mesh screen.

Class 3. The abrasive content for the type I, class 3 stripping pads shall be no more than 65 percent by weight. One hundred percent of the total abrasive particles shall pass through a 100 mesh screen. A minimum of 65 percent of the particles shall pass through a 150 mesh screen. A minimum of 45 percent of the remaining particles shall pass through a 150 mesh screen.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Type II, nylon and polyester floor pads. Type II, nylon and polyester pads, shall be made of one piece, unified mat. The materials of the pads shall be formed or bonded into a solid disc. Pads of spirally wound ribbons of interlocking fibers are not acceptable.

Class 1. The abrasive content for the type II, class 1 buffing and polishing pads shall be no more than 40 percent by weight. One hundred percent of the total abrasive particles shall pass through a 200 mesh screen. A minimum of 90 percent of the abrasive particles shall pass through a 270 mesh screen.

Class 2. The abrasive content for the type II, class 2 scrubbing pads shall be no more than 60 percent by weight. One hundred percent of the total abrasive particles shall pass through a 150 mesh screen. A minimum of 75 percent of the particles shall pass through a 200 mesh screen. A minimum of 95 percent of the remaining particles shall pass through a 270 mesh screen.

Class 3. The abrasive content for the type II, class 3 stripping pads shall be no more than 65 percent by weight. One hundred percent of the total abrasive particles shall pass through a 100 mesh screen. A minimum of 65 percent of the particles shall pass through a 150 mesh screen. A minimum of 45 percent of the remaining particles shall pass through a 150 mesh screen.

Workmanship. The floor pads shall be free from any defects, imperfections, or material that would adversely affect performance, serviceability, or appearance, or may cause any undesirable effects during use.

Quality assurance provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. Inspection records of the examinations or tests shall be kept complete and available to the Government as specified in the contract or purchase order. The Government reserves the right to perform any of the inspections set forth in the CID where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Inspection. Sampling for inspection shall be in accordance with MIL-STD-105, Sampling Procedures and Tables for Inspection by Attributes, except where otherwise indicated herein.

Visual and dimensional examination. The pad shall be examined for defects in finish, construction, workmanship, and dimensional requirements. Defects shall be as classified in Table I. The inspection level shall be level II with an acceptable quality level (AQL) of 4.0 defects per hundred units for major defects and 6.5 defects per hundred units total.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

TABLE I - Classification of defects

Examine	Defect	Classification Major	Minor
General	Not type specified	X	
	Not class specified	X	
	Not size specified	X	
	Not material specified	X	
	Thickness less than specified	X	
	Design not as specified	X	
	Workmanship not as specified		X

Abrasive distribution examination. Sampling shall be in accordance with MIL-STD-105, inspection level S-2 with an acceptable quality level (AQL) of 4.0 percent defective. The lot size shall consist of all cartons containing one type and size pad offered for acceptance at one time. The sample unit shall be one pad. One or more defects per sample shall constitute a defective carton.

Tests.

Test equipment. The test equipment required to accomplish the following tests is four vested sieves; one 100-mesh screen with a hole size of 149 microns; one 150-mesh screen with a hole size of 105 microns; one 200-mesh screen with a hole size of 74 microns; one 270-mesh screen with a hole size of 57 microns; and a bottom pan. Additional equipment shall include a gram scale calibrated in centigrams; a leveling plate 89 mm (3-1/2 inches) in diameter weighing 100 grams (g); an 85- to 100-mm diameter ashing dish; and other items as specified in the test paragraphs.

Ashing procedure. Heat a suitably clean ashing vessel, such as a porcelain dish, approximately 85 to 100 mm in diameter, at 600 degrees Celsius (C) for 15 minutes. Cool in desiccator and weigh to nearest centigram. Add samples of the floor pad to be analyzed, favoring pieces approximately 1/2 g each, confining each within the perimeter of the vessel by means of a screen or similar means. (This helps to prevent some types of pad samples from floating out of the vessel). Weigh the vessel and contents. Compute and record the sample weight with the appropriate identification data. Initial ashing to drive off obnoxious organic volatiles should occur under a fume hood until a dry char is obtained. Finish ignition of the ash in the muffle furnace. A furnace with regulated air ventilation is preferable because air circulation aids the ashing which may be completed in approximately 15 minutes. Without air circulation, one-half to one hour may be required. When ashing is complete, remove vessel with ash to a refractory plate to cool, finishing the final cooling in a desiccator. Be careful to avoid expulsion of fluffy ash particles. When cooled to room temperature, weigh the vessel with the ash and transfer the ash to a small plastic or glass vial, properly identify and retain for the abrasive (particle size) distribution test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Abrasive content. Four 25.4-mm square sections shall be cut, one from each quadrant of the sample pad. The four squares shall be ashed together using the ashing procedure above. The residue shall be considered the abrasive content. Subtract the vessel weight and record the weight of the abrasive content. Calculate the percentage of abrasive content by weight for conformance to the applicable requirements.

Abrasive distribution. Using the ash obtained above, assemble clean nested sieves with the pan in place, nesting the 100, 150, 200, and 270 mesh screens from top to bottom. Place the sample to be sieved into a small glass, agate, or polished porcelain mortar. Rub the mass, while avoiding grinding to break up agglomeration of the individual finest particles. Avoid too vigorous action that may cause static electricity on the particles. Transfer the loosened mass to the top of the sieve set. Carefully assist the particles with crosswise rather than downward actions on the top screen. Use small semi-stiff hair or fine bristle brushes trimmed to 1/2 to 3/4 inch long, and other convenient tools, such as a smooth edged scraper or spatula to move the particles back and forth over the screen until all particles of appropriate size have passed through. (Avoid shaking the sieves, because the action could cause further agglomeration and would give false results favoring the larger sizes). Remove the top screen and repeat the procedure on the next finest screen. Proceed likewise from top to bottom until the finest fraction is through to the pan. Collect, weigh, and record for each fraction noting screen size. Total the weights of all fractions recovered. (Note - This will invaribly be a little less than the total ash weight.) Compute the percentage of each size fraction on the basis of the total recovery weight for conformance to the applicable requirements.

Regulatory requirements. In accordance with the Section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or purchase order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.

Notes. Purchaser must specify type, class, and size floor pad required. The Procuring Contracting Officer (PCO) shall specify that the test for abrasive content and abrasive distribution be performed during the initial testing and and thereafter, only when changes in the manufacturer, manufacturing process, material, or design are made during the period of the contract. If the same manufacturer is awarded the contract again for the following year, and the process, material or design have not changed, the abrasive content and distribution examination is not required. If a mandatory source is awarded the contract, the raw material from the manufacturer must pass all the requirements of this CID. If the raw material is from a manufacturer whose product has passed all the requirements of this CID, and there have been no changes in the process, material or design, the abrasive distribution and content requirements may also be waived upon receipt of a certification of that fact from the manufacturer. The PCO shall require a complete set of tests and examinations be performed at least every three years regardless of past performance.

Copies of military standards may be obtained from the procuring activity or as directed by the contracting officer.

WHEN THIS COMMERCIAL ITEM DESCRIPTION IS USED FOR PROCUREMENT, THE COMMERCIAL ITEM CERTIFICATION CLAUSE DOES NOT NEED TO APPEAR IN THE SOLICITATION.

MILITARY INTEREST:

None

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:22Z
Check the source to verify that this is the current version before use.