A-A-53906
19 June 1989

COMMERCIAL ITEM DESCRIPTION

MOUTHPIECE, SALIVA EJECTOR, DENTAL, (Plastic, Disposable)

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Military Specification MIL-M-36231E which is cancelled.

Salient Characteristics:

This commercial item description covers disposable mouthpieces (saliva ejectors) suitable for removing fluids from the mouth during dental operative procedures. The following styles are covered by this commercial item description.

Style 1 - Mouthpieces with hole in center of tip.

Style 2 - Mouthpieces without hole in center of tip.

Material.

Tubing. The tubing shall be fabricated from clear or translucent, nonrigid, polyvinyl-chloride-type plastic, with no color additives.

Tip. The tip shall be fabricated from nonrigid, polyvinyl-chloride-type plastic, furnished in a blue color, or some other contrasting color.

Bonding agent. The agent for bonding the tip to the tubing shall be tetrahydrofuran or other suitable material.

Wire. The wire shall be bright basic tin-coated wire, 0.038 to 0.040 inch in diameter.

AMSC N/A FSC 6520

Distribution Statement A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Style, design and dimensions. The style, design, and dimensions of the mouthpieces shall be in accordance with Defense Personnel Support Center (DPSC) Drawing No. 24505. When inserted into the saliva ejector hose assembly of a dental operating unit and shaped to fit the mouth of the patient, the mouthpieces shall be suitable for removing fluids from the mouth, without clogging, during dental operative procedures.

Construction. Each mouthpiece shall consist of one piece of straight tubing, a tip which shall be securely bonded to one end of the tubing, and a reinforcing wire which shall be completely embedded or molded in the wall of the tubing. The wire shall not protrude by more than 1/32 inch from the free end of the tubing, and the tip shall be assembled straight on the tubing.

Finish. The tubing and tip shall have a smooth surface finish, which shall prevent any irritation to the mouth tissues.

Hardness. The tubing (without the wire) shall have a Type A Shore durometer hardness of 75 to 95 inclusive. The tip shall also have a type A Shore durometer hardness of 75 to 95 inclusive.

Tensile strength. The tubing (without the wire) shall have a minimum tensile strength of 2500 pounds per square inch (psi). The wire shall have a minimum tensile strength of 72,000 psi.

Bonding. The tip of the mouthpiece shall be securely bonded to the tubing. The bonding shall withstand a minimum pull of 5 pounds. After this pull has been exerted on the bond, there shall be no separation of the tip from the straight tubing.

Ultimate elongation. The tubing (without the wire) shall have a minimum ultimate elongation of 250%.

Quantity furnished. A minimum of 500 mouthpieces shall be furnished (on a lot average basis) in each unit package, with no individual unit package containing less than 490 mouthpieces.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Workmanship. The disposable mouthpiece shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Package (PG). One package containing five hundred mouthpieces, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, with an inspection level of II and an AQL of 2.5 (percent defective). The unit of product for examination purposes shall be one mouthpiece as specified, except a unit package shall apply for count. Examination shall include, but shall not be limited to the following defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Defects

Style and design not as specified.
Tip not free from sharp edges or parting lines.
Wire not completely embedded or molded in wall of tubing.
Any component of mouthpiece missing.
Mouthpiece not free from laminations or splits.
Any holes, deep gouges, cuts, or cracks in plastic components.
Ends of tubing clogged or otherwise obstructed.
Tin plating of wire not continuous along length of wire.
Tip not assembled straight on tubing.
Color not as specified.
Finish not as specified.
Center hole of style 1 tip not open.
Wire protrudes by more than 1/32 inch from free end of tubing.
Unit package contains fewer mouthpieces than specified.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105. The unit of product for test purposes shall be one mouthpiece. Sampling of the tip and the tubing without the wire for the Shore durometer hardness tests shall be conducted at inspection level S-2, with an AQL of 1.5 (percent defective). Sampling of the wire and of the tubing without the wire for the minimum percent (%) of ultimate elongation test shall be conducted at inspection level S-2, with an AQL of 2.5 (percent defective). Sampling for testing the bonding strength shall be conducted at inspection level S-4, with an AQL of 0.4 (percent defective). Sampling for the tip dimenstions test shall be at inspection level S-1, with an AQL of 1.5 (percent defective). Sampling for the tubing dimensions test shall be conducted at inspection level S-1, with an AQL of 2.5 (percent defective). Bonding tests shall be conducted both in-process and on the end item.

Tests. Tests shall be conducted to determine compliance with the requirements of this document.

Hardness test. Hardness shall be determined in accordance with ASTM Designation D2240. The type A hardness shall be taken using a Shore durometer with a 15 second delayed reading.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Tensile strength test. The tensile strength of the tubing shall be determined in accordance with ASTM Designation D412. The tensile strength of the wire shall be determined in accordance with ASTM Designation E8.

Bonding strength test. The bonding in the end item shall be tested as follows: The free end of the mouthpieces shall be inserted through a small hole in a horizontally mounted rigid plate until the bonded tip rests on the top surface of the plate. The hole in the plate shall be 0.010 ± 0.003 inch in diameter greater than the tubing diameter. A 5 pound (or heavier) weight shall be secured to the free end of the tubing for 10 minutes ± 15 seconds. The weight shall then be removed and the mouthpiece examined for separation of the tip from the straight tubing.

Ultimate elongation test. The percent (%) ultimate elongation of the tubing without the wire shall be determined in accordance with ASTM Designation D412.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producer's own drawings, specifications, standards and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch/pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerance specified in the inch/pound units, a request should be made to the contracting officer to determine of the product is acceptable. The contracting officer has the option of accepting or rejecting the product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug, and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maxium extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Number is covered by this document:

NATIONAL STOCK NUMBER	ITEM IDENTIFICATION
6520-00-082-2673	Mouthpiece, Saliva Ejector, Dental, Plastic, Disposable

Ordering data. Intermediate/exterior package quantities and labeling and marking must be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

PREPARING ACTIVITY:

DoD-MB

Custodians:

Army-MD
Navy-MS
Air Force-03

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

59310

Project No. 6520-2268
Location- NCR Disk 1

☆U.S. GOVERNMENT PRINTING OFFICE: 1989 - 604-633/03172

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
Attn: DPSC-BSTE
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
A-A-53906	MOUTHPIECE, SALIVA EJECTOR, DENTAL (Plastic, Disposable

3a. NAME OF SUBMITTING ORGANIZATION

b. ADDRESS *(Street, City, State, ZIP Code)*

4. TYPE OF ORGANIZATION *(Mark one)*

- ☐ VENDOR
- ☐ USER
- ☐ MANUFACTURER
- ☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:26Z
Check the source to verify that this is the current version before use.