TT-I-528C
March 19, 1974
SUPERSEDING
Fed. Spec. TT-I-528b
October 20, 1961

FEDERAL SPECIFICATION

INK, DRAWING, WATERPROOF, BLACK

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers black, waterproof drawing ink for general drafting use (drawing and tracing).

1.2 Classification.

1.2.1 Types. The ink shall be of the following types, as specified (see 6.1 and 6.2).

Type I - With temperate and tropical temperature-resistant characteristics.
Type II- With low temperature-resistant characteristics.

1.2.2 Sizes. (bottles of ink). (See 5.1.1.1.1 and 5.1.1.1.2.)

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issues in effect on date of invitations for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

UU-C-190 - Cardboard, Bristol (Drafting).
UU-P-223 - Paper, Drawing
CCC-C-531 - Cloth, Tracing.
PPP-B-566 - Boxes, Folding, Paperboard
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-T-45 - Tape, Gummed, Paper Reinforced and Plain for Sealing and Securing.

Federal Standards:

Fed. Std. No. 123- Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106 222 South Riverside Plaza, Chicago, IL 60606.)

Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Composition and stability of ink. The ink shall be composed of finely divided carbon in a stable state of suspension in a liquid medium, containing suitable waterproofing agents. The ink shall not show any coagulation, granulation, or precipitation under working and storage conditions (see 6.3). Such evidence of instability shall not be present when the ink is received nor when the sample ink is subjected to the designated stability tests specified in 4.4.1.

3.2 Performance. The ink as received and after exposure as specified in 4.4.1 shall have the following performance characteristics when tested as specified in 4.4.2: During the test, the ink shall not dry in the pen. The ink shall flow freely and produce lines of uniform width on the specified drawing paper, bristol board, and tracing cloth. The ink shall not penetrate the surface of the dull side of the tracing cloth to the extent that a complete erasure cannot be made. The color shall be intense black and the ink shall have a high degree of opacity and a low degree of gloss. The ink shall show no signs of abrasion when the test marking is cleaned with an eraser of the "art gum" type, as specified in 4.4.2.4.

3.3 Resistance to solvents. The ink, when thoroughly dried, shall be insoluble in cold water and in organic solvents, hexane and 1,1,1 - trichloroethane, when tested as specified in 4.4.3.1 and 4.4.3.2.

3.4 Specific gravity. The ink shall have a specific gravity at 25°C. of not less than 1.055 when determined as specified in 4.4.5.

3.5 Identification marking. Each bottle of ink shall be clearly and legibly lithographed or marked with water-resistant ink, or furnished with a label printed with water-resistant ink on a good grade of printing paper and firmly affixed to the bottle with a water-insoluble adhesive. The markings on the bottle and its individual box shall clearly identify the product and its manufacturer in accordance with standard commercial practice. (see 5.3).

3.6 Workmanship. Inks shall be smooth, homogeneous, black liquids free from lumps, strings, and objectionable odor. Labels shall be neatly affixed and clearly printed. Ink containers shall show no evidence of spilling or leakage.

4. QUALITY ASSURANCE PROVISIONS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

4.1 Supplier's responsibility. Unless otherwise specified (see 6.2), the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examinations and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Sampling and inspection for acceptance. The sampling and inspection shall be performed in accordance with the provisions set forth in Military Standard MIL-STD-105, except where otherwise indicated hereinafter. For purposes of sampling, an inspection lot for acceptance, inspection, and tests shall consist of all material of the same type and size submitted for inspection and delivery at the same time.

4.3 Inspection.

4.3.1 Inspection of materials and components. The supplier is responsible, in accordance with 4.1, above, for insuring that components and materials used were manufactured, tested, and inspected in accordance with the specified requirements of referenced subsidiary specifications and standards and in accordance with this specification, as applicable.

4.3.2 Inspection of end item.

4.3.2.1 Examination of end item. The end item shall be examined in accordance with the classification of defects listed for each of the applicable examinations.

4.3.2.1.1 Examination of (type I) filled bottles for defects in appearance, design, and workmanship. The sample unit for this examination shall be one filled bottle of ink. The inspection level and acceptable quality level (AQL) shall be as specified in 4.3.2.1.5 with the lot size expressed in units of bottles.

TYPE I

Examine	Defects
Appearance	Not homogeneous. Contains lumps or strings. Stray spilling of ink or leakage on outside of bottle
Design	Bottle shape or closure not as specified, or not commonly used for inks.
Fill of individual bottle (except average contents)	Empty bottle, or overfilling to extent that bottle may burst or leak in hot weather due to lack of liquid expansion space.

4.3.2.1.2 Examination of (type II) filled polyethylene containers for defects in appearance, design, and workmanship. The sample unit for this examination shall be one filled polyethylene container of ink. The inspection and acceptable quality levels shall be as specified in 4.3.2.1.5 with the lot size expressed in units of polyethylene containers.

TYPE II

Examine	Defects
Appearance	Not homogeneous. Contains lumps or strings. Stray spilling of ink or leakage on outside of containers. Malformed container.
Design	Container and closure not as specified.
Fill of individual container (except average contents)	Empty container, or filled to extent that container may burst or leak in hot weather due to lack of liquid expansion space.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

4.3.2.1.3 Examination of bottle or container for average contents. The sample unit for this examination shall be one filled glass bottle or polyethylene container as applicable. The inspection level shall be as specified in 4.3.2.1.5 with the lot size expressed in units of bottles or containers, as applicable. The average contents shall be not less than specified.

4.3.2.1.4 Examination of preparation for delivery. An examination shall be performed to determine compliance with section 5 and contract or order. The sample unit shall be one shipping container and contents fully prepared for delivery. The inspection and acceptable quality levels shall be as specified in 4.3.2.1.5 with the lot size expressed in units of shipping containers.

Examine	Defects
Markings (Unit, intermediate, and exterior containers, as applicable)	Incorrect; omitted; illegible; improper size, location, sequence, or method of application; omission "THIS SIDE UP" and other warnings. Omission of freezing warning on type I ink.
Container materials	Wrong class, type, or other category of required specifications. Material missing, damaged, or defective affecting serviceability.
Workmanship	Wrong or careless means in placement and use of labeling and packaging and packing materials such as loose or partially attached labels, incompatible adhesives, flaps of containers incompletely closed, loose or overtight straps, dangerous strap ends, protruding nails, and smeared adhesive.
Contents	Quantities of unit and intermediate containers not as specified. Wrong arrangement; bottle on side or upside down.
Gross weight of shipping container	In excess of specified weight. In excess of box limitation shown on boxmaker's certificate.

TABLE I - Instructions for testing of ink.

Characteristics	Specification reference: Requirement	Specification reference: Test Method	Requirements applicable to individual unit	Number determinations per unit	Results reported as pass or fail	Testing level
Stability.....	3.1	4.4.1.2	X	1	X	
Performance (before and after exposure)	3.2	4.4.2				
Ink flow and uniformity of line width on:						
Drawing paper.....		4.4.2.1	X	1	X	Two sample units (see 4.3.2.2)
Tracing cloth.....			X	1	X	
Bristol board.....			X	1	X	
Penetration dull side of tracing cloth.....		4.4.2.2	X	1	X	
Color, opacity, and gloss.....		4.4.2.3	X	1	X	
Abrasion resistance		4.4.2.4	X	1	X	
Resistance to solvents:	3.3	4.4.3				
Water.....			X	1	X	
Hexane.....			X	1	X	
1,1,1-trichloroethane			X	1	X	
Specific gravity at 25°C.....	3.4	4.4.5	X	1	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

4.3.2.1.5 Inspection levels and AQL's. The inspection levels and acceptable quality levels for examination of the end item shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.2.1.1	L-8	2.5
4.3.2.1.2	L-8	2.5
4.3.2.1.3	L-3	...
4.3.2.1.4	L-8	4.0

4.3.2.2 Testing of ink. Each lot or batch of drawing ink shall be tested in accordance with table I. Each sample unit shall meet all requirements. One sample unit shall consist of 1 pint from one or more bottles kept at ordinary room temperature. Another sample unit of 1 pint shall consist of ink from one or more bottles after exposure is made in the bottles as specified in 4.4.1.2.

4.3.2.3 Testing of ink-filled polyethylene containers for permeability. Five 1-ounce polyethylene containers and five 1-ounce glass containers, filled with ink from the same lot, shall be tested in accordance with 4.4.4. The average loss of the polyethylene containers shall not exceed the maximum loss specified in 3.1.1.1.1 and 3.1.1.1.2 when the loss is computed in accordance with the test method.

4.4 Tests.

4.4.1 Stability of ink.

4.4.1.1 Original stability. Examine the sample of ink in its original container for precipitation by inserting a glass rod. If present, invert bottle and shake vigorously for one minute. Examine again for sediment and coagulation. Place a few drops of ink between glass plates and rub plates together and examine for granulation. (See 6.3).

4.4.1.2 Stability to temperature changes. Samples of ink in their original closed containers shall be exposed, one container to both of the temperature conditions for the applicable type, as follows:

Type I:
(a) At 125° ± 2°F. for four hours.
(b) At 32° ± 2°F. for four hours.

Type II:

(a) At 160° ± 2°F. for four hours.
(b) At -65° ± 5°F. for three days.

The inks after exposure to the above specified temperatures and adjustment to room temperature, shall be examined for coagulation, granulation, and precipitation when tested as specified in 4.4.1.1.

4.4.2 Performance. The performance tests shall be made with clean and properly sharpened drawing pens and the ink shall be observed for drying out in the pens during these tests.

4.4.2.1 Ink flow and uniformity of line width.

4.4.2.1.1 Test 1. Set a drawing pen at an opening of 0.003 ± 0.001 inch and fill it with sufficient ink to draw at least five lines, each 6 inches long. These lines shall be drawn parallel at intervals of 1/2 minute on drawing paper conforming to Type I, Class 1, Style A of Federal Specification UU-P-223; on white tracing cloth conforming to type I of Federal Specification CCC-C-531, and on bristol board conforming to grade A, type I, class 1 of Federal Specification UU-C-190. The ink shall be considered unsatisfactory if it is not possible to draw five clean, sharp, unbroken lines of uniform width. The ruler used shall have a square edge. The pen shall release the ink immediately upon being drawn along the straight edge. The pen shall be lifted vertically from the drawing material at the end of each 6-inch line.

4.4.2.1.2 Test 2. Set a detail drawing pen with an opening of 0.025 ± 0.001 inch and draw 10 parallel lines 2 inches long, 1/4 inch apart, on the specified bristol board and drawing paper, and on both sides of the specified tracing cloth. After these lines are allowed to dry for 10 minutes, 10 parallel lines of the same width and length shall be drawn at right angles across each of the sets previously drawn. The pen shall contain approximately the same volume of ink

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

each time it is charged. There shall be no change in the setting of the pen at any time during the progress of the test. The ruler shall be as specified in 4.4.2.1.1. At the completion of the test, there shall be no noticeable difference in the thickness of the lines of any surface; the intersecting lines shall be free from distortion or blots caused by the ink spreading under the ruling edge. The pen shall release ink immediately upon being drawn along the straight edge. The pen shall be lifted vertically from the drawing material at the end of each 2-inch line.

4.4.2.2 Penetration. A sample of the markings prepared in 4.4.2.1.2 shall be rubbed with an eraser of the "Van Dyke" No. 6500 type or equal. This test shall be conducted on the dull side of the tracing cloth and over a 1-inch portion of the marking. The ink markings shall be completely erasible.

4.4.2.3 Color, opacity, and gloss. Draw two lines, 12 inches long on the specified drawing paper, with a drawing pen, using ink obtained from two different samples of the same lot. After the lines are dry, apply another coat on the second line with the second ink. Examine the middle portion of each 12-inch line for intensity of color (blackness), opacity, and degree of gloss.

4.4.2.4 Abrasion resistance. A sample of marking, prepared as specified in 4.4.2.3, shall be rubbed vigorously with an eraser of the "art gum" type or equal. There shall be no perceptible evidence of ink removal.

4.4.3 Fastness tests. Draw two parallel lines, approximately 0.025 inch wide, 1/4 inch apart, and 8 inches long on the specified bristol board, drawing paper, and tracing cloth and mark off into two equal parts. After these have been allowed to dry for at least 1 hour, each part shall be subjected to the following tests:

4.4.3.1 Solubility in water. Place four drops of water (70° -80°F) and spread it over both lines for a length of about 1 inch, without rubbing or friction. Allow the water to evaporate naturally. There shall be no dissolution of the ink and no spreading of the lines.

4.4.3.2 Resistance to organic solvents. Repeat the above operation using hexane and 1,1,1-trichloroethane on separate areas. Additional quantities of each should be added in order to keep the surface wet at least 5 minutes. Observe for evidence of dissolutuion of the ink, spreading of the lines, or reduction of intensity of color (blackness).

4.4.4 Permeability test. Five ink-filled one ounce polyethylene containers of each inspection sample and five ink-filled one-ounce glass containers of the same ink representing control samples shall be sealed with paraffin wax along the edge of the stoppers, and individually weighed at room temperature. The ink and container shall then be placed inside a temperature controlled test chamber and maintained at a temperature of 100°F. ± 1°F. for 28 consecutive days. After this period of time, the containers shall be removed, allowed to cool at room temperature for 1 day, and reweighed. The average weight loss of the test samples minus the average weight loss of the control samples shall be the average weight loss of the test samples due to permeation. If the average weight loss is greater than 0.4 gram per one-ounce container, the lot shall be rejected. (See 5.1.1.1.1 and 5.1.1.1.2.)

4.4.5 Specific gravity. The specific gravity of ink shall be determined at 25°C. by using a pycnometer.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit package.

5.1.1.1.1 Type I. One, two, four, six, eight, sixteen, and thirty-two ounces of ink shall be packaged in 1-,2-,4-,6-,8-,16-, and 32-ounce bottles, respectively, and shall be furnished as specified (see 6.2). The bottles shall be fabricated from commercial grade glass or from polyethylene material. If a polyethylene material is used, the average weight loss due to permeation of the ink through the container shall not exceed 0.4-gram per one ounce container when tested as specified in 4.4.4. The shape of the one ounce bottles shall be such that each can be inserted in the ink bottle holders commercially available. Each one ounce bottle shall be provided with a plastic continuous-thread screw-cap closure with ink applicator. The cap and applicator shall not be affected by the ink, nor shall the ink be affected by the cap and applicator. The applicator shall extend down to within one-eighth inch of the bottom of the bottle when the cap is tightly in place. Each 2-,4-,6-,8-,16-, and 32-ounce bottle shall be provided with a metal or plastic continuous-thread screw-cap closure (See 5.1.1.1.1.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

Caps shall be of adequate weight sidewall so that an average of not more than 10 out of 30 caps will be broken in application by capping machines at 30 inch-pounds torque and no individual cap will break at less than 15 inch-pounds. All screw caps shall have a nonabsorbent resilient lining or a lining backed by resilient material which will remain in the cap. An inner seal shall be used to cover and adhere to the mouth of the 2-,4-,6-,8-,16-, and 32-ounce bottles which will prevent loss of the contents should the cap become loosened. Caps shall be tightened to prevent leakage. Each glass bottle and each one-ounce plastic bottle shall be packaged in a snug-fitting box conforming to PPP-B-566, style II, type D, class a. Boxes shall have tuck ends of a lock type specified in PPP-B-566 for the style of box specified. In addition, each box containing 16- or 32-ounce glass bottles shall be fitted with a single face corrugated liner. Each individual box containing 8-,16-, or 32-ounce bottles shall be sealed with tape as specified in the appendix to the box specification.

5.1.1.1.1.1 Alternate closure. Alternate non-metal continuous-thread screw-cap closure for the 2-,4-,6-,8-,16-, and 32-ounce bottles of pourout type or other design in accordance with standard commercial practice, will be acceptable provided the alternate closure meets the quality established by this specification and is at least equally effective to that described above for the purpose intended.

5.1.1.1.2 Type II. One and one-quarter ounces of ink shall be packaged in a 1-1/4 ounce bottle. The bottle shall be molded in one piece from polyethylene plastic and shall be of the flexible squeeze bottle type fitted with an elongated polyethylene plastic or urea formaldehyde plastic applicator tip which will facilitate the dispensing of one drop of ink at a time to drafting and lettering pens and which will prevent ink from spilling from the bottle when it is accidently overturned with the cap removed. A screw-type urea formaldehyde plastic cap which screws to the bottle and effectively seals the applicator tip when in place, shall be provided. Each bottle shall be sufficiently rugged to withstand field handling and use without damage. The body of the bottle shall be roughly oval in cross section, approximately 7/8 by 1-5/8 inches, and the over-all height with the cap in place shall not exceed 3-1/2 inches. The average weight loss due to permeation of the ink through the polyethylene container shall not exceed 0.4-gram per 1-1/4 ounce bottle when tested as specified in 4.4.4.

5.1.1.2 Intermediate package. Ink, unit packaged as specified in 5.1.1.1.1 and 5.1.1.1.2, except for 16-ounce and 32-ounce bottles, shall be intermediate packaged in quantities specified in table II in a snug-fitting box as specified in 5.1.1.1.1 or alternately intermediate packaged as specified in note 1 to the table II. Sixteen ounce and thirty-two ounce bottles shall be intermediate-packaged in boxes conforming to PPP-B-636 or PPP-B-665, in quantities as indicated in table II.

TABLE II.

Size (ounces)	Quantity of unit packages per intermediate package	Quantity of unit packages per shipping container
1	1/ 12	144
1-1/4	1/ 12	144
2	1/ 12	144
4	1/ 12	144
6	6	96
8	6	96
16	6	48
32	6	24

1/ Alternate intermediate packaging: Two boxes, each tightly wrapped with kraft paper and each containing 6 unit packages as specified in 5.1.1.1.1, may be inserted in a snug-fitting box (intermediate package) as specified in 5.1.1.1.2 to comply with the requirements for 12 unit packages per intermediate package.

5.1.2 Level B. Packaging for level B shall be as specified in 5.1.1 for level A.

5.1.3 Level C. The ink shall be packaged in accordance with the manufacturer's standard practice, providing that this insures protection for the ink during shipment and provides for safe delivery at its destination.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Ink, packaged as specified in 5.1, shall be packed in quantities as specified in table II in a snug-fitting fiberboard box conforming to PPP-B-636, class weather-resistant. Closure shall be in accordance with the appendix to the box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

5.2.2 Level B. Ink, packaged as specified in 5.1, shall be packed in quantities as specified in table II in a snug-fitting fiberboard box conforming to PPP-B-636, class domestic. Closure shall be in accordance with the appendix to the box specification.

5.2.3 Level C. The ink, packaged as specified in 5.1.3, shall be packed in containers that will assure carrier acceptance and safe arrival at destination in compliance with the Uniform Freight Classification rules and the National Motor Freight Classification rules.

5.3 Marking. Marking shall be in accordance with paragraph 5.3.1 or 5.3.2 as specified (see 6.2).

5.3.1 Civil agencies. In addition to any special markings required by the contract or order, all interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123, including specification classification (such as type, class, color, etc.).

5.3.2 Military agencies. In addition to any special markings required by the contract or order, all interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.3 Special marking. Each shipping container containing glass bottles shall bear "FRAGILE" marking. Shipping containers for type I ink shall be prominently marked "KEEP FROM FREEZING" on each side in 1-inch letters. All shipping containers shall bear arrows and the word "UP" on at least one side and one end and the words "TOP" and "THIS SIDE UP" on the top surface.

6. NOTES

6.1 Intended use. Type I drawing ink covered herein is intended for use in tropic and temperate climates only. Type II is intended for use under conditions where ink may be subjected to extremely low temperatures.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type required (see 1.2.1).
(c) Data, as required, regarding examination and tests and inspection responsibility (for civil agency procurement) if other than as specified (see 4.1).
(d) Size of unit package for type I ink (see 5.1.1.1.1).
(e) Level of packaging and level of packing and any special marking required (see 5.1, 5.2, and 5.3).

6.3 Definitions. The following terminology included in this specification is defined as follows:

Coagulation - The result of gelation.
Granulation - Hard particles which can be detected by placing a few milliliters of ink between glass plates and then rubbing the plates together.
Precipitation - Precipitates are defined as particles of solids which fall out of solution or suspension and which cannot be redispersed or suspended by either inverting or shaking bottle by hand for 1 minute.

6.4 Supersession data. This specification includes the requirements of Military Specification MIL-I-13942 (CE), dated January 11, 1965.

User Interest:

Army - GL .

Preparing Activity:

GSA - FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

FED SUP CLASS 7105

LIMITATION STANDARD

This document has been promulgated by the Department of Defense as the military standard to limit the selection of the items or products (except for packaging and packing) covered herein in procurement. This standard identifies the items authorized for repetitive procurement in the military services, and shall become effective on issuance.

Index No.	FIIN	Item Name	Specification	Users
1	263-8577	MATTRESS, BED	V-M-96b, type I, size 10	N
2	263-8581	MATTRESS, BED	V-M-96b, type I, size 8	N
3	275-5873	MATTRESS, BED	MIL-M-18351, type IV	N
4	275-5874	MATTRESS, BED	MIL-M-18351, type V	N
5	290-8297	MATTRESS, BED	MIL-M-18351, type I	N
6	290-8298	MATTRESS, BED	MIL-M-18351, type II	N
7	290-8299	MATTRESS, BED	MIL-M-18351, type III, size 1	N
8	290-8300	MATTRESS, BED	MIL-M-18351, type III, size 2	N
9	274-7001	MATTRESS, BED	V-M-81c, type II, size 7, grade B	N, MC
10	205-3913	MATTRESS, BED	V-M-81c, type II, grade C, size 7	AF
11	716-0705	MATTRESS, BED	V-M-96b, type I, size 5	N, AF
12	716-0706	MATTRESS, BED	V-M-96b, type II, size 5	A, N, AF
13	269-9197	MATTRESS, BED	V-M-96b, type I, size 11	AF

APPROVED 3 Mar 1958 REVISED

CUSTODIANS	OTHER INT.
AF-GADSDEN	A-
N-DOCKS	N-
A-QMC	AF-

MILITARY STANDARD

HOUSEHOLD FURNITURE
FSC CLASS 7105 (PARTIAL)
MATTRESS, BED

MS 63002

PROCUREMENT SPECIFICATION

SUPERSEDES:

SHEET 1 OF 2

DD FORM 1 OCT 57 672

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

Index No.	FIIN	Item Name	Specification	Users
14	269-9200	MATTRESS, BED	V-M-96b, type II, size 7	A
15	263-8583	MATTRESS, BED	V-M-96b, type I, size 1	A
16	551-5152	MATTRESS, BED	ZZ-M-91a, size 1 (except for size)	AF
17	784-2120	MATTRESS, BED	Purchase Description No. 2, 17 Oct. 1955	A,N, AF
18	700-2045	MATTRESS, BED	Purchase Description No. 2, 23 Jan. 1956	A,N, AF
19	514-5837	MATTRESS, BED	Purchase Description No. 1, 27 May 1957	A,N, AF
20	716-0480	MATTRESS, BED	V-M-81c, type III, grade B, size 1	A
21	716-0602	MATTRESS, BED	MIL-M-40020	A,N, AF
22	530-3730	MATTRESS, BED	V-M-81c, type I or II, grade B, size 4	A,AF, MC
23	716-0535	MATTRESS, BED	V-M-81c, type II, grade B, size 2	A
24	716-0500	MATTRESS, BED	V-M-81c, type II, grade B, size 6	A,N, AF
25	227-1499	MATTRESS, BED	MIL-M-16039, type I, class 3	A,N
26	263-8582	MATTRESS, BED	V-M-81c, type II, grade B, size 7	MC
27	543-7860	MATTRESS, BED	V-M-96b, type II, size 4	AF

REVISED

APPROVED 3 Mar 1958

CUSTODIANS
AF-CAUSDEN
N-DOCKS
A-QMC

OTHER INT.
A-
N-
AF-

MILITARY STANDARD

HOUSEHOLD FURNITURE
FSC CLASS 7105 (PARTIAL)
MATTRESS, BED

MS 63002

PROCUREMENT SPECIFICATION

SUPERSEDES:

SHEET 2 OF 2

DD FORM 1 OCT 52 672

NOTICE: When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.