TT-W-568E
June 6, 1975
SUPERSEDING
Fed. Spec. TT-W-568D
April 10, 1967

FEDERAL SPECIFICATION

WOOD PRESERVATIVE; CREOSOTE-PETROLEUM SOLUTION

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 Scope. This specification covers creosote-petroleum solution for the preservative treatment of wood by pressure processes according to Fed. Spec. TT-W-571 (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

TT-C-645 - Creosote, Coal Tar, Technical.
TT-W-571 - Wood Preservation: Treating Practices.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks, and the Index of Federal Specifications and Standards, from established distribution points in their agencies.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Wood-Preservers' Association (AWPA) Standards:

P4 - Standard for Petroleum for Blending with Creosote.
A4 - Standard Method for Sampling Wood Preservatives.

(Application for copies should be addressed to the American Wood-Preservers' Association, 1625 I Street, NW., Washington, DC 20006.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

American Society for Testing and Materials (ASTM) Standards:

D 88 - Saybolt Viscosity.
D 93 - Flash Point by Pensky-Martens Closed Tester.
D 96 - Water and Sediment in Crude Oils.
D 287 - API Gravity of Crude Petroleum and Petroleum Products (Hydrometer Method).

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

3. REQUIREMENTS

3.1 Material. The solution shall consist of 50 ± 2 percent by volume of coal-tar-creosote (see 3.1.1) and remainder petroleum distillate by volume (see 3.1.2).

3.1.1 The coal-tar-creosote shall conform to class II, TT-C-645.

3.1.2 The petroleum distillate shall conform to AWPA Standard P4.

3.2 Mixing. The purchaser may have a representative observe the preparation of the solution or may accept certificate that the proportions are as specified in 3.1 (see 6.2).

3.3 The solution, as prepared, shall have the following properties:

Water and sediment, percent by volume, not more than 3.0.
Specific gravity at 38°C. compared with water at 15.5°C., not less than 1.01.
Flashpoint, not less than 175°F.
Viscosity: not less than 35 nor more than 55 Saybolt Universal Seconds at 210°F.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling. Sampling shall be conducted in accordance with AWPA Standard A4. The treating material shall be thoroughly agitated after which a 1-quart sample shall be taken for inspection and test purposes. The contractor shall supply such samples and containers as may be required at no cost to the Government.

4.3 Tests.

4.3.1 Test procedures. Tests to determine the requirements of creosote-petroleum solution shall be as follows:

Water and sediment - ASTM D 96.
Specific gravity - ASTM D 287.
Flashpoint - ASTM D 93.
Viscosity - ASTM D 88.

5. PREPARATION FOR DELIVERY

This specification covers material used in the processing of wood. Packaging and packing data are not applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. Creosote-petroleum solution may be used for the preservative treatment by pressure methods of crossties, switch ties, bridge ties, lumber, structural timbers, posts, and piles for land or fresh water use.

6.2 Creosote-petroleum solution shall be prepared at the treating plant. Whenever possible, a representative of the purchaser should test the properties of the two separate ingredients and observe the preparation of the solution.

6.3 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.

Military Interest:

Army - ME

Preparing Activity:

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 25 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.