H-B-56

AMENDMENT—2
June 6, 1941

SUPERSEDING
ERRATA-1
August 1933

FEDERAL SPECIFICATION

BROOMS; FIBER

This amendment was approved on the above date by the Director of Procurement, for the use of all departments and establishments of the Government, and shall become effective not later than December 15, 1941. It may be put into effect, however, at any earlier date after promulgation.

The following changes shall be made in Federal Specification H–B–56, dated December 8, 1931:

Page H–B–56—1:

Paragraph **A–1.** Delete paragraph in its entirety and substitute:

A–1. Federal Specification T–T–901 Hemp Twine, of the issue in effect on date of invitation for bids, shall form a part of this specification.

Paragraphs **D–2** and **D–3.** Delete paragraphs and substitute:

D–2. *Handle.*—Shall be of maple, beech, birch, douglas fir, southern yellow pine, or hickory, free from knots, splits and other imperfections, smoothly finished, and extending into the neck and body of the brooms not less than 2 inches. If douglas fir or southern yellow pine is used, it shall be finished with at least two coats of transparent varnish or lacquer.

D–3. *Fastening.*—The fibers shall be firmly set in cement or pitch and firmly bound with a pressed-steel cap, properly lacquered to prevent rusting. Cap shall be through-riveted with at least five metal rivets and secured to handle by two or more metal rivets, or the cap shall be through-riveted or nailed with No. 12 gage nails clinched and pressed, with the clinched side of nails protected and strengthened with extra covering. The cap shall be secured to handle by metal rivets. Black nails and rivets, if used, shall be painted or lacquered for preservation.

Source: https://assist.dla.mil -- Downl
Check the source to verify that this is th

H–B–56
Amend.—2—2
(June 1941)

Page H–B–56—2:

Paragraph **D–4.** Delete paragraph in its entirety and substitute:

D–4. *Ties and stitches:*

D–4a. The body of the 28-pound broom shall be firmly held in shape by ties of not less than 3-ply, strong, well-waxed cable laid linen twine, having not less than 2,200 feet per pound, or size No. 18, 3-ply twine made from hemp (canabis sativa) or a mixture of hemp and not more than 25 percent jute fiber, having a minimum length per pound of 1,100 feet which shall be uniformly spun and polished; or cotton twine of not less than 3 ply. All twines shall have a breaking strength of not less than 35 pounds when tested in accordance with Federal Specification for hemp twine. Ends of twine shall be adequately secured.

D–4b. The body of the 32- and the 36-pound brooms shall be held in place by ties of twine similar to that required for the 28-pound broom (paragraph D–4a), or may have a spot-welded band securely locked to the fiber by means of five staples. Ends of twine shall be adequately secured.

D–4c. On the 32- and 36-pound brooms the rows of stitches farthest from the neck may be dropped to space of greater distance.

Source: https://assist.dla.mil -- Downlo
Check the source to verify that this is th