INCH-POUND

MIL-M-14/4
AMENDMENT 1
7 November 1990

MILITARY SPECIFICATION SHEET

MOLDING COMPOUNDS, POLYESTER, THERMOSETTING, CONTAINING MINERAL/GLASS FILLERS

This amendment forms a part of MIL-M-14/4, dated 2 April 1990, and is approved for use by all Department and Agencies of the Department of the Defense.

PAGE 2

Table I, under "Mechanical/physical", column "Type MAI-60": Delete "155", and substitute "120".

PAGE 3

Table I: Delete and substitute: (see page 2)

Custodians:
Army - ME
Navy - SH
Air Force - 20

Review activities:
Army - ER, MI, MR, AR, EA
Navy - AS, OS
DLA - GS

User activities:
Navy - YD, EC

Preparing activity:
Navy - SH
(Project 9330-1169)

AMSC N/A FSC 9330

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:55Z
Check the source to verify that this is the current version before use.

TABLE I. *Qualification test requirements for polyester resin molding compounds, cellulose, mineral/glass filled – Continued.*

Requirement	Type MAG	Type MAI-30	Type MAI-60	Type MAT-30
		Electrical *(Continued)*		
Dissipation factor:				
at 1 kilohertz	0.04	0.02	0.03	0.03
	0.06	0.02	0.06	0.05
at 1 megahertz	0.02	0.01	0.03	0.03
	0.03	0.02	0.05	0.05
		Combustion		
Flame resistance:				
Ignition time	60	100	90	100
Burning time	200	75	90	50
Flammability/Thickness-Inch	V-1 / 1/8	V-1 / 1/8	V-1 / 1/8	V-1 / 1/8
Toxicity when heated:				
Carbon dioxide	15,000	15,000	15,000	15,000
Carbon monoxide	1,000	1,000	1,000	1,000
Ammonia	2,500	2,500	2,500	1,000
Aldehydes as HCHO	50	50	50	50
Cyanide as HCN	60	60	60	60
Oxide of nitrogen at NO_2	100	100	100	100
Hydrogen chloride	100	100	100	100

[1]The side of the test specimen is that area formed by the chase of the mold.

Source: https://assist.dla.mil -- Downloaded: 202610-15T15:55Z
Check the source to verify that this is the current version before use.