INCH-POUND
MIL-M-14/6
AMENDMENT 3
19 May 1993
SUPERSEDING
AMENDMENT 2
28 May 1991

MILITARY SPECIFICATION SHEET

MOLDING COMPOUNDS, DIALLYL ORTHO-PHTHALATE, THERMOSETTING, CONTAINING MINERAL FILLERS, GLASS OR POLYMERIC FILLERS

This amendment forms a part of MIL-M-14/6, dated 2 April 1990, and is approved for use by all Department and Agencies of the Department of the Defense.

PAGE 3

* Table I: Delete and substitute: (page 3 attached):

PAGE 4

* Table I: Delete and substitute: (page 4 attached):

PAGE 5

Table II: Delete and substitute: (page 5 attached):

NOTE: The margins of this amendment are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

AMSC N/A FSC 9330

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.

Custodians:
Army - AR
Navy - SH
Air Force - 11

Review activities:
Army - MI, MR, EA
Navy - AS, OS
DLA - GS

User activities:
Navy - YD, EC

Preparing activity:
Navy - SH
(Project 9330-1277)

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification test requirements for diallyl ortho-phthalate resin molding compounds, mineral, glass or polymer fiber filled.

Requirement	Type GDI-30	Type GDI-30F	Type GDI-300	Type GDI-300F	Type MDG	Type MDG-F	Type SDG	ype SDG-F	Type SDI-5	Type SDI-30
	Mechanical/physical									
Compressive strength, endwise	20,000	20,000	20,000	20,000	18,000	18,000	16,000	16,000	18,000	16,000
Dimensional stability	0.1	0.1	0.1	0.1	0.2	0.2	0.2	0.2	0.2	0.2
Flexural strength	13,000	13,000	35,000	35,000	10,000	10,000	13,000	13,000	8,000	10,000
Heat deflection temperature	180	180	200	200	148	148	160	160	100	115
Heat resistance	130	130	130	130	90	90	100	100	80	90
Impact strength,										
Side[1/]	2.75	2.75	30	30	0.35	0.35	0.50	0.50	0.60	2.75
Face[2/]	3.00	3.00	30	30	0.35	0.35	0.50	0.50	0.60	3.00
Tensile strength	6,000	6,000	18,000	18,000	6,000	6,000	6,000	6,000	3,500	3,600
Water absorption	0.5	0.5	0.5	0.5	0.7	0.7	0.5	0.5	0.5	0.5
	Electrical									
Arc Resistance	115	115	115	115	115	115	115	115	100	115
Dielectric breakdown:										
Short-time test (To be recorded as basis for initial voltage in step-by-step test)										
Step-by-step test	45	45	40	40	40	40	45	45	45	45
Short-time test (To be recorded as basis for initial voltage in step-by-step test)										
Step-by-step test	40	40	35	35	40	40	40	40	40	40
Dielectric constant:										
at 1 kilohertz	4.6	4.6	5.0	5.0	5.0	5.0	4.6	4.6	4.1	4.1
	4.7	4.7	5.0	5.0	5.2	5.2	4.7	4.7	4.2	4.2
at 1 megahertz	4.6	4.6	5.0	5.0	5.0	5.0	4.6	4.6	3.8	3.8
	4.7	4.7	5.0	5.0	5.2	5.2	4.7	4.7	3.9	3.9

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification test requirements for diallyl ortho-phthalate resin molding compounds, mineral, glass or polymer fiber filled - Continued.

Requirement	Type GDI-30	Type GDI-30F	Type GDI-300	Type GDI-300F	Type MDG	Type MDG-F	Type SDG	Type SDG-F	Type SDI-5	Type SDI-30
	Electrical (Continued)									
Dielectric strength:										
Short-time test	325	325	325	325	325	325	325	325	325	325
Step-by-step test	300	300	300	300	300	300	300	300	300	300
Short-time test	325	325	325	325	325	325	325	325	325	325
Step-by-step test	300	300	300	300	300	300	300	300	300	300
Dissipation factor										
at 1 kilohertz	0.015	0.015	0.020	0.020	0.019	0.019	0.015	0.015	0.025	0.020
	0.018	0.018	0.025	0.025	0.020	0.020	0.015	0.015	0.028	0.025
at 1 megahertz	0.020	0.020	0.025	0.025	0.025	0.025	0.020	0.020	0.035	0.025
	0.023	0.023	0.030	0.030	0.025	0.025	0.023	0.023	0.025	0.025
Surface resistance	5,000	5,000	5,000	5,000	5.0	5.0	10	5,000	100	10
Volume resistance	5,000	5,000	5,000	5,000	2.0	2.0	10	5,000	100	10
Water extract conductance	60×10^{-6}	60×10^{-6}	-	-	-	-	-	-	-	-
	Combustion									
Flame resistance:										
Ignition time	-	90	-	90	-	90	-	90	-	-
Burning time	-	90	-	90	-	90	-	90	-	-
Flammability/ Thickness-Inch:	-	V-0/1/8	-	V-0/1/8	-	V-0/1/16	-	V-0/1/16	-	-
Toxicity when heated:										
Carbon dioxide		15,000	-	15,000		15,000		15,000		
Carbon monoxide		1,000	-	1,000		1,000		1,000		
Ammonia		2,500	-	25,000		2,500		2,500		
Aldehydes as HCHO		50	-	50		50		50		
Cyanide as HCN		60	-	60		60		60		
Oxide of nitrogen as NO_2		100	-	100		100		100		
Hydrogen chloride		100	-	100		100		100		

1/ The side of the test specimen is that area formed by the chase of the mold.
2/ face of a test specimen is that area formed by t op or bottom force plug.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.

TABLE II. Batch acceptance test requirements for diallyl ortho-phthalate molding compounds, mineral, glass or polymer fiber filled.

Property to be tested	Type GDI-30	Type GDI-30F	Type GDI-300	Type GDI-300F	Type MDG	Type MDG-F	Type SDG	Type SDG-F	Type SDI-5	Type SDI-30
	Performance requirement for each compound.									
Arc resistance	115	115	115	115	115	115	115	115	115	115
Dielectric constant at 1 megahertz	4.7	4.7	5.0	5.0	5.2	5.2	4.7	4.7	3.9	3.9
Dielectric strength, step-by-step	300	300	300	300	300	300	300	300	300	300
Dissipation factor at 1 megahertz	0.023	0.023	0.030	0.030	0.025	0.025	0.023	0.023	0.025	0.025
Flexural strength	13,000	13,000	35,000	35,000	10,000	10,000	13,000	13,000	8,000	10,000
Impact strength, side 1/	2.75	2.75	30.0	30.0	0.30	0.30	0.50	0.50	0.60	2.75
Water absorption	0.5	0.5	0.5	0.5	0.7	0.7	0.5	0.5	0.5	0.5
Water extract conductance	60 x 10^{-6}	60 x 10^{-6}	-	-	-	-	-	-	-	-

1/ The side of the test specimen is that area formed by the chase of the mold.

Source: https://assist.dla.mil -- Downloaded: 2026-01-15T15:56Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.