INCH-POUND
MIL-M-14/7
AMENDMENT 2
19 May 1993
SUPERSEDING
AMENDMENT 1
7 November 1990

MILITARY SPECIFICATION SHEET

MOLDING COMPOUNDS, SILICONE, THERMOSETTING, CONTAINING MINERAL/GLASS FILLERS

This amendment forms a part of MIL-M-14/7, dated 2 April 1990, and is approved for use by all Department and Agencies of the Department of the Defense.

PAGE 2

* Table I: Delete and substitute: (page 3 attached)

PAGE 3

Table, title: Delete "milicone", and substitute "silicone".

Table I: Delete "Type MSG-30", and substitute "Type MSI-30)".

Table I: Delete "Flammability", and substitute Flammability/Thickness-Inch".

Table I: Delete "V-1" in both columns and substitute "V-1/1/16".

NOTE: The margins of this amendment are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

AMSC N/A FSC 9330

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil - Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.

Custodians:
Army - AR
Navy - SH
Air Force - 11

Review activities:
Army - MI, MR, EA
Navy - AS, OS
DLA - GS

User activities:
Navy - YD, EC

Preparing activity:
Navy - SH
(Project 9330-1278)

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.

TABLE I. Qualification test requirements for silicone resin molding compounds, mineral/glass filled.

Requirement	Type MSG	Type MSI-30
Mechanical/physical		
Compressive strength, endwise	15,000	10,000
Flexural strength	6,000	7,000
Heat deflection temperature	200	200
Heat resistance	150	150
Impact strength, side[1/]	0.25	3.2
Tensile strength	2,500	2,000
Water absorption	0.50	0.50
Electrical		
Arc resistance	210	175
Comparative track index	-	-
Dielectric breakdown:		
Short-time test	(To be recorded as basis for initial Voltage in step-by-step test)	
Step-by-step test	35	30
Short-time test	(To be recorded as basis for initial Voltage in step-by-step test)	
Step-by-step test	35	30
Dielectric constant:		
at 1 kilohertz	5.0	5.0
	5.2	5.5
at 1 megahertz	4.7	4.7
	5.0	5.1
Dielectric strength:		
Short-time test	325	160
	300	125
Step-by-step test	300	75
Short-time test	275	50
Step-by-step test		
Dissipation factor:		
at 1 kilohertz	0.015	0.015
	0.020	0.050
at 1 megahertz	0.010	0.010
	0.015	0.060
Surface reistance	1,000	-
Volume resistance	1,000	-

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:56Z
Check the source to verify that this is the current version before use.