MIL-B-83054B
AMENDMENT 1
22 October 1981

MILITARY SPECIFICATION

BAFFLE AND INERTING MATERIAL, AIRCRAFT FUEL TANK

This amendment forms a part of Military Specification MIL-B-83054B(USAF), dated 17 May 1978, and is approved for use by the Department of the Air Force and is available for use by all Departments and Agencies of the Department of Defencse.

PAGE 4

Table I, Under Type V:
Porosity (Air pressure drop): Delete "20-30" and substiture "24-34"

Air pressure drop (Inches of water): Delete "0.250-0.330" and substitute "0.270-0.370".

Fluid tetention (Volume - percent), Fuel: Delete "4.5 (Max)" and substitute "5.0 (Max)".

PAGE 11

4.6.4, lines 1 thu 7, (first thru fifth sentences): Delete and substitute "The pore size determination shall be by the air pressure drop technique specified herein. Two specimenns for each production and lot sample shall be run. For qualification, three specimens shall be tested. The cylindrical specimen shall be 10 inches in diameter by 1 $\pm$0.02 inch thick, where the 1-inch dimension is in the height direction of the test section. For production and lot testing, the porosity test specimens shall be taken within the top and bottom three inches of the test section height (foaming height)".

Custodian:
Air Force - 11

Reviewing Activity:
Air Force - 99

Preparing activity:
Air Force - 11

Project 9330-F995

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:34Z
Check the source to verify that this is the current version before use.