DOD-E-700A
12 January 1978
SUPERSEDING
JAN-P-700
29 November 1948
(See 6.7)

MILITARY SPECIFICATION

ENAMEL, DECK, INTERIOR, GRAY (FORMULA NO. 20L) (METRIC)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers gray, interior deck enamel (Formula No. 20L) for shipboard use. The product covered by this document is suitable for use where air pollution regulations apply.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL
TT-R-266 - Resin, Alkyd; Solutions.
TT-T-291 - Thinner-Paint, Volatile Spirits, Petroleum Spirits.
PPP-P-1892 - Paint, Varnish, Lacquer, and Related Materials; Packaging, Packing, and Marking of.

MILITARY
MIL-P-15173 - Pigment, Magnesium Silicate: Dry (Paint Pigment).
MIL-V-15218 - Varnish, (Mixing, Phenolic).

STANDARDS

FEDERAL
FED-STD-141 - Paint, Varnish, Lacquer, and Related Materials: Methods of Inspection, Sampling, and Testing.
FED-STD-313 - Material Safety Data Sheets, Preparation and the Submission of.
FED-STD-595 - Colors.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 93 - Flash Point by Pensky-Martens Closed Tester, Test for.
D 185 - Coarse Particles in Pigments, Pastes, and Paints, Tests for.
D 209 - Lampblack, Spec. for.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Ship Engineering Center, SEC 6124, Department of the Navy, Washington, DC 20362 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.

D 562 - Consistency of Paints Using the Stormer Viscosimeter, Test for.
D 563 - Phthalic Anhydride Content of Alkyd Resins and Resin Solutions, Test for.
D 600 - Liquid Paint Driers, Spec. for.
D 1210 - Fineness of Dispersion of Pigment-Vehicle Systems, Test for.
D 1296 - Odor of Volatile Solvents and Diluents, Test for.
D 1308 - Effect of Household Chemicals on Clear and Pigmented Organic Finishes, Test for.
D 1475 - Density of Paint, Varnish, Lacquer, and Related Products, Test for.
D 1542 - Rosin in Varnishes, Qualitative Tests for.
D 2244 - Color Differences of Opaque Materials, Instrumental Evaluation of.
D 2369 - Volatile Content of Paints, Test for.
D 3335 - Low Concentrations of Lead and Cadmium in Paint by Atomic Absorption Spectroscopy, Test for.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Toxicity. The material shall have no adverse effect on the health of personnel when used for its intended purpose (see 4.6). Questions pertinent to this effect shall be referred by the procuring activity to the appropriate service medical department which will act as advisor to the procuring activity.

3.2 Description. The enamel shall be ready-mixed and prepared in accordance with the table I formula designated as Navy Standard Formula No. 20L. When Formula No. 20L is specified, the enamel shall conform to this specification.

TABLE I. Formula No. 20L.

Ingredients	Specification	kg	(Pounds) 1/
Titanium dioxide 2/		34.091	(75)
Lampblack 3/		0.591	(1.3)
Magnesium silicate	MIL-P-15173, type A	154.545	(340)
Alkyd resin solution 4/	TT-R-266, type I, class A	86.364	(190)
Varnish, solution	MIL-V-15218, type II	100.0	(220)
Paint thinner	TT-T-291, type II, grade A	95.455	(210)
Lead naphthenate drier	ASTM D 600, class B	3.045	(6.7)
Cobalt naphthenate drier	ASTM D 600, class B	2.0	(4.4)

1/ The formula is given slightly in excess of 100 gallons (see 6.6) to allow for normal manufacturing loss.

2/ The titanium dioxide pigment shall be an aluminum oxide, modified semichalking, rutile titanium dioxide containing no less than 96 percent titanium dioxide and between 0.5 and 2.5 percent aluminum oxide.

3/ "Raven 8000" by Columbian Carbon Company or equal.

4/ The alkyd resin solution shall conform to type I, class A of TT-R-266. In addition, it shall conform to the solvent requirements of TT-R-266, applicable to alkyd resin solutions intended for use in coatings used in areas with regulations controlling the emission of solvents into the atmosphere (see 6.5).

3.3 Composition. The paint shall consist of ingredients conforming to the requirements of the applicable specifications in the proportions shown in table I, except that the amount of lampblack may be varied as necessary to meet the color requirement. Additionally, to assist in meeting brushing, condition in container, and storage stability requirements, small amounts of antisettling, antisagging, and antiskinning agents may be added, provided that all the other requirements of the specification are met and the exact formula used shall be furnished in the record required by method 1031 of FED-STD-141.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.

3.4 Manufacture. The component raw materials shall be mixed and dispersed as required to yield a product which shall be uniform and in full conformity to the requirements of this specification.

3.5 Volatile portion. The volatile portion of the enamel shall conform to the following requirements by volume:

(a) A combination of hydrocarbons, alcohols, aldehydes, ethers, esters, or ketones having an olefinic or cycloolefinic type of unsaturation except perchloroethylene: 5 percent maximum.
(b) A combination of aromatic compounds with eight or more carbon atoms to the molecule except ethylbenzene, methyl benzoate, and phenyl acetate: 8 percent maximum.
(c) A combination of ethylbenzene, ketones having branched hydrocarbon structures, trichloroethylene, or toluene: 20 percent maximum.

3.6 Quantitative requirements. The enamel shall conform to the quantitative requirements of table II when tested in accordance with 4.4.

TABLE II. Quantitative requirements.

Characteristics	Requirements	
	Minimum	Maximum
Pigment, percent by weight of enamel	39.0	43.0
Volatiles, percent by weight of enamel	31.5	35.5
Nonvolatile vehicle, percent by weight of enamel (calculated by difference)	25.0	29.0
Phthalic annydride, percent by weight of nonvolatile vehicle	11.0	---
Water, percent by weight of enamel	---	0.5
Coarse particles and skins (as residue retained on No. 325 sieve), percent by weight of enamel	---	0.2
Consistency, Krebs-Stormer shearing rate 200 RPM		
grams	140	190
equivalent Krebs units	70	80
Weight per gallon, kg (pounds)	4.591 (10.1)	4.773 (10.5)
Drying time		
set-to-touch, hours	---	2.0
hard, hours	---	7.0
Fineness of grind	4	---
Flash point, °C (°F)	38 (100)	---
Gloss, 60-degree specular	---	50
Titanium dioxide, percent by weight of pigment	16.0	19.0
Lead, percent by weight of total nonvolatile	---	0.5

3.7 Qualitative requirements.

3.7.1 Brushing properties. The enamel, when tested as specified (see 4.4.6), shall be capable of being brushed out and laid off without excess drag on the brush. When dry, the brushed surface shall be free from sags and runs and shall show a minimum of brush marks.

3.7.2 Spraying properties. The enamel, when tested as specified (see 4.4.7), shall spray satisfactorily in all respects and show no running, sagging, or streaking. The film shall show no dusting, mottling, or color separation.

3.7.3 Flexibility. A film of enamel, prepared and tested as specified (see 4.4.8), shall withstand bending without cracking or flaking when observed at seven-diameter magnification.

3.7.4 Water resistance. A film of enamel, prepared and tested as specified (see 4.4.9), shall show no wrinkling or blistering immediately after removal of the panel from water. The enamel shall be only slightly affected with regard to hardness and adhesion when observed 2 hours after removal from the water. After 24-hours air drying, the portion of the panel which was immersed shall be almost indistinguishable, with regard to hardness, adhesion, and general appearance, from the portion of the panel that was not immersed.

3.7.5 Color. The color shall match color No. 36231 of FED-STD-595 when tested as specified (see 4.4.10).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.

3.7.6 Condition in container. A freshly opened, full container of enamel, when tested as specified (see 4.4.11), shall be free from lumps, abnormal thickening, or livering and shall show no more pigment settling or caking than can be readily reincorporated to a smooth, uniform state.

3.7.7 Storage stability.

3.7.7.1 Partially full container. A three-quarter filled, closed 250-milliliter (mL) (8-ounce) glass jar of enamel shall show no skinning at the end of 48 hours when tested as specified (see 4.4.12.1). After aging as specified (see 4.4.12.1), the enamel shall show no livering, curdling, hard caking, or gummy sediment. It shall mix readily to a smooth, uniform state and skins formed shall be continuous and easily removed.

3.7.7.2 Full container. When stored as specified (see 4.4.12.2), the enamel shall be capable of being readily broken up with a paddle to a smooth, uniform consistency. It shall be free from livering, curdling, gelling, or other objectionable properties and shall not exceed 90 Krebs units in viscosity. It shall not exceed 7-hours dry hard time and shall match the specified color.

3.7.8 Dilution stability. When thinned as specified (see 4.4.13), the enamel shall remain stable and uniform, showing no precipitation, curdling, or separation. Slight pigment settling shall be permitted.

3.7.9 Rosin and rosin derivatives. The enamel shall give a negative test for the presence of rosin and rosin derivatives when tested as specified (see 4.4.14.)

3.7.10 Phenolic resins. The enamel shall give a positive test for the presence of phenolic resins when tested as specified (see 4.4.15).

3.7.11 Odor. The odor shall be characteristic of the volatiles permitted when tested as specified (see 4.4).

3.7.12 Surface appearance. A flow-out film on glass of the mixed enamel, after drying for 24 hours, shall exhibit a surface smooth in appearance and free of defect, such as pin-holes, coarse particles, skins, or agglomerates of any kind.

3.7.13 Material safety data sheet. The procuring activity shall be provided a material safety data sheet (MSDS) at the time of contract award. The MSDS is DD Form 1813 and found in and part of FED-STD-313. The MSDS shall be included with each shipment of the material covered by this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Quality conformance inspection. Quality conformance inspection shall be provided in accordance with method 1031 of FED-STD-141 as hereinafter supplemented. Submission of forms in accordance with method 1031 shall cover complete tests other than the 1-year stability in full container test. The stability requirement (see 3.7.7.2) shall apply for 1 year after manufacture regardless of other testing or prior acceptance of material.

4.2.1 Manufacturing control. In addition to the other requirements of method 1031 of FED-STD-141, the contractor shall forward to the cognizant inspection office and testing laboratory a copy of the certification that each ingredient raw material conforms to the applicable specification.

4.2.2 Ingredient materials. When requested by the procuring activity (see 6.2), 1 pint of each ingredient in the formula specified (see table I) shall be supplied for test purposes.

4.3 Acceptance. Acceptance of the enamel shall be based upon compliance of the enamel with the requirements of this specification. Failure to pass any test shall be cause for rejection of the lot.

4.4 Test procedures. The following tests shall be made in accordance with the applicable FED-STD-141 and ASTM methods.

Source: https://assist.dla.mil -- Downloaded: 202640-16T11:17Z
Check the source to verify that this is the current version before use.

TABLE III. Test procedures.

Test	Applicable method in FED-STD-141	Applicable ASTM test method
Pigment content	4021	---
Volatiles	---	D 2369
Nonvolatile vehicle content	4053	---
Phthalic anhydride	---	D 563
Water	4081	---
Coarse particles	---	D 185, section 6
Consistency	---	D 562
Weight per gallon	---	D 1475
Drying time	4061	---
Fineness of grind	---	D 1210
Flash point	---	D 93
Gloss	6101	---
Brushing properties	4321	---
Spraying properties	4331	---
Flexibility	6221	---
Water resistance	---	D 1308, section 5
Color	4250	---
Condition in container	3011	---
Stability in partially full container	3021	---
Dilution stability	4203	---
Rosin	---	D 1542, section 4
Phenolic resin	5141	---
Odor	---	D 1296
Lead content in nonvolatile	---	D 3335

4.4.1 Phthalic anhydride. Phthalic anhydride shall be determined by method 7021 of FED-STD-141. A suitable portion of the vehicle, collected during the determination of pigment and evaporated on a steam bath until the volume has been reduced to approximately 10 mL, shall be used as the sample. The alcoholate precipitate obtained shall be corrected for carbonates by use of the procedure 4.2 of method 7021 of FED-STD-141.

4.4.2 Drying time. Drying time shall be determined in accordance with method 4061 of FED-STD-141, except that the specified conditions of temperature and humidity shall apply only for referee tests in case of dispute. All other tests shall be conducted under prevailing laboratory conditions.

4.4.3 Gloss, 60-degree specular. The gloss shall be determined by method 6101 of FED-STD-141 with panels prepared as specified (see 4.4.10).

4.4.4 Pigment analyses for titanium dioxide. Weigh, to the nearest 0.1 milligram (mg), about 1 gram (g) of the extracted pigment and transfer to a porcelain crucible. Ignite in a muffle furnace at 600°C ± 50°C for 1/2 hour. Transfer the contents of the ignited crucible to a 250-mL Erlenmeyer flask. Add 15 g of ammonium sulfate and slowly add 20 mL of concentrated sulfuric acid. Heat on a very high temperature hot plate until sulfuric acid fumes reflux from the neck of the flask. Dilute to volume with water and 4 mL of 30 percent hydrogen peroxide in a 200-mL volumetric flask. Mix well. Filter a portion of this solution through a dry filter paper of fine porosity discarding the first 35 mL. Determine the absorbance of the orange solution in a spectrophotometer at 406 nanometers with 3.6 N sulfuric acid in the reference cell. If the absorbance does not fall between 0.150 and 0.600, take an appropriate aliquot and dilute with 3.6 N sulfuric acid to a measured volume and run as before. Calculate the percent titanium dioxide from a formula derived by analysis of titanium dioxide of known purity on the same instrument used for the pigment analysis.

4.4.5 Lead content in nonvolatile. Determine lead content of total nonvolatile of enamel in accordance with ASTM D 3335.

4.4.6 Brushing properties. Apply the enamel, as packaged, in accordance with method 4321 of FED-STD-141 and observe for compliance with 3.7.1.

4.4.7 Spraying properties. Reduce eight parts by volume of enamel with one part by volume of thinner conforming to TT-T-291, type II, grade A. Spray on a steel panel to a dry film thickness between 0.00204 centimeter (cm) to 0.002794 cm (0.0008 to 0.0011 inch) and observe for spraying properties in accordance with method 4331 of FED-STD-141 and for compliance with 3.7.2. For referee test, use automatic application in accordance with method 2131 of FED-STD-141.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.

4.4.8 Flexibility. Determine flexibility in accordance with method 6221 of FED-STD-141.

4.4.8.1 Panel preparation. Prepare a flat tin plate in accordance with method 2012 of FED-STD-141, using the petroleum naphtha ethylene glycol monoethyl ether mixture. Apply a 5.08-cm (2-inch) wide film of enamel on a tin plate with a film applicator that will give a dry film thickness of 0.00254 cm ± 0.00076 cm (1.0 mil ± 0.3 mil). Air dry the enamel in a horizontal position for 2 hours; then bake for 24 hours at 105°C ± 2°C (221°F ± 4°F). Condition the panel for 1/2 hour under referee testing conditions.

4.4.8.2 Procedure. Bend 180 degrees over a 0.318-cm (1/8-inch) mandrel and examine the coating for cracks over the area of the bend in a strong light at a seven-diameter magnification and for compliance with 3.7.3.

4.4.9 Water resistance. Determine water resistance in accordance with ASTM D 1308.

4.4.9.1 Panel preparation. Prepare a tin panel in accordance with method 2012 of FED-STD-141 using the petroleum naphtha ethylene glycol monoethyl ether mixture. Draw a film of the enamel to obtain a dry film thickness of 0.00254 cm ± 0.00076 cm (1.0 mil ± 0.3 mil). Air dry the enamel for 48 hours.

4.4.9.2 Procedure. Immerse in distilled water at 23°C ± 1°C for 18 hours in accordance with ASTM D 1308. Examine for compliance with 3.7.4 after 2 hours and after 24 hours after removal from the water.

4.4.10 Color. Prepare panel for test by applying a single drawdown coat of the enamel to a planar piece of opaque white glass, using a doctor blade with a clearance of 0.0152 cm (0.006 inch) [designed to give a wet film thickness of approximately 0.0076 cm (0.003 inch)]. After a 48-hour drying period, compare the panel with color No. 36231 of FED-STD-595 in accordance with method 4250 of FED-STD-141. If doubt exists as to the acceptability of the match, determine the color difference by instrument in accordance with ASTM D 2244. An acceptable color match shall be within two units (see 3.7.5).

4.4.11 Condition in container. Determine package condition in accordance with method 3011 of FED-STD-141 and observe for compliance with 3.7.6.

4.4.12 Storage stability.

4.4.12.1 Partially full container. Determine skinning after 48 hours in accordance with method 3021 of FED-STD-141. Reseal and age for 7 days at 24°C and observe for compliance with 3.7.7.1.

4.4.12.2 Full container. A 1-gallon container of the enamel shall be stored in the original, unopened container for 12 months from the date of manufacture at standard conditions and then shall be tested to determine compliance with the requirements of 3.7.7.2.

4.4.13 Dilution stability. Reduce one part by volume of enamel as packaged with one part by volume of paint thinner, conforming to type II, grade A of TT-T-291. Then test according to method 4203 of FED-STD-141 for compliance with 3.7.8.

4.4.14 Rosin and rosin derivatives. Test for rosin and rosin derivatives in accordance with section 4 of ASTM D 1542. Use a portion of the separated, nonvolatile vehicle for the test.

4.4.15 Phenolic resins. Test for phenolic resins in accordance with method 5141 of FED-STD-141. Use a portion of the separated, nonvolatile vehicle for the test.

4.4.16 Surface appearance. Prepare a flow-out film of the enamel by pouring approximately 15 mL of the mixed enamel across a glass panel near the upper edge, while the panel is lying flat. Then tilt the panel to allow the coating to spread over all but the upper edge. Next place the panel in an almost vertical position and allow to drain. After 24 hours, examine the film for compliance with 3.7.12. Coarse particles, skins, and agglomerates are characterized by being larger than the dispersed pigment in particle size and extending beyond the plane of the film.

4.5 Inspection of preparation for delivery. The packaging, packing, and marking of the enamel shall be inspected to determine compliance with section 5.

4.6 Toxicity. A manufacturer of material shall disclose the formulation of his product to the Navy Bureau of Medicine and Surgery, Navy Department, Washington, DC 20372. The disclosure of proprietary information, which shall be held in confidence by the Bureau of Medicine and Surgery, shall include: the name, formula, and approximate percentage by weight and volume of each ingredient in the product; the results of any toxicological testing of

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.

the product; identification of its pyrolysis products; and any such other information as may be needed to permit an accurate appraisal of any toxicity problem associated with the handling, storage, application, use, or disposal of the material.

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing, and marking. The enamel shall be packaged, packed, and marked in accordance with PPP-P-1892. The level of packaging shall be level A, B, or C and the level of packing shall be level A, B, or C, as specified (see 6.2). The enamel shall be furnished in 1-gallon cans or 5-gallon pails as specified (see 6.2).

5.1.1 Special marking. In addition to other markings required on the containers, there shall be the following statement: "The volatile content of the material in this container is not photochemically reactive as defined by Rule 102 of the South Coast Air Quality Management District." (See 6.4.)

6. NOTES

6.1 Intended use. The enamel covered by this specification is intended for use as a gray finish coat on deck surfaces of ships.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Special samples required (see 4.2.2).
(c) Level of packaging and packing required (see 5.1).
(d) Size of container (see 5.1).
(e) Special marking required (see 5.1).

6.2.1 Level B packaging. Level B packaging is intended to provide economical but limited protection and should be specified only when it is determined that the enamel will be held in covered storage no more than 1 year from date of initial packaging.

6.3 Unit quantities. The enamel should be purchased under this specification by volume, the unit being 1 U.S. gallon (231 cubic inches) at 15.5°C.

6.4 Volatile content. Although the container marking specifically refers to the South Coast Air Quality Management District, the enamel may be used anywhere else an enamel complying with 3.5 is required. This includes other air pollution control districts or similar areas controlling the emission of solvents into the atmosphere. Information regarding Los Angeles County Air Pollution Rules 102, 442, and 443 may be obtained from: South Coast Air Quality Management District, Metropolitan Zone, 434 South San Pedro Street, Los Angeles, California 90013.

6.5 If it is desired to use alkyd resin solution conforming to the requirements for type I, class B of TT-P-266, intended for use in coatings used in areas with regulations controlling the emission of solvents into the atmosphere, the weight of alkyd resin solution, as specified herein, should be multiplied by 1.17 and the paint thinner reduced by 0.17 times the weight of alkyd resin solution.

6.6 Composition by volume. For information only and with the understanding that weight-volume relationships of ingredients may vary slightly, the following approximation of composition by volume is included.

TABLE IV. Composition by volume.

Ingredients	Gallons
Titanium dioxide	2.1
Lampblack	0.1
Magnesium silicate	14.3
Alkyd resin solution	23.8 (15.2) 1/
Varnish	29.3 (15.8) 1/
Paint thinner	31.8
Lead naphthenate drier	0.70
Cobalt naphthenate drier	0.55
Total volume	102.7

1/ Figures in parentheses refer to volume of resin solids (nonvolatile).

Source: https://assist.dla.mil -- Downloaded: 202610-16T11:17Z
Check the source to verify that this is the current version before use.

6.7 Changes from previous issue. The symbol "*" is not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:
Army - ME
Navy - SH
Air Force - 99

User activities:
Navy - OS, MC

Preparing activity:
Navy - SH
(Project 8010-0761)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 68 WHICH MAY BE USED S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.

FOLD

COMMANDER
NAVAL SHIP ENGINEERING CENTER (SEC 6124)
DEPARTMENT OF THE NAVY
WASHINGTON, D.C. 20362

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID

DEPARTMENT OF THE NAVY

DOD 316

COMMANDER
NAVAL SHIP ENGINEERING CENTER (SEC 6124)
DEPARTMENT OF THE NAVY
WASHINGTON, D.C. 20362

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:17Z
Check the source to verify that this is the current version before use.