INTERIM AMENDMENT
MILITARY SPECIFICATION

IRON OXIDE;
FERRIC, RED DRY (NATURAL AND SYNTHETIC)

This Interim Amendment is issued for use by the U. S. Army Munitions Command with Military Specification MIL-I-706A, dated 23 August 1962.

Paragraph 1.1: Delete in its entirety and substitute the following:

"1.1 This Military Specification covers two types of iron oxide for use in the manufacture of pyrotechnic mixtures and inert fillers."

Paragraph 1.2, Classification: Delete in its entirety and substitute the following:

"1.2 Classification.-Ferric iron oxide covered by this specification shall be of the following types and classes as specified:

Type I - Synthetic

Class 1 - Coarse
Class 2 - Fine

Type II - Natural"

Paragraph 3.2, Composition: Delete in its entirety and substitute the following:

"3.2 Properties.-The properties shall be in accordance with Table I.

TABLE I

Properties	Percent	
	Type I	Type II
Water soluble material, maximum	0.30	---
Acidity, as sulfuric acid, maximum	0.01	---
Volatile matter, maximum	0.50	1.0
Silica, maximum	0.15	---
Purity (as Fe_2O_3), minimum	98.0	50.0
Calcination loss, maximum	1.50	---

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:18Z
Check the source to verify that this is the current version before use.

Paragraph 3.3, Grain size: Delete Table II in its entirety and substitute the following:

TABLE II

U. S. S. Sieve No. Percent through	Type I Class 1 Minimum	Class 2 Minumum	Type II Minimum
40	100	---	---
100	85	---	---
200	---	---	99.9
325	---	99.0	85.0

Add paragraph 6.3:

"6.3 Supersession data.-MIL-I-706A, dated 23 August 1963, with Amendment 1, dated 20 September 1968, supersedes PA-PD-656 dated 23 November 1955.

Custodian:
ARMY-MU

Preparing Acitivty:
ARMY-MU

Project Number: 6810-A851

Source: https://assist.dla.mil -- Downloaded: 202610-16T11:18Z
Check the source to verify that this is the currenversion before use.