MILITARY SPECIFICATION

CLOTH, MOMIE, COTTON OR COTTON/POLYESTER BLEND

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

* 1.1 Scope. This specification covers the requirements for one type of momie cloth of either all cotton or a blend of cotton/polyester.

2. APPLICABLE DOCUMENTS

2.1 Issue of Documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-P-1134 - Packaging and Packing of Cotton and Cotton Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760, by using the self-addressed standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, drawings, and publications required by contractor in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

U.S. Postal Service Manual

(Copies of the manual may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D.C. 20580).

3. REQUIREMENTS

3.1 Standard sample. The cloth shall match the standard sample for shade, and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

* 3.2 First article. When specified (see 6.2), the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.3).

3.3 Momie cloth. The cloth shall be either all cotton or a cotton/polyester blend.

* 3.3.1 Momie cloth, cotton. The cloth shall be of cotton which has been spun into singles yarn for both the warp and filling. The finished cloth shall conform to the requirements shown in Table I when tested as specified in 4.4.3.

Table I - Physical requirements of cotton momie cloth

Weight oz. per sq. yd. (minimum	Construction yarns/inch (min.)		Breaking strength (lbs.) (minimum)		Shrinkage (%) (Maximum	
	Warp	Filling	Warp	Filling	Warp	Filling
5.8	58	54	85	85	6.0	6.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

3.3.2 Momie cloth, cotton/polyester. The cloth shall be a blend of 50 (±3) percent cotton and 50 (±3) percent polyester fiber; spun into singles yarn for both the warp and filling. The finished cloth shall conform to the requirements shown in table II when tested as specified in 4.4.3.

Table II - Physical requirements of cotton/polyester momie cloth

Weight oz. per sq. yd. (minimum)	Construction yarns/inch (min.)		Breaking strength (lbs.) (minimum)		Shrinkage (%) (maximum)	
	Warp	Filling	Warp	Filling	Warp	Filling
* 5.0	58	54	80	70	5.0	5.0

3.4 Weave. The cloth shall be woven in an irregular pattern with each of the warp and filling yarns floating over no more than 2 yarns to produce a rough, broken surface effect.

3.5 Width. The width of the cloth shall be as specified (see 6.2).

3.6 Color. The color of the cloth shall be white, shade 3017.

3.6.1 Matching. The finished cloth shall match the standard sample artificial daylight, having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent light at 2800°Kelvin.

3.7 Finish.

3.7.1 Cotton momie cloth. The cloth shall be bleached and mercerized and shall have a clear lustrous finish.

3.7.2 Cotton/polyester momie cloth. The cloth shall have a clear lustrous finish and may be resin treated in which case the resin shall be of non-chlorine retentive type (see 4.4.1).

3.8 pH. The pH value of the water extract of the finished cloth shall not be less than 5.0 nor more than 8.5 when tested as specified in 4.5.

3.9 Nonfibrous materials.

3.9.1 Cotton momie cloth. The finished cloth shall not exceed 2.0 percent starch and protein content including chloroform-soluble and water-soluble material when tested as specified in 4.4.3.

3.9.2 Cotton/polyester momie cloth.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

3.9.2.1 Non-resin treated. The finished cloth shall not exceed 2.0 percent starch and protein content including chloroform-soluble and water-soluble material when tested as specified in 4.4.3.

3.9.2.2 Resin treated. The finished cloth shall not exceed 7.0 percent resin, starch and protein content including chloroform-soluble, water-soluble acid-hydrolyzable materials when tested as specified in 4.4.3.

3.10 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in pieces of not less than 50 continuous yards in length and shall be furnished on rolls as specified in PPP-P-1134.

3.11 Fiber identification. Each roll of cloth shall be labeled, or ticketed, for fiber content in accordance with the rules and regulations under the Textile Fiber Products Identification Act.

3.12 Face identification. The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word "Face" at each end of the piece.

3.13 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards (83.6 m^2) when calculated as specified in Section 4, shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to the prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

* 4.2 Classification of inspection. The inspection requirement specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

4.3 First article inspection. When required, the first article of the finished cloth shall be visually inspected for shade, finish and appearance and shall be tested for chemical and physical properties in accordance with the applicable test methods of FED-STD-191 specified in 4.4.3

4.4 Quality conformance inspection . Quality conformance inspection shall be conducted in a yard by yard inspection, see 4.4.2.1. The sample size shall be in accordance with the following:

Lot Size in Yards	Sample size by Roll 1/
3200 or less	8
3201 to 10,000	13
10,001 and over	20

1/ Only one roll shall be taken from any shipping container, unless the number of shipping containers in the lot is less than the number of rolls required for sampling, in which case, all shipping containers shall be sampled. The lot shall be unacceptable if the points per 100 square yards ($83.6m^2$) of the total yardage examined exceeds 30 points. The lot shall be unacceptable if the individual points per 100 square yards ($83.6m^2$) of two or more individual rolls exceeds 45 points. If one roll exceeds the point level per 100 square yards ($83.6m^2$), a second sample, the same size as the final sample, shall be examined only for individual roll quality examination. The lot shall be unacceptable if one or more rolls in the second sample exceeds 45 points per 100 square yards ($83.6m^2$). Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample X 3600}}{\text{Contracted width of cloth (inches) X total yards inspected}} = \text{Points per 100 Square yards } (83.6m^2)$$

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document. In addition, the contractor shall furnish a certificate of compliance for the fiber identification specified in 3.3.1 or 3.3.2; and for the non-chlorine retentive nature of the resin indicated in 3.7.2, when applicable.

4.4.2 Examination of the end item. Defects found during examination shall be classified in accordance with 4.4.2.1 through 4.4.2.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

4.4.2.1 Yard by yard Examination. Each roll in the sample shall be examined on the face side only. When the total yardage on roll exceeds 100 yards (91.4m) only 100 yards shall be examined but when the roll length is less than 100 yards the entire roll shall be examined. All defects as defined in section I of FED-STD-4, which are clearly noticeable at normal inspection distance (eyelevel and 3 feet from the inspector (0.91m) shall be scored and assigned demerit points as listed in 4.4.2.1.1. Except that slub and knots which exceed the limits "C" for slubs and "D" for knots as shown on Sears fabric defect scale shall be scored. The maximum number of points penalized per linear yard (increments of 1 yard on the measuring device of the inspection machine) shall be 4 points.

4.4.2.2. Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches (7.6cm) or less in any dimensions - one point
For defects exceeding 3 inches (7.6cm), but not exceeding
6 inches (15.2cm) in any directior - two points
For defects exceeding 6 inches (15.2cm), but not exceeding
9 inches (22.9cm) in any dimension - three points
For defects exceeding 9 inches (22.9cm) in any dimension - four points

The following defects, when present in the yard by yard and overall examination shall be scored 4 points for each yard (0.91m) in which they occur:

Baggy, ridgy or wavy cloth
Width less than specified
Characteristics of finish, hand and shade not equal to the standard sample
Non uniformity of shade (mottled, streaky or cloudy)
Holes, cuts, tears

4.4.2.3 Examination for length.

4.4.2.3.1 Individual rolls. During the yard-by-yard and overall examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards (1.82m) less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective with respect to length.

4.4.2.3.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets. The rolls examined shall be those selected for the examination of individual rolls.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

4.4.2.4 Examination for shade variation. During the yard-by-yard and overall examination, each roll in the sample shall be examined for shade variation. Any role in the sample exhibiting uneven shade, shade variation side to side, side to center, or end to end, shall be cause for rejection of the entire lot represented by the sample.

4.4.2.5 Examination for face identification and for compliance with the Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll in the sample shall be examined for face markings and for compliance to the Textile Fiber Products Identification Act. The lot shall be unacceptable if two or more rolls in the sample have the face identification missing from either or both ends on the face side, or if the rolls are not labeled, or ticketed, in accordance with the Textile Fiber Products Identification Act.

* 4.4.3 Physical and Chemical Testing of the end item The methods of testing specified in FED-STD-191, wherever applicable, and as listed in Table II shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test method. the sample unit shall be 3 1/2 linear yards (3.15m) on full width, of the finished cloth. The sample size shall be as shown below. The lot size shall be expressed in units of 1 yard (0.8m) each. The lot shall be unacceptable if one or more units of product fail to meet any of the requirements specified.

Lot size (yards) (0.8cm)	Sample size
800 or less	2
801 to 22,000	3
22,001 and up	5

Table III - Test method

Characteristic	Requirement reference	Test method
Fiber identification - cotton	3.3.1	1200
Fiber content - percent polyester/ cotton	3.3.2	2100/4.5.1 1/
Weave	3.4	Visual 2/

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

Table III - Test method (cont.)

Characteristic	Requirement reference	Test method
Yarns per inch		
Warp	Table I or II	5050
Filling	Table I or II	5050
Breaking strength		
Warp	Table I or II	5100
Filling	Table I or II	5100
Weight	Table I or II	5041
pH	3.8	2811
Nonfibrous materials	3.9	2611 3/
Shrinkage in laundering	Table I or II	5550

* 1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ One determination per sample unit and the result reported as "pass" or "fail".

* 3/ When finished cloth is resin treated as described in 3.7.2 and 3.9.2.2, it shall be so identified by the contractor, and the non-fibrous materials shall be determined by test method 2610.

* 4.4.3.1 Fiber content. The general procedure of method 2100 shall be followed, and the fiber content percentages calculated as follows:

$$\text{Percent polyester} = \frac{\text{Weight of dry residual fiber} \times 100}{\text{Weight of dry specimen (with non fibrous materials extracted}}$$

Percent cotton = 100 minus percent polyester.

4.4.3.1.1 Report. Two specimens shall be tested from each sample unit and the average percent polyester and the average percent cotton of the two specimens reported to the nearest 10 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

4.5 Examination of delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing and marking requirements of Section 5 of this specification are complied with.

5. PACKAGING

5.1 Preservation-packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A and C. The cloth shall be put-up and packaged in accordance with the applicable requirements of PP-P-1134.

5.2 Packing. Packing shall be level A, B or Commercial as specified (see 6.2).

5.2.1 Levels A, B, and Commercial. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1134.

6. NOTES

6.1 Intended use. The momie cloth will be utilized to manufacture tablecloths, napkins, and doilies used by the Military services.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Requirements for the First Article (see 3.2).
(c) Width required (see 3.5).
(d) Levels of packaging and packing required (see 5.1 and 5.2).

6.3 Standard sample. For access to the standard sample, address the procuring activity issuing the invitation for bids.

* 6.4 Sears Fabric Defects Scales are available from: Sears Roebuck and Co., Dept. 769; "Fabric Defect Replica Kit"; Sears Tower, Chicago, Illinois 60684.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

6.5 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:
Army - GL

Preparing activity:
Navy - NU

Project No. 8305-0573

User Activities
Army - MD
Navy - MC
Air Force - 99

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

FOLD

OFFICER IN CHARGE
NAVY CLOTHING & TEXTILE RESEARCH FACILITY
21 STRATHMORE ROAD
NATICK, MA 01760

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEPARTMENT OF THE NAVY
DoD-316

OFFICER IN CHARGE
NAVY CLOTHING & TEXTILE RESEARCH FACILITY
21 STRATHMORE ROAD
NATICK, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS This form is provided to solicit beneficial comments which may improve this document and enhance its use DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government Fold on lines on reverse side, staple in corner, and send to preparing activity Attach any pertinent data which may be of use in improving this document If there are additional papers, attach to form and place both in an envelope addressed to preparing activity A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed

NOTE This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-C-82287B CLOTH, MOMIE, COTTON OR COTTON/POLYESTER BLEND

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1 ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW

A GIVE PARAGRAPH NUMBER AND WORDING

B RECOMMENDED WORDING CHANGE

C REASON FOR RECOMMENDED CHANGE(S)

2 REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO
	DATE

DD FORM 1 OCT 76 1426 Replaces edition of 1 Jan 72 which may be used S/N 0102-LF-001-4260

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:59Z
Check the source to verify that this is the current version before use.