INCH-POUND

MIL-DTL-83723/27C
w/AMENDMENT 2
26 January 2024
SUPERSEDING
MIL-DTL-83723/27C
w/AMENDMENT 1
05 March 2021

DETAIL SPECIFICATION SHEET

CONNECTORS, ELECTRICAL, BACKSHELL, WITH HEAT-SHRINKABLE STRAIN-RELIEF BOOT (STRAIGHT AND RIGHT ANGLE), THREADED COUPLING

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-83723.

Inactive for new design as of 14 September 1993.





FIGURE 1. Completed assembly.

AMSC N/A
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

FSC 5935

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.



Shell size	SAE-AS 50151 shell size	A dia max	B dia	C dia	D dia	E	F max
08	8S	.577	.447	.284	.250	.300	.830
10	10S	.640	.510	.344	.303	.300	.830
11	10SL	.702	.572	.413	.383	.300	.830
13	12S	.765	.635	.464	.408	.300	.830
12	12	.765	.635	.464	.408	.300	.830
16	14S	.890	.760	.567	.490	.300	.830
14	14	.890	.760	.567	.490	.300	.830
17	16S	1.015	.885	.693	.609	.300	.830
16	16	1.015	.885	.693	.609	.300	.996
18	18	1.140	1.010	.810	.730	.300	.996
20	20	1.265	1.135	.947	.870	.309	.996
22	22	1.390	1.260	1.078	.978	.309	.996
24	24	1.515	1.385	1.185	1.090	.246	.996
28	28	1.765	1.635	1.406	1.250	.246	1.076
32	32	2.015	1.885	1.657	1.520	.185	1.076
36	36	2.265	2.135	1.865	1.756	.185	1.076
40	40	2.515	2.392	2.203	1.880	.570	1.222

FIGURE 2. Backshell, threaded coupling.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

Shell Size	SAE-AS 50151 shell size	G +.015 -.000	H min	K max	J min	V threads
08	8S	.365	.479	.391	.430	7/16-28UNEF-2B
10	10S	.365	.539	.451	.430	1/2-28UNEF-2B
11	10SL	.365	.608	.520	.430	9/16-24 UNEF-2B
13	12S	.365	.659	.571	.430	5/8-24 UNEF-2B
12	12	.365	.659	.571	.430	5/8-24 UNEF-2B
16	14S	.365	.782	.694	.430	3/4-20 UNEF-2B
14	14	.365	.782	.694	.430	3/4-20 UNEF-2B
17	16S	.365	.908	.820	.430	7/8-20 UNEF-2B
16	16	.521	.908	.820	.596	7/8-20 UNEF-2B
18	18	.521	1.025	.937	.596	1-20 UNEF-2B
20	20	.521	1.212	1.074	.596	1-1/8-18 UNEF-2B
22	22	.521	1.343	1.205	.596	1-1/4-18 UNEF-2B
24	24	.521	1.450	1.312	.596	1-3/8-18 UNEF-2B
28	28	.521	1.671	1.533	.596	1-5/8-18 UNEF-2B
32	32	.521	1.956	1.784	.596	1-7/8-16 UN-2B
36	36	.521	2.164	1.992	.596	2-1/8-16 UN-2B
40	40	.552	2.500	2.328	.627	2-3/8-16 UN-2B

NOTES:

1. Dimensions in inches. Unless otherwise specified tolerances shall be .XX ± .010 and .XXX ± .005, angular X°X′ ± 0°30′.
2. Dimensions apply after plating.

FIGURE 2. Backshell, threaded coupling – Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.




FIGURE 3. Heat-shrinkable strain-relief boot, straight.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

Shell size	SAE-AS 50151 shell size	H dia		J dia		
		As supplied min	Recovered max	As supplied min 1/		Recovered max
				A	B	
08	8S	.88	.45	.88	.55	.25
10	10S	.88	.45	.88	.55	.25
11	10SL	1.01	.59	1.01	.63	.29
13	12S	1.01	.59	1.01	.63	.29
12	12	1.01	.59	1.01	.63	.29
15	14S	1.16	.74	1.16	.72	.33
14	14	1.16	.74	1.16	.72	.33
17	16S	1.34	.90	1.34	.84	.38
16	16	1.34	.90	1.34	.84	.38
18	18	1.34	.90	1.34	.84	.38
20	20	1.47	1.16	1.47	.91	.41
22	22	1.72	1.34	1.72	1.07	.48
24	24	1.72	1.34	1.72	1.07	.48
28	28	1.97	1.62	1.97	1.24	.56
32	32	2.47	1.85	2.47	1.54	.69
36	36	2.47	1.85	2.47	1.54	.69
40	40	2.73	2.35	2.73	1.70	.77

FIGURE 3. Heat-shrinkable strain-relief boot, straight – Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

Shell size	SAE-AS 50151 shell size	P recovered	R recovered	S recovered	T recovered
08	8S	4.17	.46	.56	.040
10	10S	4.17	.46	.56	.040
11	10SL	4.77	.48	.59	.040
13	12S	4.77	.48	.59	.040
12	12	4.77	.48	.59	.040
15	14S	5.46	.48	.61	.040
14	14	5.46	.48	.61	.040
17	16S	6.28	.48	.62	.040
16	16	6.28	.48	.62	.040
18	18	6.28	.48	.62	.040
20	20	7.00	.55	.71	.065
22	22	8.00	.60	.78	.065
24	24	8.00	.60	.78	.065
28	28	8.00	.60	.82	.065
32	32	8.00	.63	.92	.080
36	36	8.00	.63	.92	.080
40	40	8.00	.63	.93	.080

NOTES:
1. Material:
   a. Type A: Polyolefin
   b. Type B: Fluoroelastomer
2. Boots will shrink to recovered dimensions upon application of heat in excess of 175°C.

FIGURE 3. Heat-shrinkable strain-relief boot, straight – Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.




FIGURE 4. Heat-shrinkable strain-relief boot, right angle (90°).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

Shell size	SAE-AS 50151 shell size	H dia		J dia		
		As supplied min	Recovered max	As supplied min 2/		Recovered max
				A	B	
08	8S	.88	.45	.88	.55	.25
10	10S	.88	.45	.88	.55	.25
11	10SL	1.01	.59	1.01	.63	.29
13	12S	1.01	.59	1.01	.63	.29
12	12	1.01	.59	1.01	.63	.29
15	14S	1.16	.74	1.16	.72	.33
14	14	1.16	.74	1.16	.72	.33
17	16S	1.34	.90	1.34	.84	.38
16	16	1.34	.90	1.34	.84	.38
18	18	1.34	.90	1.34	.84	.38
20	20	1.47	1.16	1.47	.91	.41
22	22	1.72	1.34	1.72	1.07	.48
24	24	1.72	1.34	1.72	1.07	.48
28	28	1.97	1.62	1.97	1.24	.56
32	32	2.47	1.85	2.47	1.54	.69
36	36	2.47	1.85	2.47	1.54	.69
40	40	2.73	2.35	2.73	1.70	.77

FIGURE 4. Heat-shrinkable strain-relief boot, right angle (90°) – Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

Shell size	SAE-AS 50151 shell size	P Recovered	R Recovered	S +/- 10%	T Recovered ref
08	8S	4.14	.73	.49	.040
10	10S	4.14	.73	.49	.040
11	10SL	4.88	.78	.59	.040
13	12S	4.88	.78	.59	.040
12	12	4.88	.78	.59	.040
15	14S	5.76	.82	.61	.040
14	14	5.76	.82	.61	.040
17	16S	6.78	.86	.65	.040
16	16	6.78	.86	.65	.040
18	18	6.78	.86	.65	.040
20	20	7.29	.96	.74	.065
22	22	8.41	1.08	.82	.065
24	24	8.41	1.08	.82	.065
28	28	8.84	1.16	.86	.065
32	32	8.95	1.31	.97	.080
36	36	8.95	1.31	.97	.080
40	40	9.19	1.38	.98	.080

NOTES:
1. Boots will shrink to recovered dimensions upon application of heat in excess of 175°C.
2. Material:
   a. Type A: Polyolefin
   b. Type B: Fluoroelastomer

FIGURE 4. Heat-shrinkable strain-relief boot, right angle (90°) – Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

TABLE I. Material requirements. 1/

Material property Physical properties:	Unit	Requirement type A (polyolefin)	Requirement type B (fluoroelastomer)	Method of test
Dimensions Dimension recovery	Inches	In accordance with figures 3 and 4	In accordance with figures 3 and 4	ASTM D876
Elastic Memory	Percent	275 min. expansion 93 min. retraction	200 min. expansion 90 min. retraction	See requirements
Tensile strength	psi	1200 minimum	1800 minimum	ASTM D412, Die D
Ultimate elongation	Percent	250 minimum	300 minimum	
Specific gravity	---	1.40 maximum	1.95 maximum	ASTM D792
Low-temperature flexibility at -55°C (-67°F)	---	No cracking	No cracking	See requirements
Heat shock (4 hours) Type A: 225°(437°F) Type B: 300°C (572°F)	---	No dripping, flowing or cracking	No dripping, flowing or cracking	See requirements
Heat aging (168 hours) Type A: 175°C Type B: 250°C	---	---	---	See requirements
Followed by tests for: Tensile strength	psi	1000 minimum	1200 minimum	ASTM D412, Die D
Elongation	Percent	200 minimum	250 minimum	
Hardness	Shore durometer	40 ± 5 (Shore D)	85 ± 5 (Shore A)	ASTM D2240
Stiffness	PSI	10000 maximum	not applicable	ASTM D747

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

TABLE I. Material requirements – Continued. 1/

Material property Chemical properties:	Unit	Requirement type A (polyolefin)	Requirement type B (fluoroelastomer)	Method of test
Flammability	---	Time: 120 seconds max to self-extinguish Extent: 1.0 inch max	Time: 60 seconds max to self-extinguish Extent: 1.0 inch max	ASTM D635
Fungus resistance	---	Rating of 1 or less	Rating of 1 or less	ASTM G21
Corrosion 16 hrs. at 17°C Copper mirror	---	Noncorrosive	Noncorrosive	ASTM D2671 appendix A.1.5.1
Fluid resistance 24 hrs at 25° Hydraulic fluid JP-4 fuel Lubricating Oil Deicing fluid Followed by tests for: Tensile strength Elongation	---	---	---	See requirements
	psi	750 minimum	1600 minimum	---
	Percent	200 minimum	200 minimum	---
Water absorption	Percent	0.5 maximum	0.5 maximum	ASTM D570
Electrical properties:	---	---	---	---
Dielectric strength	Volts/mil	200 minimum	200 minimum	ASTM D876
Volume resistivity	Ohms-cm	10^{12} minimum	10^{10} minimum	ASTM D257

1/ Material: Material shall be modified crosslinked polyolefin (type A: 150°C) or fluoroelastomer (type B: 200°C) and shall have the characteristics shown in table I above.

REQUIREMENTS:

Design and construction: See figures 1 through 4 and table I.

Material: Aluminum alloy.

Finish: Class R, 200° conductive finish.

Remove all burrs and sharp edges.

Marking: Package shall be marked with military Part or Identifying Number (PIN) and manufacturer's identification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

PIN example:

M83723/ 27 S 08 A

M83723/	Military designation
27	Specification sheet number
S	Boot configuration:
	S: Straight
	A: Right angle
	M: Backshell
08	Shell size designator
A	Component designation:
	A: Polyolefin (150□C) boot and backshell
	B: Fluoroelastomer (200□C) boot and backshell
	(M: Backshell only
	(A: Polyolefin boot only
	(B: Fluoroelastomer boot only

Elastic memory

A 6 x 1/8 inch specimen cut from a molded slab shall be marked with two parallel gage lines 1 inch apart in the central portion of the specimen. A 2 inch portion of the specimen including both gage lines shall then be heated for 5 minutes in a 200° ± 5°C (392° ± 9°F) oven or equivalent, removed from the oven, and stretched within 10 seconds until the gage lines are 4 inches apart. The extended specimen then shall be cooled at room temperature and released from tension. After 24 hours at room temperature, the distance between the gage lines shall be measured and recorded as the extended length. The portion of the specimen including both gage lines then shall be reheated for 5 minutes in a 200° ± 5° (392° ± 9°F) oven or equivalent, removed from the oven, and allowed to retract. The specimen shall again be cooled to room temperature and the distance between the gage lines then shall be measured and recorded as the retracted length. Expansion and retraction shall be calculated as follows:

$$\text{Expansion} = (\text{extended length} - 1) \text{ X } 100 \text{ percent}$$

$$\text{Retraction} = \frac{\text{extended length} - \text{retracted length} - \text{retracted length}}{\text{extended length -1}} \text{ X } 100 \text{ percent}$$

Low-temperature flexibility

A 6 x 1/4 inch specimen out from a molded slab shall be mounted in a loop position between movable, parallel jaws 2 ½ inches apart. Each end of the specimen shall be firmly fastened by at least 3/4 of an inch extending into a set of jaws. The specimen ant the test fixture shall be conditioned for 4 hours at –55° ± 2°C (-67° ± 4°F). While at this temperature, the jaws shall be moved rapidly from 2 1/2 inch to a 1 inch separation.

Heat shock

A 6-inch by 1/2 inch specimen cut from a molded slab shall be conditioned in an oven at temperature. After this conditioning, the specimen shall be visually examined for evidence of dripping, flowing, or cracking.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

Heat aging

Three specimens, prepared and measured in accordance with ASTM D412, shall be conditioned at temperature for 168 hours in an oven with an air velocity of from 100 to 200 feet per minute past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to from temperature, and tested for tensile strength elongation.

Fluid resistance

Specimens 6 x .25 x .075 shall be cut from molded slabs. Three (3) specimens shall be immersed in each of the fluids specified. The volume of fluid shall be not less than 20 times that of the specimens. After immersion, the specimens shall be lightly wiped and air dried for 30 to 60 minutes at standard conditions.

TEST FLUIDS FOR FLUID RESISTANCE

Fluid	Specification
Hydraulic fluid, petroleum base	MIL-PRF-83282 or MIL-PRF-87257
JP-4 Fuel	MIL-DTL-5624
Lubricating oil	MIL-PRF-7808
Lubricating oil	MIL-PRF-23699
Deicing fluid	SAE-AMS1424

PERFORMANCE:

Temperature life

Three straight and three 90° angle boots of each material (type A and type B) shall be installed on a connector and exposed to rated temperature (type A: 150°C) (type B: 200°C) for 1000 hours. At the end of this time, they shall be cooled to room temperature and the pull-off tests depicted below shall be performed. The minimum force required to pull boot from connector at any angle shall be 25 pounds.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.




FIGURE 5. Pull-off test method.

QUALITY ASSURANCE:

Preproduction tests

Preproduction tests shall consist of the entire list of material requirements in table I and the performance test for temperature life.

Acceptance test

Acceptance tests shall consist of dimensional recovery, tensile strength, elongation, stiffness, heat shock and hardness.

Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.

Referenced documents. In addition to MIL-DTL-83723, this document references the following:

MIL-DTL-5624
MIL-PRF-7808
MIL-PRF-23699
MIL PRF 83282
MIL PRF 87257
ASTM G21
ASTM D257
ASTM D412
ASTM D570
ASTM D635
ASTM D747
ASTM D792
ASTM D876
ASTM D2240
ASTM D2671
SAE-AMS1424

CONCLUDING MATERIAL

Custodians:
Army - CR
Navy - AS
Air Force – 85
DLA - CC

Preparing activity:
DLA - CC

(Project 5935-2024-034)

Review activity:
Army - MI

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T09:19Z
Check the source to verify that this is the current version before use.