INCH-POUND

~~MIL-C-24927A~~

1 October 1991

SUPERSEDING
MIL-C-24927
9 September 1986

# MILITARY SPECIFICATION

## CLOTH, TWILL, POLYESTER/COTTON (DURABLE PRESS)

This specification is approved for use by the Navy Clothing and Textile Research Facility, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers the requirements for a blended polyester and cotton cloth, which has been treated with durable press and soil release finishes.

1.2 Classification. The cloth shall be of the following classes as specified (see 6.2):

Class 1 - White 3053
Class 2 - Khaki 3729

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, P.O. Box 59, Natick, MA 01760-0001 by using the self addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

## 2. APPLICABLE DOCUMENTS

### 2.2 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement hereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

| | |
|---|---|
| A-A-50199 | - Thread, Polyester Core, Cotton or Polyester Covered |
| PPP-P-1134 | - Packaging of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics) |

MILITARY

| | |
|---|---|
| MIL-T-43624 | - Thread, Polyester, Spun |

STANDARDS

FEDERAL

| | |
|---|---|
| FED-STD-4 | - Glossary of Fabric Imperfections |
| FED-STD-191 | - Textile Test Methods |

MILITARY

| | |
|---|---|
| MIL-STD-105 | - Sampling Procedures and Tables for Inspection by Attributes |
| MIL-STD-2073-1 | - DOD Materials Procedures for Development and Application of Packaging Requirements |
| MIL-STD-2073-2 | - Packaging Requirement Codes |

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

RULES AND REGULATIONS UNDER THE TEXTILE FIBER PRODUCTS IDENTIFICATION ACT

(Copies may be obtained without charge from the Federal Trade Commission, Washington, DC 20580.)

2.2 Non-Government publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issue of the documents which are DOD adopted shall be those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of the documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

TECHNICAL MANUAL OF THE AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

Method No. 8 - Colorfastness to Crocking: AATCC Crockmeter Method
Method No. 61 - Colorfastness to Laundering, Home, and Laundering, Commercial: Accelerated
Method No. 124 - Appearance of Durable Press Fabrics after Repeated Home Launderings
Method No. 130 - Soil Release: Oily Stain Release Method

(Application for copies should be addressed to AATCC National Headquarters, P.O. Box 12215, Research Triangle Park, NC 27709-9989.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS

Method No. D1424 - Tear Resistance of Woven Fabrics by Falling Pendulum (Elmandorf) Apparatus

(Application for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard sample. The finished cloth shall match the standard sample for shade and uniformity of shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3). The standard sample for the class 1 White 3053 is identified under piece no. 89307 and the standard sample for the class 2 Khaki 3729 is identified under piece no. 89216.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

3.2 First article. When specified, the contractor shall furnish a sample unit for first article inspection and approval (see 4.3 and 6.2).

3.3 Material.

3.3.1 Fiber blend.

3.3.1.1 Polyester fiber. The fibers shall be polyethylene terephthalate, semi-dull. The denier shall be a minimum of 2.25 (2.5 dtex) and a maximum of 3.0 (3.3 dtex), and the staple shall be approximately 1½ inches (3.8 cm) in length (see 4.4.1).

3.3.1.2 Cotton fiber. The cotton shall be combed (see 4.4.1).

3.3.2 Yarn. The warp and filling yarn shall be a blend of 65 (±5) percent polyester and the remaining percentage cotton based on the dry weight of the desized and bleached cloth before treatment, as specified in 4.5. The warp and filling shall be a singles yarn (see 4.4.1).

3.3.3 Color. The color of the class 1 cloth shall be White 3053 and the color of the class 2 cloth shall be Khaki 3729 and both shall match the standard sample, unless otherwise specified (see 6.2).

3.3.3.1 Class 1, white. The White 3053 shall be obtained with a chemical bleach, preferably with hydrogen peroxide or peroxygen chemicals. The chemical bleach may be supplemented with fluorescent optical brighteners which fluoresce to the blue region.

3.3.4 Sulfur content. The use of sulfur dyes or dyes containing elementary sulfur or sulfur compounds capable of oxidation to sulfuric acid is prohibited. The dyed and finished cloth shall show no more than a slight trace of labile sulfur as defined in the test method and specified in 4.5.

3.3.5 Discoloration. The finished class 1 cloth shall show discoloration to wet-dry cleaning, laundering (3 cycles), perspiration, combined laundering and bleaching and light (40 SFH) equal to or better than the standard sample when tested as specified in 4.5. As a limit of acceptability, or when no standard sample is available, the discoloration of the cloth to wet-dry cleaning, laundering (3 cycles), perspiration, combined laundering and bleaching, and light (40 SFH), shall be a minimum of "good".

3.3.6 Colorfastness. The finished class 2 cloth shall show colorfastness to laundering (3 cycles), perspiration, light (40 SFH), and crocking equal to or better than the standard sample when tested as specified in 4.5. As a limit of acceptability, or when no standard sample is available, the finished cloth shall show a minimum of "good" to laundering (3 cycles) and perspiration and a minimum of "fair" to light (40 SFH), and shall show a wet and dry crocking rating not lower than 4.0.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

3.3.7 Matching. The color and appearance of the finished cloth shall match the standard sample when viewed under filtered tungsten lamps which approximate artificial daylight having a correlated color temperature of 7500K (±200K) with illumination of 100 (±20) foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300K (±200K).

3.4 Physical requirements. The finished cloth shall conform to the requirements specified in Table I when tested as specified in 4.5.

Table I - Physical Requirements

| Characteristic | Prepared State Fabric | Finished Fabric |
|---|---|---|
| Weight - oz/yd² (gm/m²) | | |
| Minimum | 7.5 (254.3) | |
| Maximum | | 8.5 (288.2) |
| Yarns Per Inch (2.54 cm) - Minimum | | |
| Warp | | 100 |
| Filling | | 50 |
| Breaking Strength - lbs (N) - Minimum | | |
| Warp | | 230 (1023.5) |
| Filling | | 72 (320.4) |
| Stiffness - in-lbs (N.m) - Maximum | | |
| Warp | | 0.010 (.0011) |
| Filling | | 0.007 (.0008) |
| Air Permeability - $ft^3/min/ft^2$ ($cm^3/sec/cm^2$) - Minimum | | 17 (8.6) |
| Tear Strength - lbs (N) - Minimum | | |
| Warp | | 12 (53.4) |
| Filling | | 5 (22.3) |

3.5 Weave. The weave shall be a 3 up, 1 down, right-hand twill, when tested as specified in 4.5.

3.6 Width. The width of the cloth shall be as specified (see 6.2), and shall be the minimum acceptable width inclusive of selvage when fly shuttle looms or shuttleless tuck-in selvage looms are used. For all other shuttleless looms, the width measurement shall be made between the last warp on each side excluding the protruding fringe(s).



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

3.7 Non-fibrous materials. The starch and protein content including chloroform-soluble and water-soluble material of the dyed and desized cloth prior to applying finish shall not exceed 2.0 percent when tested as specified in 4.5.

3.8 Finish. The cloth shall be desized, scoured, mercerized, bleached (class 1 only), heat set, and dyed (class 2 only). The cloth shall be treated with an approved precured durable press resin and approved soil release treatment (see 4.4.1, 6.6, and 6.7) to obtain a hand equal to in characteristics to that of the standard sample and shall meet the requirements specified within, when tested as specified in 4.5. The resin finish shall be a non-chlorine retentive type and the material shall show no loss of colorfastness or no more discoloration than the standard sample when tested as specified in 4.5.

3.8.1 Soil release. The finished cloth shall have an average soil release rating not less than 3.0 when tested as specified in 4.5.

3.8.2 Appearance of durable press. The finished cloth shall have an average durable press rating of not less than 3.0 after 5 launderings when tested as specified in 4.5.

3.9 pH. The pH value of the water extract of the finished cloth shall be not less than 5.0 nor more than 8.5 when tested as specified in 4.5.

3.10 Dimensional stability. The finished cloth shall not shrink nor elongate more than 2.0% in either the warp or filling direction when tested as specified in 4.5. The pre-shrinking process used shall not be identified by name or by trademark, either on the cloth, ticket, or package.

3.11 Seam efficiency. The cloth shall have a seam efficiency of not less than 85% when tested as specified in 4.5.

3.12 Toxicity approval. Only those soil release and durable press treatments already evaluated and approved by the appropriate medical service in regards to toxicity and so listed in the invitation for bids or request for proposal shall be considered acceptable for the related procurement (see 6.6 and 6.7).

3.13 Length and put-up. Unless otherwise specified (see 6.2), the finished cloth shall be furnished in continuous lengths each not less than 40 yards (36.6 m). Each length shall be put up on rolls as specified in 5.1.

3.14 Fiber identification. Each roll shall be labeled or ticketed for fiber content in accordance with the Textile Fiber Products Identification Act.

3.15 Face identification. The face side of the cloth shall be identified by stamping on the side the word "face" at each end of the roll.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

3.16 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards (83.6m²) when calculated as specified in section 4 shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of Sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the government to acceptance of defective material.

4.1.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

4.3 First article inspection. When required (see 3.2), the first article of finished cloth shall be visually inspected for uniformity of shade, color, finish, and appearance and shall be tested for chemical and physical properties in accordance with the applicable methods specified in 4.5.

4.4 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded amended, modified, or qualified in this specification or applicable procurement documents. In addition, a certificate of compliance shall be submitted for the material requirements of 3.3.1.1, 3.3.1.2, 3.3.2, and the durable press resin and soil release finish requirements of 3.8.

4.4.2 Examination of the end item. Examination of the end item shall be in accordance with 4.4.2.1 through 4.4.2.5.

4.4.2.1 Yard-by-yard examination. Each roll in the sample shall be examined on face side only. When the total yardage in the role does not exceed 100 yards (91.4m), the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards (91.4m) only 100 yards (91.4m) shall be examined. All defects as defined in Section III of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet)(0.9m) shall be scored and assigned demerit points as listed in 4.4.2.1.1, except that those slubs and knots which exceed the limits shown on Sears Fabric Defect Scale (see 6.4), "C" or "4" as applicable for slubs and "B" for knots shall be scored. No linear yard (increments of 1 yard (0.9m) on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be 20 rolls selected from 20 containers. For determination of acceptability on the average quality of the lot, the lot shall be unacceptable if the points per 100 square yards (83.6m²) exceeds 25 points. For determination of acceptability on the individual roll quality basis, the lot shall be unacceptable if two or more individual rolls exceed 38 points per 100 square yards (83.6m²). If one roll exceeds the point level, a second sample of 20 rolls shall be selected for individual roll quality examination only. If one or more rolls exceed the value, the lot shall be rejected. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 square yards (83.6m}^2\text{)}$$

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

| | |
|---|---|
| For defects 3 inches (7.6cm) or less in any dimension | - one point |
| For defects exceeding 3 inches (7.6cm), but not exceeding 6 inches (15.2cm) in any dimension | - two points |
| For defects exceeding 6 inches (15.2cm), but not exceeding 9 inches (22.9cm) in any dimension | - three points |
| For defects exceeding 9 inches (22.9cm) in any dimension | - four points |

The following defects, when present, shall be scored 4 points for each yard in which they occur:

Baggy, ridgy or wavy cloth
Width less then specified
Characteristics of finish, hand and shade not equal to the standard sample
Nonuniformity of shade (mottled, streaky or cloudy)
Holes, cuts, tears, open places



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

4.4.2.2 Examination for length.

4.4.2.2.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards (1.82m) less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective with respect to length.

4.4.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets. The rolls examined shall be those selected for the examination for the individual rolls.

4.4.2.3 Examination for shade variation. During the yard-by-yard examination, each roll in the sample shall be examined for shade variation. Any role in the sample exhibiting uneven shade, shade variation side to side, side to center, or end to end, shall be cause for rejection of the entire lot represented by the sample.

4.4.2.4 Examination for shade match and finish, individual rolls. Each roll in the lot shall be examined visually for shade match (see 3.3.7) and finish (see 3.8). A roll shall be unacceptable if it fails to meet the requirements for shade match or finish. The sample unit shall be 4 inch by 20 inch (10.2cm by 50.8cm) swatch of the cloth. A sample unit shall be drawn from each roll in the lot.

4.4.2.5 Examination for face identification and nonconformance with the Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll in the sample shall be examined for these defects. The lot shall be unacceptable if two or more rolls in the sample have face identification missing from either or both ends, or are not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.

4.4.3 Examination of packaging requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing and marking comply with Section 5 requirements of this specification.

4.5 Testing of the end item. The methods of testing specified in FED-STD-191, wherever applicable and as listed in Table II shall be followed. The physical and chemical values specified in Section 3, except where otherwise indicated, apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values utilized in expressing the final result. The sample unit shall be 3 yards (2.73m) finished cloth, and 1 yard prepared state cloth, both full width of the cloth. The lot size and the lot shall be unacceptable if one or more sample units fail to meet any requirement specified.

| Lot size (yards) | Sample size (units |
|---|---|
| 800 or less | 2 |
| 801 up to and including 22,000 | 3 |
| 22,001 and over | 5 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

Table II - Test Methods

| Characteristic | Requirement Paragraph | Test Method |
|---|---|---|
| Polyester Fiber Identification | 3.3.1.1 | 1600 1/ |
| Cotton Fiber Identification | 3.3.1.2 | 1200 1/ |
| Yarn ply | 3.3.2 | Visual |
| Fiber content | 3.3.2 | 2100 and 4.5.1 |
| Sulfur content | 3.3.4 | 2020 |
| Colorfastness to: | | |
| Laundering | 3.3.5 | 5610 3/ 4/ |
| Perspiration | 3.3.5 | 5680 |
| Light (40 SFH) | 3.3.5 | 5660 8/ |
| Crocking | 3.3.5 | AATCC No. 8 |
| Discoloration to: | | |
| Combined Laundering and Bleaching | 3.3.6 | 5605 |
| Light (40 SFH) | 3.3.6 | 5660 8/ |
| Wet-Dry Cleaning | 3.3.6 | 5621 |
| Laundering | 3.3.6 | 5610 3/ 4/ |
| Perspiration | 3.3.6 | 5680 |
| Weight | 3.4 | 5041 |
| Yarns per Inch (Warp and Filling) | 3.4 | 5050 |
| Breaking Strength (Warp and Filling) | 3.4 | 5100 |
| Stiffness | 3.4 | 5202 |
| Air Permeability | 3.4 | 5450 |
| Tear Strength (Warp and Filling) | 3.4 | ASTM D1424 |
| Weave | 3.5 | Visual 2/ |
| Non-Fibrous Material | 3.7 | 2611 |
| Soil Release | 3.8.1 | Para. 4.5.2 |
| Durable Press | 3.8.2 | AATCC No. 124 7/ |
| pH | 3.9 | 2811 |
| Dimensional Stability | 3.10 | 5556 5/ |
| Seam Efficiency | 3.11 | 5110 6/ |



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be accepted for the stated requirements.

2/ One determination shall be made from each sample unit and the result shall be reported as "pass" or "fail".

3/ The specimen must be dried after each of the 3 laundering cycles.

4/ Only the stain on the cotton and polyester fibers of the color transfer cloth shall be evaluated.

5/ Cotton laundering procedure shall be used.

6/ The needle shall measure 0.044 (±0.001) inch across the blade at the eye. The thread shall be either polyester covered in accordance with A-A-50199, ticket No. 50, 2 ply for the needle and ticket No. 70, 2 ply for the looper or spun polyester in accordance with MIL-T-43624, class 1 or class 2, ticket No. 40, 3 ply for the needle and ticket No. 70, 2 ply for the looper.

7/ Use wash procedure III, drying procedure B-tumble of AATCC 124.

8/ The calibration of the fadeometer and the definition of AATCC Fading Units shall be according to AATCC Test Method 16. Using the formula below, 16 to 22 AFU's are acceptable as 20 SFH's.

$$\text{AATCC Fading Units} = \frac{(\Delta E^*)(20)}{1.7}$$

Where ($\Delta E^*$) is the color difference in CIELAB* units of color difference.

4.5.1 Fiber content. The general procedures of test method 2100 shall be followed and the fiber content percentages shall be calculated as follows:

$$\frac{\text{Weight of dry residual fiber} \times 100}{\text{Weight of dry desized specimen}} = \text{percent polyester}$$

100 - percent polyester = percent cotton

4.5.2 Soil Release Test Procedure. The test shall be in accordance with the requirements of 4.5.2.1 through 4.5.2.4.

4.5.2.1 Specimens. There shall be three (3) 4x8 inch (10x20cm) specimens taken from different warp and filling yarns.

4.5.2.2 Staining. The test specimens shall be stained in accordance with AATCC TM 130, except for the following: (1) The test specimen shall be 4x8 inches (10x20cm). (2) Three drops of Graphite Multi-Grade Motor Oil (SAE 10W-40), supplied as GFM (see 6.5), shall be used in lieu of five drops of mineral oil.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

4.5.2.3 Laundering. The test specimens shall be laundered in accordance with AATCC TM 61, Test No. III A, except for the following: (1) The total liquor volume shall be 500 ml. (2) Fifteen grams per liter of AATCC (124 WOB) detergent shall be used. (3) A total of 50 stainless steel balls shall be used. (4) No multi-fiber test fabric or bleached cotton fabric is required. (5) At the end of the cycle, rinse in running water at 105°F, for five minutes. No scouring is required. (6) Hydroextract the test specimen to remove excess moisture. Air dry or oven dry at 220°F.

4.5.2.4 Evaluation. The test specimens shall be evaluated in accordance with AATCC TM 130 procedure, except it shall be evaluated against "NCIRF Stain Release Replica", supplied as GFM (see 6.5). The treated specimens shall have an average soil release rating of not less than 3.0 when tested as specified.

5. PACKAGING

5.1 Put-up and preservation. Put and preservation shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C. The cloth shall be put up and preserved in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Levels A, B, and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of PPP-P-1134.

5.4 MIL-STD-2073. When specified (see 6.2), Preservation and Packing shall be in accordance with MIL-STD-2073-1 and MIL-STD-2073-2.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The cloth covered by this specification is intended for use in clothing items worn by Department of Defense personnel.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification
b. Class required (see 1.2)
c. Width required (see 3.6)
d. Minimum length, if other than specified (see 3.13)
e. Issue of DODISS to be cited in the solicitation, and if required, the specific issues of individual documents referenced (see 2.1 and 2.2)
f. When first article sample is required (see 3.2). The item will be tested and should be a first article sample. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examination, quality, testing and approval of the first article.
g. Levels of preservation and packing required (see 5.1 and 5.2)
h. When all packaging data is to be found in MIL-STD-2073-1 and MIL-STD-2073-2 (see 5.4)

6.3 Standard sample. For access to standard samples, address the procuring activity issuing the invitation for bids (see 3.1).

6.4 Fabric Defect Scales. Sears Fabric Defect Scales are available from Sears, Roebuck and Company, Department 817 (ATTN: BSC 23-29), Sears Tower, Chicago, IL 60684 (see 4.4.2.1).

6.5 Government Furnished Material (GFM). The ARCO Graphite Multi-Grade Motor Oil (see 4.5.2.2) and NCTRF Stain Release Replica (see 4.5.2.4) are available after award of contract from the procuring office issuing the invitation for bids.

6.6 Soil release finishes. Only those soil release treatments listed in the invitation for bids or request for proposal shall be considered acceptable for related procurement. Information on currently approved treatments may be obtained from Defense Personnel Support Center, Philadelphia, PA 19101 (see 3.8 and 3.12).

6.7 Durable press finishes. Only those durable press finishes listed in the invitation for bids or request for proposal shall be considered acceptable for related procurement. Information on currently approved treatments may be obtained from Defense Personnel Support Center, Philadelphia, PA 19101 (see 3.8 and 3.12).

6.8 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification.

6.9 Subject term (key word) listing.

Fabric, uniform
Finish, Soil Release
Khaki 3729
White 3053



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

6.10 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodian:
Navy - NU

Preparing activity:
Navy - NU

Review activity:
DLA - CT

Project 8305-N440

User activity:
Navy - MC



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| MIL-C-24927A | CLOTH, TWILL, POLYESTER/COTTON (DURABLE PRESS) |

| 3. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR |
| | ☐ USER |
| b. ADDRESS *(Street, City, State, ZIP Code)* | ☐ MANUFACTURER |
| | ☐ OTHER *(Specify)*: _____ |

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil - Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS:** In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was uncompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE:* This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Navy Clothing and Textile Research Facility
P.O. Box 59
Natick, MA 01760-0001

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T03:03Z
Check the source to verify that this is the current version before use.