[METRIC]

A-A-1631A
March 23, 1994
SUPERSEDING
A-A-1631
May 22, 1981

COMMERCIAL ITEM DESCRIPTION

LABEL, PAPER, GUMMED (FILE FOLDER)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification UU-L-49, Class D.

This Commercial Item Description covers nonremovable gummed paper labels with water-activated adhesive intended for use in labeling folders.

CLASSIFICATION

The gummed adhesive paper labels covered by this specification shall be of the following sizes and colors.

Size 1 - 85.7 mm (3-3/8 inch) X 28.5 mm (1-1/8 inch)
2 - 98.4 mm (3-7/8 inch) X 28.5 mm (1-1/8 inch)

Color A - Blue
B - Buff
C - Canary
D - Green
E - Pink
F - White

1. SALIENT CHARACTERISTICS

A. Paper: The labels shall be made of chemical woodpulp which may contain a maximum of 25 percent unbleached or groundwood. The paper shall have a basis weight (before gumming) of 66.6 to 85.8 g/m^2 (45 to 58 lbs. 25 X 38-500) - 5%, + unlimited, when tested in accordance with TAPPI test method T410. The paper shall be uniform in texture with a smoothly finished surface and shall be sized so that inked impressions from typewriter ribbons, ball point pens, and drawing ink will be well defined and will not feather or spread.

Beneficial comments, recommendations, additions, deletions, clarification's, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278

Distribution Statement A:
Approved for public release; Distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:15Z
Check the source to verify that this is the current version before use.

B. Construction: The labels shall be furnished in a continuous fanfold of 500 labels, consisting of 100 folds of 5 labels each Labels shall be perforated on all adjoining sides for easy separation. At the option of the supplier each label shall be scored in the long dimensions 17.4 mm (11/16 inch) from the bottom edge to facilitate folding the label over the edge of a file folder.

C. Gum adhesive: The labels shall be completely coated on one sid with a uniform film of gum adhesive. The gum adhesive shall be quickly water activated and adhere immediately to paper, wood, and fiberboard. The gum adhesive shall be non-toxic and not ha an obnoxious taste or odor.

D. Tolerances: A tolerance of +/- 3.17 mm (+/- 1/8 inch) shall be permitted for the horizontal dimensions, and +/- 0.794 mm (+/- 1/64 inch) for vertical dimensions.

Workmanship: The labels shall be clean, free from lint, dust, spots, scorches, folds, wrinkles, holes and any other defects which may affect the serviceability, durability, or appearance.

2. REGULATORY REQUIREMENTS:

The contractor shall certify that the minimum content standard shal. no less than 20% post consumer materials in accordance with Executive Order 12873, section 504 (a), dated October 20, 1993 (See definitions of post consumer materials and recovered materials in sections 203 ar 205). As an alternative to meeting the standards of section 504(a) f all printing and writing papers, the minimum content standard shall b no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided f under the provisions of the contract.

To obtain an acceptable brightness, in accordance with the performanc standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleachir process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to requi proof of such conformance prior to first delivery and thereafter as m be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

3. **TABLES AND TESTS:**

Table 1. Physical requirements for paper without adhesive.

	Requirement	Test Metho
Basis Weight	66.6 to 85.5 g/m^2 (45 to 58 lbs. 25 X 38-500) tolerance: -5%, +unlimited	T410

A. **Printing and writing qualities:** The labels shall be tested for printing and writing qualities as follows: Lines or characters shall be drawn or written on the writing surface of the label with a medium point "roller ball" type pen. To be considered satisfactory there shall be no feathering of the inked lines or characters.

B. **Adhesion:** The adhesive side of each of three labels shall be moistened and firmly pressed in contact with: 1) an 215.9 mm by 279.4 mm (8-1/2 X 11 inch) specimen of standard reference material, as specified in ASTM D 3654. 2) grade V3c or V3s fiberboard. Roll the labels once in each direction with a soft rubber covered hinged iron roller. To be considered satisfactory, the labels shall immediately tack to the surfaces without curling or tearing. After two hours elapsed time, the adhesive quality shall be considered satisfactory if: the labels cannot be removed from the test surfaces without fiber separation.

4. **QUALITY ASSURANCE:**

Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government.

The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, and quality assurance practices. The government reserves the right to require proof of conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Each lot of Paper Labels shall be inspected for conformance to the requirements herein. Sampling for inspection shall be in accordance with MIL-STD-105 using the plans specified below.

A. Visual characteristics - For visual characteristics, Inspection Level II with an Acceptable Quality Level (AQL) of 2.5 percent defective. The sample unit shall be five labels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

B. Dimensional characteristics - For dimensional characteristics, Inspection Level S-2 with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be five labels.

C. Sampling for end item testing - Inspection Level S-1 with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be five labels selected at random from the unit of issue. Not more than five labels shall be selected from any one issue unit. Characteristics of the component paper stock tested for conformance to the requirements in Section 1 do not have to be retested under end item testing. A certified test report is evidence that the paper has passed the required test.

5. **PREPARATION FOR DELIVERY:**

Packaging, packing and marking shall be as specified in the contract or purchase order.

6. **REFERENCED DOCUMENTS:**

The issue of each document in effect on the date of the solicitation shall be used to determine compliance with these requirements.

TAPPI test methods are available from:

Technical Association of the Pulp and Paper Industry
Technology Park/Atlanta, P.O. Box 105113
Atlanta, GA 30348
(404) 446-1400

ASTM test methods are available from:

American Society for Testing and Materials
ATTN: Consumer Service
1916 Race Street
Philadelphia, PA 19103
(215) 299-5585

MIL-STD-105 is available from:

STANDARDIZATION DOCUMENTS ORDER DESK
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Copies of Executive Order 12873, dated October 20, 1993 may be obtained from:

The White House Publications Office
New Executive Office Building
White House
Att: Publications
Washington, DC. 20500

(202) 395-7332

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

computation used for determination of the F value for the

7. **NOTES:**

A. Ordering Data:

Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(1) Size.
(2) Color of label.
(3) Whether chlorine or chlorine compound bleaching is acceptable.
(4) Specific packaging, packing, palletization and, marking requirements.

Military custodians:

Army - GL
Navy - SA

Preparing activity:

GSA - FSS

Civil agency coordinating activities:

NASA - JFK

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.