L-P-517c
November 3, 1967
SUPERSEDING
Int. Fed. Spec. L-P-00517b(GSA-FSS)
Novermber 2, 1964

FEDERAL SPECIFICATION

PLASTIC SHEET, SCRIBE - COATED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers scribe-coated plastic material.

1.2 Classification.

1.2.1 Type. Plastic sheet, scribe-coated, covered by this specification shall be of one type.

1.2.2 Forms. Plastic sheet, scribe-coated, covered by this specification shall be furnished in sheets or rolls as specified (see 3.2 and 6.2).

1.2.3 Sizes (dimensions). (See 3.2 and 6.2.)

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

L-P-390	-	Plastic Molding Material, Polyethylene, Low and Medium Density.
UU-P-31	-	Paper; General Specifications and Methods of Testing.
PPP-B-636	-	Box, Fiberboard.
PPP-B-665	-	Boxes; Paperboard, Metal Stayped (Including Stay Material).
PPP-D-723	-	Drums, Fiber.
PPP-T-60	-	Tape: Pressure-Sensitive Adhesive, Waterproof, for Packaging.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).

Fed. Test Method Std. No. 406 - Plastics: Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington D. C., 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administraction Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks, and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

Military Specifications:

MIL-D-5480 - Data, Engineering and Technical, Reproduction Requirements For.

MIL-P-14474 - Points, Scribing Instrument, Cartographic.

MIL-B-12880 - Box, Paperboard, Metal-Stayed, Heavy Duty, Reusable, (Including Stay Material).

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards, required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material. The material shall be plastic sheet coated on one side with a layer of scribable material.

3.2 Dimensions. The size of the sheets and the width of the rolls furnished shall be specified in the contract or purchase order (see 6.2). The material shall be supplied in thickness from 0.0020 to 0.0075 inch plus or minus 20 percent of specified thickness (base material not including scribe coating). The width and length tolerances shall be ±1 percent.

3.3 Coating thickness. Thickness of coating shall be 0.00045 to 0.0006 inch when tested as specified in 4.4.1.

3.4 Finish. Sheets shall be furnished evenly coated on one side with scribable material. The color of the scribable material shall be rust or yellow unless otherwise specified.

3.5 Opacity. Actinic density of engraving layer shall be sufficient to permit the preparation of reproducibles meeting the legibility and contrast requirements of MIL-D-5480.

3.6 Flexibility. The coated surface shall not crack, craze, or decrease in opacity when tested as specified in 4.4.2.

3.7 Tensile strength. The tensile strength of the base plastic sheet material shall be not less than 15,000 pounds per square inch (p.s.i.) when tested as specified in 4.4.3.

3.8 Coating adhesion. The adhesion shall be such that the coating shall not peel from the base, when subjected to the type-pull test described in 4.4.9.

3.9 Abrasion resistance. The coated surface shall withstand the abrasive action of scribing tool legs and plastic and metal drawing instruments without decrease in opacity when tested as specified in 4.4.4.

3.10 Scribe lines. Lines of uniform widths shall be engravable with existing scribing instruments. Engraved lines shallbe clear, sharp and without ragged edges when observed with a four power hand lens. The coating shall be such that "shaving" resulting from engraving may be easily removed by wiping lightly with a felt pad or similar cloth.

3.10.1 Line weight. The lines scribed through the coating shall be smooth and with sharply defined edges. The maximum variation in line width, including variations caused by chips and edge flaking shall be not greater than plus or minus 0.001 inch of the desired line thickness when tested as specified in 4.4.5.3.

3.10.2 Scribing pressure. A scribing pressure of 6 ounces shall remove the coating completely from the base plastic and scribing pressure of one ounce shall not expose the base plastic at any point, when tested as specified in 4.4.5.2.

3.11 Surface characteristics. The surface of the base material shall be free from blemishes or imperfections which may impair engraving quality of the scribe coat.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:10Z
Check the source to verify that this is the currenversion before use.

3.12 Storage stability. The coated plastic sheet shall show no deterioration upon completion of the storage cycle and tests specified in 4.4.6.

3.13 Fold endurance. The base sheets shall withstand not less 10,000 folds when tested as specified in 4.4.7.

3.14 Dimensional stability.

3.14.1 Thermal coefficient of expansion. The material shall have a thermal coefficient of expansion not exceeding 0.000011 inch per inch for each degree (° F.) change of temperature in the range of 73.4° to 120° F. when tested as specified in 4.4.8.2.

3.14.2 Hygroscopic coefficient of expansion. The material shall have a hygroscopic coefficient of expansion not exceeding 0.000012 inch per inch for each percent change in relative humidity in the range of 20 percent relative humidity to 90 percent relative humidity and temperature of 73.4° ±2° F. when tested as specified in 4.4.8.3.

3.15 Permanence property.

3.15.1 Thermal shrinkage. The residual shrinkage of the scribe-coated material shall not exceed 0.11 percent when the material conditioned for 24 hours at 73.4° ±2° F. and 50 percent relative humidity is exposed to 180° F. for one hour and then returned to the original conditioning temperature and relative humidity for 24 hours when tested as specified in 4.4. 8.1.

3.15.2 Hygroscopic shrinkage. Residual shrinkage in scribe-coated material shall not exceed 0.07 percent when the material conditioned for 24 hours at 73.4° F. and 20 percent relative humidity is exposed to a relative humidity of 90 percent at 73.4° F. for 24 hours and returned to the original conditioning temperature and humidity for 24 hours when tested as specified in 4.4.8.4.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise speiified in the contract or purchase order, the supplier is responsible for the performance fo all inspection requirements as specified herein. except as otherwise specified, the supplier may utlize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Sampling for inspection and acceptance. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot for examinations and tests shall consist of all material of the same form and size submitted for delivery at one time.

4.2 Inspection of materials and components. In accordance with 4.1, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. Examination of the end item shall be made in accordance with the classification of defects, inspection levels and acceptable quality levels (AQLs) set forth below. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of packages of sheets or rolls, as applicable, for examination in 4.3.1.1, 4.3.1.2, 4.3.1.3 and in units of shipping containers for examination in 4.3.1.4.

4.3.1.1 Examination of the end item for defects in appearance and workmanship. The sample unit for this examination shall be one sheet (for sheets), or one linear yard (for rolls), as applicable. Examine in accordance with table I.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:10Z
Check the source to verify that this is the current version before use.

TABLE I. Examination of end item for defects in appearance and workmanship

Examine	Defect
Appearance	Not uniform texture of finish. Presence of dirt, foreign material, imbedded particles. Tears, cuts, wrinkles, scratches, pinholes, or bare spots.
Workmanship	Not coated, coated both sides. Coating not uniform color, not as specified. Edges not straight and smooth.

4.3.1.2 Examination of the end item for defects in dimensions. The sample unit for this examination shall be one sheet or roll. Examine in accordance with table II.

TABLE II. Examination of end item for defects in dimensions

Examine	Defect
Length (sheets)	Unless otherwise specified, varies by more than 1 percent from the length required by contract.
Width (sheets and roll	Unless otherwise specified, varies by more than 1 percent from the width required by contract.

4.3.1.3 Examination of end item for defects in the count per package of sheets or length per roll. The sample unit for this examination shall be one package of sheets or one roll, as applicable. The average count of sheets or linear footage per sample unit shall be not less than the specified or indicated quantity. Failure of the sample to conform to this examination shall cause the lot to be rejected.

4.3.1.4 Examination of preparation for delivery. An examination shall be made in accordance with table III to determine that packaging, packing, and markings comply with the requirements of section 5. The sample unit shall be one shipping container fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

TABLE III. Examination of preparation for delivery

Examine	Defect
Packaging	Not level specified; not in accordance with contract requirements. Sheets or rolls not unit wrapped and packaged as required. Packaging material not as specified; closures not made by specified or required methods or materials.
Packing	Not level specified; not in accordance with contract requirements. Any nonconforming component, component missing, damaged, or otherwise defective affecting serviceability. Inadequate application of components such as incomplete enclosures of case liners, container flaps, loose or inadequate strapping, bulged or distorted containers.
Count	Less than specified or indicated quantity or packages or rolls per shipping container.
Weight	Gross weight exceeds specified requirements.
Markings	Interior or exterior markings (as applicable), omitted, illegible, incorrect, incomplete, or not in accordance with contract requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

4.3.1.5 Inspection levels and AQLs for examinations. The inspection levels for determining the sample size and the AQLs expressed in defects per 100 units, shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.1.1	II	1.5
4.3.1.2	S-4	2.5
4.3.1.3	S-3	Acceptance number zero
4.3.1.4	S-3	4.0

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics as indicated in table IV for each lot submitted for inspection. The sample unit shall be 3 full sheets (42 by 42 inches or largest size obtainable from stock of the same origin as the lot submitted) or the equivalent area if supplied in rolls. The inspection level for determining the sample size shall be S-3 except that not less than three sample units shall be randomly selected throughout the lot. If one or more sample units fail to meet the specified requirements, the lot represented shall be rejected.

4.4 Test methods.

4.4.1 Coating thickness. Using a micrometer, measure the thickness of a coated sheet, then completely remove the coating with a solvent. Determine the thickness of the sheet with the coating removed, using the same micrometer. The difference in measurements obtained on the coated sheet and after removal of the coating is the thickness of the coating. A total of 6 measurements shall be made on the coated sheet and after removal of the coating (see 3.3).

4.4.2 Flexibility. The sheets shall be bent around a cylindrical rod or mandrel having a diameter of 1/4 inch maintaining full contract with the surface of the rod over at least one-half of its circumference. The area of contact shall be flexed once over the test rod with the uncoated surface of the sheet in contact. The coating shall then be carefully examined over the coated contact area for evidence of cracking, crazing, or delamination for compliance with 3.6.

4.4.3 Tensile strength. Sample shall be tested in accordance with method 1013 of Fed. Test Method Std. No. 406, at a jaw separation rate of 2 inches per minute to determine compliance with 3.7.

4.4.4 Abrasion resistance. Slide a scribing instrument over the flat coated surface of a plastic sheet a total of 6 times. Any damage to the scribe coating shall be cause for rejection.

4.4.5 Scribing characteristics. Each specimen shall be tested for scribing characteristics as specified herein.

4.4.5.1 Apparatus. A scribing point conforming to MIL-P-14474, type I, size 0.004 inch, shall be used to determine the scribing characteristics. The point shall be mounted in an instrument which is capable of controlling and indicating the pressure in ounces at the tip of the point and, also, is capable of orienting and maintaining the point on a vertical position to within plus or minus $1/2^{\circ}$.

4.4.5.2 Pressures. Using apparatus specified in 4.4.5.1, a total pressure of $6 \pm 1/2$ ounce, shall be maintained at the point. The point shall be moved horizontally over the coated surface and two 12-inch lines shall be scribed, one parallel to the length and one parallel to the width. The lines shall be brushed with a clean cloth and the lines inspected under a magnification of approximately 4 times for evidence of incomplete removal of the coating from the base plastic. The aforementioned procedure shall be repeated except that a pressure of $1 \pm 1/4$ ounce, shall be maintained at the tip of the point, and the coated side shall be examined for exposure of base plastic. The testing and inspection shall be performed over a tracing table.

4.4.5.3 Examination for line weight variations. Scribed lines made under a total pressure of 6 ounces shall be examined for line weight variation using a measuring microscope calibrated to 0.001 inch. Using the microscope, the defects which increase the nominal line width by 0.001 inch or more shall be counted (see 3.10.1). If the number of defects in any scribed line is equal to or greater than the length of the line in inches divided by 2, the sample shall have failed to pass the test.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:10Z
Check the source to verify that this is the current version before use.

TABLE IV. Instructions for testing (sample unit)

Characteristic	Specification reference		Rqmts. appl. to		Number determinations per sample unit	Results reported as	
	Requirement	Test method	Indiv. unit	Lot average		Pass or fail 1/	Numerically to nearest 2/
Opacity	3.5	MIL-D-5480	X	-	1	X	-
Thickness							
Base plastic sheet	3.2	4.4.1	X	-	Avg. of 5	-	0.001 inch
Coating	3.3	4.4.1	X	-	Avg. of 5	-	0.001 inch
Flexibility	3.6	4.4.2	X	-	1	X	-
Tensile strength	3.7	4.4.3	X	-	Avg. of 10 in each direction	-	lbs. per sq. in.
Coating adhesion	3.8	4.4.9	X	-	1	X	-
Abrasion resistance	3.9	4.4.4	X	-	1	X	-
Scribing characteristics	3.10	4.4.5					
Line weight	3.10.1	4.4.5.3	X	-	1	X	-
Scribing pressure 6 oz.	3.10.2	4.4.5.2	X	-	1	X	-
Scribing pressure 1 oz.	3.10.2	4.4.5.2	X	-	1	X	-
Storage stability test	3.12	4.4.6					
Flexibility	3.6	4.4.2	X	-	1	X	-
Abrasion resistance	3.9	4.4.4	X	-	1	X	-
Tensile strength	3.7	4.4.3	X	-	Avg. of 10 in each direction	-	lbs. per sq. in.
Fold endurance	3.13	4.4.7	X	-	Avg. of 10 in each direction	X	-
Dimensional stability	3.14	4.4.8					
Thermal coefficient of expansion	3.14.1	4.4.8.2	X	-	1	-	percent
Hygroscopic coefficient of expansion	3.14.2	4.4.8.3	X	-	1	-	percent
Permanence property	3.15	4.4.8					
Thermal shrinkage	3.15.1	4.4.8.1	X	-	5	-	percent
Hygroscopic shrinkage	3.15.2	4.4.8.4	X	-	1	-	percent

1/ If failure is indicated report description of failure.
2/ Test reports shall include all values on which results are based.

Source: https://assist.dla.mil -- Downloaded: 2026/10-26T11:10Z
Check the source to verify that this is the current version before use.

4.4.6 Storage stability. Coated sample sheets shall be subjected to a cycle of temperature and relative humidity extremes in the following order:

(a) A high temperature series, consisting of three exposures of 4 hours each on successive days at a temperature of 155° ±5° F., and a relative humidity of 15 ± 5 percent.

(b) A low temperature condition, consisting of 24 hours exposure at a temperature of minus 65° F. ±5° F.

(c) A high humidity condition, consisting of 24 hours exposure at a relative humidity of 90 ±1 percent and a temperature of 80° ±2° F.

(d) A normal temperature and humidity condition, consisting of 8 hours or more at a temperature of neither less than 65° nor more than 85° F. and a relative humidity of neither less than 20 nor more than 80 percent. Upon the completion of the cycle, the samples shall be tested as specified in 4.4.2 through 4.4.4.

4.4.7 Fold endurance. The fold endurance shall be tested in accordance with methods 131 or 132 of UU-P-31.

4.4.8 Dimensional stability.

4.4.8.1 Thermal shrinkage. Cut five, 10 by 10 inch samples of the material and mark the midpoints of each edge for use as reference points. Condition the five samples at 73.4° ±2° F. and 50 ± 2 percent relative humidity for 24 hours. At the end of the conditioning period (24 hours) measure and record the distance between the opposite edges of the test samples at the reference marks to the nearest 0.01 inch. Place the samples for 1 hour in a circulating air oven heated to 180° ± 2° F. At the end of the oven-exposure period, allow the specimen to cool for 24 hours to the original conditioning temperature and relative humidity. Measure and record the distance between the opposite edges of the test samples at the reference marks to the nearest 0.01 inch. The percent shrinkage is calcualted as follows:

$$\text{Thermal shrinkage, percent} = \frac{D_o - D_f}{D_o} \times 100$$

D_o = original length (or width) of test sample in inches.

D_f = final length (or width) of test sample in inches.

Average the values obtained for each length and width directions.

4.4.8.2 Thermal coefficient of expansion. Cut a 42 by 42 inch sample very accurately. Condition the sheet material at 73.4° ±2°F., and 50 ±2 percent relative humidity for 24 hours and immediately measure the sheet with accurate graduated calipers or steel rule. Locate the exact positions where the measurements were taken. Place the sample in controlled container having a temperature of 120° ±2° F. and a constant relative humidity of 50 ±2 percent. Maintain this condition for 24 hours and measure the test sample at this temperature at the locations previously marked and record the change. The thermal coefficient of expansion is calcualted as follows:

$$\text{Thermal coefficient of expansion} = \frac{D_f - D_o}{46.6 \times D_o}$$

D_o = original length (or width) before heat aging.

D_f = final length (or width) after heat aging.

46.6 = difference in temperature (120° - 73.4° F.).

4.4.8.3 Hygroscopic coefficient of expansion. Cut a 42 by 42 inch sample very accurately. Condition the sheet material at 72° ±2° F., and 20 ±2 percent relative humidity for 24 hours and immediately measure the sheet with accurate graduated calipers or steel rule. Locate the exact positions where measurements were taken. Place the sample in a controlled container having a relative humidity of 90 ±2 percent, and a constant temperature of 73.4° ±2° F. Maintain this condition for 24 hours and measure the test sample at the locations previously marked and record the change. The hygroscopic coefficient of expansion is calculated as follows;

$$\text{Hygroscopic coefficient of exapnsion} = \frac{D_f - D_o}{70 \times D_o}$$

D_o = original length (or width) before humidity aging.

D_f = final length (or width) after humidity aging.

70 = difference in relative humidity (90° - 20° percent).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

4.4.8.4 Hygroscopic shrinkage. Return the sample from 4.4.8.3 to the original condition of 20 ±2 percent relative humidity and 73.4° ±2° F., and allow the sample to condition for 24 hours. Measure the sheet with accurate graduated calipers or steel rule. The percent hygroscopic shrinkage is calculated as follows:

$$\text{Percent hygroscopic shrinkage} = \frac{D_o - D_f}{D_o} \times 100$$

D_o = original length (or width) of test sample in inches.

D_f = final length (or width) of test sample in inches.

4.4.9 Coating adhesion. Coating adhesion shall be determined using a transparent pressure sensitive tape conforming to PPP-T-60, which is placed firmly on a minimum 1/2 by 2 inch area of the coating surface and pulled away with a sharp tug in a direction 90° from the sheet.

5. PREPARATION FOR DELIVERY

5.1 Packaging. (See 6.2.)

5.1.1 Level A or B.

5.1.1.1 Sheets. Sheets of the same size shall be packaged flat, faced top and bottom with a sheet of paperboard or chip board of commerical quality and grade, 50 sheets per package, wrapped in 50-pound kraft paper, ends of wrap neatly foled and secured by adhesive or tape. The container shall be closed and strapped in accordance with appendix of the applicable container specification.

5.1.1.2 Rolls. Each roll, after forming on a 4-inch diameter core, shall be completely wrapped in 50-pound kraft paper, ends neatly folded and secured by application of 50-pound kraft paper caps or disks over the folded ends, secured by a suitable adhesive.

5.1.2 Level C. Unless otherwise specified, sheets and rolls shall be packaged in accordance with standard commercial practice.

5.2 Packing. (See 6.2.)

5.2.1 Level A.

5.2.1.1. Sheets. The sheets packaged as specified in 5.1.1.1 shall be packed in fiber or paperboard boxes in accordance with PPP-B-636, PPP-B-665 and MIL-B-19880, respectively.

5.2.1.2 Rolls. Thr rolls packaged as specified in 5.1.1.2 shall be packed in fiber drums conforming to PPP-D-723, type II, grade A. Fiber drums shall be furnished with 0.004 inch minimum thickness polyethylene liners conforming to L-P-390, type I, grade 1. Liner closure shall be effected by twisting top, folding it back on itself, and tying it with string or commercial metal fasteners; or the liner may be heat sealed to form a vaporproof barrier. Closure of the containers shall be made in accordance with the applicable specification.

5.2.2 Level B.

5.2.2.1 Sheets. Four packages of 50 sheets, packaged as specified in 5.1.1.1 shall be packed in new shipping containers conforming to PPP-B-636 type CF, class domestic, style FTC or RSC, burst test of board not less than 275 p.s.i. with closure in accordance with the appendix thereto.

5.2.2.2 Rolls. Rolls shall be packaged in accordance with 5.2.1.2.

5.2.3 Level C. Unless otherwise specified, shipping containers shall be in accordance with standard commercial practice and shall comply with the carrier rules and regulations applicable to the mode of transportation, at the lowest transportation rate for such supplies.

5.3 Marking.

5.3.1 Civil agencies.

5.3.1.1 Packages (sheets and rolls). In addition to any special marking required in the contract or order, packages of sheets shall be marked with applicable Federal Stock Number, item name, size of sheets, quantity contained therein (e.g., 50 sheets), and name of manufacturer and contractor, if different. No marking will be required on kraft-paper-wrapped rolls.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

5.3.1.2 Exterior containers. In addition to any special marking required in the contract or order, exterior containers shall be marked in accordance with Fed. Std. No. 123 including specification (form, size, etc.).

5.3.2 Military agencies. In addition to any special marking required by the contract or order, unit packages, intermediate packages, and shipping containers shall be marked in accordance with the requirements of MIL-STD-129.

6. NOTES

6.1 Intended use. Plastic rolls and sheets covered ty this specification are intended for use in drawings, the development of original drawings, and for other purposes requiring material coated with an engraving layer on which drawings are rendered using a scriber.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number and date of this specification.
(b) Dimensions and tolerances.
(c) Quantity.
(d) Whether the material is to be supplied in sheets or rolls.
(e) Selection of applicable level of packaging and packing required (see 5.1 and 5.2).

MILITARY INTEREST:

Custodians:

Army - EL
Navy - AS
Air Force - 11

Review activities:

Army - EL
Navy - OS
Air Force - 11, 69

Preparing activity:

Navy - AS

CIVIL AGENCY INTEREST

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price **10** cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:10Z
Check the source to verify that this is the currentversion before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof).*

SPECIFICATION

L-P-517c PLASTIC SHEET, SCRIBE - COATED

ORGANIZATION *(Of submitter)*	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED *(Printed or typed name and activity)*	DATE

DD FORM 1 NOV 64 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE C-8279

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

BuWeps Engineering Standardization Office (Code X)
Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:10Z
Check the source to verify that this is the current version before use.