L-T-774
JULY 8, 1958

FEDERAL SPECIFICATION

TOOTH ASSORTMENT AND TOOTH SET, PROSTHETIC

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers artificial teeth made of synthetic resin, which reproduce the characteristics of natural teeth, in forms harmonizing with the forms of human teeth and of human faces. Teeth shall be suitable for the construction of complete and partial dentures by technics in general use by the dental profession.

1.2 Classification.

1.2.1 *Types and classes.* — Plastic teeth shall be of the following types and classes, as specified (see 6.1) :

Type I.—Anterior teeth.
Type II.—Posterior teeth.
Class 1.—Anatomic posterior teeth.
Class 2. — Non-anatomic posterior teeth.

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:
U–R–179—Resin, Acrylic, Dental.
PPP–B–585—Boxes; Wood, Wirebound.
PPP–B–601—Boxes, Wood, Cleated-Plywood.
PPP–B–621—Boxes, Wood, Nailed and Lock-Corner.
PPP–B–636—Boxes, Fiber.
PPP–B–676—Boxes, Set-Up, Paperboard.

Federal Standards:
Fed. Std. No. 102—Preservation, Packaging and Packing Levels.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Specifications:
MIL–B–10377—Box, Wood, Cleated, Veneer, Paper Overlaid.
MIL–L–10547 — Liners, Case, Waterproof.

Military Standards:
MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.
MIL–STD–129 — Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material. — Plastic shall be methyl methacrylate polymer, copolymer of methacrylates, or combinations of resins having suitable properties for use as artificial teeth. The manufacturer shall furnish a certificate stating that the teeth are not toxic or irritating to the oral tissues.

3.2 Sizes and shapes (mould numbers).— Teeth shall be furnished in the sizes and shapes as specified. When mould numbers are indicated for sizes and shapes, they shall conform to the corresponding teeth in manufacturer's mould guide.

3.3 Shade numbers.—Teeth shall be furnished in the shade numbers as specified. The shades of teeth shall be reproductions of those found in the human mouth, ranging from the light shades of young persons to the dark shades of elderly, as found in natural teeth. The shades of the teeth shall colormatch the corresponding teeth in the manufacturer's shade guide within the limits of professional acceptance.

3.4 Tooth set, anterior.—Set shall consist of six either upper or lower anterior teeth in accordance with mould and shade, as specified.

3.5 Tooth set, posterior.—Set shall consist of eight either upper or lower posterior teeth in accordance with mould and shade as specified.

3.6 Tooth assortment. — Unless otherwise specified, an assortment shall consist of 108 sets of upper anterior teeth, 36 sets of lower anterior teeth, and 96 sets each of upper and lower posterior teeth, or a total of 336 sets of anterior and posterior plastic teeth. Teeth shall be furnished in the moulds and shades as specified.

3.6.1 *Tooth set replenishment.*—When required by procuring activity in order to replenish stock or fill in broken sets, anterior teeth will be furnished in full or broken sets of 1 x 6's and posterior teeth in full or broken sets of 1 x 8's, or their multiple.

3.7 Blend.—Anterior and posterior plastic teeth shall consist of a gingival, or body, portion and a more translucent incisal or occlusal portion; the two to be blended in such a manner as to simulate natural teeth, with no line of demarcation between incisal (occlusal) and gingival portions on the labial (buccal) aspects of the teeth.

3.8 Types.

3.8.1 *Anterior teeth.*—Anterior teeth shall approximate the various forms of human anterior teeth.

3.8.2 *Posterior teeth.*—Posterior teeth shall be either anatomic (class 1) or non-anatomic (class 2) as specified. Class 1 teeth shall approximate the forms of human posterior teeth. Class 2 teeth shall approximate the forms of human posterior teeth but shall have modified occlusal surfaces.

3.9 Physical properties.—Plastic teeth shall comply with the following physical properties;

3.9.1 *Porosity.* — When prepared as described in 4.3.2, teeth shall be free of porosity, either on or within 2 mm. of the surface when sectioned and observed by low magnification (10 X).

3.9.2 *Surface finish.*—When tested and prepared as described in 4.3.3, the original finish of the teeth shall be maintained during processing and reprocessing to a degree that a light buffing shall restore them to their original condition. The teeth shall be capable of being ground and polished to a glossy surface which shall be maintained under conditions found in the oral cavity. The manufacturer shall furnish a certificate stating that the teeth will not stain in service and that any deposit will be removed by light buffing without marring of the original surface.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

3.9.3 *Bonding.*—The ridge lap portion of the teeth shall form a chemical bond with acrylic denture base resin, when processed by the heat-curing technic. Strength of the bond and/or the tensile strength of the teeth shall be not less than 4500 pounds per square inch, when tested as specified in 4.3.4.

3.9.4 *Hardness.*—The enamel portion of the teeth shall have a Knoop Indentation Hardness of not less than 15.0 kg/mm^2 when tested as described in 4.3.5.

3.9.5 *Indentation resistance.*—When tested as described in 4.3.6, the body (gingival) portion of the teeth shall not be indented more than 0.11 mm. (0.0043 inch) by a ½-inch (12.7 mm.) steel ball loaded at 30 kg. (66.2 lb.) for 10 minutes. The recovery of the depth of the indentation shall be at least 80 percent in 10 minutes after the 30 kg. load is released.

3.9.6 *Blushing.*—The teeth shall not blush, blanch, or change color when heated in water at 100° C. (212° F.) for 3 hours, when tested as described in 4.3.7.

3.9.7 *Distortion.*—The teeth shall not distort or change in shape when heated in boiling water at 100° C. (212° F.) for 3 hours, when tested as described in 4.3.7.

3.9.8 *Craze resistance.*—The teeth shall be craze resistant to solvents both before and after being subjected to the curing cycle in a water bath, when tested as described in 4.3.7.

3.9.9 *Color stability.*—When tested as described in 4.3.8, the teeth shall not show more than a slight color change.

3.10 **Workmanship.** — Workmanship shall be first class in every respect. Teeth shall be smoothly and properly finished and shall be free from imperfections which will affect their appearance or may impair their serviceability.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Sampling.**—Sampling procedures shall be conducted in accordance with the procedures set forth in Military Standard MIL–STD–105. In addition, samples may be requested by the procuring activity for testing at government laboratory.

4.2 **Inspection.**—Inspection may be made throughout the entire process of manufacture. The passing as satisfactory of any detail of construction or materials shall not relieve the contractor of responsibility for faulty workmanship or materials which may be discovered at any time prior to final acceptance. Final inspection of the finished article shall be made either at point of production or at point of delivery, as specified (see 6.1). In case of factory inspection, every facility shall be afforded inspectors, by the manufacturer, for the prosecution of their work.

4.3 **Tests.**—Tests shall be conducted, as necessary, to determine compliance with this specification.

4.3.1 *Standard testing conditions.* — All tests shall be made at a temperature of 23° ± 1.1° C. (73° ± 2° F.). Equipment and material shall be conditioned at this temperature for not less than 12 hours prior to making the tests.

4.3.2 *Porosity.*—Examination by 10X magnification shall be made on the surface of four teeth and on specimens cut and prepared as described in 4.3.5.

4.3.3 *Surface finish.* — Three teeth to be tested for surface finish shall be processed to a denture base resin which complies with Federal Specification U–R–179, using the customary denture compression packing technic. The teeth shall be in contact with artificial stone (hydrocal) used as the investing material. The flask shall be heated in a water bath for 1½ hours at 73° ± 1° C. (163.4° ± 1.8° F.) and then in boiling water for 30 minutes.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:11Z
Check the source to verify that this is the current version before use.

The flask shall then be cooled in air at 23° ± 10° C. (73° ± 18° F.) for 30 minutes and then in water at this temperature for 15 minutes. After removal from the flask, the teeth shall be polished briefly (for no longer than 1 minute) with a soft muslin wheel using chalk as a polishing agent. The surface of one tooth shall be ground away and the tooth shall be polished using the muslin wheel and chalk for the final polish. The surface finish of the teeth, after polishing, shall be compared by visual inspection with the surface finish of teeth as received.

4.3.4 *Bonding.*—Prepare three cylindrical specimens of wax, approximately 0.3 inch in diameter, each containing a tooth with its ridge lap surface approximately normal to the long axis of the cylinder. The tooth may be located either at one end or in the center of the test specimen. Imbed cylinders in a flask so that the ridge lap of teeth is normal or at a natural angle to the direction of flask closure. Flush the mould with three applications of hot modern synthetic household detergent solution (one tablespoon to one pint of water) and rinse with clean boiling water. Pack the moulds, with the teeth in place, by the standard packing technic using denture base resin which complies with Federal Specification U–R–179. Close the flask, process for 1½ hours at 73° ± 1° C. (163.4° ± 1.8° F.), and then place the flask in boiling water for 30 minutes, remove it and allow it to cool in air at 23° ± 10° C. (73° ± 18° F.) for 30 minutes, and then immerse in water at this temperature for 15 minutes. Open the flask, remove each specimen of resin and machine it to 0.25 ± 0.01 inch diameter in the ridge lap area, being sure that none of the base resin remains on the sides of the tooth. Small diameters may be used when testing anterior teeth (class 1). Place the specimen in a suitable tension testing machine and load at 200 ± 50 pounds per minute until fracture occurs. The tooth shall not be required to bond at the occlusal surface. The average of the values obtained for three specimens shall be recorded to the nearest 100 lb/in.[2]

4.3.5 *Hardness.*—The hardness shall be determined on the occlusal (incisal) portion of the teeth by the Knoop indentation method, using 10 seconds descent and 20 seconds contact with a 100 gram load. Specimens shall be made by taking one transverse section from each of four teeth. The occlusal (incisal) side of the section shall be 1.5 ± 0.5 mm. from the tip of the cusps (incisal edge). The gingival side of the section shall be 4.5 ± 0.5 mm. from the tip of the cusps (incisal edge). The specimens shall be 2.5 ± 0.5 mm. thick and shall be polished flat and parallel using progressively finer polishing paper. The final finish shall be a smooth glossy surface produced with No. 3/0 emery paper, followed by magnesium oxide powder, on a wet polishing wheel. Ten evenly spaced indentations shall be made on the occlusal (incisal) side of each of the four specimens and the average of the 40 indentations shall be recorded to the nearest 0.1 kg/mm.[2] All indentations shall be so spaced that they will not be affected by the adjacent indentations.

4.3.6 *Indentation resistance.*—Indentation resistance shall be determined on the gingival or body portion of the teeth with a Rockwell Superficial Hardness Tester. Specimens shall be made as described in 4.3.5. Indentations shall be made in the center of the gingival side of three sections. Each specimen shall be subjected to a minor load of 3 kg. on a ½ inch diameter steel ball; then a major load of 30 kg. shall be applied. The major load shall be allowed to contact the specimen for 10 minutes and the depth of indentation of the ball due to the major load shall be read from the dial gage and recorded as reading A. The major load shall then be released leaving the minor load on the specimen. The reading of the dial gage at 10 minutes after the release of the major load shall be recorded as reading B. Readings of the dial gage shall be made to the nearest 0.001 mm. The average of the three values for reading A to the nearest 0.01 mm. shall be reported as the indentation. The recovery to the nearest whole percent shall be obtained as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

$$\text{Recovery in percent} = \frac{\text{Average A} - \text{Average B}}{\text{Average A}} \times 100$$

4.3.7 *Blushing, distortion and craze resistance.*—One or more teeth of each shade shall be examined for blushing and distortion after being subjected to the following testing cycle. The teeth shall be submerged in test tubes of water placed in a water bath so that the tubes do not contact the vessel. The water bath shall be heated from room temperature to 100°C. (212°F.) in from 5 to 20 minutes and held at boiling temperature 100°C. (212°F.) for three hours. The teeth shall be removed, surface dried, and cooled to room temperature in approximately 10 minutes, and tested without further delay. Tests for craze resistance shall be made on one or more teeth of each shade in the "as received" condition, and one or more teeth of each shade after the teeth have been subjected to the above testing cycle. The teeth shall be immersed in methyl methacrylate monomer for 5 seconds and removed. This immersion shall be repeated after 1 minute and the teeth shall then be allowed to dry on a towel for two hours, at room temperature. If any blushing, blanching or change in color, any distortion or any cracks can be seen by visual examination, or low power magnification (10 X), when viewed by transmitted light the teeth fail to meet these requirements.

4.3.8 *Color stability.*—Two teeth shall be exposed to the radiation of a lamp with an S–1 bulb which has been in use not less than 50 nor more than 400 hours. The light source shall be a combination tungsten filament mercury enclosed in Corex D or other glass which has a low transmission below 2800° A (Angstrom). The lamp shall be rated at 400 watts. The specimen shall be carried on an aluminum disk which shall be centered under the S–1 bulb and which shall rest on a phonograph turntable operated at 33 revolutions per minute. The specimen shall be held approximately 5 mm. (0.2 in.) above and 12.7 cm. (5 in.) from center of the disk. The specimen shall be approximately 17.8 cm. (7 in.) from the bottom of the S–1 bulb and shall be maintained between 60° and 65°C. (140° and 149°F.). After exposure for 24 hours, the specimen shall be compared with an unexposed tooth from the same mould shade and of the same anatomic type. The exposed specimens shall not show more than a slight change in color (perceptible with difficulty). The comparison shall be made by visual inspection in daylight.

4.4 Supplier responsibilities for inspection.—The supplier shall perform examinations and tests set forth in this specification to substantiate conformance of supplies to specification requirements. The examinations and tests shall be at the expense of the supplier. Suppliers shall have adequate test facilities or shall arrange for test facilities acceptable to the Government to be used for executing specific prescribed tests. Records of examinations and tests performed by the supplier shall be maintained by the supplier and made available to the Government upon the Government's request, at any time or from time to time for a period of 2 years after the delivery of the supplies to which these records relate. The supplier shall be responsible for compliance with all requirements of this specification, and all other technical requirements of the contract.

5. PREPARATION FOR DELIVERY

The levels of preservation, packaging and packing used are defined in Fed. Std. No. 102 (for civil agencies only).

5.1 Packaging.

5.1.1 *Unit of issue.*

5.1.1.1 *Stock No. 6520–560–0250.* — One (1) set of six (6) teeth, type I, as specified, constitutes one unit.

5.1.1.2 *Stock No. 6520–560–0350.* — One (1) set of eight (8) teeth, type II, as specified, constitutes one unit.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

5.1.1.3 *Stock No. 6520–560–0400.* — One (1) assortment of type I and type II teeth, as specified, constitutes one unit.

5.1.2 *Level A.*

5.1.2.1 *Unit package.*

5.1.2.1.1 *Stock No. 6520–560–0250 or 6520–560–0350.*—One set of teeth (1 unit) shall be mounted on a block of suitable size and design.

5.1.2.1.2 *Stock No. 6520–560–0400.* — Six anteriors or eight posteriors shall be mounted on a block of suitable size and design. A convenient number or blocks of anteriors or posteriors shall be packaged in a carton of appropriate size constructed in accordance with Federal Specification PPP–B–676. Carton shall contain sufficient cushioning material to prevent shifting or breakage. The number of cartons comprising one unit of issue shall be packaged in a box of appropriate size constructed in accordance with Federal Specification PPP–B–636, type I, class 1. Closure shall be adequate to prevent spillage of contents under normal handling.

5.1.2.2 *Intermediate package.*

5.1.2.2.1 *Stock No. 6520–560–0250 or 6520–560–0350.*—A number of units not exceeding twenty, of like mould and shade, shall be packaged in a carton of appropriate size constructed in accordance with Federal Specification PPP–B–676. Carton shall contain sufficient cushioning material to prevent shifting or breakage.

Note.—When sets are procured in amounts less than contractor's standard quantity to be contained in an intermediate package, the amount procured shall be packaged in such manner as to insure against shifting or breakage.

5.1.2.2.2 *Stock No. 6520–560–0400.*—Intermediate package is not required.

5.1.3 *Level C.*—Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose within the continental limits of the United States of America.

5.2 Packing.

5.2.1 *Level A.*

5.2.1.1 *Stock No. 6520–560–0250 or 6520–560–0350.*—Level A packing is not applicable.

5.2.1.2 *Stock No. 6520–560–0400.*

5.2.1.2.1 *Exterior container.* — Six unit packages shall be overpacked in an exterior container designed for type 2 load and constructed in accordance with Federal Specification PPP–B–585, style 3, designed for class 3 use; PPP–B–601, table II, using type III, class 1 plywood; PPP–B–621, table IV; or Military Specification MIL–B–10377, table II.

5.2.1.2.2 *Case liner.* — Each level A box shall be lined with a waterproof case liner conforming to Military Specification MIL–L–10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto.

5.2.1.2.3 *Strapping.*—Strapping, when required, shall be in accordance with applicable box specification.

Note.—Strapping will not be required for shipment forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.2 *Level B.*

5.2.2.1 *Stock No. 6520–560–0250 or 6520–560–0350.*

5.2.2.1.1 *Exterior container.* — A number of intermediate cartons containing sets of teeth, of the same shade and mould shall be overpacked in an exterior container constructed in accordance with Federal Specification PPP–B–621, table I, or PPP–B–636, type I, class 1. Gross weight of wood shipping container shall not exceed 100 pounds. Gross weight of fiberboard shipping container shall not exceed 40 pounds.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:11Z
Check the source to verify that this is the currentversion before use.

5.2.2.1.2 *Multiple packing.* — Where the quantities of like sets of teeth of same shade and mould procured are too small to meet packing requirements as outlined above, multiple packing will be permitted in a manner as described herewith: One or more intermediate packages containing like sets of teeth of the same shade and mould shall be cartonized or wrapped as one package and identified with a label showing contents contained therein. Two or more properly prepared packages shall be overpacked as outlined in paragraph 5.2.2.1.1.

5.2.2.2 *Stock No. 6520–560–0400.* — Six unit packages shall be overpacked in an exterior container conforming to Federal Specification PPP–B–601, table I, using type III, class 1 plywood, or designed for type 2 load, and constructed in accordance with Federal Specification PPP–B–585, style 3, designed for class 2 use; PPP–B–621, table II; or Military Specification MIL–B–10377, table I.

5.2.3 *Level C.* — The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 **Marking.**

5.3.1 *Interior packages.*

5.3.1.1 *Stock No. 6520–560–0250 or 6520–560–0350.*

5.3.1.1.1 *Unit package.*—Each set of teeth shall be marked with mould number and shade designation.

5.3.1.1.2 *Intermediate package.*—Each intermediate package shall be marked with stock number, item identification, unit, quantity, mould and shade designation, contract number, and name of contractor.

5.3.1.2 *Stock No. 6520–560–0400.*

5.3.1.2.1 *Blocks.* — Each block shall be marked with mould number, shade number, and name or registered trade-mark of the contractor.

5.3.1.2.2 *Cartons.*—Each carton shall have affixed to it a list showing the contents (quantity of each mould number, shade number, and the number of upper, lower, anterior, and posterior teeth) contained therein.

5.3.1.2.3 *Unit packages.*—Each unit carton shall be marked with stock number, item identification, unit, quantity, name of contractor, and a list showing the contents (quantity of each mould number, shade number, and the number of upper, lower, anterior, and posterior teeth) contained in each unit.

5.3.2 *Shipping container.*—Shipping container shall be marked in accordance with Military Standard MIL–STD–129. Service color and service symbol markings are required only on direct shipment from the contractor's plant to overseas activities. The shipping container for each multiple pack shall be marked as specified in 2.2.2.1 of Military Standard MIL–STD–129 and shall be furnished with packing lists as specified in 6.8.1 of same standard.

6. **NOTES**

6.1 **Ordering data.** — Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title number and date of this specification.
(*b*) Type required (see 1.2).
(*c*) Class required for type II (see 1.2).
(*d*) Size and shape (mould numbers) required (see 3.2).
(*e*) Shade number required (see 3.3).
(*f*) Tooth assortment, if other than specified (see 3.6).
(*g*) Inspection required (see 4.2).
(*h*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

6.2 This specification covers the following items appearing in the Armed Services Medical Stock List:

6520–560–0250 TOOTH SET, PROSTHETIC, Plastic, Anterior, Set of 6.

6520–560–0350 TOOTH SET, PROSTHETIC, Plastic, Posterior, Set of 8.

6520–560–0400 TOOTH ASSORTMENT, Plastic.

6.3 This specification does not include all types, classes, grades, sizes, etc., of the commodity indicated by the title of the specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet Federal Government requirements.

6.4 **Transportation description.**—Transportation description applicable to this item is:

Dental Goods, not otherwise indexed by name.

Carload minimum weight, 20,000 pounds subject to Rule 34, Uniform Freight Classification.

Motor volume minimum weight, 12,000 pounds.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—M
Navy—Md
Air Force.

★ U. S. GOVERNMENT PRINTING OFFICE: 1958

Copies of this specification may be purchased for 5 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)*

CITY AND STATE

CONTRACT NO.

QUANTITY OF ITEMS PROCURED

DOLLAR AMOUNT
$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*

DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE PLATE NO. 15419

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:11Z
Check the source to verify that this is the current version before use.