MIL-R-25988A(USAF)
AMENDMENT 1

23 November 1971

MILITARY SPECIFICATION

RUBBER, FLUOROSILICONE ELASTOMER, OIL- AND FUEL-RESISTANT, SHEETS, STRIPS, MOLDED PARTS, AND EXTRUDED SHAPES

This Amendment forms a part of Military Specification MIL-R-25988A(USAF) dated 29 July 1969.

Page 1

Paragraph 1.2: Clarify Type I as follows: "Type I. O-Rings (Available only in certain classes and grades)."

Page 2

Paragraph 2.1: Under "SPECIFICATIONS, Military", add:

"MIL-R-25988/1 Rubber, Fluorosilicone Elastomer, Oil- and Fuel-Resistant, O-Rings, Class 1, Grade 70

MIL-R-25988/2 Same as above, except (O-Rings, Class 3)

MIL-R-25988/3 Same as above, except (O-Rings, Class 1, Grade 60)

MIL-R-25988/4 Same as above, except (O-Rings, Class 1, Grade 80)"

Under "STANDARDS, Military", add:

"MIL-STD-831 Test Report, Preparation of"

Page 4

Paragraph 3.3.1: Delete and substitute:

"3.3.1 Sheets and strips. Unless otherwise specified (see 6.2) sheets and strips shall be supplied in the lengths and widths and to the length and width tolerances specified in 3.3.1.1 and 3.3.1.2, and the tolerance on thickness shall be as shown in Table I. The dimensions and tolerances of shapes cut from sheet and strip shall be as specified on the detail drawings.

3.3.1.1 Sheets. The width of sheet material shall be 36 ± 1 inch and the length shall be 120 inches ± 1 percent.

3.3.1.2 Strips. The width of strip shall be 4 inches ± percent and the length shall be 75 feet ± 1 foot."

FSC 5330

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:40Z
Check the source to verify that this is the current version before use.

Paragraph 3.3.2: Change "(including O-rings)" to "(excluding O-rings)" in two places."

Paragraph 3.3.3: Delete and substitute:
"3.3.3 O-Rings. Dimensions and tolerances of O-rings shall be in accordance with the applicable Military Specification Sheet. Those are as follows:

a.	Class 1, Grade 60	MIL-R-25988/3(USAF)
b.	Class 1, Grade 70	MIL-R-25988/1(USAF)
c.	Class 1, Grade 80	MIL-R-25988/4(USAF)
d.	Class 3	MIL-R-25988/2(USAF)

Table I: Delete and substitute:

Table I. Thickness tolerances of sheet and strip

Nominal thickness (inch)	Tolerances (inch)
.031 and less	± .010
over .031 to .063 inclusive	± .012
over .063 to .125 inclusive	± .016
over .125 to .188 inclusive	± .020
over .188 to .375 inclusive	± .031
over .375 to .563 inclusive	± .047
over .563 to .750 inclusive	± .063
over .750 to 1.000 inclusive	± .093
over 1.000	± 10%

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:40Z
Check the source to verify that this is the current version before use.

Table II: Delete and substitute:

Table II. Physical properties

Physical property	Class 1					Class 2	Class 3
	Grade 40	Grade 50	Grade 60	Grade 70	Grade 80	Grade 50	Grade 75
Original:							
Test strength psi, min							
Type I:	--	--	700	650	750	--	700
Type II:	800	900	900	850	750	1150	800
Ultimate elongation, %, min							
Type I:	--	--	150	100	70	--	90
Type II:	225	200	175	125	70	350	100
Tensile stress at 100% elongation, psi, min (class 3 only)							
Type II	NA	NA	NA	NA	NA	NA	700
Hardness, Type A Durometer, points	40±5	50±5	60±5	70±5	80±5	50±5	75±5
Tear strength, die B, ppi, min							
Type II:	40	40	40	40	40	150	40
Temperature retraction 10% (TR-10), °F, max	-70	-70	-70	-70	-70	-70	-70
Compression set: % of original Deflection after 70 hr. at 75° +5°F, max							
Type I:							
Under 0.110 in	--	--	20	25	25	--	25
Over 0.110 in	--	--	15	20	20	--	20
Type II:	15	15	15	15	15	15	15

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:40Z
Check the source to verify that this is the current version before use.

Table II. Physical properties (Cont'd)

Physical property	Class 1					Class 2	Class 3
	Grade 40	Grade 50	Grade 60	Grade 70	Grade 80	Grade 50	Grade 75
Air-aged 70 hr. at temperatures indicated:	392°F ±5°F	392°F ±5°F	392°F ±5°F	392°F ±5°F	392°F ±5°F	392°F ±5°F	437°F ±5°F
Tensile strength decrease, % max	30	25	25	20	20	30	35
Ultimate elongation decrease, %, max	25	25	25	20	20	30	45
Hardness change, Type A Durometer, points, max	+10,-5	+10,-5	+10,-5	+10,-5	+10,-5	+10,-5	+10,-5
Weight loss, %, max	2	2	2	2	2	2	2
Air-aged 22 hr. at temperatures indicated:	347°F ±5°F	347°F ±5°F	347°F ±5°F	347°F ±5°F	347°F ±5°F	347°F ±5°F	347°F ±5°F
Compression set: % of original deflection, max							
a. Standard reading:							
Type I:							
Under 0.110 in	--	--	45	50	50	--	45
Over 0.110 in	--	--	40	45	45	--	35
Type II:	25	35	40	40	45	40	35

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:40Z
Check the source to verify that this is the current version before use.

Table II. Physical properties (Cont'd)

Physical property	Class 1					Class 2	Class 3
	Grade 40	Grade 50	Grade 60	Grade 70	Grade 80	Grade 50	Grade 75
Aged 70 hr. in Stauffer Blend 7700 fluid at temperatures indicated:	302°F ±5°F	302°F ±5°F	302°F ±5°F	302°F ±5°F	302°F ±5°F	302°F ±5°F	347°F ±5°F
Tensile strength decrease, %, max	45	45	45	35	30	40	30
Ultimate elongation decrease, %, max	30	30	30	20	15	30	20
Hardness change, Type A Durometer, points, max	15	15	15	15	15	15	20
Volume change, %	1 to 15	1 to 15	1 to 15	1 to 15	1 to 15	1 to 15	1 to 15
Compression set: % of original deflection, max							
a. Standard reading:							
Type I:							
Under 0.110 in.	--	--	50	55	65	--	85
Over 0.110 in.	--	--	45	45	60	--	80
Type II:	35	35	45	45	60	45	80
b. 18 hr. cooling:							
Type I:							
Under 0.110 in.	--	--	60	60	75	--	85
Over 0.110 in.	--	--	55	55	70	--	80
Type II:	45	45	55	55	70	50	80

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:40Z
Check the source to verify that this is the current version before use.

Page 5 (Cont'd)

Table II. Physical properties (Cont'd)

Physical property	Class 1					Class 2	Class 3
	Grade 40	Grade 50	Grade 60	Grade 70	Grade 80	Grade 50	Grade 75
Aged 22 hr. in TT-S-735, type III, fluid at 75° ± 5°F:							
Tensile strength decrease, %, max	65	55	50	45	30	40	35
Ultimate elongation decrease, %, max	60	50	40	30	30	30	30
Hardness decrease, Type A Durometer, points, max	15	15	20	20	20	25	15
Volume change, %	1 to 30	1 to 25	1 to 25	1 to 25	1 to 25	1 to 25	1 to 25

Page 9

Paragraph 4.3.3: Add:
"4.3.3 Preproduction test report. Preproduction tests are required for each type, class, and grade of material furnished to this specification. After the supplier completes the preproduction inspection he shall prepare a preproduction test report in accordance with MIL-STD-831. Three copies of this report shall be furnished to the procuring activity and one copy to AFML/LAE, Wright-Patterson AFB, Ohio 45433. The preproduction test need not be repeated for new orders or different parts provided the materials and processes have not been changed and a certified statement to this effect is furnished to the procuring activity. The waiving of the preproduction tests will be strictly at the discretion of the procuring activity. Test results to previous revision of this specification are not acceptable. Preproduction tests will not be acceptable if they are more than 3 years old."

Paragraph 4.4.2: Add following the last sentence: "If the end item is an O-ring with an inside diameter of less than 0.5 inch, -214 size O-rings should be used for test samples."

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:40Z
Check the source to verify that this is the current version before use.

Page 16

Paragraph 6.3: Delete in its entirety.

Custodian:
Air Force - 11

Review activity:
Air Force - 82

Preparing activity:
Air Force - 11

Project Number: 5330-F018

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T07:40Z
Check the source to verify that this is the current version before use.