INCH-POUND

MIL-DTL-27072/88D
8 August 2006
SUPERSEDING
MIL-DTL-27072/88C
8 December 2000

DETAIL SPECIFICATION SHEET

CABLE, SPECIAL PURPOSE, ELECTRICAL, MULTICONDUCTOR (2 CONDUCTORS) AND SINGLE SHIELDED

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-27072.

Inactive for new design. For new design use MIL-DTL-55021/2.




FIGURE 1. Cable configuration.

Note: The Part or Identifying Number (PIN) requires a color code designator (see table I).

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T10:56Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Design and construction:	See figure 1
Number of conductors:	2
Temperature rating:	200°C
Component:	
Basic wire:	Either NEMA-HP3 or SAE-AS22759 (see table I)
Conductor:	Silver-coated copper
Primary insulation:	Polytetrafluoroethylene
Colors:	White Black
Jacket over insulation:	Not applicable
Filler:	Not applicable
Cabling:	Not applicable
Binder tape material:	Not applicable
Marking tape:	Marking tape will be placed under the sheath or shield
Shield:	
Material:	Silver-coated copper
Construction:	See table I
Braid angle:	Braid 20 to 40 degrees
Jacket undershield:	Not applicable
Sheath:	
Material:	Polytetrafluoroethylene
Wall thickness:	.011 ± .003 inch (.28 +/-.08 mm)
Tensile strength:	In accordance with MIL-DTL-27072
Ultimate elongation:	In accordance with MIL-DTL-27072
Accelerated aging:	Not applicable
Color:	See MIL-DTL-27072

Surface resistance (sheath): When tested in accordance with method 6041 of FED-STD-228, the initial surface resistance shall be not less than 5 megohms. The final surface resistance shall be within 50 percent of the initial surface resistance. (Note: The specimen for this inspection test shall not be subjected to any other electrical tests.)

Finished cable:	See table I
Cold bend:	Mandrel size in accordance with MIL-DTL-27072
Dielectric withstanding voltage:	2,000 V rms
Conductor resistance:	In accordance with basic wire specification

Heat resistance: A specimen of finished cable shall be subjected to 250±5 °C in an air oven for 96 hours minimum. The specimen shall be removed from the oven and allowed to cool to room temperature. After 1 hour at room temperature, the insulation and jacket shall be checked for shrinkage of not more than .125 inch (3.17 mm). The specimen shall then be wound 5 close turns around the mandrel of 10 times

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T10:56Z
Check the source to verify that this is the current version before use.

the cable diameter. In this position, the specimen shall be subjected to the dielectric strength test in MIL-DTL-27072. If the cable fails the dielectric strength test or shrinks more than .125 inch (3.17 mm), the lot shall be rejected.

TABLE I. Construction data.

PIN M27072/88	Conductor			Nominal cable lay	Overall shield parameters 1/				Finished cable dia. Inch (mm) 2/	
	AWG	Stranding AWG	Nominal dia. Inch (mm) 2/		d	N	P	D	Min.	Max.
TDDE*	28	7/36	.0150 (.38)	.935	.005	5	18	.078	.097 (2.46)	.113 (2.87)
SDDE*	26	7/34	.0189 (.48)	1.030	.005	4	18	.086	.105 (2.67)	.126 (3.20)
NDDE*	24	19/36	.0248 (.63)	1.150	.005	5	17	.096	.115 (2.92)	.137 (3.48)
LDDE*	22	19/34	.0312 (.79)	1.300	.005	5	16	.108	.127 (3.23)	.149 (3.78)
JDDE*	20	19/32	.0396 (1.01)	1.490	.005	5	15	.124	.143 (3.63)	.166 (4.22)
GDDE*	18	19/30	.0495 (1.26)	1.770	.005	6	13	.148	.163 (4.14)	.189 (4.80)
FDDE*	16	19/29	.0570 (1.45)	2.090	.005	7	11	.174	.181 (4.60)	.212 (5.38)

PIN M27072/88	Approx. weight per 1,000ft (lb)	Basic wire (reference) (either / or may be used)		Formerly basic wire M16878/4 or M16878/21 (reference)
		SAE-AS22759	NEMA HP3	
TDDE*	10.2	/11-28*	EWBCB*	BCB*
SDDE*	12.6	-	EXBDB* EWBDB*	BDB*
NDDE*	17.2	/11-24*	EWBEE*	BEE*
LDDE*	19.0	/11-22*	EWBFE*	BFE*
JDDE*	23.5	/11-20*	EWBGE*	BGE*
GDDE*	31.0	/11-18*	EWBHE	BHE*
FDDE*	37.7	/11-16*	EWBJE*	BJE*

1/ See MIL-DTL-27072, overall shielding to determine braid coverage. Optional shields are acceptable provided the shields meet the requirements of MIL-DTL-27072.

2/ Dimensions are in inches. Metric equivalents are given for information only.

Asterisks (*) shall be replaced by the appropriate color designator in accordance with MIL-STD-681 and table I. If a stripe or a band is to be added, it shall be in accordance with MIL-DTL-27072.

Marginal notations are not used in this revision to identify changes with respect to the previous issues due to the extensiveness of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T10:56Z
Check the source to verify that this is the current version before use.

Referenced documents. In addition to MIL-DTL-27072, this document references the following:

MIL-DTL-55021/2
NEMA-HP3
SAE-AS22759
FED-STD-228
MIL-STD-681

CONCLUDING MATERIAL

Custodians:
Army - CR
Navy - SH
Air Force - 11
DLA – CC

Preparing activity:
DLA - CC

(Project 6145-2006-016)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organization and responsibilities can change, please verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T10:56Z
Check the source to verify that this is the current version before use.