MIL-C-915/14B
1 August 1972
SUPERSEDING
MIL-C-00915/14A(SHIPS)
20 March 1972
MIL-C-915/14
15 March 1968

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE MHOF

(B) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor - Navy standard size 2-1/2(19), uncoated.
Second - Polyvinyl chloride insulation, black, (105°C.), nominal wall thickness 0.020 inch. Standard Identification Code, applied by Method 1.
Third - The specified number of conductors (see Details) cabled together in one or more layers, all in left-hand direction, with the minimum amount of fibrous fillers necessary to form a firm, round assembly. Cabling sequence shall be consecutive, starting with No. 1, from center outward. The length of lay shall be determined to permit the completed cable to meet the twisting and bending endurance tests. A single conductor shall not be used as a center for the cable core.
Fourth - Binder tape applied helically with overlap.
Fifth - Standard thermoplastic jacket (gray). Nominal wall thickness 0.060 inch. Cable surface marking required.

(B)

Details

Type and size	No. of condrs.	Overall diameter Min. (inch)	Overall diameter Max. (inch)	Bending endurance roller diameter, Max. (inches)
MHOF-7	7	0.465	0.500	2.50
MHOF-10	10	.540	.585	2.50
MHOF-14	14	.585	.635	3.00
MHOF-19	19	.650	.705	3.00
MHOF-24	24	.735	.795	3.50
MHOF-30	30	.775	.835	4.00
MHOF-37	37	.855	.925	4.00
MHOF-44	44	.925	1.000	4.50
MHOF-61	61	1.100	1.175	5.00

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Conductor resistance - Ohms/1000 ft. at 25°C., maximum.	4.89
Voltage withstand - Volts, rms, minimum	2000
Insulation resistance - Megohms/1000 ft., minimum	500

(B) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
(B) Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	125
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	225
Twisting and bending endurance (see Details for roller diameter)	
At 75°C., cycles, minimum	6000
(B) At minus 30° ± 2°C., cycles, minimum	2000
Group C:	
Flammability - Inches, maximum	2
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	90
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (conductor) - Cycles, minimum	50
Permanence of printing (jacket) - Cycles, minimum	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of groups A, B, and C.

UNIT ORDERING LENGTHS:

Size	Feet (Nominal)
7 and 10	1500
14 through 61	1000

(B) Custodians:
Army - MI
Navy - SH
Air Force - 80

(B) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(B) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-10)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.