MILITARY SPECIFICATION SHEET

CORD, ELECTRICAL, 300 VOLTS, TYPE MMOP

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cord described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, Navy Standard size 1/2(21), uncoated.
Second - Polyvinyl chloride insulation, (80°C.) nominal wall thickness 0.020 inch. Standard Identification Code, applied by Method 3.
(D) Third - Five conductors cabled together with a lay not greater than 2 inches. A tie cord shall be laid straight as the central core. Fibrous fillers shall be used as necessary to make a firm, round cord. Cabling sequence shall be consecutive.
(D) Fourth - A binder of polyester tape, cotton braid, or rayon braid.
Fifth - Standard thermoplastic jacket (black).

Details

Type and size	Number of conductors	Diameters	
		Insulated conductor minimum (inch)	Overall maximum (inch)
MMOP-5	5	0.065	0.305

EXAMINATION AND TESTS

	Requirements:
Basic electrical:	
Conductor resistance - Ohms/1000 ft. at 25°C., maximum.	21.52
Voltage withstand - Volts, rms, minimum	
Conductor to conductor	1000
Insulation resistance - Megohms/1000 ft., minimum	100
Group A:	
Visual and dimensional	
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	125
Jacket (cord)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	225

(D) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.

	Requirements:
Group B (Cont'd):	
Twisting and bending endurance (bending endurance mandrel 0.8 inch diameter, maximum)	
At 75° ± 2°C., cycles, minimum	6000
At minus 30° ± 2°C., cycles, minimum	2000
Cold bending, cord	
At minus 40° ± 2°C.	No failure
Group C:	
Flammability - inches, maximum	2
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	80
Jacket (cord)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B, and C.

UNIT ORDERING LENGTHS:

500 feet (nominal - coils)

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-5)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.