MIL-C-915/18D
5 April 1973
SUPERSEDING
MIL-C-915/18C
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL 600 VOLTS, TYPE SSF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS
Qualification not required.

Construction

First - Copper conductor, Navy standard size 300(259), uncoated (see Note 1)
Second - Separator.
Third - Synthetic rubber insulation. Nominal wall thickness 0.075 inch.
Fourth - Reinforcement at manufacturer's option.
Fifth - Polychloroprene jacket bonded to the underlying insulation. Nominal wall thickness 0.075 inch.

NOTE 1. The copper shall be hard drawn, having a minimum tensile strength of 67,200 psi, and minimum elongation of 0.85 percent in 60-inch lengths before stranding. The resistance specified is based on 102.7 percent of the values required for annealed copper.

Details

Type and size	Conductor size Navy standard	Overall diameter	
		Minimum (inches)	Maximum (inches)
SSF-300	300(259)	1.020	1.100

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
(D) Conductor resistance - Ohms/1000 ft. at 25°C., Maximum	0.0388
(D) Voltage withstand - Conductor to ground, Volts, rms, minimum . . .	2500
(D) Insulation resistance - Megohms/1000 ft., minimum.	100
Group A:	
Visual and dimensional	
Group B:	
Cold bending, cable - At minus 30° ± 2°C., two turns around mandrel with diameter eight times that of specimen.	No damage

(D) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.

	Requirements:
Group B (Cont'd):	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum.	700
Elongation - Percent, minimum.	300
Jacket (cable)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum	300
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Tensile strength - Percent of unaged, minimum . . .	75
Elongation - Percent of unaged, minimum	75
Jacket (cable)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum . . .	50
Elongation - Percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - Percent of unaged, minimum . . .	60
Elongation - Percent of unaged, minimum	60

UNIT ORDERING LENGTH:
Minimum 1045, Maximum 1155 feet

Custodians:
Army - MI
Navy - SH
Air Force - 80
Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80
User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-20)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.