MIL-C-915/19D
1 August 1972
SUPERSEDING
MIL-C-00915/19C(SHIPS)
20 March 1972
MIL-C-915/19A
25 September 1968

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE TPU

(D) This specification is approved for use by all Departments and Agencies of the Department of the Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction (Watertight)

(D) First - A conductor consisting of 19 strands of 0.0095-inch wire, steel, Number 1010, Finish 5, tensile strength - Medium, Class 1 in accordance with QQ-W-461.

(D) Second - Polyvinyl chloride insulation (80°C.). Nominal wall thickness 0.025-inch. Telephone Identification Code, applied by Method 3.

Third - Two conductors cabled together to form a pair, with a nominal lay of 2-1/4 inches.

Fourth - Six twisted pairs shall be cabled together. Non-fibrous fillers shall be used. The length of lay shall be determined to permit the completed cable to meet the bending endurance test. Cabling sequence shall be consecutive.

Fifth - Binder tape applied helically with overlap.

(D) Sixth - Polychloroprene jacket. Reinforcement shall be applied under the jacket, or approximately near the middle of the jacket thickness (see details) so as not to show as an overall surface marking.

Details

Type and size	Number of pairs	Insulation thickness nominal (inch)	Cable jacket thickness nominal (inch)	Overall diameter maximum (inch)
TPU-6	6	0.025	0.125	1.000

EXAMINATION AND TESTS

	Requirements:
Basic electrical:	
Voltage withstand - Volts, rms, minimum	
Conductor to conductor	2000
Conductor to water	1000
Insulation resistance - Megohms/1000 ft., minimum	100
Group A:	
Visual and dimensional	
(D) Watertightness - Cubic inches, maximum.	1
Bending endurance - At minus 30° + 2°C. 3-inch maximum diameter mandrel, cycles, minimum	500
Breaking strength - Pounds, minimum	1100

(D) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.

	Requirements:
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	125
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	300
Set - Inch, maximum	3/8
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	80
Jacket (cable)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - Percent of unaged, minimum	60
Elongation - Percent of unaged, minimum	60

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTH: 1000 feet (Nominal) (minimum acceptable length 250 feet)

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-14)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:07Z
Check the source to verify that this is the current version before use.